

INTERNATIONAL STANDARD

QC 300100

**Fixed capacitors for use in electronic equipment –
Part 11: Sectional specification – Fixed polyethylene-terephthalate film dielectric
metal foil d.c. capacitors**

IECNORM.COM: Click to view the full PDF of IEC 60384-11:2008

Without watermark



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2008 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/customerserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch
Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00

IECNORM.COM: Click to download full PDF of IEC 60384-11:2008

INTERNATIONAL STANDARD

QC 300100

**Fixed capacitors for use in electronic equipment –
Part 11: Sectional specification – Fixed polyethylene-terephthalate film dielectric
metal foil d.c. capacitors**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE

U

CONTENTS

FOREWORD.....	4
1 General.....	6
1.1 Scope.....	6
1.2 Object.....	6
1.3 Normative references.....	6
1.4 Information to be given in a detail specification.....	6
1.4.1 Outline drawing and dimensions.....	7
1.4.2 Mounting.....	7
1.4.3 Ratings and characteristics.....	7
1.4.4 Marking.....	8
1.5 Terms and definitions.....	8
1.6 Marking.....	8
2 Preferred ratings and characteristics.....	9
2.1 Preferred characteristics.....	9
2.1.1 Preferred climatic categories.....	9
2.2 Preferred values of ratings.....	9
2.2.1 Rated capacitance (C_R).....	9
2.2.2 Tolerance on rated capacitance.....	9
2.2.3 Rated voltage (U_R).....	9
2.2.4 Category voltage (U_C).....	9
2.2.5 Rated temperature.....	10
3 Quality assessment procedures.....	10
3.1 Primary stage of manufacture.....	10
3.2 Structurally similar components.....	10
3.3 Certified records of released lots.....	10
3.4 Qualification approval.....	10
3.4.1 Qualification approval on the basis of the fixed sample size procedure.....	10
3.4.2 Tests.....	11
3.5 Quality conformance inspection.....	16
3.5.1 Formation of inspection lots.....	16
3.5.2 Test schedule.....	17
3.5.3 Delayed delivery.....	17
3.5.4 Assessment levels.....	17
4 Test and measurement procedures.....	18
4.1 Visual examination and check of dimensions.....	18
4.2 Electrical tests.....	18
4.2.1 Voltage proof.....	18
4.2.2 Capacitance.....	18
4.2.3 Tangent of loss angle ($\tan \delta$).....	19
4.2.4 Insulation resistance.....	19
4.2.5 Characteristics depending on temperature (if required in the detail specification).....	20
4.3 Robustness of terminations.....	21
4.3.1 Initial measurements.....	21
4.4 Resistance to soldering heat.....	21

4.4.1	Conditions	21
4.4.2	Final inspection, measurements and requirements	21
4.5	Solderability	21
4.6	Rapid change of temperature	21
4.6.1	Initial measurement	21
4.6.2	Number of cycles: 5.....	22
4.7	Vibration.....	22
4.8	Bump	22
4.8.1	Initial measurements	22
4.8.2	Severities	22
4.8.3	Final inspection, measurements and requirements	22
4.9	Shock.....	22
4.9.1	Initial measurements	22
4.10	Climatic sequence.....	23
4.10.1	Initial measurements	23
4.10.2	Dry heat	23
4.10.3	Damp heat, cyclic, Test Db, first cycle.....	23
4.10.4	Cold	23
4.10.5	Low air pressure.....	23
4.10.6	Damp heat, cyclic, Test Db, remaining cycles.....	24
4.11	Damp heat, steady state.....	24
4.11.1	Initial measurements	24
4.12	Endurance.....	24
4.13	Component solvent resistance (if applicable).....	25
4.14	Solvent resistance of the marking (if applicable).....	25
Bibliography.....		26
Table 1 – Fixed sample size test plan for qualification approval – Assessment level EZ.....		12
Table 2 – Test schedule for qualification approval.....		13
Table 3 – Lot-by-lot inspection.....		17
Table 4 – Periodic tests		18
Table 5 – Test voltages.....		18
Table 6 – Insulation resistance		19
Table 7 – Correction factor dependent on test temperature.....		20
Table 8 – Characteristics at lower category temperature.....		20
Table 9 – Characteristics at upper category temperature		21
Table 10 – Acceleration and duration of the pulse.....		23
Table 11 – Endurance test		24

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FIXED CAPACITORS FOR USE IN ELECTRONIC EQUIPMENT –

**Part 11: Sectional specification –
Fixed polyethylene-terephthalate film
dielectric metal foil d.c. capacitors**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60384-11 has been prepared by IEC technical committee 40: Capacitors and resistors for electronic equipment.

This third edition cancels and replaces the second edition published in 1988 and constitutes a minor revision related to tables, figures and references.

The text of this standard is based on the following documents:

CDV	Report on voting
40/1839/CDV	40/1864/RVC

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The list of all parts of the IEC 60384 series, under the (new) general title *Fixed capacitors for use in electronic equipment*, can be found on the IEC web site.

The QC number that appears on the front cover of this publication is the specification number in the IEC Quality Assessment System for Electronic Components (IECQ).

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IECNORM.COM: Click to view the full PDF of IEC 60384-11:2008
Withdrawn

FIXED CAPACITORS FOR USE IN ELECTRONIC EQUIPMENT –

Part 11: Sectional specification – Fixed polyethylene-terephthalate film dielectric metal foil d.c. capacitors

1 General

1.1 Scope

This part of IEC 60384 applies to fixed direct current capacitors, for rated voltages not exceeding 6 300 V, using as dielectric a polyethylene-terephthalate film and electrodes of thin metal foils. For capacitors with rated voltages exceeding 1 000 V, additional tests and requirements may be specified in the detail specification.

The capacitors covered by this standard are intended for use in electronic equipment.

NOTE Capacitors for radio interference suppression are not included, but are covered by IEC 60384-14 (see bibliography).

1.2 Object

The object of this standard is to prescribe preferred ratings and characteristics and to select from IEC 60384-1, the appropriate quality assessment procedures, tests and measuring methods and to give general performance requirements for this type of capacitor. Test severities and requirements prescribed in detail specifications referring to this sectional specification shall be of equal or higher performance level, because lower performance levels are not permitted.

1.3 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60062, *Marking codes for resistors and capacitors*

IEC 60063, *Preferred number series for resistors and capacitors*¹⁾

IEC 60068-1, *Environmental testing – Part 1: General and guidance*

IEC 60384-1:1999, *Fixed capacitors for use in electronic equipment – Part 1: Generic specification*

IEC 60410:1973, *Sampling plans and procedures for inspection by attributes*

ISO 3: *Preferred numbers – Series of preferred numbers.*

1.4 Information to be given in a detail specification

Detail specifications shall be derived from the relevant blank detail specification.

¹⁾ Second edition (1963) incorporating Amendments 1 (1967) and 2 (1977).

Detail specifications shall not specify requirements inferior to those of the generic, sectional or blank detail specification. When more severe requirements are included, they shall be listed in 1.9 of the detail specification and indicated in the test schedules, for example by an asterisk.

NOTE The information given in 1.4.1 may, for convenience, be presented in tabular form.

The following information shall be given in each detail specification and the values quoted shall preferably be selected from those given in the appropriate clause of this sectional specification.

1.4.1 Outline drawing and dimensions

There shall be an illustration of the capacitor as an aid to easy recognition and for comparison of the capacitor with others. Dimensions and their associated tolerances, which affect interchangeability and mounting, shall be given in the detail specification. All dimensions shall preferably be stated in millimetres, however, when the original dimensions are given in inches, the converted metric dimensions in millimetres shall be added.

Normally the numerical values shall be given for the length of the body, the width and height of the body and the wire spacing, or for cylindrical types, the body diameter, and the length and diameter of the terminations. When necessary, for example when a number of items (capacitance values/voltage ranges) are covered by a detail specification, the dimensions and their associated tolerances shall be placed in a table below the drawing.

When the configuration is other than described above, the detail specification shall state such dimensional information as will adequately describe the capacitor. When the capacitor is not designed for use on printed boards, this shall be clearly stated in the detail specification.

1.4.2 Mounting

The detail specification shall specify the method of mounting to be applied for normal use and for the application of the vibration and the bump or shock tests. The capacitors shall be mounted by their normal means. The design of the capacitor may be such that special mounting fixtures are required in its use. In this case the detail specification shall describe the mounting fixtures and they shall be used in the application of the vibration and bump or shock tests.

1.4.3 Ratings and characteristics

The ratings and characteristics shall be in accordance with the relevant clauses of this specification, together with the following:

1.4.3.1 Rated capacitance range

See 2.2.1.

NOTE When products approved to the detail specification have different ranges, the following statement should be added: "The range of values available in each voltage range is given in the qualified products list".

1.4.3.2 Particular characteristics

Additional characteristics may be listed, when they are considered necessary to specify adequately the component for design and application purposes.

1.4.3.3 Soldering

The detail specification shall prescribe the test methods, severities and requirements applicable for the solderability and the resistance to soldering heat test.

1.4.4 Marking

The detail specification shall specify the content of the marking on the capacitor and on the package. Deviations from 1.6 of this sectional specification, shall be specifically stated.

1.5 Terms and definitions

For the purposes of this document the terms and definitions of IEC 60384-1, as well as the following apply.

1.5.1

rated voltage (U_R)

maximum d.c. voltage which may be applied continuously to a capacitor at the rated temperature

NOTE The sum of the d.c. voltage and the peak a.c. voltage applied to the capacitor shall not exceed the rated voltage. The value of the peak a.c. voltage shall not exceed the following percentages of the rated voltage at the frequencies stated and shall not be greater than 280 V,

50 Hz	20 %
100 Hz	15 %
1 000 Hz	3 %
10 000 Hz	1 %

unless otherwise specified in the detail specification.

1.6 Marking

See 2.4 of IEC 60384-1, with the following details.

1.6.1 The information given in the marking is normally selected from the following list. The relative importance of each item is indicated by its position in the list:

- a) rated capacitance (in clear or code according to IEC 60062);
- b) rated voltage (d.c. voltage may be indicated by the symbol --- or —);
- c) tolerance on rated capacitance;
- d) category voltage;
- e) year and month (or week) of manufacture;
- f) manufacturer's name or trade mark;
- g) climatic category;
- h) manufacturer's type designation;
- i) reference to the detail specification.

1.6.2 The capacitor shall be clearly marked with a), b) and c) above and with as many as possible of the remaining items as is considered necessary. Any duplication of information in the marking on the capacitor should be avoided.

1.6.3 The package containing the capacitor(s) shall be clearly marked with all the information listed in 1.6.1.

1.6.4 Any additional marking shall be so applied that no confusion can arise.

2 Preferred ratings and characteristics

2.1 Preferred characteristics

The values given in detail specifications shall preferably be selected from the following:

2.1.1 Preferred climatic categories

The capacitors covered by this specification are classified into climatic categories according to the general rules given in IEC 60068-1.

NOTE For the tests in the IEC 60068 series of publications, the editions referenced in the applicable test clauses of the generic specification are used.

The lower and upper category temperatures and the duration of the damp heat, steady state test shall be chosen from the following.

Lower category temperature: –55 °C, –40 °C and –25 °C.

Upper category temperature: +85 °C, +100 °C, +105 °C and +125 °C.

Duration of the damp heat, steady state test: 4, 10, 21, and 56 days.

The severities for the cold and dry heat tests are the lower and upper category temperatures respectively.

2.2 Preferred values of ratings

2.2.1 Rated capacitance (C_R)

Preferred values of rated capacitance are:

1 μ F, 1,5 μ F, 2,2 μ F, 3,3 μ F, 4,7 μ F and 6,8 μ F and their decimal multiples.

These values conform to the E6 series of preferred values given in IEC 60063.

If other values are required they shall preferably be chosen from the E12 series.

2.2.2 Tolerance on rated capacitance

The preferred tolerances on the rated capacitance are ± 5 %, ± 10 % and ± 20 %.

2.2.3 Rated voltage (U_R)

The preferred values of rated voltage are: 40 V, 63 V, 100 V, 160 V and 250 V and their decimal multiples. These values conform to the basic series of preferred values R5 and R10 given in ISO 3.

2.2.4 Category voltage (U_C)

The category voltage is:

0,8 U_R for upper category temperature 100 °C and

0,75 U_R for upper category temperature 105 °C and

0,5 U_R for upper category temperature 125 °C.

2.2.5 Rated temperature

The standard value of rated temperature is 85 °C.

3 Quality assessment procedures

3.1 Primary stage of manufacture

The primary stage of manufacture is the winding of the capacitor element or the equivalent operation.

3.2 Structurally similar components

Capacitors considered as being structurally similar are capacitors produced with similar processes and materials, though they may be of different case sizes and values.

3.3 Certified records of released lots

The information required in 3.5.1 of IEC 60384-1 shall be made available when prescribed in the detail specification and when requested by a purchaser. After the endurance test the parameters for which variables information is required are the capacitance change, $\tan \delta$ and the insulation resistance.

3.4 Qualification approval

The procedures for qualification approval testing are given in 3.5 of IEC 60384-1.

The schedule to be used for Qualification Approval testing on the basis of lot-by-lot and periodic tests is given in 3.5. The procedure using a fixed sample size schedule is given in 3.4.1 and 3.4.2 below.

3.4.1 Qualification approval on the basis of the fixed sample size procedure

3.4.1.1 Sampling

The fixed sample size procedure is described in 3.5.3 b) of IEC 60384-1. The sample shall be representative of the range of capacitors for which approval is sought. This may or may not be the complete range covered by the detail specification.

The sample shall consist of specimens having the lowest and highest voltages, and for these voltages the lowest and highest capacitances. When there are more than four rated voltages an intermediate voltage shall also be tested. Thus, for the approval of a range, testing is required of either four or six values (capacitance/voltage combinations). When the range consists of less than four values, the number of specimens to be tested shall be that required for four values.

Spare specimens are permitted as follows.

- a) One per value which may be used to replace the permitted defective in Group 0.
- b) One per value which may be used as replacements for specimens which are defective because of incidents not attributable to the manufacturer.

The numbers given in Group 0 assume that all groups are applicable. If this is not so the numbers may be reduced accordingly.

When additional groups are introduced into the Qualification Approval test schedule, the number of specimens required for Group 0 shall be increased by the same number as that required for the additional groups.

Table 1 gives the number of samples to be tested in each group or subgroup together with the permissible number of defectives for qualification approval tests.

3.4.2 Tests

The complete series of tests specified in Table 1 and Table 2 are required for the approval of capacitors covered by one detail specification. The tests of each group shall be carried out in the order given.

The whole sample shall be subjected to the tests of Group 0 and then divided for the other groups.

Specimens found defective during the tests of Group 0 shall not be used for the other groups.

"One non-conforming item" is counted when a capacitor has not satisfied the whole or a part of the tests of a group.

The approval is granted when the number of non-conforming items does not exceed the specified number of permissible non-conforming items for each group or subgroup and the total number of permissible non-conformances.

NOTE Table 1 and Table 2 together form the fixed sample size test schedule, for which Table 1 includes the details for the sampling and permissible defectives for the different tests or groups of tests, whereas Table 2 together with the details of test contained in Clause 4 gives a complete summary of test conditions and performance requirements and indicates where, for example for the test method or conditions of test, a choice has to be made in the detail specification.

The conditions of test and performance requirements for the fixed sample size test schedule shall be identical to those prescribed in the detail specification for quality conformance inspection.

IECNORM.COM: Click to view the full PDF IEC 60384-11:2008

Table 1 – Fixed sample size test plan for qualification approval – Assessment level EZ

Group No.	Test	Subclause of this publication	Number of specimens <i>n</i> ^a	Permissible number of non-conforming items <i>c</i>
0	Visual examination	4.1	108	0
	Dimensions	4.1		
	Capacitance	4.2.2		
	Tangent of loss angle (tan δ)	4.2.3		
	Voltage proof	4.2.1		
	Insulation resistance	4.2.4		
	Spare specimens		12	
1A	Robustness of terminations	4.3	12	0
	Resistance to soldering heat	4.4		
	Component solvent resistance ^b	4.13		
1B	Solderability	4.5	12	0
	Solvent resistance of the marking	4.14		
	Rapid change of temperature	4.6		
	Vibration	4.7		
	Bump or shock ^b	4.8 or 4.9		
1	Climatic sequence	4.10	24	0
2	Damp heat, steady state	4.11	24	0
3	Endurance	4.12	36	0
4	Characteristics depending on temperature ^b	4.2.5	24	0

^a Capacitance/voltage combinations, see 3.4.1.
^b If required in the detail specification.

Table 2 – Test schedule for qualification approval

Subclause number and test ^a	D or ND ^b	Conditions of test ^a	Number of specimens (n) and number of permissible non-conformances (c)	Performance requirements ^a
Group 0	ND		See Table 1	
4.1 Visual examination				As in 4.1 Legible marking and as specified in the detail specification
4.1 Dimensions (detail)				See detail specification
4.2.1 Voltage proof		See detail specification for the method		No breakdown or flashover
4.2.2 Capacitance				Within specified tolerance
4.2.3 Tangent of loss angle ($\tan \delta$)		Frequency: 1 kHz		As in 4.2.3.2
4.2.4 Insulation resistance		See detail specification for the method		As in 4.2.4.2
Group 1A	D		See Table 1	
4.3.1 Initial measurements		Capacitance Tangent of loss angle ($\tan \delta$): For $C_R \leq 10 \mu\text{F}$: at 1 kHz $C_R > 10 \mu\text{F}$: at 50 Hz to 120 Hz		
4.3 Robustness of terminations		Visual examination		No visible damage
4.4 Resistance to soldering heat		No pre-drying See detail specification for the method (1A or 1B)		
4.4.2 Final measurements		Visual examination Capacitance		No visible damage Legible marking $\Delta C/C: \leq 2\%$ of value measured in 4.3.1
4.13 Component solvent resistance (if applicable)		Solvent: ... Solvent temperature: ... Method 2 Recovery: ...		See detail specification

Table 2 (continued)

Subclause number and test ^a	D or ND ^b	Conditions of test ^a	Number of specimens (n) and number of permissible non-conformances (c)	Performance requirements ^a
Group 1B	D		See Table 1	
4.5 Solderability		Without ageing See detail specification for the method		Good tinning as evidenced by free flowing of the solder with wetting of the terminations or solder shall flow within ...s, as applicable
4.14 Solvent resistance of the marking (if applicable)		Solvent: ... Solvent temperature: ... Method 1 Rubbing material: cotton wool Recovery: ...		See detail specification
4.6.1 Initial measurements		Capacitance Tangent of loss angle (tan δ): For $C_R \leq 10 \mu\text{F}$: at 1 kHz $C_R > 10 \mu\text{F}$: at 50 Hz to 120 Hz		
4.6 Rapid change of temperature		T_A = Lower category temperature T_B = Upper category temperature Five cycles Duration $t_1 = 30$ min Visual examination		No visible damage
4.7 Vibration		For mounting method, see detail specification Procedure B4 Frequency range: from ... Hz to ... Hz Amplitude: 0,75 mm or acceleration 98 m/s ² (whichever is the less severe) Total duration: 6 h		
4.7.2 Final inspection		Visual examination		No visible damage
4.8 Bump (or shock, see 4.9)		For mounting method see detail specification Number of bumps: ... Acceleration: ...m/s ² Duration of pulse: ... ms		
4.9 Shock (or bump, see 4.8)		For mounting method see detail specification Acceleration: ...m/s ² Duration of pulse: ... ms		
4.8.3 Final measurements or 4.9.3		Visual examination Capacitance Tangent of loss angle (tan δ)		No visible damage $\Delta C/C \leq 5$ % of value measured in 4.6.1 See detail specification

Table 2 (continued)

Subclause number and test ^a	D or ND ^b	Conditions of test ^a	Number of specimens (n) and number of permissible non-conformances (c)	Performance requirements ^a
Group 1	D		See Table 1	
4.10 Climatic sequence				
4.10.2 Dry heat		Temperature: upper category temperature Duration: 16 h		
4.10.3 Damp heat, cyclic, Test Db, first cycle				
4.10.4 Cold		Temperature: lower category temperature Duration: 2 h		
4.10.5 Low air pressure (if required by the detail specification)		Air pressure: 8,5 kPa (85 mbar)		
4.10.5.3 Intermediate inspection		Visual examination		No permanent breakdown, flashover or harmful deformation of the case
4.10.6 Damp heat, cyclic, Test Db, remaining cycles		Recovery: 1 h to 2 h		
4.10.6.2 Final measurements		Visual examination Capacitance Tangent of loss angle ($\tan \delta$) Insulation resistance		No visible damage Legible marking $\Delta C/C \leq 5\%$ of value measured in 4.4.2, 4.8.3 or 4.9.3 as applicable $\tan \delta \leq 0,01$ or 1,2 times values measured in 4.3.1 or 4.6.1, as applicable, whichever is the greater $\geq 50\%$ of values in 4.2.4.2
Group 2	D		See Table 1	
4.11 Damp heat, steady state				
4.11.1 Initial measurements		Capacitance Tangent of loss angle ($\tan \delta$) For $C_R \leq 10 \mu\text{F}$: at 1 kHz $C_R > 10 \mu\text{F}$: at 50 Hz to 120 Hz		
4.11.3 Final measurements		Visual examination Capacitance Tangent of loss angle ($\tan \delta$) Insulation resistance		No visible damage Legible marking $\Delta C/C \leq 5\%$ of value measured in 4.11.1 $\tan \delta \leq 0,01$ or 1,2 times values measured in 4.11.1, whichever is the greater $\geq 50\%$ of values in 4.2.4.2

Table 2 (continued)

Subclause number and test ^a	D or ND ^b	Conditions of test ^a	Number of specimens (n) and number of permissible non-conformances (c)	Performance requirements ^a
Group 3 4.12 Endurance 4.12.1 Initial measurements 4.12.5 Final measurements	D	Duration: 1 000 h Capacitance Tangent of loss angle (tan δ) For $C_R \leq 10 \mu\text{F}$: at 1 kHz $C_R > 10 \mu\text{F}$: at 50 Hz to 120 Hz Recovery: 1 to 2 h Visual examination Capacitance Tangent of loss angle (tan δ) Insulation resistance	See Table 1 ↓	No visible damage Legible marking $\Delta C/C \leq 5\%$ of value measured in 4.12.1 $\tan \delta \leq 0,01$ or 1,2 times values measured in 4.12.1, whichever is the greater $\geq 50\%$ of values in 4.2.4.2
Group 4 4.2.5 Characteristics depending on temperature (if applicable)	ND	Capacitance	See Table 1 ↓	As in 4.2.5
^a Subclause numbers of test and performance requirements refer to Clause 4.				
^b In this table: D = destructive, ND = non-destructive				

3.5 Quality conformance inspection

3.5.1 Formation of inspection lots

a) Groups A and B inspection

These tests shall be carried out on a lot-by-lot basis.

A manufacturer may aggregate the current production into inspection lots subject to the following safeguards:

- 1) The inspection lot shall consist of structurally similar capacitors (see 3.2).
- 2a) The sample tested shall be representative of the values and dimensions contained in the inspection lot:
 - in relation to their number;
 - with a minimum of five of any one value.
- 2b) If there are less than five of any one value in the sample the basis for the drawing of samples shall be agreed between the manufacturer and the National Supervising Inspectorate.

b) Group C inspection

These tests shall be carried out on a periodic basis.

Samples shall be representative of the current production of the specified periods and shall be divided into high, medium and low voltage ratings. In order to cover the range of approvals in any period one case size shall be tested from each voltage group. In subsequent periods other case sizes and/or voltage ratings in production shall be tested with the aim of covering the whole range.

3.5.2 Test schedule

The schedule for the lot-by-lot and periodic tests for quality conformance inspection is given in Clause 2, Table 4 of the blank detail specification, IEC 60384-11-1.

3.5.3 Delayed delivery

When, according to the procedures of IEC 60384-1, 3.5.3, re-inspection has to be made, solderability and capacitance shall be checked as specified in Group A and B inspection.

3.5.4 Assessment levels

The assessment level(s) given in the blank detail specification shall preferably be selected from the following Table 3 and Table 4.

Table 3 – Lot-by-lot inspection

Inspection subgroup ^b	D ^c		E ^z			F ^c		G ^c	
	IL ^a	AQL ^a %	IL ^a	n ^a	c ^a	IL ^a	AQL ^a %	IL ^a	AQL ^a %
A0			100% ^d						
A1			S-3	e	0				
A2			S-3	e	0				
B1			S-3	e	0				
<p>^a IL = inspection level AQL = acceptable quality level n = sample size c = permissible number of non-conforming items</p> <p>^b The content of the inspection subgroup is described in Clause 2 of the relevant blank detail specification.</p> <p>^c The assessment levels D, F and G are under consideration.</p> <p>^d 100 % testing shall be followed by re-inspection by sampling in order to monitor the outgoing quality level by non-conforming items per million (ppm). The sampling level shall be established by the manufacturer. For the calculation of ppm values, any parametric failure shall be counted as a non-conforming item. If one or more non-conforming items occur in a sample, this lot shall be rejected.</p> <p>^e Number to be tested: sample size as directly allotted to the code letter for IL in Table 2a of IEC 60410 (single sampling plan for normal inspection).</p>									

Table 4 – Periodic tests

Inspection subgroup ^b	D ^c			EZ			F ^c			G ^c		
	<i>p</i> ^a	<i>n</i> ^a	<i>c</i> ^a	<i>p</i> ^a	<i>n</i> ^a	<i>c</i> ^a	<i>p</i> ^a	<i>n</i> ^a	<i>c</i> ^a	<i>p</i> ^a	<i>n</i> ^a	<i>c</i> ^a
C1A				6	5	0						
C1B				6	5	0						
C1				6	10	0						
C2				6	10	0						
C3				6	10	0						
C4				6	10	0						

^a *p* = periodicity in months
^b *n* = sample size
^c *c* = permissible number of non-conforming items

^b The content of the inspection subgroup is described in Clause 2 of the relevant blank detail specification.

^c The assessment levels D, F and G are under consideration.

4 Test and measurement procedures

4.1 Visual examination and check of dimensions

See 4.4 of IEC 60384-1.

4.2 Electrical tests

4.2.1 Voltage proof

See 4.6 of IEC 60384-1, with the following details:

4.2.1.1 Test circuit

The product of R_1 and the rated capacitance C_x shall be smaller than or equal to 1 s and greater than 0,01 s.

R_1 includes the internal resistance of the power supply.

R_p shall limit the discharge current to a value equal to or less than 1 A.

4.2.1.2 The following voltages shall be applied between the measuring points of Table 3 of IEC 60384-1, for a period of 1 min for qualification approval testing and for a period of 1 s for the lot-by-lot quality conformance testing.

Table 5 – Test voltages

Measuring points in accordance with Table 3 of IEC 60384-1	Test voltage
1a)	$2U_R$
1b) and 1c)	$2 U_R$ with a minimum of 200 V

4.2.2 Capacitance

See 4.7 of IEC 60384-1, with the following details:

4.2.2.1 The capacitance shall be measured at, or corrected to, a frequency of 1 000 Hz. For rated capacitance values >10 μF , 50 Hz to 120 Hz may be used.

The applied peak voltage at 1 000 Hz shall not exceed 3 % of the rated voltage, and the applied peak voltage at 50 Hz to 120 Hz shall not exceed 20 % of the rated voltage with a maximum of 100 V (70 V r.m.s.)

4.2.2.2 The capacitance shall be within the specified tolerance.

4.2.3 Tangent of loss angle ($\tan \delta$)

See 4.8 of IEC 60384-1, with the following details:

4.2.3.1 Measuring conditions for measurements at 1 000 Hz

Tan δ shall be measured as follows:

- Frequency: 1 000 Hz.
- Peak voltage: ≤ 3 % of the rated voltage.
- Inaccuracy: $\leq 10 \times 10^{-4}$ (absolute value).

4.2.3.2 Requirement for measurements at 1 000 Hz

Tan δ shall not exceed 10×10^{-4} .

4.2.4 Insulation resistance

See 4.5 of IEC 60384-1, with the following details:

4.2.4.1 Before measurement, the capacitor shall be fully discharged. The product of the resistance of the discharge circuit and the rated capacitance of the capacitor under test shall be $\geq 0,01$ s or any other value prescribed in the detail specification.

4.2.4.2 The measuring voltage shall be in accordance with 4.5.2 of IEC 60384-1.

The voltage shall be applied immediately at the correct value through the internal resistance of the voltage source.

The product of the internal resistance and the rated capacitance of the capacitor shall be smaller than 1 s or any other value prescribed in the detail specification.

The insulation resistance shall meet the following requirements:

Table 6 – Insulation resistance

Measuring points in accordance with Table 3 of IEC 60384-1	Requirements		
	Minimum RC product (R = insulation resistance between the terminations C_R = rated capacitance) s	Minimum insulation resistance between the terminations M Ω	Minimum insulation resistance between terminations and case M Ω
	$C_R > 0,33 \mu\text{F}$	$C_R \leq 0,33 \mu\text{F}$	
1a)	10 000	30 000	–
1b) and 1c)	–	–	3 000

4.2.4.3 When the test is made at a temperature other than 20 °C, the result shall, when necessary, be corrected to 20 °C by multiplying the result of the measurement by the appropriate correction factor. In case of doubt, measurement at 20 °C is decisive. The following correction factors can be considered as an average for polyethylene-terephthalate film dielectric metal foil capacitors:

Table 7 – Correction factor dependent on test temperature

Temperature °C	Correction factor
15	0,79
16	0,83
17	0,87
18	0,91
19	0,95
20	1,00
21	1,05
22	1,10
23	1,15
24	1,20
25	1,26
26	1,32
27	1,38
28	1,45
29	1,52
30	1,59
31	1,66
32	1,74
33	1,82
34	1,91
35	2,00

4.2.5 Characteristics depending on temperature (if required in the detail specification)

See 4.24.1 "Static method" of IEC 60384-1 with the following details:

The capacitance measurements shall be carried out at points b), d) and f).

Table 8 – Characteristics at lower category temperature

Test temperature at point b)	Temperature characteristic of capacitance
-10 °C and -25 °C	$-5 \% \leq \frac{\Delta C}{C} \leq 0 \%$
-40 °C	$-7 \% \leq \frac{\Delta C}{C} \leq 0 \%$
-55 °C	$-10 \% \leq \frac{\Delta C}{C} \leq 0 \%$

Table 9 – Characteristics at upper category temperature

Test temperature at point f)	Temperature characteristic of capacitance
85 °C	$0 \% \leq \frac{\Delta C}{C} \leq 5 \%$
100 °C	$0 \% \leq \frac{\Delta C}{C} \leq 10 \%$
105 °C	$0 \% \leq \frac{\Delta C}{C} \leq 13 \%$
125 °C	$0 \% \leq \frac{\Delta C}{C} \leq 20 \%$

4.3 Robustness of terminations

See 4.13 of IEC 60384-1, with the following details.

4.3.1 Initial measurements

The capacitance shall be measured according to 4.2.2. The tangent of loss angle shall be measured according to 4.2.3.1.

4.4 Resistance to soldering heat

See 4.14 of IEC 60384-1, with the following details:

4.4.1 Conditions

No pre-drying.

4.4.2 Final inspection, measurements and requirements

The capacitors shall be visually examined and measured and shall meet the requirements given in Table 2.

4.5 Solderability

See 4.15 of IEC 60384-1, with the following details.

4.5.1 Test conditions: No ageing.

The requirements for the globule test method shall be prescribed in the detail specification. When neither the solder bath nor the solder globule method is appropriate the soldering iron test shall be used with soldering iron Size A.

4.5.2 The performance requirements are given in Table 2.

4.6 Rapid change of temperature

See 4.16 of IEC 60384-1, with the following details.

4.6.1 Initial measurement

Initial measurements shall be made as prescribed in 4.3.1.

4.6.2 Number of cycles: 5

Duration of exposure at the temperature limits: 30 min.

4.7 Vibration

See 4.17 of IEC 60384-1, with the following details.

4.7.1 Procedure B4 and the following degree of severity of test Fc apply: 0,75 mm displacement or 98 m/s², whichever is the lower amplitude, over one of the following frequency ranges: 10 Hz to 55 Hz, 10 Hz to 500 Hz, 10 Hz to 2 000 Hz. The total duration shall be 6 h.

The detail specification shall specify the frequency range and shall also prescribe the mounting method to be used. For capacitors with axial leads and intended to be mounted by the leads only, the distance between the body and the mounting point shall be 6 mm ± 1 mm.

4.7.2 Final inspection, measurements and requirements

See Table 2.

4.8 Bump

See 4.18 of IEC 60384-1, with the following details:

The detail specification shall state whether the bump or the shock test applies.

4.8.1 Initial measurements

Not required.

4.8.2 Severities

The detail specification shall state which of the following preferred severities applies.

Total number of bumps:	1 000 or 4 000	} or {	100 m/s ²
Acceleration:	400 m/s ²		
Pulse duration:	6 ms		

The detail specification shall also prescribe the mounting method to be used. For capacitors with axial leads and intended to be mounted by the leads only, the distance between the body and the mounting point shall be 6 mm ± 1 mm.

4.8.3 Final inspection, measurements and requirements

The capacitors shall be visually examined and measured and shall meet the requirements given in Table 2.

4.9 Shock

See 4.19 of IEC 60384-1, with the following details:

The detail specification shall state whether the bump or the shock test applies.

4.9.1 Initial measurements

Not required.