

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes –
Part 3-7: Specifications for individual materials – Requirements for rigid laminated sheets based on polyimide resins**

**Matériaux isolants – Stratifiés industriels rigides en planches à base de résines thermodurcissables à usages électriques –
Partie 3-7: Spécifications pour matériaux particuliers – Prescriptions pour stratifiés rigides en planches à base de résine polyimide**



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2009 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch

Tel.: +41 22 919 02 11

Fax: +41 22 919 03 00

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

- Catalogue des publications de la CEI: www.iec.ch/searchpub/cur_fut-f.htm

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

- Just Published CEI: www.iec.ch/online_news/justpub

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

- Electropedia: www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.

- Service Clients: www.iec.ch/webstore/custserv/custserv_entry-f.htm

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: csc@iec.ch

Tél.: +41 22 919 02 11

Fax: +41 22 919 03 00

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes –
Part 3-7: Specifications for individual materials – Requirements for rigid laminated sheets based on polyimide resins**

**Matériaux isolants – Stratifiés industriels rigides en planches à base de résines thermodurcissables à usages électriques –
Partie 3-7: Spécifications pour matériaux particuliers – Prescriptions pour stratifiés rigides en planches à base de résine polyimide**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
INTRODUCTION (to amendment 1).....	5
1 Scope.....	6
2 Normative references.....	6
3 Designation	6
4 Requirements	7
Bibliography	12
Table 1 – Type of industrial rigid laminated sheets based on polyimide resins.....	7
Table 2 – Tolerances on thickness (Test method: see 4.1 of IEC 60893-2)	8
Table 3 – Flatness (Test method: see 4.2 of IEC 60893-2).....	8
Table 4 – Tolerances on width of cut strips (minus tolerances only)	9
Table 5 – Property requirements	10
Table 6 – Electric strength at 90 °C in oil, perpendicular to laminations (1 min proof test or 20 s step-by-step test) (kV/mm)	11

IECNORM.COM : Click to view the full PDF of IEC 60893-3-7:2003+AMD1:2009 CSV

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**INSULATING MATERIALS –
INDUSTRIAL RIGID LAMINATED SHEETS
BASED ON THERMOSETTING RESINS FOR ELECTRICAL PURPOSES –****Part 3-7: Specifications for individual materials –
Requirements for rigid laminated sheets based on polyimide resins**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60893-3-7 has been prepared by subcommittee 15C: Specifications, of IEC technical committee 15: Insulating materials.

This consolidated version of IEC 60893-3-7 consists of the second edition (2003) [documents 15C/1527/FDIS and 15C/1541/RVD] and its amendment 1 (2009) [documents 15/493/CDV and 15/533/RVC].

The technical content is therefore identical to the base edition and its amendment and has been prepared for user convenience.

It bears the edition number 2.1.

A vertical line in the margin shows where the base publication has been modified by amendment 1.

In this revision of the IEC 60893 series of specifications, new material types have been included, changes have been made to the property requirements of some existing types, a new method for testing permittivity and dissipation factor has been added, and all non-specification data for each type has been moved to a new Part 4 document – IEC 60893-4; Typical values.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of the base publication and its amendments will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IECNORM.COM : Click to view the full PDF of IEC 60893-3-7:2003+AMD1:2009 CSV

INTRODUCTION

This part of IEC 60893 is one of a series which deals with industrial rigid laminated sheets based on thermosetting resins for electrical purposes.

This series consists of four parts:

- Part 1: Definitions, designations and general requirements. (IEC 60893-1)
- Part 2: Methods of test (IEC 60893-2)
- Part 3: Specifications for individual materials (IEC 60893-3)
- Part 4: Typical values (IEC 60893-4)

IEC 60893-3-7 contains one of the specification sheets comprising Part 3, as follows:

Sheet 7: Requirements for rigid laminated sheets based on polyimide resins

INTRODUCTION (to amendment 1)

This amendment introduces revised limits for CHARPY and IZOD impact strengths for the requirements of all types of rigid laminated sheets based on polyimide resins. These revised limits are based on the results of round-robin testing.

INSULATING MATERIALS – INDUSTRIAL RIGID LAMINATED SHEETS BASED ON THERMOSETTING RESINS FOR ELECTRICAL PURPOSES –

Part 3-7: Specifications for individual materials – Requirements for rigid laminated sheets based on polyimide resins

1 Scope

This part of IEC 60893 gives the requirements for industrial rigid laminated sheets for electrical purposes based on polyimide resins and different reinforcements.

Applications and distinguishing properties are given in Table 1.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application should be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60893-1, *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 1: Definitions, designations and general requirements*

IEC 60893-2:2003, *Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 2: Methods of test*

3 Designation

The sheets covered by this specification are classified into types, which differ in the reinforcement employed and in their distinguishing properties. The sheets are designated by

- the IEC standard number;
- a two-letter abbreviation, denoting the resin;
- a second two-letter abbreviation denoting the reinforcement;
- a serial number;
- nominal thickness x width x length in mm.

Example of designation: Industrial rigid laminated sheet of type PI GC 301 with a nominal thickness of 10 mm, 500 mm wide, 1 000 mm long.

Sheet IEC 60893-3-7 – PI GC 301 – 10 x 500 x 1 000

The following abbreviations are used in this Part 3 sheet:

<i>Type of resin</i>	<i>Type of reinforcement</i>
PI Polyimide	GC Woven glass cloth

4 Requirements

In addition to the general requirements given in IEC 60893-1, the laminated sheets shall also comply with the dimensional requirements given in Tables 2, 3 and 4 and with the other requirements given in Tables 5, 6 and 7.

**Table 1 – Type of industrial rigid laminated sheets
based on polyimide resins**

Type designation	Applications and distinguishing characteristics ^a
PI GC 301	Electrical and mechanical applications. Very good mechanical and electrical properties at high temperature.
^a It should not be inferred from the contents of Table 1 that laminates of any particular type are necessarily unsuitable for applications other than those listed for them, or that specific laminates will be suitable for all applications within the wide description given.	

Table 2 – Tolerances on thickness
(Test method: see 4.1 of IEC 60893-2)

Where the nominal thickness is not one of the preferred thicknesses listed, then the tolerance for the next highest preferred nominal thickness shall apply.

Nominal thickness mm	Tolerance ±mm
0,8	0,16
1,0	0,18
1,2	0,21
1,5	0,24
2,0	0,28
2,5	0,33
3,0	0,37
4,0	0,45
5,0	0,52
6,0	0,60
8,0	0,72
10,0	0,82
12,0	0,94
14,0	1,02
16,0	1,12
20,0	1,30
25,0	1,50
30,0	1,70
NOTE Other tolerances may be agreed between the supplier and the purchaser.	

Table 3 – Flatness
(Test method: see 4.2 of IEC 60893-2)

Thickness d mm	Length of straight edge mm	
	1 000	500
$3 < d \leq 6$	10	2,5
$6 < d \leq 8$	8	2,0
$8 < d$	6	1,5

**Table 4 – Tolerances on width of cut strips
(minus tolerances only)**

Nominal thickness d mm	Nominal width, all types mm					
	$3 < b \leq 50$	$50 < b \leq 100$	$100 < b \leq 160$	$160 < b \leq 300$	$300 < b \leq 500$	$500 < b \leq 600$
0,8	0,5	0,5	0,5	0,6	1,0	1,0
1,0	0,5	0,5	0,5	0,6	1,0	1,0
1,2	0,5	0,5	0,5	1,0	1,2	1,2
1,5	0,5	0,5	0,5	1,0	1,2	1,2
2,0	0,5	0,5	0,5	1,0	1,2	1,5
2,5	0,5	1,0	1,0	1,5	2,0	2,5
3,0	0,5	1,0	1,0	1,5	2,0	2,5
4,0	0,5	2,0	2,0	3,0	4,0	5,0
5,0	0,5	2,0	2,0	3,0	4,0	5,0

NOTE Unilateral, all-negative tolerances are normally applied to the width of cut strips, and are given in the above table. Other tolerances may be agreed upon between purchaser and supplier.

Table 5 – Property requirements

Property	Test method in IEC 60893-2 Subclause	Unit	Minimum or Maximum	Nominal thickness of sheet to which test is applicable mm	Type	Remarks
					PI GC 301	
Flexural strength	5.1	MPa	Minimum	≥1,5	400 300	Measured at 23 °C ± 2 K Measured at 200 °C ± 5 K after 1 h at 200 °C ± 5 K
Charpy impact strength or Izod impact strength parallel to laminations	5.4.2 or 5.4.3	kJ/m ²	Minimum	≥5	45	Conformance with the requirements for either the Charpy or Izod test constitutes, in this respect, conformance with this specification.
Electric strength at 90 °C in oil perpendicular to laminations	6.1	kV/mm	Minimum	≤3	See Table 6	
Breakdown voltage at 90 °C in oil parallel to laminations	6.1	kV	Minimum	>3	40	
Insulation resistance after immersion in water	6.3	MΩ	Minimum	All	100	
Flammability	7.2	Category		3	HB	The small-scale laboratory test used in this standard for assigning a flammability category is primarily for monitoring consistency of production of laminates. The results so obtained should not in any circumstances be considered as an overall indication of the potential fire hazards presented by these laminates under actual conditions of use.
Water absorption	8.2	mg	Maximum	All	See Table 7	

Table 6 – Electric strength at 90 °C in oil, perpendicular to laminations
(1 min proof test or 20 s step-by-step test)^a (kV/mm)

Type	Mean measured thickness of test specimen ^b mm											
	0,8	0,9	1,0	1,2	1,5	1,8	2,0	2,2	2,4	2,5	2,6	3,0
PI GC 301	15,0	14,6	14,0	13,2	12,0	11,6	11,2	10,8	10,5	10,4	10,2	10,1
												10,0

^a The two tests are alternatives. A material meeting either requirement shall be deemed to comply with the specification with respect to electric strength at 90 °C in oil, perpendicular to laminations.

^b If the arithmetic mean of the measured values of thickness of the test specimen lies between two values of thickness shown in the above table, the limit shall be obtained by interpolation. If the arithmetic mean of the measured values of thickness is below the minimum thickness for which a limit is given, the electric strength limit appropriate to the minimum thickness shall apply. If the nominal thickness is 3 mm and the arithmetic mean measured thickness exceeds 3 mm, the limit for 3 mm shall apply.

Table 7 – Limits for water absorption (mg)

Type	Mean measured thickness of test specimen ^a mm															
	0,8	1,0	1,2	1,5	2,0	2,5	3,0	4,0	5,0	6,0	8,0	10,0	12,0	14,0	16,0	25,0
PI GC 301	60	64	66	71	74	77	80	87	93	100	113	127	140	153	166	227
																250

^a If the arithmetic mean of the measured values of thickness of the test specimen lies between two values of thickness shown in the above table, the limit shall be obtained by interpolation. If the arithmetic mean of the measured values of thickness is below the minimum thickness for which a limit is given, the water absorption limit appropriate to the minimum thickness shall apply. If the nominal thickness is 25 mm and the arithmetic mean measured thickness exceeds 25 mm, the limit for 25 mm shall apply.

^b Sheets of nominal thicknesses greater than 25 mm shall be machined to a relatively smooth surface on one face to a thickness of 22,5 mm ± 0,3 mm.

Bibliography

- [1] IEC 60893-3-1:2003, *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 3-1: Specifications for individual materials – Requirements for types of industrial rigid laminated sheets*
- [2] IEC 60893-4, *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 4: Typical values*

IECNORM.COM : Click to view the full PDF of IEC 60893-3-7:2003+AMD1:2009 CSV

IECNORM.COM : Click to view the full PDF of IEC 60893-3-7:2003+AMD1:2009 CSV

SOMMAIRE

AVANT-PROPOS	15
INTRODUCTION	17
INTRODUCTION (à l'amendement 1)	17
1 Domaine d'application	18
2 Références normatives	18
3 Désignation	18
4 Prescriptions	19
 Bibliographie	 24
 Tableau 1 – Type de stratifiés industriels rigides en planches à base de résine polyimide	 19
Tableau 2 – Tolérances d'épaisseur (Méthode d'essai: voir 4.1 de la CEI 60893-2)	20
Tableau 3 – Planéité (Méthode d'essai: voir 4.2 de la CEI 60893-2)	20
Tableau 4 – Tolérance sur la largeur des bandes coupées (tolérances négatives uniquement)	21
Tableau 5 – Exigences relatives aux propriétés	22
Tableau 6 – Rigidité diélectrique à 90 °C dans l'huile, perpendiculairement au plan de la stratification (essai de tenue 1 min ou méthode des paliers de 20 s) (kV/mm)	23
Tableau 7 – Valeurs limites de l'absorption d'eau (mg)	23

IECNORM.COM : Click to view the full PDF of IEC 60893-3-7:2003+AMD1:2009 CSV

COMMISSION ÉLECTROTECHNIQUE INTERNATIONALE

**MATÉRIAUX ISOLANTS –
STRATIFIÉS INDUSTRIELS RIGIDES EN PLANCHES
À BASE DE RÉSINES THERMODURCISSABLES
À USAGES ÉLECTRIQUES –****Partie 3-7: Spécifications pour matériaux particuliers –
Prescriptions pour stratifiés rigides en planches
à base de résine polyimide**

AVANT-PROPOS

- 1) La Commission Electrotechnique Internationale (CEI) est une organisation mondiale de normalisation composée de l'ensemble des comités électrotechniques nationaux (Comités nationaux de la CEI). La CEI a pour objet de favoriser la coopération internationale pour toutes les questions de normalisation dans les domaines de l'électricité et de l'électronique. A cet effet, la CEI – entre autres activités – publie des Normes internationales, des Spécifications techniques, des Rapports techniques, des Spécifications accessibles au public (PAS) et des Guides (ci-après dénommés "Publication(s) de la CEI"). Leur élaboration est confiée à des comités d'études, aux travaux desquels tout Comité national intéressé par le sujet traité peut participer. Les organisations internationales, gouvernementales et non gouvernementales, en liaison avec la CEI, participent également aux travaux. La CEI collabore étroitement avec l'Organisation Internationale de Normalisation (ISO), selon des conditions fixées par accord entre les deux organisations.
- 2) Les décisions ou accords officiels de la CEI concernant les questions techniques représentent, dans la mesure du possible, un accord international sur les sujets étudiés, étant donné que les Comités nationaux de la CEI intéressés sont représentés dans chaque comité d'études.
- 3) Les Publications de la CEI se présentent sous la forme de recommandations internationales et sont agréées comme telles par les Comités nationaux de la CEI. Tous les efforts raisonnables sont entrepris afin que la CEI s'assure de l'exactitude du contenu technique de ses publications; la CEI ne peut pas être tenue responsable de l'éventuelle mauvaise utilisation ou interprétation qui en est faite par un quelconque utilisateur final.
- 4) Dans le but d'encourager l'uniformité internationale, les Comités nationaux de la CEI s'engagent, dans toute la mesure possible, à appliquer de façon transparente les Publications de la CEI dans leurs publications nationales et régionales. Toutes divergences entre toutes Publications de la CEI et toutes publications nationales ou régionales correspondantes doivent être indiquées en termes clairs dans ces dernières.
- 5) La CEI elle-même ne fournit aucune attestation de conformité. Des organismes de certification indépendants fournissent des services d'évaluation de conformité et, dans certains secteurs, accèdent aux marques de conformité de la CEI. La CEI n'est responsable d'aucun des services effectués par les organismes de certification indépendants.
- 6) Tous les utilisateurs doivent s'assurer qu'ils sont en possession de la dernière édition de cette publication.
- 7) Aucune responsabilité ne doit être imputée à la CEI, à ses administrateurs, employés, auxiliaires ou mandataires, y compris ses experts particuliers et les membres de ses comités d'études et des Comités nationaux de la CEI, pour tout préjudice causé en cas de dommages corporels et matériels, ou de tout autre dommage de quelque nature que ce soit, directe ou indirecte, ou pour supporter les coûts (y compris les frais de justice) et les dépenses découlant de la publication ou de l'utilisation de cette Publication de la CEI ou de toute autre Publication de la CEI, ou au crédit qui lui est accordé.
- 8) L'attention est attirée sur les références normatives citées dans cette publication. L'utilisation de publications référencées est obligatoire pour une application correcte de la présente publication.
- 9) L'attention est attirée sur le fait que certains des éléments de la présente Publication de la CEI peuvent faire l'objet de droits de propriété intellectuelle ou de droits analogues. La CEI ne saurait être tenue pour responsable de ne pas avoir identifié de tels droits de propriété et de ne pas avoir signalé leur existence.

La Norme internationale CEI 60893-3-7 a été établie par le sous-comité 15C: Spécifications, du comité d'études 15 de la CEI: Matériaux isolants.

Cette version consolidée de la CEI 60893-3-7 comprend la deuxième édition (2003) [documents 15C/1527/FDIS et 15C/1541/RVD] et son amendement 1 (2009) [documents 15/493/CDV et 15/533/RVC].

Le contenu technique de cette version consolidée est donc identique à celui de l'édition de base et à son amendement; cette version a été préparée par commodité pour l'utilisateur.

Elle porte le numéro d'édition 2.1.

Une ligne verticale dans la marge indique où la publication de base a été modifiée par l'amendement 1.

Dans cette révision de la série de spécifications CEI 60893, de nouveaux matériaux ont été introduits, des modifications ont été faites aux prescriptions pour les propriétés de certains types existants, une nouvelle méthode pour l'essai de la permittivité et du facteur de dissipation a été ajoutée et, pour chaque type, les valeurs n'étant pas des spécifications ont été déplacées dans un nouveau document de Partie 4 – CEI 60893-4: Valeurs typiques.

Cette publication a été rédigée selon les Directives ISO/CEI, Partie 2.

Le comité a décidé que le contenu de la publication de base et de ses amendements ne sera pas modifié avant la date de maintenance indiquée sur le site web de la CEI sous "<http://webstore.iec.ch>" dans les données relatives à la publication recherchée. A cette date, la publication sera

- reconduite,
- supprimée,
- remplacée par une édition révisée, ou
- amendée.

IECNORM.COM : Click to view the full PDF of IEC 60893-3-7:2003+AMD1:2009 CSV

INTRODUCTION

La présente partie de la CEI 60893 est l'une des normes constituant une série traitant des stratifiés industriels rigides en planches à base de résines thermodurcissables à usages électriques.

Cette série comporte quatre parties:

Partie 1: Définitions, désignations et prescriptions générales (CEI 60893-1)

Partie 2: Méthodes d'essai (CEI 60893-2)

Partie 3: Spécifications pour matériaux particuliers (CEI 60893-3)

Partie 4: Valeurs typiques (CEI 60893-4)

La CEI 60893-3-7 comprend une des feuilles de spécifications qui composent la Partie 3 comme suit:

Feuille 7: Prescriptions pour stratifiés rigides en planches à base de résine polyimide.

INTRODUCTION (à l'amendement 1)

Cet amendement introduit une révision des limites des résistances au choc CHARPY et IZOD pour les exigences de tous les types de stratifiés rigides en planches à base de résine polyimide. Ces révisions de limites sont fondées sur les résultats des essais inter-laboratoires.

MATÉRIAUX ISOLANTS – STRATIFIÉS INDUSTRIELS RIGIDES EN PLANCHES À BASE DE RÉSINES THERMODURCISSABLES À USAGES ÉLECTRIQUES –

Partie 3-7: Spécifications pour matériaux particuliers – Prescriptions pour stratifiés rigides en planches à base de résine polyimide

1 Domaine d'application

La présente partie de la CEI 60893-3-7 donne les prescriptions pour les stratifiés industriels rigides en planches à usages électriques, à base de résine polyimide et de différents renforts.

Leurs applications et propriétés distinctives sont indiquées au Tableau 1.

Les matériaux conformes à la présente spécification satisfont aux niveaux de performances établis. Cependant, il convient que le choix d'un matériau, par un utilisateur, pour une application spécifique, soit fondé sur les prescriptions réelles nécessaires pour obtenir les performances satisfaisantes pour cette application, et qu'il ne soit pas fondé sur cette seule spécification.

2 Références normatives

Les documents de référence suivants sont indispensables pour l'application du présent document. Pour les références datées, seule l'édition citée s'applique. Pour les références non datées, la dernière édition du document de référence s'applique (y compris les éventuels amendements).

CEI 60893-1, *Matériaux isolants – Stratifiés industriels rigides en planches à base de résines thermodurcissables à usages électriques – Partie 1: Définitions, désignations et prescriptions générales*

CEI 60893-2:2003, *Stratifiés industriels rigides en planches à base de résines thermodurcissables à usages électriques – Partie 2: Méthodes d'essai*

3 Désignation

Les planches faisant l'objet de cette spécification sont classées en types, qui diffèrent par les matériaux de renfort utilisés et par leurs propriétés distinctives. Les planches sont désignées par:

- la référence de la norme CEI;
- une abréviation de deux lettres indiquant la résine;
- une seconde abréviation de deux lettres, indiquant le matériau de renfort;
- un numéro de série;
- l'épaisseur nominale x largeur x longueur en mm.

Exemple de désignation: Planche de stratifié industriel rigide du type PI GC 301 d'une épaisseur nominale de 10 mm, d'une largeur de 500 mm et d'une longueur de 1 000 mm.

Planche IEC 60893-3-7 – PI GC 301 – 10 × 500 × 1 000

Les abréviations suivantes sont utilisées dans la présente feuille de cette Partie 3:

<i>Types de résine</i>		<i>Type de matériaux de renfort</i>	
PI	Polyimide	GC	Tissu de verre

4 Prescriptions

En plus des prescriptions générales données dans la CEI 60893-1, les stratifiés en planches doivent être conformes aux prescriptions dimensionnelles données dans les Tableaux 2, 3 et 4 et aux autres prescriptions données dans les tableaux 5, 6 et 7.

**Tableau 1 – Type de stratifiés industriels rigides en planches
à base de résine polyimide**

Désignation du type	Applications et propriétés distinctives ^a
PI GC 301	Applications électriques et mécaniques. Très bonnes propriétés mécaniques et électriques à haute température
^a Le contenu du Tableau 1 n'entraîne pas obligatoirement que les stratifiés d'un type particulier sont nécessairement impropres à des applications autres que celles indiquées en regard, ni que des stratifiés particuliers conviendront à toutes les applications données dans le cadre des descriptions générales fournies ci-dessus.	

Tableau 2 – Tolérances d'épaisseur
(Méthode d'essai: voir 4.1 de la CEI 60893-2)

Si l'épaisseur nominale n'est pas l'une des épaisseurs nominales préférentielles de la liste, les tolérances à appliquer doivent alors être celles qui seraient appliquées à l'épaisseur préférentielle immédiatement supérieure.

Epaisseur nominale mm	Tolérance ± mm
0,8	0,16
1,0	0,18
1,2	0,21
1,5	0,24
2,0	0,28
2,5	0,33
3,0	0,37
4,0	0,45
5,0	0,52
6,0	0,60
8,0	0,72
10,0	0,82
12,0	0,94
14,0	1,02
16,0	1,12
20,0	1,30
25,0	1,50
30,0	1,70

NOTE D'autres tolérances peuvent être retenues par accord entre le fournisseur et l'acheteur.

Tableau 3 – Planéité
(Méthode d'essai: voir 4.2 de la CEI 60893-2)

Epaisseur d mm	Longueur de la règle mm	
	1 000	500
3 $< d \leq 6$	10	2,5
6 $< d \leq 8$	8	2,0
8 $< d$	6	1,5