

# INTERNATIONAL STANDARD

**Multicore and symmetrical pair/quad cables for digital communications –  
Part 8: Symmetrical pair/quad cables with transmission characteristics up to  
1 200 MHz – Work area wiring – Sectional specification**

IECNORM.COM : Click to view the full PDF of IEC 61156-8:2009



## THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2009 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland  
Email: [inmail@iec.ch](mailto:inmail@iec.ch)  
Web: [www.iec.ch](http://www.iec.ch)

### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

### About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: [www.iec.ch/searchpub](http://www.iec.ch/searchpub)

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: [www.iec.ch/online\\_news/justpub](http://www.iec.ch/online_news/justpub)

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: [www.electropedia.org](http://www.electropedia.org)

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: [www.iec.ch/webstore/custserv](http://www.iec.ch/webstore/custserv)

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: [csc@iec.ch](mailto:csc@iec.ch)  
Tel.: +41 22 919 02 11  
Fax: +41 22 919 03 00

IECNORM.COM : Click to view the full PDF of IEC 61156-8:2009

# INTERNATIONAL STANDARD

---

**Multicore and symmetrical pair/quad cables for digital communications –  
Part 8: Symmetrical pair/quad cables with transmission characteristics up to  
1 200 MHz – Work area wiring – Sectional specification**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

PRICE CODE

Q

---

ICS 33.120.20

ISBN 978-2-88910-428-4

## CONTENTS

FOREWORD.....	4
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions .....	6
4 Installation considerations.....	7
4.1 Installation conditions .....	7
4.2 Climatic conditions.....	7
5 Materials and cable construction .....	7
5.1 General remarks.....	7
5.2 Cable construction.....	7
5.2.1 Conductor.....	7
5.2.2 Insulation.....	7
5.2.3 Cable element .....	7
5.2.4 Cable make-up .....	8
5.2.5 Screening of cable core .....	8
5.2.6 Sheath.....	8
5.2.7 Identification .....	8
5.2.8 Finished cable .....	8
6 Characteristics and requirements.....	8
6.1 General remarks.....	8
6.2 Electrical characteristics .....	9
6.2.1 Conductor resistance .....	9
6.2.2 Resistance unbalance.....	9
6.2.3 Dielectric strength.....	9
6.2.4 Insulation resistance.....	9
6.2.5 Mutual capacitance.....	9
6.2.6 Capacitance unbalance.....	9
6.2.7 Transfer impedance.....	9
6.2.8 Coupling attenuation .....	10
6.2.9 Current-carrying capacity .....	10
6.2.10 Shield resistance .....	10
6.3 Transmission characteristics.....	10
6.3.1 Velocity of propagation (phase velocity) .....	10
6.3.2 Phase delay and differential delay (delay skew).....	10
6.3.3 Attenuation .....	11
6.3.4 Unbalance attenuation .....	11
6.3.5 Near-end crosstalk ( <i>NEXT</i> ).....	11
6.3.6 Far-end crosstalk ( <i>FEXT</i> ) .....	12
6.3.7 Alien (exogenous) near-end crosstalk .....	12
6.3.8 Alien (exogenous) far-end crosstalk .....	12
6.3.9 Alien (exogenous) crosstalk of bundled cables .....	12
6.3.10 Impedance.....	12
6.3.11 Return loss ( <i>RL</i> ).....	12
6.4 Mechanical and dimensional characteristics and requirements .....	13
6.4.1 Dimensional requirements.....	13
6.4.2 Elongation at break of the conductors .....	13

6.4.3	Tensile strength of the insulation.....	13
6.4.4	Elongation at break of the insulation.....	13
6.4.5	Adhesion of the insulation to the conductor .....	13
6.4.6	Elongation at break of the sheath .....	13
6.4.7	Tensile strength of the sheath .....	13
6.4.8	Crush test of the cable .....	13
6.4.9	Impact test of the cable.....	13
6.4.10	Bending under tension .....	13
6.4.11	Repeated bending of the cable.....	13
6.4.12	Tensile performance of the cable .....	13
6.4.13	Shock test of the cable.....	14
6.4.14	Bump test of the cable .....	14
6.4.15	Vibration test of a cable .....	14
6.5	Environmental characteristics .....	14
6.5.1	Shrinkage of insulation.....	14
6.5.2	Wrapping test of insulation after thermal ageing .....	14
6.5.3	Bending test of insulation at low temperature .....	14
6.5.4	Elongation at break of the sheath after ageing.....	14
6.5.5	Tensile strength of the sheath after ageing.....	14
6.5.6	Sheath pressure test at high temperature.....	14
6.5.7	Cold bend test of the cable .....	14
6.5.8	Heat shock test.....	14
6.5.9	Damp heat steady state .....	14
6.5.10	Solar radiation .....	15
6.5.11	Solvents and contaminating fluids .....	15
6.5.12	Salt mist and sulphur dioxide .....	15
6.5.13	Water immersion .....	15
6.5.14	Hygroscopicity .....	15
6.5.15	Wicking .....	15
6.5.16	Flame propagation characteristics of a single cable.....	15
6.5.17	Flame propagation characteristics of bunched cables.....	15
6.5.18	Halogen gas evolution.....	15
6.5.19	Smoke generation.....	15
6.5.20	Toxic gas emission .....	15
6.5.21	Integrated fire test .....	15
7	Introduction to the blank detail specification .....	16
	Bibliography.....	17
	Table 1 – Transfer impedance.....	10
	Table 2 – Coupling attenuation.....	10
	Table 3 – Attenuation, constant values .....	11
	Table 4 – Return loss ( <i>RL</i> ).....	12

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

---

**MULTICORE AND SYMMETRICAL PAIR/QUAD CABLES  
FOR DIGITAL COMMUNICATIONS –**
**Part 8: Symmetrical pair/quad cables  
with transmission characteristics up to 1 200 MHz –  
Work area wiring – Sectional specification**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61156-8 has been prepared by subcommittee 46C: Wires and symmetric cables, of IEC technical committee 46: Cables, wires, waveguides, R.F. connectors, R.F. and microwave passive components and accessories.

The text of this standard is based on the following documents:

FDIS	Report on voting
46C/887/FDIS	46C/894/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 61156 series, under the general title: *Multicore and symmetrical pair/quad cables for digital communications*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

The contents of the corrigendum of July 2009 have been included in this copy.

IECNORM.COM : Click to view the full PDF of IEC 61156-8:2009

## MULTICORE AND SYMMETRICAL PAIR/QUAD CABLES FOR DIGITAL COMMUNICATIONS –

### Part 8: Symmetrical pair/quad cables with transmission characteristics up to 1 200 MHz – Work area wiring – Sectional specification

#### 1 Scope

This sectional specification relates to IEC 61156-1 and IEC 61156-7. The cables described herein are specified up to 1 200 MHz and are specifically designed to build patch, equipment, and work area cables as defined in ISO/IEC 11801 and ISO/IEC 15018.

It covers a cable having four individually screened (STP) pairs. The cable may be provided with a common screen over the cable core. The transmission characteristics are specified for a frequency range 4 MHz to 1 200 MHz and at 20 °C.

These cables can be used for various communication channels which use as many as four pairs simultaneously. In this sense, this sectional specification provides the cable characteristics required by system developers to evaluate new systems.

The cables covered by this sectional specification are intended to operate with voltages and currents normally encountered in communication systems. These cables are not intended to be used in conjunction with low impedance sources, for example the electric power supplies of public utility mains.

#### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60304, *Standard colours for insulation for low-frequency cables and wires*

IEC 61156-1:2007, *Multicore and symmetrical pair/quad cables for digital communications – Part 1: Generic specification*

IEC 61156-7, *Multicore and symmetrical pair/quad cables for digital communications – Part 7: Symmetrical pair cables with transmission characteristics up to 1 200 MHz – Sectional specification for digital and analog communication cables*

#### 3 Terms and definitions

For the purposes of this document, the terms and definitions defined in IEC 61156-1 apply.

## 4 Installation considerations

### 4.1 Installation conditions

Installation considerations are defined in Clause 4 of IEC 61156-1.

### 4.2 Climatic conditions

Under static conditions, the cables shall operate in the temperature range from  $-20\text{ °C}$  to  $+60\text{ °C}$ . The temperature dependence of the cables is specified, and should be taken into account for the design of an actual cabling system.

## 5 Materials and cable construction

### 5.1 General remarks

The choice of materials and cable construction shall be suitable for the intended application and installation of the cable. Particular care shall be taken to meet any special requirements for the fire performance (such as burning properties, smoke generation, evolution of halogen gas, etc.).

### 5.2 Cable construction

The cable construction shall be in accordance with the details and dimensions given in the relevant detail specification.

#### 5.2.1 Conductor

The conductor shall be solid or stranded annealed copper conductor, in accordance with IEC 61156-1 and shall have a nominal diameter between 0,4 mm to 0,65 mm. The stranded conductor should have preferably seven strands. Higher conductor diameters may be used if compatible with the connecting hardware.

#### 5.2.2 Insulation

The conductor shall be insulated with a suitable thermoplastic material. Examples of suitable materials are

- polyolefin;
- fluoropolymer;
- low-smoke zero-halogen thermoplastic material.

The insulation may be solid or cellular with or without a solid dielectric skin. The insulation shall be continuous and shall have a thickness such that the completed cable meets the specified requirements.

The insulation colour code is not specified but shall be indicated in the relevant detail specification. The colours shall be readily identifiable and shall correspond reasonably with the standard colours shown in IEC 60304.

NOTE It is acceptable to mark or stripe the "a" wire with the colour of the "b" wire to facilitate pair identification.

#### 5.2.3 Cable element

The cable element shall be screened pair or quad adequately twisted.

The screen of the cable element shall be in accordance with 5.2.3.1 of IEC 61156-1.

#### 5.2.4 Cable make-up

A spacer may be used to separate the cable elements. The cable elements, including spacers, shall be assembled to form the cable core.

The core of the cable may be wrapped with a protective layer of non-hygroscopic and not-wicking material.

#### 5.2.5 Screening of cable core

When required by the relevant detail specification, a screen for the cable core shall be provided.

The screen shall be in accordance with 5.2.5 of IEC 61156-1.

#### 5.2.6 Sheath

The sheath material shall consist of a suitable thermoplastic material.

Examples of suitable materials are

- polyolefin;
- PVC;
- fluoropolymer;
- low-smoke zero-halogen thermoplastic material.

The sheath shall be continuous, having a thickness as uniform as possible. A non-metallic ripcord may be provided. When provided, the ripcord shall be non-hygroscopic and not-wicking.

The colour of the sheath is not specified, but it shall be stated in the relevant detail specification.

#### 5.2.7 Identification

Each length of cable shall be identified as to the manufacturer, and when required, the year of manufacture, using one of the following methods:

- a) appropriately coloured threads or tapes;
- b) with a printed tape;
- c) printing on the cable core wrapping;
- d) marking on the sheath.

Additional markings, such as length marking, etc., are permitted. If used, such markings shall refer to this specification.

#### 5.2.8 Finished cable

The finished cable shall be adequately protected for storage and shipment.

### 6 Characteristics and requirements

#### 6.1 General remarks

This clause lists the characteristics and minimum requirements of a cable complying with this sectional specification. Test methods shall be in accordance with Clause 6 of IEC 61156-1.

All the tests shall be carried out on a cable length of 100 m, unless otherwise specified.

## 6.2 Electrical characteristics

The tests shall be carried out on a cable length of not less than 100 m, unless otherwise specified.

### 6.2.1 Conductor resistance

The maximum resistance shall not exceed 14,5  $\Omega$  for 100 m of cable.

### 6.2.2 Resistance unbalance

#### 6.2.2.1 Resistance unbalance within a pair

The resistance unbalance shall not exceed 1,5 %.

#### 6.2.2.2 Resistance unbalance between pairs

The pair-to-pair resistance unbalance shall not exceed 4 %.

### 6.2.3 Dielectric strength

There shall be no failures when a test is performed on conductor/conductor and conductor/screen with 1,0 kV d.c. for 1 min or, alternately, with 2,5 kV d.c. for 2 s. An a.c. voltage may be used. The a.c. voltage levels in these cases shall be 0,7 kV a.c. for 1 min or, alternately, 1,7 kV a.c. for 2 s.

### 6.2.4 Insulation resistance

The test shall be performed on

- conductor/conductor;
- conductor/screen.

The minimum insulation resistance at 20 °C shall not be less than 5 000 M $\Omega$ ·m.

### 6.2.5 Mutual capacitance

The mutual capacitance is not specified but may be indicated in the relevant detail specification.

### 6.2.6 Capacitance unbalance

The maximum capacitance unbalance pair to ground shall not exceed 1 200 pF/km at a frequency of 1 kHz.

### 6.2.7 Transfer impedance

The transfer impedance shall not exceed the values shown in Table 1 at the discrete frequencies indicated.

**Table 1 – Transfer impedance**

Frequency MHz	Maximum surface transfer impedance mΩ/m
1	10
10	10
30	30
100	60

**6.2.8 Coupling attenuation**

When measured using the absorbing clamp method, the coupling attenuation in the frequency range from  $f = 30$  MHz to 1 200 MHz shall be equal to or greater than the values indicated in Table 2.

**Table 2 – Coupling attenuation**

Frequency range MHz	Coupling attenuation dB
30 to 100	≥85,0
100 to 1 200	≥85,0 – 20 × log <sub>10</sub> (f/100)

**6.2.9 Current-carrying capacity**

The maximum current-carrying capacity is not specified but may be indicated in the relevant detail specification.

**6.2.10 Shield resistance**

The d.c. resistance of the individual screens or an overall screen is not specified but may be indicated in the relevant detail specification.

**6.3 Transmission characteristics**

All the tests shall be carried out on a cable length of 50 m, unless otherwise specified.

**6.3.1 Velocity of propagation (phase velocity)**

The requirement is not specified but may be indicated in the relevant detail specification.

**6.3.2 Phase delay and differential delay (delay skew)**

The phase delay  $\tau$  shall be less than or equal to

$$\tau = 500 + \frac{36}{\sqrt{f}} \quad (\text{ns}/100 \text{ m}) \quad (1)$$

where

$\tau$  is the phase delay in ns/100 m;

$f$  is the frequency in MHz.

When the delay is measured at  $(10 \pm 2) ^\circ\text{C}$  and  $(40 \pm 1) ^\circ\text{C}$ , the maximum delay skew between any two pairs at a given temperature shall not be greater than 25 ns/100 m in the frequency range from 4 MHz to 1 200 MHz.

The differential delay (delay skew) between any two pairs due to temperature shall not vary by more than  $\pm 10$  ns/100 m over the temperature range from  $-20 ^\circ\text{C}$  to  $+60 ^\circ\text{C}$ .

### 6.3.3 Attenuation

#### 6.3.3.1 General figures

The maximum attenuation  $\alpha$  of any pair in the frequency range indicated in Table 2 shall not exceed the value obtained from equation (2) using the corresponding values of the constants given in Table 3.

$$\alpha = a \times \sqrt{f} + b \times f + \frac{c}{\sqrt{f}} \quad (\text{dB}/100 \text{ m}) \quad (2)$$

**Table 3 – Attenuation, constant values**

Frequency range MHz	Constants		
	a	B	c
4 – 1 200	2,70	0,015	0,3

#### 6.3.3.2 Attenuation at elevated operating temperature

The increase in maximum attenuation requirement obtained from equation (2) due to elevated temperature shall be 0,2 %/ $^\circ\text{C}$  for screened cables.

#### 6.3.4 Unbalance attenuation

The minimum unbalance attenuation near-end (transverse conversion loss or *TCL*) shall be equal to or greater than the value obtained from equation (3) for the frequency range 1 MHz to 200 MHz.

NOTE The need for *TCL* values above 200 MHz is under consideration.

$$TCL = 40,0 - 10 \times \log_{10}(f) \quad (\text{dB}) \quad (3)$$

The minimum equal level unbalance attenuation far end (equal level transverse conversion transfer loss or *EL TCTL*) shall be equal to or greater than the value obtained from equation (4) for all frequencies in the range from 1 MHz to 30 MHz.

The formula for the *EL TCTL* is

$$EL \ TCTL = 35,0 - 20 \times \log_{10}(f) \quad (\text{dB}) \quad (4)$$

#### 6.3.5 Near-end crosstalk (*NEXT*)

The worst pair power sum near-end crosstalk, *PS NEXT*, of any pair in the frequency range 4 MHz to 1 200 MHz shall be equal to or greater than the value obtained from equation (5).

$$PS \ NEXT(f) = 103,0 - 15 \times \log_{10}(f) \quad (\text{dB}) \quad (5)$$

For those frequencies where the calculated value of *PS NEXT* is greater than 75 dB, the requirement shall be 75 dB.

The minimum pair-to-pair NEXT for any pair combination shall be at least 3 dB better than the *PS NEXT* for any pair.

### 6.3.6 Far-end crosstalk (*FEXT*)

The worst pair power sum equal level far-end crosstalk, *PS EL FEXT*, of any pair in the frequency range 4 MHz to 1 200 MHz shall be not less than the value obtained from equation (6).

$$PS\ EL\ FEXT(f) = 91,0 - 20 \times \log_{10}(f) \quad (\text{dB for 100 m}) \quad (6)$$

For those frequencies where the calculated value of *PS EL FEXT* is greater than 75 dB, the requirement shall be 75 dB.

The minimum pair-to-pair *EL FEXT* for any pair combination shall be at least 3 dB better than the *PS EL FEXT* for any pair.

### 6.3.7 Alien (exogenous) near-end crosstalk

Generally proven by design.

### 6.3.8 Alien (exogenous) far-end crosstalk

Generally proven by design.

### 6.3.9 Alien (exogenous) crosstalk of bundled cables

The minimum requirement is not specified but it should be stated in the relevant detail specification.

### 6.3.10 Impedance

The mean characteristic impedance shall be within  $\pm 5\%$  of the requested nominal impedance at 100 MHz.

### 6.3.11 Return loss (*RL*)

The minimum return loss of any pair in the frequency 1 MHz to 1 200 MHz shall be equal to or greater than the values obtained from Table 4.

**Table 4 – Return loss (*RL*)**

Frequency range MHz	Return loss dB
4 to 10	$20,0 + 5 \cdot \log_{10}(f)$
10 to 20	25,0
20 to 250	$25,0 - 8,6 \cdot \log_{10}(f/20)$
250 to 600	15,6
600 to 1 200	$15,6 - 10 \cdot \log_{10}(f/600)$

## **6.4 Mechanical and dimensional characteristics and requirements**

### **6.4.1 Dimensional requirements**

The overall diameter of insulation, the nominal thickness of the sheath and the maximum overall diameter of the sheath are not specified, but shall be indicated in the relevant detail specification.

### **6.4.2 Elongation at break of the conductors**

The minimum elongation of the conductor shall not be less than 8 %.

### **6.4.3 Tensile strength of the insulation**

The tensile strength of the insulation is not specified, but may be specified in the relevant detail specification.

### **6.4.4 Elongation at break of the insulation**

The minimum value of the elongation at break of the insulation shall not be less than 100 %.

### **6.4.5 Adhesion of the insulation to the conductor**

The adhesion of the insulation to the conductor is not specified, but may be specified in the relevant detail specification.

### **6.4.6 Elongation at break of the sheath**

The minimum value of the elongation at break of the sheath shall not be less than 100 %.

### **6.4.7 Tensile strength of the sheath**

The minimum tensile strength of the sheath shall not be less than 9 MPa.

### **6.4.8 Crush test of the cable**

The minimum force shall be 1 000 N.

### **6.4.9 Impact test of the cable**

The impact resistance of the cable is not specified but shall be indicated in the relevant detail specification.

### **6.4.10 Bending under tension**

The bending performance of the cable is not specified but shall be indicated in the relevant detail specification.

### **6.4.11 Repeated bending of the cable**

The cable shall withstand 500 cycles without cracking of the insulation or sheath or loss of continuity of the metallic components.

### **6.4.12 Tensile performance of the cable**

The tensile strength of the cable is not specified but may be indicated in the relevant detail specification.

**6.4.13 Shock test of the cable**

Not applicable.

**6.4.14 Bump test of the cable**

Not applicable.

**6.4.15 Vibration test of a cable**

Not applicable.

**6.5 Environmental characteristics**

**6.5.1 Shrinkage of insulation**

When tested at  $(100 \pm 2)$  °C for 1 h, the shrinkage of the insulation shall not exceed 5 %. The length of the sample shall be 150 mm, and the shrink-back shall be measured as the sum from both ends.

**6.5.2 Wrapping test of insulation after thermal ageing**

Not applicable.

**6.5.3 Bending test of insulation at low temperature**

The bending test of the insulated conductor shall be carried out at  $(-20 \pm 2)$  °C. The mandrel diameter shall be 6 mm. There shall be no cracks in the insulation.

**6.5.4 Elongation at break of the sheath after ageing**

The ageing regime shall be 7 days at  $(100 \pm 2)$  °C. The tensile strength shall not be less than 50 % of the unaged value.

**6.5.5 Tensile strength of the sheath after ageing**

The ageing regime shall be 7 days at  $(100 \pm 2)$  °C. The elongation shall not be less than 70 % of the unaged value.

**6.5.6 Sheath pressure test at high temperature**

Not applicable.

**6.5.7 Cold bend test of the cable**

The bending test shall be carried out at  $(-20 \pm 2)$  °C. The mandrel diameter shall be eight times the overall diameter of the cable. There shall be no cracks in the sheath.

**6.5.8 Heat shock test**

Not applicable.

**6.5.9 Damp heat steady state**

Not applicable.

**6.5.10 Solar radiation**

The requirement is not specified but it may be specified in the relevant detail specification.

**6.5.11 Solvents and contaminating fluids**

The requirement is not specified but it may be specified in the relevant detail specification.

**6.5.12 Salt mist and sulphur dioxide**

Not applicable.

**6.5.13 Water immersion**

Not applicable.

**6.5.14 Hygroscopicity**

The amount of moisture gained shall not exceed 1 % by weight.

**6.5.15 Wicking**

The test solution shall not wet the filter paper at the end of 6 h.

**6.5.16 Flame propagation characteristics of a single cable**

When required, the test shall be performed in accordance with IEC 61156-1.

**6.5.17 Flame propagation characteristics of bunched cables**

When required, the test shall be performed in accordance with IEC 61156-1.

**6.5.18 Halogen gas evolution**

When required, the test shall be performed in accordance with IEC 61156-1.

**6.5.19 Smoke generation**

When required, the test shall be performed in accordance with IEC 61156-1.

**6.5.20 Toxic gas emission**

When required, the test shall be performed in accordance with IEC 61156-1.

**6.5.21 Integrated fire test**

When required, the test shall be performed in accordance with IEC 61156-1.