

INTERNATIONAL STANDARD

**Coaxial communication cables –
Part 1-305: Mechanical test methods – Solderability and resistance to soldering**

IECNORM.COM : Click to view the full PDF of IEC 61196-1-305:2015



THIS PUBLICATION IS COPYRIGHT PROTECTED
Copyright © 2015 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in 15 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

More than 60 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

IECNORM.COM : Click to view the full text of IEC Standard IEC 6196-1-305:2015



IEC 61196-1-305

Edition 1.0 2015-08

INTERNATIONAL STANDARD

**Coaxial communication cables –
Part 1-305: Mechanical test methods – Solderability and resistance to soldering**

IECNORM.COM : Click to view the full PDF of IEC 61196-1-305:2015

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 33.120.10

ISBN 978-2-8322-2853-1

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD	3
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Solderability	5
4.1 Procedure	5
4.2 Test report	5
4.3 Requirements	5
5 Resistance to soldering	6
5.1 Procedure	6
5.2 Test report	6
5.3 Requirements	6

IECNORM.COM : Click to view the full PDF of IEC 61196-1-305:2015

INTERNATIONAL ELECTROTECHNICAL COMMISSION

COAXIAL COMMUNICATION CABLES –**Part 1-305: Mechanical test methods –
Solderability and resistance to soldering**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61196-1-305 has been prepared by subcommittee 46A: Coaxial cables, of IEC technical committee 46: Cables, wires, waveguides, R.F. connectors, R.F. and microwave passive components and accessories.

The text of this standard is based on the following documents:

FDIS	Report on voting
46A/1261A/FDIS	46A/1266/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This standard is intended to be read in conjunction with IEC 61196-1. It is based on the second edition (2005) of that standard.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 61196 series published under the general title *Coaxial communication cables* can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IECNORM.COM : Click to view the full PDF of IEC 61196-1-305:2015

COAXIAL COMMUNICATION CABLES –

Part 1-305: Mechanical test methods – Solderability and resistance to soldering

1 Scope

This part of IEC 61196 applies to coaxial communication cables. It specifies the test methods to determine solderability and the resistance to soldering of inner and outer conductors of cables used in analogue and digital communication systems. Resistance to soldering details the test method to determine the dimensional stability of cable components after soldering.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 61196-1, *Coaxial communication cables – Part 1: Generic specification – General, definitions and requirements*

IEC 60068-2-20, *Environmental testing – Part 2-20: Tests – Test T: Test methods for solderability and resistance to soldering heat of devices with leads*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 61196-1 apply.

4 Solderability

4.1 Procedure

A specimen without sheath (or with sheath stripped when sheath exists) long enough to allow the immersion of a 25 mm length shall be submitted to test Ta, Method 1 (solder bath at 235 °C) of IEC 60068-2-20.

4.2 Test report

The test report shall give the test conditions:

- temperature,
- sample length

and record the corrected values for the reference length.

4.3 Requirements

The surface of the tubular outer conductor corresponding to the immersed length shall be correctly tinned, i.e. more than 95 % of this surface shall be wetted by solder, the spots and marks of soldering shall not be concentrated in one area and they shall not exceed 5 % of the immersed surface, unless otherwise specified in the relevant cable specification.

NOTE The percentage of the tinned surface as well as spots and marks of soldering can be determined with assistance of a magnifier capable of giving a magnification of 4 x to 25 x, see IEC 60068-2-20. A detailed procedure to measure or inspect the samples after soldering is under consideration.

5 Resistance to soldering

5.1 Procedure

A 150 mm \pm 10 mm length specimen shall be very carefully curved at 30 mm from its end according to a bending radius as specified in the detail specification. The included angle thus formed in the specimen shall be 135° \pm 5°.

The end of the bent sample shall then be immersed in a solder bath in accordance with test Tb, method 1A (solder bath at 260 °C) of IEC 60068-2-20.

Flux to be used: flux as indicated in IEC 60068-2-20, plus a 0,5 % mass of hydroxylamine-chlorhydrate.

Immersion depth: 25 mm \pm 1 mm.

At the end of the test, the specimen shall be allowed to cool and the two ends checked to measure (with an accuracy of 0,1 mm):

- a) the displacement of the insulation with respect to the outer conductor;
- b) the displacement of the inner conductor with regard to the insulation.

5.2 Test report

The test report shall give the test conditions:

- temperature;
- duration of sample in solder bath;
- sample length;
- cable component displacement.

5.3 Requirements

Every measured displacement shall be less than the values indicated in the detail specification.
