

# INTERNATIONAL STANDARD



**Terrestrial photovoltaic (PV) modules – Design qualification and type approval –  
Part 1-1: Special requirements for testing of crystalline silicon photovoltaic (PV)  
modules**

IECNORM.COM : Click to view the full PDF of IEC 61215-1-1:2021 RLV



**THIS PUBLICATION IS COPYRIGHT PROTECTED**  
**Copyright © 2021 IEC, Geneva, Switzerland**

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland

Tel.: +41 22 919 02 11  
[info@iec.ch](mailto:info@iec.ch)  
[www.iec.ch](http://www.iec.ch)

**About the IEC**

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

**About IEC publications**

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

**IEC publications search - [webstore.iec.ch/advsearchform](http://webstore.iec.ch/advsearchform)**

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

**IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)**

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

**IEC Customer Service Centre - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)**

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: [sales@iec.ch](mailto:sales@iec.ch).

**IEC online collection - [oc.iec.ch](http://oc.iec.ch)**

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

**Electropedia - [www.electropedia.org](http://www.electropedia.org)**

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 18 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IECNORM.COM : Click to view the full PDF of IEC 60211-1:2021 PLV



IEC 61215-1-1

Edition 2.0 2021-02  
REDLINE VERSION

# INTERNATIONAL STANDARD



**Terrestrial photovoltaic (PV) modules – Design qualification and type approval –  
Part 1-1: Special requirements for testing of crystalline silicon photovoltaic (PV)  
modules**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

ICS 27.160

ISBN 978-2-8322-9487-1

**Warning! Make sure that you obtained this publication from an authorized distributor.**

## CONTENTS

FOREWORD .....	4
1 Scope <del>and object</del> .....	6
2 Normative references .....	7
3 Terms and definitions .....	7
4 Test samples .....	7
5 Marking and documentation .....	7
6 Testing .....	7
7 Pass criteria .....	7
8 Major visual defects .....	7
9 Report .....	7
10 Modifications .....	7
11 Test flow and procedures .....	8
11.1 Visual inspection (MQT 01) .....	8
11.2 Maximum power determination (MQT 02) .....	8
11.3 Insulation test (MQT 03) .....	8
11.4 Measurement of temperature coefficients (MQT 04) .....	8
11.5 <del>Measurement of nominal module operating temperature (NMOT) (MQT 05)</del> Placeholder section, formerly NMOT .....	8
11.6 Performance at STC (MQT 06.1) <del>and NMOT (MQT 06.2)</del> .....	8
11.7 Performance at low irradiance (MQT 07) .....	8
11.8 Outdoor exposure test (MQT 08) .....	8
11.9 Hot-spot endurance test (MQT 09) .....	8
11.9.1 Purpose .....	8
11.9.2 Classification of cell interconnection .....	8
11.9.3 Apparatus .....	8
11.9.4 Procedure .....	9
11.9.5 Final measurements .....	9
11.9.6 Requirements .....	9
11.10 UV preconditioning test (MQT 10) .....	9
11.11 Thermal cycling test (MQT 11) .....	9
11.12 Humidity-freeze test (MQT 12) .....	9
11.13 Damp heat test (MQT 13) .....	9
11.14 Robustness of terminations <del>test</del> (MQT 14) .....	10
11.15 Wet leakage current test (MQT 15) .....	10
11.16 Static mechanical load test (MQT 16) .....	10
11.17 Hail test (MQT 17) .....	10
11.18 Bypass diode <del>thermal</del> testing (MQT 18) .....	10
11.19 Stabilization (MQT 19) .....	10
11.19.1 Criterion definition for stabilization .....	10
11.19.2 Light induced stabilization procedures .....	10
11.19.3 Other stabilization procedures .....	10
11.19.4 Initial stabilization (MQT 19.1) .....	10
11.19.5 Final stabilization (MQT 19.2) .....	11
11.20 Cyclic (dynamic) mechanical load test (MQT 20) .....	12
11.21 Potential induced degradation test (MQT 21) .....	12

11.22 Bending test (MQT 22)..... 12

Figure 1 – Flow chart summary of MQT 19.2..... 12

IECNORM.COM : Click to view the full PDF of IEC 61215-1-1:2021 RLV

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

**TERRESTRIAL PHOTOVOLTAIC (PV) MODULES –  
DESIGN QUALIFICATION AND TYPE APPROVAL –****Part 1-1: Special requirements for testing of crystalline  
silicon photovoltaic (PV) modules**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

**This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition IEC 61215-1-1:2016. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.**

International Standard IEC 61215-1-1 has been prepared by IEC technical committee 82: Solar photovoltaic energy systems.

This second edition cancels and replaces the first edition of IEC 61215-1-1, issued in 2016, and constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) A cyclic (dynamic) mechanical load test (MQT 20) added.
- b) A test for detection of potential-induced degradation (MQT 21) added.
- c) A bending test (MQT 22) for flexible modules added.
- d) A procedure for stress specific stabilization – BO LID (MQT 19.3) added.
- e) A final stabilization procedure for modules undergoing PID testing added.

Informative Annex A of IEC 61215-1:2021 explains the background and reasoning behind some of the more substantial changes that were made in the IEC 61215 series in progressing from edition 1 to edition 2.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
82/1824/FDIS	82/1849/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

This standard is to be read in conjunction with IEC 61215-1:2021 and IEC 61215-2:2021.

A list of all parts in the IEC 61215 series, published under the general title *Terrestrial photovoltaic (PV) modules – Design qualification and type approval*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

**IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.**

# TERRESTRIAL PHOTOVOLTAIC (PV) MODULES – DESIGN QUALIFICATION AND TYPE APPROVAL –

## Part 1-1: Special requirements for testing of crystalline silicon photovoltaic (PV) modules

### 1 ~~Scope and object~~

~~This part of IEC 61215 lays down IEC requirements for the design qualification and type approval of terrestrial photovoltaic modules suitable for long-term operation in general open air climates, as defined in IEC 60721-2-1. This standard is intended to apply to all crystalline silicon terrestrial flat plate modules.~~

~~This standard does not apply to modules used with concentrated sunlight although it may be utilized for low concentrator modules (1 to 3 suns). For low concentration modules, all tests are performed using the current, voltage and power levels expected at the design concentration.~~

~~The object of this test sequence is to determine the electrical and thermal characteristics of the module and to show, as far as possible within reasonable constraints of cost and time, that the module is capable of withstanding prolonged exposure in climates described in the scope. The actual lifetime expectancy of modules so qualified will depend on their design, their environment and the conditions under which they are operated.~~

This document lays down requirements for the design qualification of terrestrial photovoltaic modules suitable for long-term operation in open-air climates. The useful service life of modules so qualified will depend on their design, their environment and the conditions under which they are operated. Test results are not construed as a quantitative prediction of module lifetime. In climates where 98<sup>th</sup> percentile operating temperatures exceed 70 °C, users are recommended to consider testing to higher temperature test conditions as described in IEC TS 63126.

Users desiring qualification of PV products with lesser lifetime expectations are recommended to consider testing designed for PV in consumer electronics, as described in IEC 63163 (under development). Users wishing to gain confidence that the characteristics tested in IEC 61215 appear consistently in a manufactured product may wish to utilize IEC 62941 regarding quality systems in PV manufacturing.

This document is intended to apply to all crystalline silicon terrestrial flat plate modules.

This document does not apply to modules used with concentrated sunlight although it may be utilized for low concentrator modules (1 to 3 suns). For low concentration modules, all tests are performed using the irradiance, current, voltage and power levels expected at the design concentration.

The objective of this test sequence is to determine the electrical characteristics of the module and to show, as far as possible within reasonable constraints of cost and time, that the module is capable of withstanding prolonged exposure outdoors. Accelerated test conditions are empirically based on those necessary to reproduce selected observed field failures and are applied equally across module types. Acceleration factors may vary with product design and thus not all degradation mechanisms may manifest. Further general information on accelerated test methods including definitions of terms may be found in IEC 62506.

Some long-term degradation mechanisms can only reasonably be detected via component testing, due to long times required to produce the failure and necessity of stress conditions that are expensive to produce over large areas. Component tests that have reached a sufficient

level of maturity to set pass/fail criteria with high confidence are incorporated into the IEC 61215 series via addition to Table 1 in IEC 61215-1:2021. In contrast, the tests procedures described in this series, in IEC 61215-2, are performed on modules.

This document defines PV technology dependent modifications to the testing procedures and requirements per IEC 61215-1:2016:2021 and IEC 61215-2:2016:2021.

## 2 Normative references

The normative references of IEC 61215-1:2016:2021 and IEC 61215-2:2016:2021 are applicable without modifications.

## 3 Terms and definitions

This clause of IEC 61215-1:2016:2021 is applicable without modifications.

## 4 Test samples

This clause of IEC 61215-1:2016:2021 is applicable without modifications.

## 5 Marking and documentation

This clause of IEC 61215-1:2016:2021 is applicable without modifications.

## 6 Testing

This clause of IEC 61215-1:2016:2021 is applicable without modifications.

## 7 Pass criteria

This clause of IEC 61215-1:2016:2021 is applicable ~~without~~ with the modifications listed below:

The maximum allowable value of reproducibility is set to  $r = 1,0$  %.

The maximum allowable value of measurement uncertainty is set to  $m_1 = 3,0$  %.

## 8 Major visual defects

This clause of IEC 61215-1:2016:2021 is applicable without modifications.

## 9 Report

This clause of IEC 61215-1:2016:2021 is applicable without modifications.

## 10 Modifications

This clause of IEC 61215-1:2016:2021 is applicable without modifications.

## 11 Test flow and procedures

The test flow from IEC 61215-1:2016:2021 is applicable.

### 11.1 Visual inspection (MQT 01)

This test of IEC 61215-2:2016:2021 is applicable without modifications.

### 11.2 Maximum power determination (MQT 02)

This test of IEC 61215-2:2016:2021 is applicable without modifications.

### 11.3 Insulation test (MQT 03)

This test of IEC 61215-2:2016:2021 is applicable without modifications.

### 11.4 Measurement of temperature coefficients (MQT 04)

This test of IEC 61215-2:2016:2021 is applicable without modifications.

### 11.5 ~~Measurement of nominal module operating temperature (NMOT) (MQT 05)~~ Placeholder section, formerly NMOT

~~This test of IEC 61215-2:2016 is applicable without modifications.~~

This subclause of IEC 61215-2:2021 does not require technology-specific modifications.

### 11.6 Performance at STC (MQT 06.1) ~~and NMOT (MQT 06.2)~~

This test of IEC 61215-2:2016:2021 is applicable without modifications.

### 11.7 Performance at low irradiance (MQT 07)

This test of IEC 61215-2:2016:2021 is applicable without modifications.

### 11.8 Outdoor exposure test (MQT 08)

This test of IEC 61215-2:2016:2021 is applicable without modifications.

### 11.9 Hot-spot endurance test (MQT 09)

The relevant subclause of IEC 61215-2:2016:2021, test MQT 09, is applicable without modifications.

#### 11.9.1 Purpose

The relevant subclause of IEC 61215-2:2016:2021, test MQT 09, is applicable without modifications.

#### 11.9.2 Classification of cell interconnection

The relevant subclause of IEC 61215-2:2016:2021, test MQT 09, is applicable without modifications.

#### 11.9.3 Apparatus

The relevant subclause of IEC 61215-2:2016:2021, test MQT 09, is applicable without modifications.

**11.9.4 Procedure**

MQT 09.1 shall be performed in accordance to IEC 61215-2:20162021.

**11.9.5 Final measurements**

The relevant subclause of IEC 61215-2:20162021, test MQT 09, is applicable without modifications.

**11.9.6 Requirements**

The relevant subclause of IEC 61215-2:20162021, test MQT 09, is applicable without modifications.

**11.10 UV preconditioning test (MQT 10)**

This test of IEC 61215-2:20162021 is applicable without modifications.

**11.11 Thermal cycling test (MQT 11)**

This test of IEC 61215-2:20162021 is applicable without modifications.

~~The technology specific current which needs to be applied according to test MQT 11 of IEC 61215-2:2016, shall be equal to the STC peak power current.~~

For monofacial modules, the technology specific current which needs to be applied according to test MQT 11 of IEC 61215-2:2021, shall be equal to the STC peak power current. For bifacial modules, the technology specific current which needs to be applied according to test MQT 11 of IEC 61215-2:2021, shall be equal to the peak power current at the elevated irradiance level BSI, as defined in IEC 61215-1,3.12. The peak power current at irradiance BSI ( $I_{mp-BSI}$ ) may be determined either by a measurement (MQT 06.1) at irradiance BSI, or by assuming linearity of peak power current with irradiance. Assuming linearity allows one to calculate  $I_{mp-BSI}$ , using  $I_{mp}$  values measured for Gate No. 1 ( $I_{mp-STC}$  and  $I_{mp-BNPI}$ ), and the relevant equivalent irradiances:  $1\ 000\ \text{Wm}^{-2}$ ,  $G_{BNPI}$ , and  $G_{BSI}$ . To extrapolate  $I_{mp-BSI}$ , these quantities are combined as follows:

$$I_{mp-BSI} = I_{mp-BNPI} + \frac{(I_{mp-BNPI} - I_{mp-STC})}{G_{BNPI} - 1000\ \text{Wm}^{-2}} \times (G_{BSI} - G_{BNPI})$$

In the above formula, equivalent irradiance is calculated as in IEC TS 60904-1-2, specifically:

$$G_{BNPI} = 1\ 000\ \text{Wm}^{-2} + \varphi \times 135\ \text{Wm}^{-2}$$

$$G_{BSI} = 1\ 000\ \text{Wm}^{-2} + \varphi \times 300\ \text{Wm}^{-2}$$

$$\varphi = \text{Min}(\varphi_{ISC}, \varphi_{Pmax})$$

**11.12 Humidity-freeze test (MQT 12)**

This test of IEC 61215-2:20162021 is applicable without modifications.

**11.13 Damp heat test (MQT 13)**

This test of IEC 61215-2:20162021 ~~is applicable~~ shall be performed without modifications. Modules shall be subject to the requirements in MQT 19.2 prior to evaluation of gate No. 2.

#### 11.14 Robustness of terminations ~~test~~ (MQT 14)

This test of IEC 61215-2:2016:2021 is applicable without modifications.

#### 11.15 Wet leakage current test (MQT 15)

This test of IEC 61215-2:2016:2021 is applicable without modifications.

#### 11.16 Static mechanical load test (MQT 16)

This test of IEC 61215-2:2016:2021 is applicable without modifications.

#### 11.17 Hail test (MQT 17)

This test of IEC 61215-2:2016:2021 is applicable without modifications.

#### 11.18 Bypass diode ~~thermal~~ testing (MQT 18)

This test of IEC 61215-2:2016 is applicable without modifications.

#### 11.19 Stabilization (MQT 19)

This test of IEC 61215-2:2016:2021 is applicable with the following modifications:

##### 11.19.1 Criterion definition for stabilization

For the definition of stabilization as per test MQT 19 of IEC 61215-2:2016:2021,  $x = 0,01$  shall be used for crystalline silicon PV modules.

~~Temperature is a critical parameter. For the measurement MQT 06.1 of IEC 61215-2:2016 it shall be ensured that measurement is performed at  $(25 \pm 2)$  °C module temperature.~~

##### 11.19.2 Light induced stabilization procedures

This test of IEC 61215-2:2021 is applicable without modifications.

##### 11.19.3 Other stabilization procedures

~~At present no alternative stabilization methods are applicable.~~

This test of IEC 61215-2:2021 is applicable without modifications.

##### 11.19.4 Initial stabilization (MQT 19.1)

Initial stabilization of c-Si modules shall be obtained by exposing all modules to sunlight (either real or simulated) to an irradiation dose level of  $\geq 10$  kWh/m<sup>2</sup>. After this preconditioning all of the test modules shall be measured for STC power (MQT 06.1).

To fulfil MQT 19 requirements two intervals of at least 5 kWh/m<sup>2</sup> each are required.

If stabilization is performed outdoors no module temperature limits apply.

A validated alternative procedure can be used in accordance to MQT 19 of IEC 61215-2:2021.

After module stabilization ~~time~~, the timeframe for the subsequent tests is not critical. Perform all measurements within a comparable timeframe and state time in report.

**11.19.5 Final stabilization (MQT 19.2)**

Final stabilization (MQT 19.2) is not required, except for modules that have been tested according to MQT 21, Potential induced degradation test (in sequence F), or MQT 13, Damp heat test (in sequence E). Final stabilization requirements differ depending on whether the module has been subjected to MQT 13 or MQT 21.

For modules that have been tested according to MQT 13, damp heat test (in sequence E), a choice of two final stabilization methods, "Method 1" or "Method 2", is available:

## Method 1)

- Perform MQT 19.3 as defined in IEC 61215-2.
- Record choice of stabilization method 1) in the test report.
- Final stabilization is complete. Proceed with the test flow defined in IEC 61215, which involves MQT 06.1 and gate No. 2.

## Method 2)

- Perform MQT 06.1 and evaluate the gate No. 2 formula defined in IEC 61215-1.
- If the module passes gate No. 2, then final stabilization, MQT 06.1, and gate No. 2 are all complete. In the test report, record stabilization method 2, MQT 06.1 results, and the following text: "This module was not stabilized, and therefore the amount of degradation observed may be larger than what would have been obtained if the module had been stabilized, due to destabilization artifacts." Proceed to the next step of the test flow defined in IEC 61215, which is MQT 03.
- If the module does not pass gate No. 2, record the initial MQT 06.1 result, then perform each step of Method 1).

For modules that have been tested according to MQT 21, PID (in sequence F) a choice of two final stabilization methods, "Method 3" or "Method 4", is available:

## Method 3)

- Modules shall be exposed to an irradiation of  $(2,0 \pm 0,2)$  kWh/m<sup>2</sup>.
- Exposure shall be performed as per IEC 61215-2:2021 MQT 10, with the temperature and spectrum meeting the requirements specified therein. Heat-up, exposure, and cool-down shall be performed such that the module spends less than 24 h above 40 °C. The only differences between the exposure in Method 3 and that in MQT 10 are the total dose, which side of the module is exposed, and the addition of a time limit.
- For bifacial modules, the irradiance shall be applied to the rear side, whereas for monofacial modules, the irradiance shall be applied to the front side.
- The class CCC solar simulator listed as required apparatus in MQT 19.2 shall fulfill the class C spectral requirements over at least the short-wavelength portion of the extended wavelength range described in IEC 60904-9.
- Record choice of stabilization method 3) in the test report.
- Final stabilization is complete. Proceed with the test flow defined in IEC 61215, which involves MQT 06.1 and gate No. 2.

## Method 4)

- Perform MQT 06.1 and evaluate the gate No. 2 formula defined in IEC 61215-1.
- If the module passes gate No. 2, then final stabilization, MQT 06.1, and gate No. 2 are all complete. In the test report, record stabilization method 4, MQT 06.1 results, and the following text: "This module was not stabilized, and therefore the amount of degradation observed may be larger than what would have been obtained if the module had been

stabilized, due to polarization artifacts." Proceed to the next step of the test flow defined in IEC 61215, which is MQT 03.

- If the module does not pass gate No. 2, record the initial MQT 06.1 result, then perform each step of Method 3).

Final stabilization requirements are summarized in the Figure 1 flow chart.




Figure 1 – Flow chart summary of MQT 19.2

**11.20 Cyclic (dynamic) mechanical load test (MQT 20)**

This test of IEC 61215-2:2021 is applicable without modifications.

**11.21 Potential induced degradation test (MQT 21)**

This test of IEC 61215-2:2021 is applicable without modifications.

**11.22 Bending test (MQT 22)**

This test of IEC 61215-2:2021 is applicable to flexible modules without modifications.

# INTERNATIONAL STANDARD

**Terrestrial photovoltaic (PV) modules – Design qualification and type approval –  
Part 1-1: Special requirements for testing of crystalline silicon photovoltaic (PV)  
modules**

IECNORM.COM : Click to view the full PDF of IEC 61215-1-1:2021 RLV

## CONTENTS

FOREWORD .....	4
1 Scope .....	6
2 Normative references .....	6
3 Terms and definitions .....	7
4 Test samples .....	7
5 Marking and documentation .....	7
6 Testing .....	7
7 Pass criteria .....	7
8 Major visual defects .....	7
9 Report .....	7
10 Modifications .....	7
11 Test flow and procedures .....	7
11.1 Visual inspection (MQT 01) .....	7
11.2 Maximum power determination (MQT 02) .....	7
11.3 Insulation test (MQT 03) .....	7
11.4 Measurement of temperature coefficients (MQT 04) .....	8
11.5 Placeholder section, formerly NMOT .....	8
11.6 Performance at STC (MQT 06.1) .....	8
11.7 Performance at low irradiance (MQT 07) .....	8
11.8 Outdoor exposure test (MQT 08) .....	8
11.9 Hot-spot endurance test (MQT 09) .....	8
11.9.1 Purpose .....	8
11.9.2 Classification of cell interconnection .....	8
11.9.3 Apparatus .....	8
11.9.4 Procedure .....	8
11.9.5 Final measurements .....	8
11.9.6 Requirements .....	8
11.10 UV preconditioning test (MQT 10) .....	8
11.11 Thermal cycling test (MQT 11) .....	9
11.12 Humidity-freeze test (MQT 12) .....	9
11.13 Damp heat test (MQT 13) .....	9
11.14 Robustness of terminations (MQT 14) .....	9
11.15 Wet leakage current test (MQT 15) .....	9
11.16 Static mechanical load test (MQT 16) .....	9
11.17 Hail test (MQT 17) .....	9
11.18 Bypass diode testing (MQT 18) .....	9
11.19 Stabilization (MQT 19) .....	10
11.19.1 Criterion definition for stabilization .....	10
11.19.2 Light induced stabilization procedures .....	10
11.19.3 Other stabilization procedures .....	10
11.19.4 Initial stabilization (MQT 19.1) .....	10
11.19.5 Final stabilization (MQT 19.2) .....	10
11.20 Cyclic (dynamic) mechanical load test (MQT 20) .....	12
11.21 Potential induced degradation test (MQT 21) .....	12
11.22 Bending test (MQT 22) .....	12

Figure 1 – Flow chart summary of MQT 19.2..... 12

IECNORM.COM : Click to view the full PDF of IEC 61215-1-1:2021 RLV

# INTERNATIONAL ELECTROTECHNICAL COMMISSION

## TERRESTRIAL PHOTOVOLTAIC (PV) MODULES – DESIGN QUALIFICATION AND TYPE APPROVAL –

### Part 1-1: Special requirements for testing of crystalline silicon photovoltaic (PV) modules

#### FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61215-1-1 has been prepared by IEC technical committee 82: Solar photovoltaic energy systems.

This second edition cancels and replaces the first edition of IEC 61215-1-1, issued in 2016, and constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) A cyclic (dynamic) mechanical load test (MQT 20) added.
- b) A test for detection of potential-induced degradation (MQT 21) added.
- c) A bending test (MQT 22) for flexible modules added.
- d) A procedure for stress specific stabilization – BO LID (MQT 19.3) added.

e) A final stabilization procedure for modules undergoing PID testing added.

Informative Annex A of IEC 61215-1:2021 explains the background and reasoning behind some of the more substantial changes that were made in the IEC 61215 series in progressing from edition 1 to edition 2.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
82/1824/FDIS	82/1849/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

This standard is to be read in conjunction with IEC 61215-1:2021 and IEC 61215-2:2021.

A list of all parts in the IEC 61215 series, published under the general title *Terrestrial photovoltaic (PV) modules – Design qualification and type approval*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IECNORM.COM : Click to view the full PDF of IEC 61215-1-1:2021 REV

# TERRESTRIAL PHOTOVOLTAIC (PV) MODULES – DESIGN QUALIFICATION AND TYPE APPROVAL –

## Part 1-1: Special requirements for testing of crystalline silicon photovoltaic (PV) modules

### 1 Scope

This document lays down requirements for the design qualification of terrestrial photovoltaic modules suitable for long-term operation in open-air climates. The useful service life of modules so qualified will depend on their design, their environment and the conditions under which they are operated. Test results are not construed as a quantitative prediction of module lifetime. In climates where 98<sup>th</sup> percentile operating temperatures exceed 70 °C, users are recommended to consider testing to higher temperature test conditions as described in IEC TS 63126.

Users desiring qualification of PV products with lesser lifetime expectations are recommended to consider testing designed for PV in consumer electronics, as described in IEC 63163 (under development). Users wishing to gain confidence that the characteristics tested in IEC 61215 appear consistently in a manufactured product may wish to utilize IEC 62941 regarding quality systems in PV manufacturing.

This document is intended to apply to all crystalline silicon terrestrial flat plate modules.

This document does not apply to modules used with concentrated sunlight although it may be utilized for low concentrator modules (1 to 3 suns). For low concentration modules, all tests are performed using the irradiance, current, voltage and power levels expected at the design concentration.

The objective of this test sequence is to determine the electrical characteristics of the module and to show, as far as possible within reasonable constraints of cost and time, that the module is capable of withstanding prolonged exposure outdoors. Accelerated test conditions are empirically based on those necessary to reproduce selected observed field failures and are applied equally across module types. Acceleration factors may vary with product design and thus not all degradation mechanisms may manifest. Further general information on accelerated test methods including definitions of terms may be found in IEC 62506.

Some long-term degradation mechanisms can only reasonably be detected via component testing, due to long times required to produce the failure and necessity of stress conditions that are expensive to produce over large areas. Component tests that have reached a sufficient level of maturity to set pass/fail criteria with high confidence are incorporated into the IEC 61215 series via addition to Table 1 in IEC 61215-1:2021. In contrast, the tests procedures described in this series, in IEC 61215-2, are performed on modules.

This document defines PV technology dependent modifications to the testing procedures and requirements per IEC 61215-1:2021 and IEC 61215-2:2021.

### 2 Normative references

The normative references of IEC 61215-1:2021 and IEC 61215-2:2021 are applicable without modifications.

### **3 Terms and definitions**

This clause of IEC 61215-1:2021 is applicable without modifications.

### **4 Test samples**

This clause of IEC 61215-1:2021 is applicable without modifications.

### **5 Marking and documentation**

This clause of IEC 61215-1:2021 is applicable without modifications.

### **6 Testing**

This clause of IEC 61215-1:2021 is applicable without modifications.

### **7 Pass criteria**

This clause of IEC 61215-1:2021 is applicable with the modifications listed below:

The maximum allowable value of reproducibility is set to  $r = 1,0$  %.

The maximum allowable value of measurement uncertainty is set to  $m_1 = 3,0$  %.

### **8 Major visual defects**

This clause of IEC 61215-1:2021 is applicable without modifications.

### **9 Report**

This clause of IEC 61215-1:2021 is applicable without modifications.

### **10 Modifications**

This clause of IEC 61215-1:2021 is applicable without modifications.

### **11 Test flow and procedures**

The test flow from IEC 61215-1:2021 is applicable.

#### **11.1 Visual inspection (MQT 01)**

This test of IEC 61215-2:2021 is applicable without modifications.

#### **11.2 Maximum power determination (MQT 02)**

This test of IEC 61215-2:2021 is applicable without modifications.

#### **11.3 Insulation test (MQT 03)**

This test of IEC 61215-2:2021 is applicable without modifications.

#### **11.4 Measurement of temperature coefficients (MQT 04)**

This test of IEC 61215-2:2021 is applicable without modifications.

#### **11.5 Placeholder section, formerly NMOT**

This subclause of IEC 61215-2:2021 does not require technology-specific modifications.

#### **11.6 Performance at STC (MQT 06.1)**

This test of IEC 61215-2:2021 is applicable without modifications.

#### **11.7 Performance at low irradiance (MQT 07)**

This test of IEC 61215-2:2021 is applicable without modifications.

#### **11.8 Outdoor exposure test (MQT 08)**

This test of IEC 61215-2:2021 is applicable without modifications.

#### **11.9 Hot-spot endurance test (MQT 09)**

The relevant subclause of IEC 61215-2:2021, test MQT 09, is applicable without modifications.

##### **11.9.1 Purpose**

The relevant subclause of IEC 61215-2:2021, test MQT 09, is applicable without modifications.

##### **11.9.2 Classification of cell interconnection**

The relevant subclause of IEC 61215-2:2021, test MQT 09, is applicable without modifications.

##### **11.9.3 Apparatus**

The relevant subclause of IEC 61215-2:2021, test MQT 09, is applicable without modifications.

##### **11.9.4 Procedure**

MQT 09.1 shall be performed in accordance to IEC 61215-2:2021.

##### **11.9.5 Final measurements**

The relevant subclause of IEC 61215-2:2021, test MQT 09, is applicable without modifications.

##### **11.9.6 Requirements**

The relevant subclause of IEC 61215-2:2021, test MQT 09, is applicable without modifications.

#### **11.10 UV preconditioning test (MQT 10)**

This test of IEC 61215-2:2021 is applicable without modifications.