

INTERNATIONAL STANDARD

Liquid crystal display devices –
Part 40-1: Mechanical testing of display cover glass for mobile devices –
Guidelines

IECNORM.COM : Click to view the full PDF of IEC 61747-40-1:2019



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2019 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IECNORM.COM : Click to view the IEC Standard IEC 617-401:2019

INTERNATIONAL STANDARD

**Liquid crystal display devices –
Part 40-1: Mechanical testing of display cover glass for mobile devices –
Guidelines**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 31.120

ISBN 978-2-8322-6800-1

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	6
4 Mechanical performance testing guidelines.....	7
4.1 General.....	7
4.2 Mechanical testing guidelines for display cover glass for mobile devices.....	8
5 Brief overview of mechanical test methods	9
5.1 Edge strength	9
5.2 Surface impact resistance (energy-to-failure).....	9
5.3 Surface strength	9
5.4 Resistance against sharp contact surface damage and propagation under rigid support (energy-to-failure).....	9
5.5 Retained surface strength	10
Bibliography.....	11
Table 1 – Comprehensive list of cover glass testing methods.....	8
Table 2 – Matrix of cover glass test methods and glass condition	9

IECNORM.COM : Click to view the full PDF of IEC 61747-40-1:2019

INTERNATIONAL ELECTROTECHNICAL COMMISSION

LIQUID CRYSTAL DISPLAY DEVICES –

**Part 40-1: Mechanical testing of display cover glass
for mobile devices – Guidelines**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61747-40-1 has been prepared by IEC technical committee 110: Electronic displays.

This second edition cancels and replaces the first edition published in 2013. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) withdrawal of test methods unsuitable for mobile display cover,
- b) revision of test methods based on newly developed market relevance,
- c) addition of test method for abraded strength,
- d) addition of explanations about the relevance between the test methods and the fracture mode, and

e) revision of terms and definitions.

The text of this International Standard is based on the following documents:

CDV	Report on voting
110/1040/CDV	110/1093/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

A list of all parts in the IEC 61747 series, published under the general title *Liquid crystal display devices*, can be found on the IEC website.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IECNORM.COM : Click to view the full PDF of IEC 61747-40-1:2019

INTRODUCTION

Mobile electronic devices have become increasingly sophisticated and often incorporate displays for the purposes of user interface and viewing. Such displays commonly incorporate a transparent cover glass which aids in protecting the display against the introduction of damage through routine device transport and use, as well as occasional or accidental misuse.

The purpose of this document is to provide mechanical testing guidelines for cover glasses used in such applications. Such glasses can be strengthened or not, for example via an ion-exchange process, which acts to increase mechanical strength through the introduction of a surface compressive layer.

It is assumed that all measurements – described in detail in individual test method standards – are performed by personnel skilled in the general art of mechanical property measurements. Furthermore, it is recommended that all equipment is suitably calibrated as is known to skilled personnel and that records of the calibration data and traceability are kept.

IECNORM.COM : Click to view the full PDF of IEC 61747-40-1:2019

LIQUID CRYSTAL DISPLAY DEVICES –

Part 40-1: Mechanical testing of display cover glass for mobile devices – Guidelines

1 Scope

This part of IEC 61747 provides mechanical performance testing guidelines for cover glass used in electronic flat panel displays in mobile devices. This document focuses on key mechanical testing performance parameters and covers mainly strength and damage resistance attributes. The test methods focus on the cover glass level testing only.

NOTE The glass used for cover glasses for electronic mobile devices can be chemically strengthened by an ion-exchange process. This ion exchange process increases the mechanical strength of the glass.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

abraded

subjected to a defined process which introduces mechanical abrasive damage to a portion of the specimen to be placed under tension during subsequent flexural strength testing

EXAMPLE Biaxial flexure via ring-on-ring.

3.2

as-received

representative of standard sample preparation and handling practices, and therefore free of intentional mechanical damage such as abrasion, scratching, or indentation

Note 1 to entry: The strength of glass is not an intrinsic material property, and like other brittle elastic materials, is highly dependent upon the surface flaw population. The term "as-received" is meant to represent the surface condition upon specimen receipt and is distinguished from a condition where damage has been intentionally introduced prior to testing.

3.3

central tension

CT

tensile stress generated within the interior of a glass article which serves to counteract (i.e., force balance) compressive stress acting at or near the article surface

3.4**chemically strengthened**

subjected to a molten salt bath containing alkali ions typically larger than those residing in the glass, resulting in the generation of residual compressive stress (3.5) and central tension (3.3)

3.5**compressive stress****CS**

maximum residual stress in compression measured near the glass surface

3.6**cover glass**

glass that typically protects an optical component such as a display from damage

3.7**damage resistance**

ability to resist certain potential damage-inducing events such as abrasion

3.8**edge strength**

measured stress at failure in the case where failure is known to have originated from a specimen edge

3.9**mobile device**

electronic device that includes a battery and is designed to be carried about by consumers

3.10**retained surface strength**

measured stress (or measured load or impact energy when stress cannot be measured) at failure in the case where failure is known to have originated from a specimen surface which has experienced a specified abrasion or mechanical damage event

3.11**strength**

stress, load, or impact energy at which a specimen fails for a given loading condition

3.12**thermally strengthened**

subjected to fast cooling of the glass exterior relative to the glass interior, resulting in the generation of residual compressive stress (3.5) and central tension (3.3)

4 Mechanical performance testing guidelines**4.1 General**

The appropriate attribute(s) and test method(s) shall be selected based on the detail specification or depending on the purpose of the evaluation.

The standard environment for testing shall be as follows:

- temperature: 23 °C ± 3 °C
- relative humidity: 50 % ± 5 %

unless otherwise specified in the detail specification. These standard requirements are established to control fatigue effects when performing mechanical testing on glass. If environmental conditions differ from the standard environment, the conditions shall be reported with the test data.

4.2 Mechanical testing guidelines for display cover glass for mobile devices

A comprehensive list of all cover glass test methods and failure mechanisms is given in Table 1.

Table 1 – Comprehensive list of cover glass testing methods

Failure location	Failure mechanism	Subject (typical)	Attribute	Test methods	Units	Corresponding document
Edge	Overstress of edge flaws	As-received glass	Edge strength	Uniaxial flexure strength (four-point bend)	MPa	IEC 61747-40-2
Surface	Overstress from blunt impact	As-received glass	Surface impact resistance	Biaxial flexure energy-to-failure (ball drop)	J	IEC 61747-40-3
Surface	Overstress of surface flaws	As-received glass	Surface strength	Biaxial flexure stress (ring-on-ring)	N	IEC 61747-40-4
Surface	Sharp contact damage introduction propagated by central tension under rigid support condition	As-received glass	Resistance against surface sharp contact damage and propagation under rigid support condition	Sharp contact impact under rigid support condition (ball drop on coated abrasives)	J	IEC 61747-40-5
Surface	Sharp contact damage in combination with or followed immediately by flexural stress	Abraded glass	Retained strength	Abraded biaxial flexural strength (abraded ring-on-ring)	N	IEC 61747-40-6

In case the samples to be tested are that of strengthened glass – for example, via chemical or thermal means – the results of mechanical testing will depend on the degree of strengthening. This degree of strengthening may be characterized by attributes such as compressive stress, depth of layer, or other attributes. While these are to be stated in the test reports, the measurement methods for these parameters are outside the scope of this document.

Strengthened glass may result in non-linearities (such as in load to stress conversion) due to high deformations and the formation of membrane stresses, which shall be taken into consideration during data analysis and reporting.

Table 2 summarizes the comprehensive list of test methods for cover glasses described in Table 1. Test methods described in IEC 61747-40 (all parts) can be classified according to the types of external load applied and pre-conditioning. In Table 2, “n/a” means that a test method does not exist for the condition because the failure mechanism is not well understood, the failure mechanism is not common, the failure mechanism has not been observed for cover glasses, or the pre-condition is not relevant to the failure mechanism being tested.

Table 2 – Matrix of cover glass test methods and glass condition

Strength evaluation Pre-conditioning	(Quasi) Static		Dynamic	
	Uniaxial bend	Biaxial bend	Biaxial bend	Concentrated load
	Four-point bend	Ring-on-ring	Ball drop	Contact with coated abrasives
None (pristine or as-received)	IEC 61747-40-2	IEC 61747-40-4	IEC 61747-40-3	IEC 61747-40-5
Grit particle abrasion	n/a	IEC 61747-40-6	n/a	n/a

5 Brief overview of mechanical test methods

5.1 Edge strength

Uniaxial flexural strength (four-point bend):

A uniaxial flexural test via a four-point bend methodology has been selected as the best representative test for edge strength. This is related to the observations of failures occurring from edge flaws rather than surface flaws in the specimen.

The test method can be used to evaluate cover glass edge failures caused by uniaxial stress to edge flaws, for example.

5.2 Surface impact resistance (energy-to-failure)

Biaxial flexural energy-to-failure (ball drop):

A biaxial flexural test via a ball drop provides an indirect measurement of surface strength by applying a biaxial stress to the glass surface upon ball impact. Measurement of the impact energy is used to approximate equivalent performances for different ball sizes, weights and drop heights.

The test method can be used to assess cover glass surface failures caused by biaxial stress to pre-existing surface damage (e.g. damage caused to the surface during the fabrication process), for example.

5.3 Surface strength

Biaxial flexural strength (ring-on-ring):

A biaxial flexural test via a ring-on-ring methodology is designed to test surface strength. It is important to be aware that when the specimen deflects more than 1/2 of its thickness, the load-to-stress relationship is no longer linear, and non-linear effects shall be taken into account to properly convert load to stress.

The test method can be used to assess cover glass surface failures caused by biaxial stress to pre-existing surface damage, for example.

5.4 Resistance against sharp contact surface damage and propagation under rigid support (energy-to-failure)

Sharp contact impact resistance under rigid support condition (ball drop on coated abrasives):

Ball drop methodology with rigid support is employed to indirectly measure surface strength during sharp particle impact. This is achieved by dropping a ball onto a glass specimen with a sheet of coated abrasives placed on top of the glass. The test is focused on glass surface flaw generation and propagation by central tension when the glass is rigidly supported.

The test method can be used to assess cover glass surface failures caused by sharp contact damage penetration into the central tension region.

5.5 Retained surface strength

Abraded biaxial flexural strength (ring-on-ring):

An abraded biaxial flexural test (via ring-on-ring) can be an effective measure of the retained surface strength of a test specimen. The surface of the specimen is abraded by grit particle abrasion using a pre-determined apparatus and abrasives.

Grit particle abrasion is employed as the method to introduce damage to the glass surface. As mentioned in 5.3, deflections during loading of more than 1/2 of the glass thickness can lead to non-linearity of the load-to-stress relationship.

The test method can be used to assess cover glass surface failures caused by sharp contact damage accompanied by, or simultaneous with, bending.

IECNORM.COM : Click to view the full PDF of IEC 61747-40-1:2019