

INTERNATIONAL STANDARD



**Printed electronics –
Part 202-8: Materials – Conductive ink – Measurement of difference in resistance
of printing direction of conductive film fabricated with wire-shaped materials**

IECNORM.COM : Click to view the full PDF of IEC 62899-202-8:2024





THIS PUBLICATION IS COPYRIGHT PROTECTED
Copyright © 2024 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Secretariat
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews, graphical symbols and the glossary. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 500 terminological entries in English and French, with equivalent terms in 25 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IECNORM.COM : Click to view the full PDF IEC 60399-202-8:2024

INTERNATIONAL STANDARD



**Printed electronics –
Part 202-8: Materials – Conductive ink – Measurement of difference in
resistance of printing direction of conductive film fabricated with wire-shaped
materials**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 31.180; 87.080

ISBN 978-2-8322-8432-2

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	6
4 Test sample, apparatus and measuring device	7
4.1 Measurement environmental conditions	7
4.2 Test apparatus.....	7
4.3 Measuring device.....	8
4.4 Sample preparation for measuring resistance difference with printing direction.....	8
5 Test procedure	9
6 Report	9
6.1 Reporting the resistance	9
6.2 Report of the results	10
Annex A (informative) Measurement of difference of printing direction of printed conductive film.....	11
A.1 Sample preparation.....	11
A.2 Settings for the test sample	11
Bibliography.....	13
Figure 1 – Schematic diagram of printed conductive film with screws for a four-wire measurement.....	8
Figure 2 – Samples with printing direction of conductive film fabricated with wire- shaped materials	9
Figure A.1 – Sample preparation.....	11
Figure A.2 – Holder with setting a test sample	12
Table 1 – Resistance range of the test piece and the applied current.....	8
Table A.1 – Test results	12

INTERNATIONAL ELECTROTECHNICAL COMMISSION

PRINTED ELECTRONICS –

**Part 202-8: Materials – Conductive ink – Measurement of difference
in resistance of printing direction of conductive film
fabricated with wire-shaped materials**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 62899 has been prepared by IEC technical committee 119: Printed electronics. It is an International Standard.

The text of this International Standard is based on the following documents:

Draft	Report on voting
119/476/FDIS	119/483/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts in the IEC 62899 series, published under the general title *Printed electronics*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

IMPORTANT – The "colour inside" logo on the cover page of this document indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

IECNORM.COM : Click to view the full PDF of IEC 62899-202-8:2024

INTRODUCTION

The printing process for fabricating flexible devices is a very promising technology due to its high conductivity and efficiency. Specifically, a printed metal-based conductive layer on a flexible substrate can be employed as electrode or be interconnected for flexible devices. It can be commercialized as a type of composite material where the conductive layer is formed on the substrate as a conductor.

For metal-based transparent conductive (TC) films, silver or copper nanowires or metal mesh on a flexible substrate are a key component for many recently developed electronic products, ranging from smartphones to keypads of appliances such as refrigerators and washing machines. While indium tin oxide (ITO) is the conventional material for TC films, metal-based TC films fabricated using printed electronics technologies are being increasingly used as an alternative. TC film-fabricated nanowires have superior intrinsic properties owing to their wire shape. Their electrical performance can differ based on the printing direction and ink properties. The alignment of a wire depends on the printing equipment, ink composition, printing process, etc. [1] to [3]¹.

In this document, a method to evaluate the difference in electrical properties based on the printing direction is proposed. In particular, the proposed method monitors changes in the resistance of a printed metal-based TC film on a flexible substrate.

¹ Numbers in square brackets refer to the Bibliography.

PRINTED ELECTRONICS –

Part 202-8: Materials – Conductive ink – Measurement of difference in resistance of printing direction of conductive film fabricated with wire-shaped materials

1 Scope

This part of IEC 62899 provides a method for measuring the resistance difference of the printing direction of a printed conductive layer with wire-shaped or wire-type conducting materials. The method described in this document offers a measurement method and conditions for solution processed conductive films, fabricated by coating and printing process.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 62899-201, *Printed electronics – Part 201: Materials – Substrates*

IEC 62899-202, *Printed electronics – Part 202: Materials – Conductive ink*

ISO 291, *Plastics – Standard atmospheres for conditioning and testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

conductive material

ingredient of a printing or coating material, which itself is electrically conductive or becomes electrically conductive by post treatment such as heating

Note 1 to entry: The ingredient can be one or more small molecules, precursors, polymers, or particles.

Note 2 to entry: The ingredient might require post treatment to provide electrical conductivity.

[SOURCE: IEC 62899-101:2019, 3.19, modified – the notes have been added.]

3.2

conductive ink

fluid in which one or more conductive materials are dissolved or dispersed, and which is used to form a conducting structure

[SOURCE: IEC 62899-101:2019, 3.17, modified – “chemical precursors, polymers, or particles” have been replaced with “fluid in which one or more conductive materials”, “and which is used to form a conducting structure” has been added to the definition, and Note 1 has been removed.]

3.3

conductive film

substrate (sheet or roll) with a conductive layer

[SOURCE: IEC 62899-101:2019, 3.16]

3.4

flexible substrate

substrate showing reversible (i.e. elastic) mechanical behaviour within a certain range of applied mechanical stress

[SOURCE: IEC 62899-101:2019, 3.60, modified – the example has been removed.]

3.5

wire-shaped material

wire-type material

material with a high aspect ratio of length to diameter or width

3.6

machine direction

MD

direction in which the substrate or stock moves during printing

[SOURCE: IEC 62899-101:2019, 3.80]

3.7

cross direction

CD

direction at right angles to the machine direction of a substrate

[SOURCE: IEC 62899-101:2019, 3.25]

4 Test sample, apparatus and measuring device

4.1 Measurement environmental conditions

The temperature and humidity conditions for evaluation tests shall be at a temperature of 23 °C ± 1 °C, relative humidity of (50 ± 5) %, and an atmospheric pressure in accordance with ISO 291 unless otherwise specified.

4.2 Test apparatus

The difference in resistance based on the printing direction can be evaluated by connecting the metal grip and electrical connection to the silver paste and protective layer.

To measure resistance, the test sample can be placed on a rigid plate that connects to the measuring equipment as in Figure 1. The test sample is connected to the measuring equipment with two or four conductive wires.




Figure 1 – Schematic diagram of printed conductive film with screws for a four-wire measurement

4.3 Measuring device

The electrical resistance of a printed conductive film shall be measured using the four-wire measurement method. The conditions for electrical measurement are listed in Table 1.

Table 1 – Resistance range of the test piece and the applied current

Resistance range of the test piece	< 20 mΩ	< 200 mΩ	< 20 Ω	< 2 kΩ	< 20 kΩ	< 200 kΩ	< 20 MΩ
Applied current	1 A	100 mA	10 mA	1 mA	100 μA	10 μA	1 μA

NOTE Table 1 is taken from IEC 62899-202:2023, Table 2.

4.4 Sample preparation for measuring resistance difference with printing direction

To reduce the line interference of equipment when measuring resistance, a rectangular shaped sample with a ratio over 30 shall be used.

The recommended sample size is 300 mm of length × 10 mm of width.

The tolerance of width and length is ±0,2 mm. The tolerance is based on IEC 62899-201 and IEC 62899-202.

Another size sample whose ratio of the longer side over the shorter side is at least 30 may be used for measuring the resistance anisotropy of the printed conductive layer.

To prepare the printed conductive film samples with different angles as shown in Figure 2 the angles should be measured from the machine direction (MD) as shown in Figure 2. The cross direction (CD) in Figure 2 means the transverse direction of the MD. The CD is at an angle of 90° from the MD. The samples can be prepared with angles of 0° to 180° from the machine direction (MD). The angles for the samples shall be agreed in advance between the trade partners.




Figure 2 – Samples with printing direction of conductive film fabricated with wire-shaped materials

5 Test procedure

The test procedure is as follows:

- Cut out a mother conductive film of minimum size that can be sampled from the film roll.
- Record the sampling area in the report.
- Cut out the individual sample pieces with angles from a mother conductive film.
- Prepare the printed conductive lines.
- Place the printed conductive film sample on a rigid plate as in Figure 1.
- The wire connected to the printed conductive film samples is connected to the test equipment.
- Measure the resistance.
- Measure at least three strips per sample/angle with an accuracy of two decimals.

The detailed procedure of sample preparation should be referred to as indicated in Annex A.

6 Report

6.1 Reporting the resistance

The electrical resistance shall be reported as a table or a graph with angles as indicated in Annex A.

To evaluate the resistance difference, the resistance may be reported at various angles.

Report the resistance of at least three strips per sample/angle with an accuracy of two decimals.

6.2 Report of the results

The report shall include the following items:

- a) specimen identification;
- b) temperature;
- c) humidity;
- d) pressure;
- e) angle;
- f) resistance;
- g) standard deviation of resistance.

IECNORM.COM : Click to view the full PDF of IEC 62899-202-8:2024

Annex A (informative)

Measurement of difference of printing direction of printed conductive film

A.1 Sample preparation

The sample is prepared as illustrated in Figure A.1.



Figure A.1 – Sample preparation

A.2 Settings for the test sample

The settings, tests conditions and test results for the test sample are as follows (see Figure A.2 and Table A.1):

- 1) mother film size: 800 mm × 600 mm
- 2) sample size: 300 mm × 10 mm



Figure A.2 – Holder with setting a test sample

3) Test results:

Table A.1 – Test results

Angle	Samples	Resistance (kΩ)					
		1 st	2 nd	3 rd	Average resistance of sample	Standard deviation (×10 ⁻³)	Average resistance
0°	1	1,02	1,01	1,01	1,01	5,77	1,01
	2	0,97	0,96	0,97	0,97	5,77	
	3	1,05	1,06	1,03	1,05	15,28	
45°	1	0,92	0,91	0,91	0,91	5,77	0,95
	2	0,91	0,92	0,95	0,93	20,82	
	3	1,02	1,04	0,99	1,02	25,17	
90°	1	0,91	0,90	0,90	0,90	5,77	0,89
	2	0,88	0,88	0,88	0,88	0,00	
	3	0,90	0,90	0,89	0,90	5,77	