

TECHNICAL REPORT

**Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes –
Part 4: Typical values**

IECNORM.COM : Click to view the full PDF of IEC TR 60893-4:2014



THIS PUBLICATION IS COPYRIGHT PROTECTED
Copyright © 2014 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in 14 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

More than 55 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

IECNORM.COM : Click to view the full text of IEC TC 37 908934:2014

TECHNICAL REPORT

**Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes –
Part 4: Typical values**

IECNORM.COM : Click to view the full PDF of IEC TR 60893-4:2014

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE

P

ICS 29.035.01

ISBN 978-2-8322-1908-9

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Typical values for industrial rigid laminated sheets	7
3.1 Typical values for industrial rigid laminated sheets based on epoxy resin	7
3.2 Typical values for industrial rigid laminated sheets based on melamine resin.....	7
3.3 Typical values for industrial rigid laminated sheets based on phenolic resin.....	7
3.4 Typical values for industrial rigid laminated sheets based on polyester resin	7
3.5 Typical values for industrial rigid laminated sheets based on silicone resin	7
3.6 Typical values for industrial rigid laminated sheets based on polyimide resin	7
Bibliography.....	15
Table 1 – Typical values for EP types (Reference: IEC 60893-3-2:2003/AMD1:2011, Table 5) (1 of 2).....	8
Table 2 – Typical values for MF types (Reference: IEC 60893-3-3:2003/AMD1:2011, Table 5)	10
Table 3 – Typical values for PF types (Reference: IEC 60893-3-4:2003/AMD1:2012, Table 5) (1 of 2).....	11
Table 4 – Typical values for UP types (Reference: IEC 60893-3-5:2003/AMD1:2009, Table 5).....	13
Table 5 – Typical values for SI types (Reference: IEC 60893-3-6:2003/AMD1:2009, Table 5).....	14
Table 6 – Typical values for PI type (Reference: IEC 60893-3-7:2003/AMD1:2009, Table 5).....	14

IECNORM.COM : Click to view the full PDF of IEC TR 60893-4:2014

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**INSULATING MATERIALS –
INDUSTRIAL RIGID LAMINATED SHEETS BASED
ON THERMOSETTING RESINS FOR ELECTRICAL PURPOSES –****Part 4: Typical values****FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a technical report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC 60893-4, which is a technical report, has been prepared by IEC technical committee 15: Solid electrical insulating materials.

This second edition cancels and replaces the first edition, published in 2003. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) the typical values of modulus of elasticity in flexure and of comparative tracking index of EPGC (Epoxy Glass Cloth) types have been changed;
- b) the typical values of new material types introduced in IEC 60893-3-2:2003/AMD1:2011 have been included.

The text of this technical report is based on the following documents:

Enquiry draft	Report on voting
15/705/DTR	15/714A/RVC

Full information on the voting for the approval of this technical report can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60893 series, published under the general title *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes* can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IECNORM.COM : Click to view the full PDF of IEC TR 60893-4:2014

INTRODUCTION

This part of IEC 60893 is one of a series which deals with industrial rigid laminated sheets based on thermosetting resins for electrical purposes.

The series consists of four parts:

- Part 1: Definitions, designations and general requirements (IEC 60893-1)
- Part 2: Methods of test (IEC 60893-2)
- Part 3: Specifications for individual materials (IEC 60893-3)
- Part 4: Typical values (IEC 60893-4)

IEC 60893-4 is a technical report that deals with typical value information that is not part of the requirements for these laminates.

IECNORM.COM : Click to view the full PDF of IEC TR 60893-4:2014

INSULATING MATERIALS – INDUSTRIAL RIGID LAMINATED SHEETS BASED ON THERMOSETTING RESINS FOR ELECTRICAL PURPOSES –

Part 4: Typical values

1 Scope

This part of IEC 60893 serves as a technical report and presents tables of typical values for properties that are not studied and not given in Table 5 of IEC 60893-3-2:2003/AMD1:2011, IEC 60893-3-3:2003/AMD1:2011, IEC 60893-3-4:2003/AMD1:2012, IEC 60893-3-5:2003/AMD1:2009, IEC 60893-3-6:2003/AMD1:2009, IEC 60893-3-7:2003/AMD1:2009. The purpose of these typical values is to give general guidance and should not be considered as specification requirements.

The following tables give typical values for the different types of industrial laminated sheets for electrical purposes described in the Part 3 sheets of IEC 60893.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60893-2:2003, *Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 2: Methods of test*

IEC 60893-3-2:2003, *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 3-2: Specifications for individual materials – Requirements for rigid laminated sheets based on epoxy resins*
IEC 60893-3-2:2003/AMD1:2011

IEC 60893-3-3:2003, *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 3-3: Specifications for individual materials – Requirements for rigid laminated sheets based on melamine resins*
IEC 60893-3-3:2003/AMD1:2011

IEC 60893-3-4:2003, *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 3-4: Specifications for individual materials – Requirements for rigid laminated sheets based on phenolic resins*
IEC 60893-3-4:2003/AMD1:2012

IEC 60893-3-5:2003, *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 3-5: Specifications for individual materials – Requirements for rigid laminated sheets based on polyester resins*
IEC 60893-3-5:2003/AMD1:2009

IEC 60893-3-6:2003, *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 3-6: Specifications for individual materials – Requirements for rigid laminated sheets based on silicone resins*
IEC 60893-3-6:2003/AMD1:2009

IEC 60893-3-7:2003, *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 3-7: Specification for individual materials – Requirements for rigid laminated sheets based on polyimide resins*
IEC 60893-3-7:2003/AMD1:2009

3 Typical values for industrial rigid laminated sheets

3.1 Typical values for industrial rigid laminated sheets based on epoxy resin

See Table 1.

3.2 Typical values for industrial rigid laminated sheets based on melamine resin

See Table 2.

3.3 Typical values for industrial rigid laminated sheets based on phenolic resin

See Table 3.

3.4 Typical values for industrial rigid laminated sheets based on polyester resin

See Table 4.

3.5 Typical values for industrial rigid laminated sheets based on silicone resin

See Table 5.

3.6 Typical values for industrial rigid laminated sheets based on polyimide resin

See Table 6.

IECNORM.COM : Click to view the full PDF of IEC TR 60893-4:2014

Table 1 – Typical values for EP types
 (Reference: IEC 60893-3-2:2003/AMD1:2011, Table 5) (1 of 2)

Property	Test method in IEC 60893-2:2003 Subclause	Unit	Nominal thickness of sheet to which test is applicable mm	Type								
				EP CC 301	EP CP 201	EP GC 201	EP GC 202	EP GC 203	EP GC 204	EP GC 205	EP GC 306	
Apparent modulus of elasticity in flexure	5.2	MPa	≥1,5	6 000	6 000	22 000	22 000	22 000	22 000	22 000	24 000	22 000
Compressive strength perpendicular to laminations	5.3	MPa	≥5	230	160	350	350	350	350	350	350	350
Shearing strength parallel to laminations	5.5	MPa	≥5	10	–	30	30	30	30	30	20	30
Tensile strength	5.6	MPa	≥1,5	100	80	300	300	300	300	300	300	300
Permittivity at 48 Hz-62 Hz	6.2	–	≤3	5,3	5,0	5,5	5,5	5,5	5,5	5,5	5,5	5,5
Permittivity at 1 MHz	6.2	–	≤3	5,3	5,0	5,5	5,5	5,5	5,5	5,5	5,5	5,5
Dissipation factor at 48 Hz-62 Hz	6.2	–	≤3	0,04	0,05	0,04	0,04	0,04	0,04	0,04	0,04	0,04
Dissipation factor at 1 MHz	6.2	–	≤3	0,04	0,05	0,04	0,04	0,04	0,04	0,04	0,04	0,04
Comparative tracking index	6.4	–	≥3	500	100	200	200	200	175	175	175	500
Thermal endurance	7.1	TI	≥3	130	110	130	130	130	155	155	155	155
Density	8.1	g/cm ³	All	1,2-1,4	1,3-1,4	1,8-2,0	1,8-2,0	1,8-2,0	1,8-2,0	1,8-2,0	1,8-2,0	1,8-2,0

IECNORM.COM : Click to View the Full PDF of IEC TR 60893-4:2014

Table 2 – Typical values for MF types
(Reference: IEC 60893-3-3:2003/AMD1:2011, Table 5)

Property	Test method in IEC 60893-2:2003 Subclause	Unit	Nominal thickness of sheet to which test is applicable mm	Type	
				MF CC 201	MF GC 201
Apparent modulus of elasticity in flexure	5.2	MPa	≥1,5	5 000	14 000
Compressive strength perpendicular to laminations	5.3	MPa	≥5	90	275
Shearing strength parallel to laminations	5.5	MPa	≥5	8	12
Tensile strength	5.6	MPa	≥1,5	60	150
Permittivity at 48 Hz-62 Hz	6.2	-	≤3	8,0	7,5
Permittivity at 1 MHz	6.2	-	≤3	8,0	7,5
Dissipation factor at 48 Hz-62 Hz	6.2	-	≤3	0,03	0,02
Dissipation factor at 1 MHz	6.2	-	≤3	0,03	0,02
Comparative tracking index	6.4	-	≥3	500	500
Thermal endurance	7.1	TI	≥3	130	130
Density	8.1	g/cm ³	All	1,3-1,5	1,8-2,0

IECNORM.COM : Click to view the full PDF of IEC TR 60893-4:2014

Table 3 – Typical values for PF types
(Reference: IEC 60893-3-4:2003/AMD1:2012, Table 5) (1 of 2)

Property	Test method in IEC 60893-2:2003 Subclause	Unit	Nominal thickness of sheet to which test is applicable mm	Type									
				PF CC 201	PF CC 202	PF CC 203	PF CC 204	PF CC 305	PF CP 201	PF CP 202	PF CP 203	PF CP 204	
Apparent modulus of elasticity in flexure	5.2	MPa	≥1,5	7 000	7 000	7 000	7 000	7 000	7 000	7 000	7 000	7 000	7 000
Compressive strength perpendicular to laminations	5.3	MPa	≥5	-	-	-	-	-	-	300	250	250	250
Shearing strength parallel to laminations	5.5	MPa	≥5	25	20	25	20	20	20	10	10	10	20
Tensile strength	5.6	MPa	≥1,5	80	60	85	80	80	80	120	100	100	70
Permittivity at 48 Hz-62 Hz	6.2	-	≤3	-	5,5	-	5,5	-	-	-	-	-	-
Permittivity at 1 MHz	6.2	-	≤3	-	-	-	-	-	-	-	5,5	5,5	5,5
Dissipation factor at 48 Hz-62 Hz	6.2	-	≤3	-	-	-	-	-	-	-	-	-	-
Dissipation factor at 1 MHz	6.2	-	≤3	-	-	-	-	-	-	-	0,05	0,05	0,05
Comparative tracking index	6.4	-	≥3	100	100	100	100	100	100	100	100	100	100
Thermal endurance	7.1	TI	≥3	120	120	120	120	120	120	120	120	105	105
Density	8.1	g/cm ³	All	1,3-1,4	1,3-1,4	1,3-1,4	1,3-1,4	1,3-1,4	1,3-1,4	1,3-1,4	1,3-1,4	1,3-1,4	1,3-1,4

NOTE A dash (-) signifies no data available.

Table 3 (2 of 2)
(Reference: IEC 60893-3-4:2003/AMD1:2012, Table 5)

Property	Test method in IEC 60893-2:2003 Subclause	Unit	Nominal thickness of sheet to which test is applicable mm	Type									
				PF CP 205	PF CP 206	PF CP 207	PF CP 308	PF GC 201	PF WV 201	PF WV 202	PF WV 303	PF WV 304	
Apparent modulus of elasticity in flexure	5.2	MPa	≥1,5	5 000	7 000	5 000	7 000	14 000	14 000	14 000	14 000	18 000	18 000
Compressive strength perpendicular to laminations	5.3	MPa	≥5	250	250	300	250	-	220	220	220	80	80
Shearing strength parallel to laminations	5.5	MPa	≥5	20	20	10	20	-	15	15	15	15	15
Tensile strength	5.6	MPa	≥1,5	60	70	100	70	100	60	60	60	120	120
Permittivity at 48 Hz-62 Hz	6.2	-	≤3	-	-	-	-	5	-	-	-	-	-
Permittivity at 1 MHz	6.2	-	≤3	5,5	6,0	-	6,0	-	-	-	-	-	-
Dissipation factor at 48 Hz-62 Hz	6.2	-	≤3	-	-	-	-	-	-	-	0,1	-	0,1
Dissipation factor at 1 MHz	6.2	-	≤3	0,05	0,05	-	0,05	-	-	-	-	-	-
Comparative tracking index	6.4	-	≥3	100	100	100	100	100	100	100	100	100	100
Thermal endurance	7.1	TI	≥3	100	105	105	100	120	120	120	120	120	120
Density	8.1	g/cm ³	All	1,3-1,4	1,3-1,4	1,3-1,4	1,3-1,4	1,6-1,8	1,3-1,4	1,3-1,4	1,3-1,4	1,3-1,4	1,3-1,4

NOTE A dash (-) signifies no data available.

Table 4 – Typical values for UP types
(Reference: IEC 60893-3-5:2003/AMD1:2009, Table 5)

Property	Test method in IEC 60893-2:2003 Subclause	Unit	Nominal thickness of sheet to which test is applicable mm	Type				
				UP GM 201	UP GM 202	UP GM 203	UP GM 204	UP GM 205
Apparent modulus of elasticity in flexure	5.2	MPa	≥1,5	8 000	8 000	8 000	10 000	10 000
Compressive strength perpendicular to laminations	5.3	MPa	≥5	200	200	200	250	250
Shearing strength parallel to laminations	5.5	MPa	≥5	20	20	20	20	20
Tensile strength	5.6	MPa	≥1,5	70	70	70	120	120
Permittivity at 48 Hz-62 Hz	6.2	-	≤3	4,5	4,5	4,5	4,5	4,5
Permittivity at 1 MHz	6.2	-	≤3	4,5	4,5	4,5	4,5	4,5
Dissipation factor at 48 Hz-62 Hz	6.2	-	≤3	0,05	0,05	0,05	0,05	0,05
Dissipation factor at 1 MHz	6.2	-	≤3	0,05	0,05	0,05	0,05	0,05
Comparative tracking index	6.4	-	≥3	600	600	600	600	600
Thermal endurance	7.1	TI	≥3	130	140	130	140	140
Density	8.1	g/cm ³	All	1,5-1,9	1,5-1,9	1,5-1,9	1,5-1,9	1,5-1,9

Table 5 – Typical values for SI types
(Reference: IEC 60893-3-6:2003/AMD1:2009, Table 5)

Property	Test method in IEC 60893-2:2003 Subclause	Unit	Nominal thickness of sheet to which test is applicable mm	Type	
				SI GC 201	SI GC 202
Apparent modulus of elasticity in flexure	5.2	MPa	≥1,5	13 000	13 000
Compressive strength perpendicular to laminations	5.3	MPa	≥5	160	160
Shearing strength parallel to laminations	5.5	MPa	≥5	20	20
Tensile strength	5.6	MPa	≥1,5	70	90
Permittivity at 48 Hz-62 Hz	6.2	–	≤3	4,5	6,0
Permittivity at 1 MHz	6.2	–	≤3	4,5	6,0
Dissipation factor at 48 Hz-62 Hz	6.2	–	≤3	0,02	0,07
Dissipation factor at 1 MHz	6.2	–	≤3	0,02	0,07
Comparative tracking index	6.4	–	≥3	450	450
Thermal endurance	7.1	TI	≥3	180	180
Density	8.1	g/cm ³	All	1,6-1,9	1,6-1,9

Table 6 – Typical values for PI type
(Reference: IEC 60893-3-7:2003/AMD1:2009, Table 5)

Property	Test method in IEC 60893-2:2003 Subclause	Unit	Nominal thickness of sheet to which test is applicable mm	Type
				PI GC 301
Apparent modulus of elasticity in flexure	5.2	MPa	≥1,5	22 000
Compressive strength perpendicular to laminations	5.3	MPa	≥5	400
Shearing strength parallel to laminations	5.5	MPa	≥5	35
Tensile strength	5.6	MPa	≥1,5	250
Permittivity at 48 Hz-62 Hz	6.2	–	≤3	5,5
Permittivity at 1 MHz	6.2	–	≤3	5,5
Dissipation factor at 48 Hz-62 Hz	6.2	–	≤3	0,03
Dissipation factor at 1 MHz	6.2	–	≤3	0,03
Comparative tracking index	6.4	–	≥3	150
Thermal endurance	7.1	TI	≥3	160
Density	8.1	g/cm ³	All	1,9-2,1