

---

---

**Classification of dense shaped refractory products —**

Part 3:

**Basic products containing from 7 % to 50 % residual carbon**

*Classification des produits réfractaires façonnés denses —*

*Partie 3: Produits basiques contenant de 7 % à 50 % de carbone résiduel*



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 10081-3:2003

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10081-3 was prepared by Technical Committee ISO/TC 33, *Refractories*.

The various parts of this revised series of ISO 10081 will cancel and replace ISO 1109:1975. Part 1 is a partial revision of ISO 1109:1975, Part 2 cancels and replaces ISO 10081-1:1991, and Part 3 is new.

ISO 10081 consists of the following parts, under the general title *Classification of dense shaped refractory products*:

- *Part 1: Alumina-silica*
- *Part 2: Basic products containing less than 7 % residual carbon*
- *Part 3: Basic products containing from 7 % to 50 % residual carbon*

Part 4 is under preparation and is intended to cover special products as given in Clause 2 of ISO 1109:1975.

STANDARDSISO.COM : Click to view the full PDF of ISO 10081-3:2003

# Classification of dense shaped refractory products —

## Part 3: Basic products containing from 7 % to 50 % residual carbon

### 1 Scope

This part of ISO 10081 specifies the classification and designation of dense shaped basic refractory products containing 7 % or more but less than 50 % residual carbon after coking. It is applicable to products with or without antioxidant additives, with or without metal plates and reinforcement.

NOTE 1 ISO 10081-2 covers the classification of dense shaped basic products containing less than 7 % residual carbon.

NOTE 2 All bricks can be encased in metal plate and can be reinforced by means of an internal metal plate and/or mixed metal fibre.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10058, *Magnesites and dolomites — Chemical analysis*

ISO 10060, *Dense, shaped refractory products — Test methods for products containing carbon*

ISO 12677, *Chemical analysis of refractory products by XRF — Fused cast bead method*

### 3 Classification

#### 3.1 Basis of classification

Dense shaped basic products containing 7 % or more but less than 50 % residual carbon after coking shall be classified according to the following five criteria:

- a) the type of product;
- b) the group determined by its magnesia and carbon content as well as the presence of antioxidant additives;
- c) the state of the raw materials;
- d) the nature of the bond;
- e) any post-treatment.

#### 3.2 Type of product

The types of dense shaped refractory products of the basic series included in this classification are

- a) magnesia carbon (MC),
- b) magnesia lime carbon (MLC) (containing lime and/or synthetic MgO-CaO co-clinker),

- c) magnesia doloma carbon (MDC) (containing sintered natural dolomite), and
- d) doloma carbon (DC) (containing sintered natural co-clinker).

These product types shall be classified in accordance with Table 1, by their chemical analysis carried out on the calcined products in accordance with ISO 10058 and ISO 12677.

Residual carbon content shall be determined in accordance with ISO 10060.

### 3.3 Classification groups

The product types shall be classified into groups according to their magnesia and carbon contents and according to the presence or absence of antioxidant additives.

The product types without antioxidant additives shall be classified into groups according to Table 1. Two criteria shall be used for defining the group classification:

- a) the magnesia content of the product type;
- b) the residual carbon content after carbonization.

For magnesia lime carbon and lime carbon products, limits on lime content is imposed on the various groups.

The product types with antioxidant additives shall be classified according to the same criteria with the addition of a suffix A indicating the presence of antioxidant additives.

**Table 1 — Classification of magnesia carbon, magnesia doloma carbon and doloma carbon products**

Product type	Group	Contents		Residual carbon content % (mass fraction)
		% (mass fraction) (calcined sample)		
		MgO	CaO	
Magnesia carbon	MC 98/7	MgO ≥ 98		7 ≤ C < 10
	MC 98/10	MgO ≥ 98		10 ≤ C < 15
	MC 98/15	MgO ≥ 98		15 ≤ C < 20
	MC 98/20	MgO ≥ 98		20 ≤ C < 25
	MC 98/25	MgO ≥ 98		25 ≤ C < 30
	MC 98/30	MgO ≥ 98		30 ≤ C < 50
Magnesia carbon	MC 95/7	95 ≤ MgO < 98		7 ≤ C < 10
	MC 95/10	95 ≤ MgO < 98		10 ≤ C < 15
	MC 95/15	95 ≤ MgO < 98		15 ≤ C < 20
	MC 95/20	95 ≤ MgO < 98		20 ≤ C < 25
	MC 95/25	95 ≤ MgO < 98		25 ≤ C < 30
	MC 95/30	95 ≤ MgO < 98		30 ≤ C < 50
Magnesia carbon	MC 90/7	90 ≤ MgO < 95		7 ≤ C < 10
	MC 90/10	90 ≤ MgO < 95		10 ≤ C < 15
	MC 90/15	90 ≤ MgO < 95		15 ≤ C < 20
	MC 90/20	90 ≤ MgO < 95		20 ≤ C < 25
	MC 90/25	90 ≤ MgO < 95		25 ≤ C < 30
	MC 90/30	90 ≤ MgO < 95		30 ≤ C < 50

**Table 1 — Classification of magnesia carbon, magnesia doloma carbon and doloma carbon products (continued)**

Product type	Group	Contents % (mass fraction) (calcined sample)		Residual carbon content % (mass fraction)
		MgO	CaO	
Magnesia carbon	MC 85/7	$85 \leq \text{MgO} < 90$		$7 \leq \text{C} < 10$
	MC 85/10	$85 \leq \text{MgO} < 90$		$10 \leq \text{C} < 15$
	MC 85/15	$85 \leq \text{MgO} < 90$		$15 \leq \text{C} < 20$
	MC 85/20	$85 \leq \text{MgO} < 90$		$20 \leq \text{C} < 25$
	MC 85/25	$85 \leq \text{MgO} < 90$		$25 \leq \text{C} < 30$
	MC 85/30	$85 \leq \text{MgO} < 90$		$30 \leq \text{C} < 50$
Magnesia carbon	MC 80/7	$80 \leq \text{MgO} < 85$		$7 \leq \text{C} < 10$
	MC 80/10	$80 \leq \text{MgO} < 85$		$10 \leq \text{C} < 15$
	MC 80/15	$80 \leq \text{MgO} < 85$		$15 \leq \text{C} < 20$
	MC 80/20	$80 \leq \text{MgO} < 85$		$20 \leq \text{C} < 25$
	MC 80/25	$80 \leq \text{MgO} < 85$		$25 \leq \text{C} < 30$
	MC 80/30	$80 \leq \text{MgO} < 85$		$30 \leq \text{C} < 50$
Magnesia lime carbon	MLC 80/7	$80 \leq \text{MgO} < 90$	$\text{CaO} \geq 10$	$7 \leq \text{C} < 10$
	MLC 80/10	$80 \leq \text{MgO} < 90$	$\text{CaO} \geq 10$	$10 \leq \text{C} < 15$
	MLC 80/15	$80 \leq \text{MgO} < 90$	$\text{CaO} \geq 10$	$15 \leq \text{C} < 20$
	MLC 80/20	$80 \leq \text{MgO} < 90$	$\text{CaO} \geq 10$	$20 \leq \text{C} < 25$
	MLC 80/25	$80 \leq \text{MgO} < 90$	$\text{CaO} \geq 10$	$25 \leq \text{C} < 30$
	MLC 80/30	$80 \leq \text{MgO} < 90$	$\text{CaO} \geq 10$	$30 \leq \text{C} < 50$
Magnesia lime carbon	MLC 70/7	$70 \leq \text{MgO} < 80$	$\text{CaO} \geq 20$	$7 \leq \text{C} < 10$
	MLC 70/10	$70 \leq \text{MgO} < 80$	$\text{CaO} \geq 20$	$10 \leq \text{C} < 15$
	MLC 70/15	$70 \leq \text{MgO} < 80$	$\text{CaO} \geq 20$	$15 \leq \text{C} < 20$
	MLC 70/20	$70 \leq \text{MgO} < 80$	$\text{CaO} \geq 20$	$20 \leq \text{C} < 25$
	MLC 70/25	$70 \leq \text{MgO} < 80$	$\text{CaO} \geq 20$	$25 \leq \text{C} < 30$
	MLC 70/30	$70 \leq \text{MgO} < 80$	$\text{CaO} \geq 20$	$30 \leq \text{C} < 50$
Magnesia lime carbon	MLC 60/7	$60 \leq \text{MgO} < 70$	$\text{CaO} \geq 30$	$7 \leq \text{C} < 10$
	MLC 60/10	$60 \leq \text{MgO} < 70$	$\text{CaO} \geq 30$	$10 \leq \text{C} < 15$
	MLC 60/15	$60 \leq \text{MgO} < 70$	$\text{CaO} \geq 30$	$15 \leq \text{C} < 20$
	MLC 60/20	$60 \leq \text{MgO} < 70$	$\text{CaO} \geq 30$	$20 \leq \text{C} < 25$
	MLC 60/25	$60 \leq \text{MgO} < 70$	$\text{CaO} \geq 30$	$25 \leq \text{C} < 30$
	MLC 60/30	$60 \leq \text{MgO} < 70$	$\text{CaO} \geq 30$	$30 \leq \text{C} < 50$
Magnesia lime carbon	MLC 50/7	$50 \leq \text{MgO} < 60$	$\text{CaO} \geq 40$	$7 \leq \text{C} < 10$
	MLC 50/10	$50 \leq \text{MgO} < 60$	$\text{CaO} \geq 40$	$10 \leq \text{C} < 15$
	MLC 50/15	$50 \leq \text{MgO} < 60$	$\text{CaO} \geq 40$	$15 \leq \text{C} < 20$
	MLC 50/20	$50 \leq \text{MgO} < 60$	$\text{CaO} \geq 40$	$20 \leq \text{C} < 25$
	MLC 50/25	$50 \leq \text{MgO} < 60$	$\text{CaO} \geq 40$	$25 \leq \text{C} < 30$
	MLC 50/30	$50 \leq \text{MgO} < 60$	$\text{CaO} \geq 40$	$30 \leq \text{C} < 50$
Magnesia lime carbon	MLC 40/7	$40 \leq \text{MgO} < 50$	$\text{CaO} \geq 50$	$7 \leq \text{C} < 10$
	MLC 40/10	$40 \leq \text{MgO} < 50$	$\text{CaO} \geq 50$	$10 \leq \text{C} < 15$
	MLC 40/15	$40 \leq \text{MgO} < 50$	$\text{CaO} \geq 50$	$15 \leq \text{C} < 20$
	MLC 40/20	$40 \leq \text{MgO} < 50$	$\text{CaO} \geq 50$	$20 \leq \text{C} < 25$
	MLC 40/25	$40 \leq \text{MgO} < 50$	$\text{CaO} \geq 50$	$25 \leq \text{C} < 30$
	MLC 40/30	$40 \leq \text{MgO} < 50$	$\text{CaO} \geq 50$	$30 \leq \text{C} < 50$

Table 1 — Classification of magnesia carbon, magnesia doloma carbon and doloma carbon products (continued)

Product type	Group	Contents % (mass fraction) (calcined sample)		Residual carbon content % (mass fraction)
		MgO	CaO	
Magnesia lime carbon	MLC 7	MgO < 40	CaO ≥ 50	7 ≤ C < 10
	MLC 10	MgO < 40	CaO ≥ 50	10 ≤ C < 15
	MLC 15	MgO < 40	CaO ≥ 50	15 ≤ C < 20
	MLC 20	MgO < 40	CaO ≥ 50	20 ≤ C < 25
	MLC 25	MgO < 40	CaO ≥ 50	25 ≤ C < 30
	MLC 30	MgO < 40	CaO ≥ 50	30 ≤ C < 50
Magnesia doloma carbon	MDC 80/7	80 ≤ MgO < 90	CaO ≥ 10	7 ≤ C < 10
	MDC 80/10	80 ≤ MgO < 90	CaO ≥ 10	10 ≤ C < 15
	MDC 80/15	80 ≤ MgO < 90	CaO ≥ 10	15 ≤ C < 20
	MDC 80/20	80 ≤ MgO < 90	CaO ≥ 10	20 ≤ C < 25
	MDC 80/25	80 ≤ MgO < 90	CaO ≥ 10	25 ≤ C < 30
Magnesia doloma carbon	MDC 70/7	70 ≤ MgO < 80	CaO ≥ 20	7 ≤ C < 10
	MDC 70/10	70 ≤ MgO < 80	CaO ≥ 20	10 ≤ C < 15
	MDC 70/15	70 ≤ MgO < 80	CaO ≥ 20	15 ≤ C < 20
	MDC 70/20	70 ≤ MgO < 80	CaO ≥ 20	20 ≤ C < 25
	MDC 70/25	70 ≤ MgO < 80	CaO ≥ 20	25 ≤ C < 30
Magnesia doloma carbon	MDC 60/7	60 ≤ MgO < 70	CaO ≥ 30	7 ≤ C < 10
	MDC 60/10	60 ≤ MgO < 70	CaO ≥ 30	10 ≤ C < 15
	MDC 60/15	60 ≤ MgO < 70	CaO ≥ 30	15 ≤ C < 20
	MDC 60/20	60 ≤ MgO < 70	CaO ≥ 30	20 ≤ C < 25
	MDC 60/25	60 ≤ MgO < 70	CaO ≥ 30	25 ≤ C < 30
Magnesia doloma carbon	MDC 50/7	50 ≤ MgO < 60	CaO ≥ 40	7 ≤ C < 10
	MDC 50/10	50 ≤ MgO < 60	CaO ≥ 40	10 ≤ C < 15
	MDC 50/15	50 ≤ MgO < 60	CaO ≥ 40	15 ≤ C < 20
	MDC 50/20	50 ≤ MgO < 60	CaO ≥ 40	20 ≤ C < 25
	MDC 50/25	50 ≤ MgO < 60	CaO ≥ 40	25 ≤ C < 30
Magnesia doloma carbon	MDC 40/7	40 ≤ MgO < 50	CaO ≥ 50	7 ≤ C < 10
	MDC 40/10	40 ≤ MgO < 50	CaO ≥ 50	10 ≤ C < 15
	MDC 40/15	40 ≤ MgO < 50	CaO ≥ 50	15 ≤ C < 20
	MDC 40/20	40 ≤ MgO < 50	CaO ≥ 50	20 ≤ C < 25
	MDC 40/25	40 ≤ MgO < 50	CaO ≥ 50	25 ≤ C < 30
Doloma carbon	DC 40/7	MgO < 40	CaO ≥ 50	7 ≤ C < 10
	DC 40/10	MgO < 40	CaO ≥ 50	10 ≤ C < 15
	DC 40/15	MgO < 40	CaO ≥ 50	15 ≤ C < 20
	DC 40/20	MgO < 40	CaO ≥ 50	20 ≤ C < 25
	DC 40/25	MgO < 40	CaO ≥ 50	25 ≤ C < 30