



**International
Standard**

ISO 10350-1

**Plastics — Acquisition and
presentation of comparable single-
point data —**

**Part 1:
Moulding materials**

*Plastiques — Acquisition et présentation de caractéristiques
intrinsèques comparables —*

Partie 1: Matériaux pour moulage

**Fourth edition
2025-01**

STANDARDSISO.COM : Click to view the full PDF of ISO 10350-1:2025



COPYRIGHT PROTECTED DOCUMENT

© ISO 2025

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	3
4 Specimen preparation and conditioning.....	3
5 Test requirements.....	4
6 Presentation of results.....	4
Bibliography.....	10

STANDARDSISO.COM : Click to view the full PDF of ISO 10350-1:2025

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 2, *Mechanical behavior*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 10350-1:2017), which has been technically revised.

The main changes are as follows:

- “Specimen type” columns have been clarified by adding specimen type designations specified in ISO 20753;
- symbols of the stress at break and the strain at break have been harmonized with those used in ISO 527-1;
- the formula attached to the x-axis has been corrected;
- “Property” column 2.12 has been corrected to “2.12 Charpy unnotched impact strength”.

A list of all parts in the ISO 10350 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The ISO 10350 series identifies specific test procedures for the acquisition and presentation of comparable data for certain basic properties of plastics. In general, each property is specified by a single experimental value, although in certain cases properties are represented by two values obtained under different test conditions. The properties included are those presented conventionally in manufacturers' data sheets.

NOTE ISO 10350-2 deals specifically with long- or continuous-fibre-reinforced plastics. For the purpose of this document, long-fibre-reinforced plastics are considered to have fibre length greater than 7,5 mm prior to moulding.

The ISO 10350 series has been prepared because users of plastics find that available data cannot always be readily used to compare the properties of similar materials, especially when the data have been supplied by different sources. Even when the same standard tests have been used, they often allow the adoption of a wide range of alternative test conditions, and the data obtained are not necessarily comparable. The purpose of this document is to identify specific methods and conditions of test to be used for the acquisition and presentation of data in order that valid comparisons between materials can be made.

The ISO 10350 series is concerned with tests employed to present "single-point" data on the limited range of properties commonly included in data sheets and used for the preliminary selection of materials. Such data represent the most basic approach to the specification of properties of materials, and the ISO 10350 series thus facilitates the first steps towards more efficient selection and use of plastics in the many applications to which they are suited.

Complementary International Standards (i.e. ISO 11403-1, ISO 11403-2 and ISO 11403-3) are concerned with the standardized acquisition and presentation of multipoint data, to demonstrate how properties vary with important factors such as time, temperature and the presence of particular natural and chemical environments. In these documents, some additional properties are included. Their use will provide a more substantial database than one containing only single-point data, and so will enable improved assessment of the fitness of a material for any particular application. In addition, ISO 11403-1, which deals with mechanical properties, assists predictions of the performance of components and ISO 11403-2, covering thermal and processing properties, aids predictions of melt-flow behaviour during manufacturing. ISO 11403-3 is concerned with environmental influences on properties, and other parts may be prepared to cover additional properties.

STANDARDSISO.COM : Click to view the full PDF of ISO 10350-1:2025

Plastics — Acquisition and presentation of comparable single-point data —

Part 1: Moulding materials

1 Scope

This document defines test procedures for the acquisition and presentation of comparable data for moulding materials. This document applies predominantly to unreinforced and reinforced thermoplastic and thermosetting materials that can be injection- or compression-moulded or prepared as sheets of specified thickness.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 62, *Plastics — Determination of water absorption*

ISO 75-1, *Plastics — Determination of temperature of deflection under load — Part 1: General test method*

ISO 75-2, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite*

ISO 178, *Plastics — Determination of flexural properties*

ISO 179-1, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*

ISO 179-2, *Plastics — Determination of Charpy impact properties — Part 2: Instrumented impact test*

ISO 293, *Plastics — Compression moulding of test specimens of thermoplastic materials*

ISO 294-1, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens*

ISO 294-3, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 3: Small plates*

ISO 294-4, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 4: Determination of moulding shrinkage*

ISO 295, *Plastics — Compression moulding of test specimens of thermosetting materials*

ISO 306, *Plastics — Thermoplastic materials — Determination of Vicat softening temperature (VST)*

ISO 527-1, *Plastics — Determination of tensile properties — Part 1: General principles*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 899-1, *Plastics — Determination of creep behaviour — Part 1: Tensile creep*

ISO 1133-1, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method*

- ISO 1133-2, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 2: Method for materials sensitive to time-temperature history and/or moisture*
- ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*
- ISO 1183-2, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method*
- ISO 1183-3, *Plastics — Methods for determining the density of non-cellular plastics — Part 3: Gas pycnometer method*
- ISO 2577, *Plastics — Thermosetting moulding materials — Determination of shrinkage*
- ISO 2818, *Plastics — Preparation of test specimens by machining*
- ISO 3915, *Plastics — Measurement of resistivity of conductive plastics*
- ISO 4589-2, *Plastics — Determination of burning behaviour by oxygen index — Part 2: Ambient-temperature test*
- ISO 6603-2, *Plastics — Determination of puncture impact behaviour of rigid plastics — Part 2: Instrumented impact testing*
- ISO 8256, *Plastics — Determination of tensile-impact strength*
- ISO 10724-1, *Plastics — Injection moulding of test specimens of thermosetting powder moulding compounds (PMCs) — Part 1: General principles and moulding of multipurpose test specimens*
- ISO 10724-2, *Plastics — Injection moulding of test specimens of thermosetting powder moulding compounds (PMCs) — Part 2: Small plates*
- ISO 11357-2, *Plastics — Differential scanning calorimetry (DSC) — Part 2: Determination of glass transition temperature and step height*
- ISO 11357-3, *Plastics — Differential scanning calorimetry (DSC) — Part 3: Determination of temperature and enthalpy of melting and crystallization*
- ISO 11359-2, *Plastics — Thermomechanical analysis (TMA) — Part 2: Determination of coefficient of linear thermal expansion and glass transition temperature*
- ISO 20753, *Plastics — Test specimens*
- IEC 60112, *Method for the determination of the proof and the comparative tracking indices of solid insulating materials*
- IEC 60243-1, *Electrical strength of insulating materials — Test methods — Part 1: Tests at power frequencies*
- IEC 60296, *Fluids for electrotechnical applications — Unused mineral insulating oils for transformers and switchgear*
- IEC 60695-11-10, *Fire hazard testing — Part 11-10: Test flames — 50 W horizontal and vertical flame test methods*
- IEC 60695-11-20, *Fire hazard testing — Part 11-20: Test flames — 500 W flame test methods*
- IEC 62631-2-1, *Dielectric and resistive properties of solid insulating materials — Part 2-1: Relative permittivity and dissipation factor — Technical frequencies (0,1 Hz to 10 MHz) — AC methods*
- IEC 62631-3-1, *Dielectric and resistive properties of solid insulating materials — Part 3-1: Determination of resistive properties (DC methods) — Volume resistance and volume resistivity — General method*
- IEC 62631-3-2:2023, *Dielectric and resistive properties of solid insulating materials — Part 3-2: Determination of resistive properties (DC methods) — Surface resistance and surface resistivity*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 single-point data

data characterizing a plastics material by means of those property tests in which important aspects of performance can be described with single-value results

4 Specimen preparation and conditioning

In the preparation of specimens by injection moulding, the procedures described in ISO 294-1 and ISO 294-3 or ISO 10724-1 and ISO 10724-2 shall be used. For compression moulding, the procedures described in ISO 293 or ISO 295 shall be used. The moulding method and the conditions depends upon the material being moulded. If these conditions are specified in the International Standard appropriate to the material, then they shall be adopted for the preparation of every specimen on which data are obtained using this document. For those plastics for which moulding conditions have not yet been standardized, the conditions employed shall be within the range recommended by the polymer manufacturer and shall, for each of the processing methods, be the same for every specimen.

Where moulding conditions are not stipulated in any International Standard, the values used for the parameters in [Table 1](#) shall be recorded with the single-point data for that material. Where specimens are prepared by machining from sheet, the machining shall be performed in accordance with ISO 2818 and the dimensions of the specimen shall comply with those for the appropriate specimen in [Table 2](#).

For materials that have properties that are not significantly sensitive to any absorbed water, specimens shall be conditioned in accordance with the International Standard appropriate to the material concerned. If no materials standard is available, condition test specimens at $23\text{ °C} \pm 2\text{ °C}$ and $(50 \pm 10)\%$ relative humidity (RH) for a minimum length of time of 88 h (see ISO 291).

For those materials having properties that are significantly dependent upon the concentration of any absorbed water, data shall be presented both for material that is dry and also for material that is in equilibrium with an atmosphere of 50 % RH at 23 °C but with the following exceptions (see [Table 2](#)):

Rheological properties, 1.1 to 1.6	dry only
Creep modulus, 2.8 and 2.9	50 % RH only
Thermal properties, 3.1 to 3.8	dry only
Surface resistivity and comparative tracking index, 4.6 and 4.9	50 % RH only

For these materials, consult the relevant materials standard for procedures for conditioning specimens to achieve material that is dry or in equilibrium under 50 % RH. Following such conditioning, all test specimens shall be stored at $23\text{ °C} \pm 2\text{ °C}$ for a minimum of 16 h before testing. The storage atmosphere shall then be either dry or at 50 % RH, depending upon the condition of the specimen.

Table 1 — Moulding parameters

Moulding-material type	Moulding method and standard (where applicable)	Moulding parameters
Thermoplastic	Injection ISO 294-1 and ISO 294-3	Melt temperature Mould temperature Injection velocity ^a Cavity pressure at hold ^b
	Compression ISO 293	Moulding temperature Moulding time Cooling rate Demoulding temperature
Thermosetting	Injection ISO 10724-1 and ISO 10724-2	Injection temperature Mould temperature Injection velocity Cure time
	Compression ISO 295	Mould temperature Mould pressure Cure time

^a For the preparation of standard specimens of the 80 mm × 10 mm × 4 mm bar (ISO 294-1, mould type B), values for the injection velocity shall be chosen to give an injection time comparable to that achieved with the multipurpose test specimen (ISO 294-1, mould type A).

^b Only to be recorded for the 60 mm × 60 mm × 2 mm plate specimen in ISO 294-3 and ISO 294-4 when used for the determination of moulding shrinkage.

5 Test requirements

The test methods, test conditions and units specified in [Table 2](#) shall be used when determining data.

6 Presentation of results

The presentation of data shall be as shown in [Table 2](#), and the data shall be preceded by information that identifies the material together with the information required by [Clause 4](#), where appropriate. Indicate also whether the specimens tested were dry, in equilibrium with an atmosphere of 50 % RH at 23 °C or whether properties are insensitive to the presence of water.

The minimum number of specimens tested shall be the number specified for each property in the associated test method standard. Record the mean value for each property (or the central value if this is stipulated in the test method standard) in the “value” column.

In order that the value recorded for each property is as representative as possible of the material being tested, it is recommended that test specimens be prepared from at least three samples of the material taken from the production of the material over an extended timescale.

Table 2 — Test conditions and format for the presentation of single-point data^a

Property		Symbol	Standard	Specimen type (dimensions in mm)	Value	Unit	Test conditions and supplementary instructions	
1	Rheological properties (for properties 1.1 to 1.6, see statement regarding water content in Clause 4)							
1.1	Melt mass-flow rate	MFR	ISO 1133-1 or ISO 1133-2	Moulding compound		g/10 min	Use and record test conditions for temperature and load specified in the appropriate materials standard	
1.2	Melt volume-flow rate (see Note 1)	MVR				cm ³ /10 min		
1.3	Moulding shrinkage of thermosetting polymers	S_{Mp}	ISO 2577	See ISO 2577		%	Parallel	See Note 2
1.4		S_{Mn}					Normal	
1.5	Moulding shrinkage of thermoplastics	S_{Mp}	ISO 294-4	60 × 60 × 2 ISO 20753/D12 ISO 294-3 type D2 (see Note 3)		%	Parallel	See Note 2
1.6		S_{Mn}					Normal	
2	Mechanical properties (for properties 2.8 and 2.9, see statement regarding water content in Clause 4)							
2.1	Tensile modulus	E_t	ISO 527-1 and ISO 527-2	ISO 20753/A1 ^b		MPa	See Note 4 and Figure 1	Test speed 1 mm/min
2.2	Yield stress	σ_y						Failure with yielding; test speed 50 mm/min ^c
2.3	Yield strain	ε_y						
2.4	Nominal strain at break	ε_{tb}						
2.5	Stress at 50 % strain	σ_{50}						
2.6	Stress at break	σ_b				MPa		
2.7	Strain at break	ε_b				%		
2.8	Tensile creep modulus	E_{tc1}	ISO 899-1			MPa	At 1 h	Strain < 0,5 %
2.9		E_{tc10^3}				At 1 000 h		
2.10	Flexural modulus	E_f	ISO 178	80 × 10 × 4 ^b ISO 20753/B2		MPa	Test speed 2 mm/min Optional extra information for brittle materials ^e	
2.11	Flexural strength	σ_{fM}						
2.12	Charpy unnotched impact strength	a_{cU}	ISO 179-1 or ISO 179-2	80 × 10 × 4 ^b ISO 20753/B2		kJ/m ²	Edge-wise impact Also record type of failure (see Note 5)	
2.13	Charpy notched impact strength	a_{cN}		80 × 10 × 4 ^b ISO 20753/B2 Machined V-notch, $r = 0,25$				
2.14	Tensile-impact strength	a_{tN}	ISO 8256	80 × 10 × 4 ^b ISO 20753/B2 Machined double V-notch, $r = 1$				
2.15	Puncture impact behaviour	F_M	ISO 6603-2	60 × 60 × 2 ISO 20753/D12 (see Note 3)		N	Maximum force	Striker velocity 4,4 m/s Striker diameter 20 mm Lubricate the striker ^f Clamp the specimen sufficiently to prevent any out of plane movement of its outer regions
2.16		E_p				J	Puncture energy at 50 % decrease in force after the maximum	

Table 2 (continued)

Property		Symbol	Standard	Specimen type (dimensions in mm)	Value	Unit	Test conditions and supplementary instructions		
3 Thermal properties (for properties 3.1 to 3.8, see statement regarding water content in Clause 4)									
3.1	Melting temperature	T_m	ISO 11357-3	Moulding compound		°C	Record peak melting temperature Use 10 K/min ^g		
3.2	Glass transition temperature	$T_{1/2,g}$	ISO 11357-2					Record midpoint temperature Use 10 K/min ^g Use the half-step-height method.	
3.3	Temperature of deflection under load	$T_f 1,8$	ISO 75-1 and ISO 75-2	80 × 10 × 4 ^b ISO 20753/B2		°C	Flexural stress (MPa)	1,8	Use 1,8 MPa and one other value
3.4		$T_f 0,45$						0,45	
3.5		$T_f 8,0$						8	
3.6	Vicat softening temperature (see Note 6)	VST B50	ISO 306	≥ 10 × 10 × 4 Central region prepared from ISO 20753/A1 (see Note 9)		°C	Heating rate 50 °C/h Load 50 N		
3.7	Coefficient of linear thermal expansion	α_p	ISO 11359-2	Prepared from ISO 20753/A1 (see Note 7)		°C ⁻¹	Parallel	Record the secant value over the temperature range 23 °C to 55 °C ^j (see Note 2)	
3.8		α_n			Transverse				
3.9	Burning behaviour	B50/3	IEC 60695- 11-10	125 × 13 × 3 Additional thickness <i>h</i>		Record one of the classifications V-0, V-1, V-2, HB40 or HB75			
3.10		B50/h							
3.11		B500/3	IEC 60695- 11-20	≥150 × ≥150 × 3 Additional thickness <i>h</i>		Record classification 5VA, 5VB or N (see Note 8)			
3.12		B500/h							
3.13	Oxygen index	OI	ISO 4589-2	80 × 10 × 4 ^b		%	Use procedure A (top surface ignition)		
4 Electrical properties (for properties 4.6 and 4.9, see statement regarding water content in Clause 4)									
4.1	Relative permittivity	ϵ_r 100	IEC 62631-2-1	≥60 × ≥60 × 2 e.g. ISO 20753/D12			100 Hz	Compensate for electrode edge effects	
4.2		ϵ_r 1M					1 MHz		
4.3	Dissipation factor	$\tan \delta$ 100					100 Hz		
4.4		$\tan \delta$ 1M					1 MHz		
4.5	Volume resistivity	ρ_e	IEC 62631-3-1	≥60 × ≥60 × 2 e.g. ISO 20753/D12		Ω·m	Voltage 500 V	Value at 1 min Used for materials having volume resistivity 10 ⁴ Ω·m or more.	
			ISO 3915	Type A1 or ≥10 × 75 to 150 × 2			≤ 10 V	Used for materials having volume resistivity less than 10 ⁴ Ω·m.	
4.6	Surface resistivity	σ_e	IEC 62631-3-2	≥60 × ≥60 × 2 e.g. ISO 20753/D12		Ω	Voltage 500 V	Use contacting line electrodes 1 mm to 2 mm wide, 50 mm long and 5 mm apart or circular electrodes as shown in IEC 62631-3-2:2023, Figure 3	

Table 2 (continued)

Property		Symbol	Standard	Specimen type (dimensions in mm)	Value	Unit	Test conditions and supplementary instructions
4.7	Electric strength	E_B 1	IEC 60243-1	$\geq 60 \times \geq 60 \times 1^h$ e.g. ISO 20753/D11 (see Note 3)		kV/mm	Use 20 mm diameter spherical electrodes Immerse in transformer oil in accordance with IEC 60296 Use a voltage application rate of 2 kV/s
4.8		E_B 2		$\geq 60 \times \geq 60 \times 2^{h,i}$ e.g. ISO 20753/D12 (see Note 3)			
4.9	Comparative tracking index	CTI	IEC 60112	$\geq 20 \times \geq 20 \times 4$ (see Note 9)			Use solution A
5	Other properties						
5.1	Water absorption	w_w	ISO 62	Thickness ≥ 1 (see Note 3)		%	Saturation value in water at 23 °C
5.2		w_H					Equilibrium value at 23 °C, 50 % RH
5.3	Density	ρ	ISO 1183-1, or ISO 1183-2, or ISO 1183-3	Central part prepared from ISO 20753/A1		kg/m ³	See Note 10

Table 2 (continued)

Property	Symbol	Standard	Specimen type (dimensions in mm)	Value	Unit	Test conditions and supplementary instructions
NOTE 1						The ratio of melt mass-flow rate to melt volume-flow rate gives an estimate of the melt density.
NOTE 2						Where specimens are prepared by injection moulding, record property values both parallel and normal to the direction of flow into the mould.
NOTE 3						For test specimens prepared by injection moulding, use mould type D1 for specimens of 1 mm thickness and type D2 for specimens of 2 mm thickness (see ISO 294-3 for thermoplastics and ISO 10724-2 for thermosets). Refer to the appropriate material standard for details of the moulding conditions for this specimen. Where these are not given, use the conditions specified for preparing the ISO 20753 multipurpose specimen, but employing an injection velocity that gives the same injection time as that obtained with the multipurpose specimen.
NOTE 4						The data to be recorded for the properties in 2.1 to 2.7 are intended to give a fair impression of the nature of the stress-strain curve to failure (see Figure 1).
NOTE 5						After testing, classify test results according to the three types of failure defined in ISO 179-1 and ISO 179-2:
C						complete break or hinge break;
P						partial break;
N						no break.
Select the test results for the type of failure that occurs most frequently and record the mean value of the impact strength and the corresponding failure type: C, P or N.						
NOTE 6						This property is less suitable for thermosets and semicrystalline materials.
NOTE 7						For injection-moulded test specimens, carry out the test at the central region of the multipurpose test specimen whenever possible.
NOTE 8						The classification N denotes that the material does not satisfy any of the classifications of the method.
NOTE 9						For injection-moulded specimens, use test specimens from the shoulder of the multipurpose test specimen.
NOTE 10						The methods specified in ISO 1183-1, ISO 1183-2 and ISO 1183-3 are regarded as equivalent for the purposes of this document.
^a Use of the parameters in Table 2 is essentially for the comparison of data, and certain of the instructions listed may not be appropriate for all plastics. ^b ISO 20753 describes two types of specimen for tensile tests. The type A1 specimen has a lower value for the radius of the shoulders of 23 mm to 25 mm which thereby enables a central region to be obtained of length at least 80 mm. The standard ISO bar having dimensions 80 mm × 10 mm × 4 mm can thus be cut from the central region of this type of test specimen which is therefore recommended for directly moulded specimens. The type A2 specimen has a larger shoulder radius of (60,0 ± 1,0) mm and is recommended for machined specimens. ^c If the specimen shows yielding when tested at a speed of 50 mm/min, then the test speed for data acquisition shall be 50 mm/min and the values for yield stress and strain and the nominal strain at break shall be recorded. If rupture occurs above 50 % nominal strain, record either the measured value of the nominal strain at break or simply record ">50". ^d If the specimen has a breaking strain beyond 10 % when tested at a speed of 50 mm/min but does not show a yield point below 50 % strain, record the stress and strain at break. If rupture occurs above 50 % strain, record the stress at 50 % strain and either the measured strain at break or ">50" for this value. If the specimen shows rupture without yielding and with a strain at break of less than or equal to 10 % when tested at a speed of 50 mm/min, then the test speed for data acquisition shall be 5 mm/min and the values for stress and strain at break shall be recorded. ^e The flexure test generates a non-uniform stress across the cross-section of the specimen. For materials that show significantly nonlinear behaviour up to failure, the derived flexural-strength value will thus depend upon the thickness of the specimen. This test is therefore not recommended for these materials. For materials that show predominantly linear behaviour up to failure, the inclusion of data using this test is optional. However, it should be noted that, for injection-moulded or reinforced materials, where the structure often varies through the cross-section of the specimen, values for flexural properties may be different from those obtained in tension. ^f In order to achieve comparable data with this test, the application of a lubricant to the striking surface is specified to minimize the friction between the striker and the test specimen. See the test method standard for details of suitable lubricants and their application. Results from an unlubricated test may be higher, owing to friction, and the mode of failure may be different from the lubricated test. ^g A heating rate of 20 K/min is recommended in ISO 11357-3. The lower rate of 10 K/min is specified here. ^h The specimen shall be sufficiently wide to prevent discharge along the surface. ⁱ A measurement at the greater thickness of 2 mm shall be presented for those materials that do not give realistic properties when moulded with a thickness of 1 mm. Since measurements of electric strength are dependent upon the thickness of the specimen, an additional value may be recorded here, for those materials that can be moulded with a thickness of 1 mm, to demonstrate the dependence on thickness. ^j The case in the temperature range where a glass transition point was prescribed, the linear expansion coefficient shall be measured in the range before and after the glass transition point domain and record it.						