
Textiles — Tests for colour fastness —

Part C08:

**Colour fastness to domestic and
commercial laundering using a non-
phosphate reference detergent
incorporating a low temperature bleach
activator**

Textiles — Essais de solidité des teintures —

*Partie C08: Solidité des teintures aux lavages domestiques et industriels,
utilisant un détergent de référence sans phosphate comprenant un
activateur de blanchiment à basse température*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 105-C08:2001

© ISO 2001

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

	Page
1 Scope	1
2 Normative references	1
3 Principle	2
4 Reagents and materials	2
5 Apparatus	3
6 Test specimen	3
7 Test procedure	4
8 Test report	4
 Annex	
A ECE non-phosphate reference detergent/TAED procedure	5

STANDARDSISO.COM : Click to view the full PDF of ISO 105-C08:2001

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 105 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 105-C08 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

ISO 105 was previously published in thirteen "parts", each designated by a letter (e.g., "Part A"), with publication dates between 1978 and 1985. Each part contained a series of "sections", each designated by the respective part letter and by a two-digit serial number (e.g. "Section A01"). These sections are now being republished as separate documents, themselves designated "parts" but retaining their earlier alphanumeric designations. A complete list of these parts is given in ISO 105-A01.

Annex A forms a normative part of this part of ISO 105.

Introduction

The test methods specified in ISO 105-C06 and that specified in this part of ISO 105 are intended to reflect the effect of laundering by domestic or commercial laundering procedures, as distinct from the washing test methods given in ISO 105-C01 to ISO 105-C05.

The general principles of testing described in ISO 105-A01 should be understood before using this part of ISO 105.

STANDARDSISO.COM : Click to view the full PDF of ISO 105-C08:2001

STANDARDSISO.COM : Click to view the full PDF of ISO 105-C08:2007

Textiles — Tests for colour fastness —

Part C08:

Colour fastness to domestic and commercial laundering using a non-phosphate reference detergent incorporating a low temperature bleach activator

1 Scope

This part of ISO 105 specifies methods intended for determining the resistance of the colour of textiles of all kinds and in all forms to domestic or commercial laundering procedures used for normal household articles using a reference detergent incorporating a low temperature bleach activator.

The colour loss and staining resulting from desorption and/or abrasive action in one single test closely approximates to one domestic or commercial laundering.

This method does not reflect the effect of optical brighteners present in some commercial washing products.

Annex A of this procedure incorporates the use of ECE¹⁾. Non-Phosphate Reference Detergent, sodium perborate tetrahydrate, and the bleach activator tetra-acetythylenediamine, (TAED). An alternative test procedure using the AATCC 1993 Zero Phosphate Reference Detergent (without optical brightener), and incorporating sodium perborate monohydrate and the bleach activator, sodium nonanoyloxybenzene sulfonate (SNOBS) is currently under development.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 105. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 105 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 105-A01:1994, *Textiles — Tests for colour fastness — Part A01: General principles of testing.*

ISO 105-A02:1993, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour.*

ISO 105-A03:1993, *Textiles — Tests for colour fastness — Part A03: Grey scale for assessing staining.*

ISO 105-A04:1989, *Textiles — Tests for colour fastness — Part A04: Method for the instrumental assessment of the degree of staining of adjacent fabrics.*

ISO 105-A05:1996, *Textiles — Tests for colour fastness — Part A05: Instrumental assessment of change in colour for determination of grey scale rating.*

ISO 105-F:1985, *Textiles — Tests for colour fastness — Part F: Standard adjacent fabrics.*

1) European Colourfastness Establishment (ECE), BAM, Unter den Eichen 87, D-12203, Berlin, Germany.

ISO 105-F10:1989, *Textiles — Tests for colour fastness — Part F10: Specification for adjacent fabric: Multifibre.*

ISO 105-J01:1997, *Textiles — Tests for colour fastness — Part J01: General principles for measurement of surface colour.*

ISO 105-J03:1995, *Textiles — Tests for colour fastness — Part J03: Calculation of colour differences.*

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods.*

3 Principle

A specimen of the textile in contact with specified adjacent fabric or fabrics is laundered, rinsed and dried. Specimens are laundered under appropriate conditions of temperature, alkalinity, bleaching and abrasive action such that the result is obtained in a conveniently short time. The abrasive action is accomplished by the use of an appropriate number of steel balls. The change in colour of the specimen and the staining of the adjacent fabric or fabrics are assessed with reference to the original fabric, either with the grey scales or instrumentally.

4 Reagents and materials

4.1 Reference detergent.

4.1.1 ECE non-phosphate reference detergent base powder (1998 formulation).

4.1.2 Bleach activator, tetra-acetylene diamine, TAED.

4.1.3 Sodium perborate tetrahydrate.

4.2 Non-corrodible (stainless) steel balls, approximately 6 mm in diameter.

4.3 Adjacent fabrics (see 8.2 of ISO 105-A01:1994).

Either

4.3.1 A multifibre adjacent fabric, complying with ISO 105-F10, according to the temperature used:

- a multifibre adjacent fabric (DW) containing wool and acetate (for tests at 40 °C and 50 °C and in certain cases, to be indicated in the test report, at 60 °C);
- a multifibre adjacent fabric (TV) not containing wool and acetate (in certain tests at 60 °C, and in all tests at 95 °C).

Or

4.3.2 Two single-fibre adjacent fabrics, complying with the relevant section F01 to F08 of ISO 105-F:1985. One of the adjacent fabrics shall be made of the same kind of the fibre as that of the textile to be tested or that predominating in the case of blends, and the second piece made of the fibre as indicated in Table 1 or, in the case of blends, of the kind of fibre second in order of predominance, or as otherwise specified.

Table 1 — Pairs of adjacent fabrics

First piece	Second piece	
	For tests at 40 °C and 50 °C	For tests at 60 °C and 95 °C
cotton	wool	viscose
wool	cotton	—
silk	cotton	—
viscose	wool	cotton
acetate	viscose	viscose
polyamide	wool or cotton	cotton
polyester	wool or cotton	cotton
acrylic	wool or cotton	cotton

4.3.3 **Non-dyeable fabric**, e.g. polypropylene, if required.

4.4 **Grade 3 water**, complying with ISO 3696.

4.5 **Grey scale**, for assessing change in colour and staining (ISO 105-A02; ISO 105-A03), or a spectrophotometer for assessing change in colour and staining complying with ISO 105-J01.

4.6 **Acetic acid solution**, containing 0,2 g of glacial acetic acid per litre if required for souring treatment.

5 Apparatus

5.1 **Suitable mechanical laundering device**, consisting of a water bath containing a rotatable shaft which supports, radially, stainless steel containers (75 mm ± 5 mm diameter × 125 mm ± 10 mm high) of capacity (550 ± 50) ml, the bottom of the containers being (45 mm ± 10 mm) from the centre of the shaft.

The shaft/container assembly is rotated at a frequency of (40 ± 2) min⁻¹. The temperature of the water bath is thermostatically controlled to maintain the test solution at the prescribed temperature ± 2 °C.

NOTE Other mechanical devices may be used for this test, provided that the results are identical with those obtained by the apparatus described in 5.1.

5.2 **Balance**, accurate to 0,01 g (see ISO 105-A01).

5.3 **Mechanical Stirrer**, minimum speed 16,667 s⁻¹ (1 000 r/min) to ensure thorough dispersion and prevent settling.

5.4 **Flat-iron** (if required for pressing treatment), of mass not exceeding 2,5 kg and capable of giving the temperature indicated in [see A.9 b)].

6 Test specimen

6.1 If the textile to be tested is fabric, either

a) attach a specimen 100 mm × 40 mm to a piece of the multifibre adjacent fabric (4.3.1), also 100 mm × 40 mm, by sewing along one of the shorter edges, with the multifibre adjacent fabric next to the face side of the specimen

or

b) attach a specimen 100 mm × 40 mm between the two single-fibre adjacent fabrics (4.3.2), also 100 mm × 40 mm, by sewing along one of the shorter edges.

6.2 Yarn may be knitted into fabric and tested in this form. Where yarns or loose fibres are to be tested, take a mass of the yarn or loose fibre approximately equal to one-half of the combined mass of the adjacent fabrics and either:

a) place it between a 100 mm × 40 mm piece of the multifibre fabric (4.3.1) and a piece of the non-dyeable fabric (4.3.3), and sew them along four sides (see 9.3.3.4 of ISO 105-A01:1994)

or

b) place it between 100 mm × 40 mm pieces of the two specified single-fibre fabrics (4.3.2) and sew them along all four sides.

6.3 Determine the mass, in grams, of the composite specimen using the balance (5.2) to aid accurate liquor ratio volumes.

7 Test procedure

Provision is made in annex A for a washing procedure using a bleach activator and reference detergent.

8 Test report

The test report shall include the following information:

- a) reference to this part of ISO 105, i.e. ISO 105-C08;
- b) all details necessary for complete identification of sample tested;
- c) the temperature of the method of test used (as listed in Table A.2);
- d) the numerical grey scale rating or instrumental assessment for change in colour of the specimen;
- e) if single-fibre adjacent fabrics were used, the numerical grey scale rating or instrumental assessment for staining of each kind of adjacent fabric used;
- f) if a multifibre adjacent fabric was used, the type of multifibre adjacent fabric used and the numerical grey scale rating or instrumental assessment for staining of each fibre in the multifibre adjacent fabric;
- g) whether steel balls have been used in the 40 °C or 50 °C tests;
- h) whether the treatment in the acetic acid reagent described in A.7 was conducted;
- i) whether the specimen was air dried or dried by pressing as described in A.9. If the latter, the temperature of the pressing treatment shall be reported;
- j) the reference detergent and bleach activator.

Annex A (normative)

ECE non-phosphate reference detergent/TAED procedure

A.1 The reference detergent is supplied in three separate parts and the composition as given in Table A.1:

- a) ECE non phosphate reference detergent base powder (1998 formulation);
- b) Bleach activator, tetra-acetylenediamine (TAED);
- c) Sodium perborate tetrahydrate ($\text{Na BO}_3 \cdot 4\text{H}_2\text{O}$).

For details of supply apply to: The Society of Dyers & Colourists, PO Box 244, 82 Grattan Road, Bradford BD1 2JB, England or Deutsche Echtheitskommission, Institutsweg 1, 85435 Erding, Germany.

Table A.1 — ECE 1998 non-phosphate reference detergent (without optical brightener)

Base detergent	%
Linear sodium alkyl benzene sulphonate (mean length of alkane chain $\text{C}_{11,5}$)	9,7
Ethoxylated fatty alcohol C_{12-18} (7EO)	5,2
Sodium soap, chain length C_{12-17} 46 % : C_{18-20} 54 %	3,6
Foam inhibitor (DC-42485)	4,5
Sodium aluminium silicate (zeolite 4A)	32,5
Sodium carbonate	11,8
Sodium salt of a copolymer from acrylic and maleic acid	5,2
Sodium silicate ($\text{SiO}_2:\text{Na}_2\text{O} = 3,3:1$)	3,4
Carboxymethylcellulose (CMC)	1,3
Diethylene triamine penta (methylene phosphonic acid)	0,8
Sodium sulfate	9,8
Water	12,2
Tetra-acetylenediamine (TAED) (100 % active)^a	As separate addition
Sodium perborate tetrahydrate	As separate addition
^a The activity of the supplied TAED will be specified and is likely to be less than 100 %. The required amount, in grams, of TAED per litre of wash liquor is calculated: $\frac{0,15 \times 100}{\% \text{ activity}}$	

If it is desired to evaluate the effect of enzymes the optional addition of the following enzymes can be made with a corresponding reduction in the base detergent powder.

- Protease: Savinase 12T, reduction of 0,5 %
- Lipase: Lipolase 100T, reduction of 0,1 %
- Amylase: Thermamyl 60T, reduction of 0,3 %
- Cellulase: Celluzyme 0,7T, reduction of 0,3 %