

---

---

**Textiles — Tests for colour fastness —**  
**Part E06:**  
**Colour fastness to spotting: Alkali**

*Textiles — Essais de solidité des teintures —*  
*Partie E06: Solidité des teintures aux alcalis*

STANDARDSISO.COM : Click to view the full PDF of ISO 105-E06:2006



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 105-E06:2006

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 105-E06 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

This fourth edition cancels and replaces the third edition (ISO 105-E06:1989), which has been technically revised. It also incorporates Technical Corrigendum ISO 105-E06:1989/Cor. 1:2002.

ISO 105 was previously published in 13 "parts", each designated by a letter (e.g. "Part A"), with publication date between 1978 and 1985. Each part contained a series of "sections", each designated by the respective part letter and by a two-digit serial number (e.g. "Section A01"). These sections are now being republished as separate documents, themselves designated "parts" but retaining their earlier alphanumeric designations. A complete list of these parts is given in ISO 105-A01.



# Textiles — Tests for colour fastness —

## Part E06: Colour fastness to spotting: Alkali

### 1 Scope

This part of ISO 105 specifies a method for determining the resistance of the colour of textiles of all kinds, and in all forms, to the action of dilute alkaline solutions.

Three tests differing in severity are provided. Any or all may be used, depending on the nature of the fibre.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A01, *Textiles — Tests for colour fastness — Part A01: General principles of testing*

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 105-A05, *Textiles — Tests for colour fastness — Part A05: Instrumental assessment of change in colour for determination of grey scale rating*

ISO 105-E07, *Textiles — Tests for colour fastness — Part E07: Colour fastness to spotting: Water*

### 3 Principle

The specimens are steeped in or spotted with prepared reagents by means of simple laboratory equipment. The change in the colour of the textile, while it is still wet and after drying, is assessed either visually or instrumentally.

### 4 Reagents and materials

4.1 **Pipette or dropper.**

4.2 **Glass rod**, with rounded end.

4.3 **Glass beaker.**

4.4 **Grey scale for assessing change in colour**, complying with ISO 105-A02.

4.5 **Sodium carbonate solution**, containing 100 g of anhydrous sodium carbonate ( $\text{Na}_2\text{CO}_3$ ) per litre of water (4.8).

**4.6 Calcium hydroxide paste**, containing 1 g of calcium hydroxide  $[\text{Ca}(\text{OH})_2]$  mixed with 1 g to 2 g of water (4.8).

**4.7 Ammonium hydroxide**, solution containing 28 % of ammonium hydroxide ( $\text{NH}_4\text{OH}$ ).

**4.8 Grade 3 water** (see ISO 105-A01).

NOTE See Table 1 for a list of the chemicals and pH levels of the reagents used in this method.

## 5 Test specimen

**5.1** Prepare a test specimen as described in 5.2 to 5.4 for each alkali to be used.

**5.2** If the textile to be tested is fabric, use a specimen measuring 40 mm × 100 mm.

**5.3** If the textile to be tested is yarn, knit it into fabric and use a specimen measuring 40 mm × 100 mm, or make a wick of parallel lengths 100 mm long and about 5 mm in diameter, tied near both ends.

**5.4** If the textile to be tested is loose fibre, comb and compress enough of it to form a sheet measuring 40 mm × 100 mm.

## 6 Procedure

### 6.1 Sodium carbonate

**6.1.1** Place the specimen in a clean dry flat-bottomed dish. Spot the specimen at room temperature with the sodium carbonate solution (4.5) so that after working the solution into the specimen with the glass rod, a spot of diameter approximately 20 mm is formed. In the case of water-repellent fabrics, the amount of solution shall not exceed 0,5 ml.

**6.1.2** Place the specimen on a flat surface and allow to dry at room temperature; brush it to remove the sodium carbonate residues.

**6.1.3** If brushing is not enough to completely eliminate the whitish ring caused by spotting with sodium carbonate, rinse the specimen in a glass beaker for 1 min with 100 ml of Grade 3 water (4.8) at room temperature. Allow the specimen to dry at room temperature.

### 6.2 Calcium hydroxide

**6.2.1** Spot the specimen at room temperature with the calcium hydroxide paste (4.6).

**6.2.2** Place the specimen on a flat surface and allow to dry at room temperature; brush it to remove the calcium hydroxide residues.

**6.2.3** If brushing is not enough to completely eliminate the whitish ring caused by spotting with calcium hydroxide, rinse the specimen in a glass beaker for 1 min with 100 ml of Grade 3 water (4.8) at room temperature. Allow the specimen to dry at room temperature.

### 6.3 Ammonium hydroxide

**6.3.1** Steep the specimen for 2 min in ammonium hydroxide solution (4.7) at room temperature.

**6.3.2** Place the specimen on a flat surface and allow to dry at room temperature without rinsing.