
Ceramic tiles —

**Part 1:
Sampling and basis for acceptance**

Carreaux et dalles céramiques —

Partie 1: Échantillonnage et conditions de réception

STANDARDSISO.COM : Click to view the full PDF of ISO 10545-1:2014



STANDARDSISO.COM : Click to view the full PDF of ISO 10545-1:2014



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Terms and definitions	1
3 Principle	2
4 Constitution of inspection lots	2
5 Extent of the inspection	2
6 Sampling	2
7 Inspection	2
8 Determination of acceptability of inspection lots	3
8.1 Inspection by attributes	3
8.2 Inspection by the average value	3
9 Acceptance Report	3
Bibliography	8

STANDARDSISO.COM : Click to view the full PDF of ISO 10545-1:2014

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 189, *Ceramic Tiles*.

This second edition cancels and replaces the first edition (ISO 10545-1:1995), which has been technically revised.

ISO 10545 consists of the following parts, under the general title *Ceramic Tiles*:

- *Part 1: Sampling and basis for acceptance*
- *Part 2: Determination of dimensions and surface quality*
- *Part 3: Determination of water absorption, apparent porosity, apparent relative density and bulk density*
- *Part 4: Determination of modulus of rupture and breaking strength*
- *Part 5: Determination of impact resistance by measurement of coefficient of restitution*
- *Part 6: Determination of resistance to deep abrasion for unglazed tiles*
- *Part 7: Determination of resistance to surface abrasion for glazed tiles*
- *Part 8: Determination of linear thermal expansion*
- *Part 9: Determination of resistance to thermal shock*
- *Part 10: Determination of moisture expansion*
- *Part 11: Determination of crazing resistance for glazed tiles*
- *Part 12: Determination of frost resistance*
- *Part 13: Determination of chemical resistance*
- *Part 14: Determination of resistance to stains*

- *Part 15: Determination of lead and cadmium given off by glazed tiles*
- *Part 16: Determination of small colour differences*

STANDARDSISO.COM : Click to view the full PDF of ISO 10545-1:2014

STANDARDSISO.COM : Click to view the full PDF of ISO 10545-1:2014

Ceramic tiles —

Part 1: Sampling and basis for acceptance

1 Scope

This part of ISO 10545 specifies rules for batching, sampling, inspection, and acceptance/rejection of ceramic tiles.

2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

2.1

order

quantity of tiles ordered at one time

Note 1 to entry: An order may consist of one or more consignments.

2.2

consignment

quantity of tiles delivered during a period of 2 d

2.3

homogeneous consignment/subconsignment

consignment or subconsignment that consists of tiles from one manufacturer, produced under conditions and with properties that are presumed uniform

2.4

inspection lot

quantity of tiles submitted for inspection manufactured by one manufacturer under conditions and with properties that are presumed uniform

2.5

sample

specified number of tiles taken from an inspection lot

2.6

sample size

number of tiles to be tested for each property

2.7

requirement

required characteristic as specified for the property in the relevant product standard

2.8

non-conforming unit

tile that does not meet the requirement for the property concerned

3 Principle

This part of ISO 10545 provides for a sampling inspection system with a double sampling plan, partly for the method of inspection by attributes (individual values) and partly for a method of inspection by average values (variables).

The number of tiles to be tested varies for each property (see [Table 1](#)).

4 Constitution of inspection lots

An inspection lot can consist of one or more homogeneous consignments or subconsignments.

Any consignment which is not homogeneous shall be divided into subconsignments which are assumed to be homogeneous and which might then constitute inspection lots.

If non-homogeneity is not relevant to the properties to be tested, by agreement between the supplier and consumer, the consignment can be treated as homogeneous.

NOTE For example, a consignment of tiles, of the same type with different glazes, can be homogeneous with regard to dimensions and water absorption and non-homogeneous with regard to surface quality. In the same way, accessories which differ only in shape from the remaining tiles in the sample can be considered homogeneous with respect to the other properties.

5 Extent of the inspection

The choice of properties to be considered for inspection shall be subject to agreement between the supplier and consumer and might depend on the size of the inspection lot.

NOTE In principle, a complete range of tests has to only be executed for inspection lots of more than 5 000 m² of tiles. Testing is usually not considered to be necessary for inspection lots of less than 1 000 m² of tiles.

The number of inspection lots to be drawn for testing shall be subject to agreement between the parties concerned.

6 Sampling

6.1 The sampling location shall be subject to agreement between the supplier and consumer.

6.2 One or more representatives of each party concerned can be present at the time the sample is taken. Samples shall be taken at random from the inspection lot. Two samples shall be taken. It might not be necessary to test the second sample. Each sample shall be packed separately and shall be sealed and marked as agreed by the parties concerned.

6.3 For each property, the number of tiles to be tested is indicated as "sample size" in column 2 of [Table 1](#).

7 Inspection

7.1 The tiles in the sample shall be tested according to the test methods specified in the relevant product standards.

7.2 The test results shall be evaluated according to [Clause 8](#).

8 Determination of acceptability of inspection lots

8.1 Inspection by attributes

8.1.1 When the number of non-conforming units found in the initial sample is less than or equal to the acceptance number Ac_1 , indicated in column 3 of [Table 1](#), the inspection lot from which the sample was drawn shall be considered acceptable.

8.1.2 When the number of non-conforming units found in the initial sample is greater than or equal to the rejection number Re_1 , indicated in column 4 of [Table 1](#), this justifies rejection of the inspection lot.

8.1.3 When the number of non-conforming units found in the initial sample lies between the acceptance number and the rejection number (columns 3 and 4 of [Table 1](#)), a second sample of the same size as the initial sample shall be taken and tested.

8.1.4 The number of non-conforming units found in the initial and second samples shall be totaled.

8.1.5 If the total number of non-conforming units is less than or equal to the acceptance number Ac_2 , indicated in column 5 of [Table 1](#), the inspection lot shall be considered acceptable.

8.1.6 If the total number of non-conforming units is greater than or equal to the second rejection number Re_2 , indicated in column 6 of [Table 1](#), this justifies rejection of the inspection lot.

8.1.7 When the relevant product standard calls for more than one property to be tested, the second sample taken (see [8.1.3](#)) shall only be inspected in accordance with those tests which, at the time of inspection of the initial sample, gave numbers of non-conforming units between the acceptance number Ac_1 and the rejection number Re_1 .

8.2 Inspection by the average value

8.2.1 If the average value (\bar{x}_1) of the test results of the initial sample meets the requirements, the inspection lot shall be considered acceptable (column 7 of [Table 1](#)).

8.2.2 If the average value (\bar{x}_1) does not meet the requirements, a second sample of the same size as the initial sample shall be taken (column 8 of [Table 1](#)).

8.2.3 If the average value (\bar{x}_2) of the test results of the combined initial and second samples meets the requirements, the inspection lot shall be considered acceptable (column 9 of [Table 1](#)).

8.2.4 If the average value (\bar{x}_2) does not meet the requirements, this justifies rejection of the inspection lot (column 10 of [Table 1](#)).

9 Acceptance Report

The acceptance report shall include the following information:

- a) a reference to this part of ISO 10545 (i.e. ISO 10545-1);
- b) a description of the tiles;
- c) the sampling procedure;
- d) the constitution of the inspection lot;

- e) the determination of acceptability for each of the tested characteristics.

STANDARDSISO.COM : Click to view the full PDF of ISO 10545-1:2014

Table 1 — Sampling Criteria

1	2		3	4			5			6			7	8		9	10	11
	Sample size			Inspection by attribute, if required			Inspection by average value, if required			Inspection by attribute, if required		Inspection by average value, if required		Test method				
Properties	Initial	Second	Acceptance number A_{C1}	Rejection number Re_1	Acceptance number A_{C2}	Rejection number Re_2	Initial sample	Acceptable if	Second sample to be drawn if	Initial sample	Acceptable if	Second sample to be drawn if	Initial + second sample	Acceptable if	Second sample to be drawn if	Test method		
	Dimensions ^a	10	10	0	2	1	2	—	—	—	—	—	—	—	—	—	2	
30		30	1	3	3	4	—	—	—	—	—	—	—	—	—			
Surface quality ^b	40	40	1	4	4	5	—	—	—	—	—	—	—	—	—			
	50	50	2	5	5	6	—	—	—	—	—	—	—	—	—			
	60	60	2	5	6	7	—	—	—	—	—	—	—	—	—			
	70	70	2	6	7	8	—	—	—	—	—	—	—	—	—	2		
	80	80	3	7	8	9	—	—	—	—	—	—	—	—	—			
	90	90	4	8	9	10	—	—	—	—	—	—	—	—	—			
	100	100	4	9	10	11	—	—	—	—	—	—	—	—	—			
	1 m ²	1 m ²	4%	9%	5%	>5%	—	—	—	—	—	—	—	—	—			
	Water absorption ^c	5 ^d	5 ^d	0	2	1	2	—	$\bar{x}_1 > L^e$	$\bar{x}_1 < L$	—	$\bar{x}_2 > L$	$\bar{x}_2 < L$	—	$\bar{x}_2 > L$	$\bar{x}_2 < L$	3	
		10	10	0	2	1	2	—	$\bar{x}_1 < U^f$	$\bar{x}_1 > U$	—	$\bar{x}_2 < U$	$\bar{x}_2 > U$	—	$\bar{x}_2 < U$	$\bar{x}_2 > U$		
Modulus of rupture ^c	7 ^g	7 ^g	0	2	1	2	—	$\bar{x}_1 > L$	$\bar{x}_1 < L$	—	$\bar{x}_2 > L$	$\bar{x}_2 < L$	—	$\bar{x}_2 > L$	$\bar{x}_2 < L$	4		
	10	10	0	2	1	2	—	$\bar{x}_1 > L$	$\bar{x}_1 < L$	—	$\bar{x}_2 > L$	$\bar{x}_2 < L$	—	$\bar{x}_2 > L$	$\bar{x}_2 < L$			
Breaking Strength ^c	7 ^g	7 ^g	0	2	1	2	—	$\bar{x}_1 > L$	$\bar{x}_1 < L$	—	$\bar{x}_2 > L$	$\bar{x}_2 < L$	—	$\bar{x}_2 > L$	$\bar{x}_2 < L$	4		
	10	10	0	2	1	2	—	$\bar{x}_1 > L$	$\bar{x}_1 < L$	—	$\bar{x}_2 > L$	$\bar{x}_2 < L$	—	$\bar{x}_2 > L$	$\bar{x}_2 < L$			
Deep Abrasion UGL	5	5	0	2 ^h	1 ^h	2 ^h	—	—	—	—	—	—	—	—	—	6		
Coefficient of linear thermal expansion	2	2	0	2 ⁱ	1 ⁱ	2 ⁱ	—	—	—	—	—	—	—	—	—	8		

Table 1 (continued)

1	2	3			4			5			6			7		8		9		10		11
		Sample size		Acceptance number Ac_1	Initial sample		Rejection number Re_1	Inspection by attribute, if required		Acceptance number Ac_2	Rejection number Re_2	Initial sample		Inspection by average value, if required		Acceptable if	Second sample to be drawn if	Initial + second sample	Acceptable if	Second sample to be drawn if	Test method	
Crazing resistance	5	5	0		2	1		2	—			—	—	—	—							—
Chemical resistance	5	5	0	2	1	2	—	—	—	—	—	—	—	—	—	—	—	—	—	—	13	
Stain resistance	5	5	0	2	1	2	—	—	—	—	—	—	—	—	—	—	—	—	—	—	14	
Frost resistance	10	—	0	1	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	12	
Thermal shock resistance	5	5	0	2	1	2	—	—	—	—	—	—	—	—	—	—	—	—	—	—	9	
Moisture expansion	5	—	—	—	—	—	Attribution by manufacturer's declaration					—	—	—	—	—	—	—	—	—	10	
Resistance to abrasion G_k	11	—	—	—	—	—	Attribution by manufacturer's declaration					—	—	—	—	—	—	—	—	—	7	
Colour difference	5	—	—	—	—	—	Attribution by manufacturer's declaration					—	—	—	—	—	—	—	—	—	—	16
Impact resistance	5	—	—	—	—	—	Attribution by manufacturer's declaration					—	—	—	—	—	—	—	—	—	—	5
Lead and cadmium release	5	—	—	—	—	—	Attribution by manufacturer's declaration					—	—	—	—	—	—	—	—	—	—	15