
**Intravascular catheters — Sterile and
single-use catheters —**

Part 7:
**Peripherally inserted central
catheters**

*Cathéters intravasculaires — Cathéters stériles et non réutilisables —
Partie 7: Cathéters centraux à insertion périphérique*

STANDARDSISO.COM : Click to view the full PDF of ISO 10555-7:2023



STANDARDSISO.COM : Click to view the full PDF of ISO 10555-7:2023



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

| | Page |
|---|----------|
| Foreword..... | iv |
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Terms and definitions | 1 |
| 4 Requirements | 2 |
| 4.1 General..... | 2 |
| 4.2 Distance markings..... | 2 |
| 4.3 Lumen markings..... | 2 |
| 4.4 Peak tensile force..... | 2 |
| 4.4.1 General..... | 2 |
| 4.4.2 Catheters excluding the tip..... | 2 |
| 4.4.3 Tip tensile force..... | 2 |
| 4.5 Information to be supplied by the manufacturer..... | 3 |
| Annex A (informative) Rationale and guidance | 4 |
| Bibliography | 5 |

STANDARDSISO.COM : Click to view the full PDF of ISO 10555-7:2023

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 84, *Devices for administration of medicinal products and catheters*.

A list of all parts in the ISO 10555 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Intravascular catheters — Sterile and single-use catheters —

Part 7: Peripherally inserted central catheters

1 Scope

This document specifies general requirements and test method for peripherally inserted central catheters (PICC), supplied in the sterile condition and intended for single use, for any application.

It is not applicable to intravascular catheter accessories, e.g. those covered by ISO 11070.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10555-1, *Intravascular catheters — Sterile and single-use catheters — Part 1: General Requirements*

ISO 10555-3, *Intravascular catheters — Sterile and single-use catheters — Part 3: Central venous catheters*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 10555-1 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

peripherally inserted central catheter

PICC

type of central catheter where the tip resides centrally but the insertion into the vasculature is performed in the peripheral veins (typically upper arm, but other peripheral sites as well)

3.2

outside diameter

largest diameter of the catheter or pre- and post-hydration largest diameters of hydratable catheters along the non-tapered length

Note 1 to entry: The tapered length is the proximal portion of the effective length where the nominal diameter of the catheter is gradually increased (from distal to proximal direction).

4 Requirements

4.1 General

Catheters shall conform to ISO 10555-1, except for the peak tensile force for which the requirements in [4.4](#) of this document shall apply.

4.2 Distance markings

If the catheter is provided with distance markings, the marking system shall indicate the length of the catheter. From the first mark, the distance between marks shall not exceed 5 cm.

4.3 Lumen markings

For multi-lumen catheters, the identification of each lumen shall be apparent to the user, and for catheters with staggered tips (exit points) the relative position of the distal opening to the tip of the catheter shall be apparent to the user.

4.4 Peak tensile force

4.4.1 General

Test the catheter for peak tensile force in accordance with ISO 10555-1 using the requirement values listed in the following subclauses.

4.4.2 Catheters excluding the tip

- a) For catheters not constructed with silicone materials, the peak tensile force of each test piece shall be as given in ISO 10555-1.
- b) For catheters constructed with silicone materials, the peak tensile force shall be as given in [Table 1](#).

This document does not specify requirements for peak tensile force for tubing of less than 0,75 mm outside diameter (pre-hydration outside diameter for hydratable intravascular catheters). For those cases, the peak tensile force shall be determined by the manufacturer based on risk assessment.

Table 1 — Peak tensile force of silicone catheter test pieces

| Effective outside diameter range of tubular portion of test piece mm | Minimum peak tensile force N |
|---|---------------------------------|
| ≥ 0,75 and < 1,15 | 1,6 |
| ≥ 1,15 and < 1,85 | 3,4 |

NOTE See [Annex A](#) for supplementary information.

4.4.3 Tip tensile force

For catheter tips not exceeding 20 mm in length, the minimum peak tensile force of the tip shall be as given in [Table 1](#) for silicone-based catheters and as given in [Table 2](#) for any other material-based catheters when tested in accordance with the method given in ISO 10555-1.

For distal tips of less than 3 mm length, the peak tensile force requirement shall be as given in ISO 10555-1.

**Table 2 — Minimum peak tensile force of tips of length not exceeding 20 mm
(for non-silicone PICCs)**

| Smallest outside diameter of catheter body mm | Minimum peak tensile force N |
|---|------------------------------------|
| $\geq 0,55$ and $< 0,75$ | 3 |
| $\geq 0,75$ and $< 1,85$ | 4 |
| $\geq 1,85$ | 5 |

4.5 Information to be supplied by the manufacturer

Information supplied by the manufacturer shall conform to ISO 10555-1 and ISO 10555-3 and shall also indicate, for each lumen, whether the lumen is compatible with power injection.

STANDARDSISO.COM : Click to view the full PDF of ISO 10555-7:2023

Annex A (informative)

Rationale and guidance

A.1 General

This annex provides a rationale for tensile requirements for silicone catheters of this document.

A.2 Background

The peak tensile requirements for the catheter shaft and associated junctions were established in 1995 with the first edition of ISO 10555-1 (ISO 10555-1:1995, Table 1). These requirements have remained unchanged since the first edition. Prior to 1995, small-bore silicone PICCs [\leq 5 Fr (1,67 mm) outer diameter] were present on the market and some of these products are still in use to this day. One of the notable aspects of these small-bore silicone PICCs is that many of these products do not meet the peak tensile requirements, even though some products predate the original publication of ISO 10555-1 by 5 years to 10 years. As such, an assessment of the current state of silicone PICCs on the market was undertaken to determine whether a more appropriate tensile standard was necessary for these products.

A.3 Method

In order to capture an accurate picture of the silicone PICCs currently on the market, a benchmarking of silicone PICCs was conducted. Catheters from 5 different manufacturers were used, ranging in size from 1,98 Fr to 4 Fr (0,66 mm to 1,33 mm), with a requirement that a minimum sample size of $N = 10$ per catheter configuration be provided for testing. The catheters were tested for shaft tensile and shaft to hub tensile at 3 different manufacturer's laboratories in order to ensure unbiased testing.

A.4 Findings and discussion related to [Table 1](#)

The conclusions from the benchmarking testing were that almost all of the silicone catheters tested did not meet the tensile requirements in the first edition of ISO 10555-1 (ISO 10555-1:1995, Table 1), which raises questions about the origins of the tensile requirements and whether silicone catheters on the market in 1995 were adequately considered when developing the tensile requirements. The catheter shaft and shaft to hub tensile data were pooled for each French size, and the 3 Fr (1 mm) and 4 Fr (1,33 mm) catheter data were further analysed to determine an appropriate tensile specification for these two sizes of silicone PICCs. Using a requirement of 95 % CI/95 % reliability, a tensile value that captured 95 % of the tensile values was generated and is shown in [Table 1](#). These values provide an accurate assessment of the tensile performance of silicone PICCs ranging from 3 Fr to 4 Fr (1 mm to 1,33 mm) and create realistic tensile requirements for this size and material of catheter.

Another important conclusion was that the values listed in [Table 1](#) are only applicable to silicone catheters. The main reason for this is that, while silicone has a lower tensile value than other materials commonly used in PICCs (such as polyurethane), silicones have a high elongation at break relative to other materials. PICCs are subjected to a range of forces while they are implanted in the vasculature. However, pure axial forces, i.e. those tested in ISO 10555-1:2013, Annex B, are not readily present except when attempting to remove a catheter where a portion of implanted catheter is adhered to the patient (i.e. fibrin sheath formation, deep vein thrombosis (DVT), etc.). When these conditions are significant enough to provide tensile force during removal, the high elongation of silicone provides a visual cue ("early warning indication") that the catheter is being subjected to higher-than-normal strain and further investigation should be conducted before continuing to remove the catheter.