

---

---

**Fibre ropes of polyester/polyolefin dual  
fibres**

*Cordages en fibres bi-matériaux polyester/polyoléfines*

STANDARDSISO.COM : Click to view the full PDF of ISO 10556:2009



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 10556:2009



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10556 was prepared by Technical Committee ISO/TC 38, *Textiles*.

STANDARDSISO.COM : Click to view the full PDF of ISO 10556:2009

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 10556:2009

# Fibre ropes of polyester/polyolefin dual fibres

## 1 Scope

This International Standard specifies requirements for 3-strand hawser-laid, 8-strand and 12-strand braided fibre ropes made of polyester in combination with polyolefin, and gives rules for their designation.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1968, *Fibre ropes and cordage — Vocabulary*

ISO 2307, *Fibre ropes — Determination of certain physical and mechanical properties*

ISO 9554:2005, *Fibre ropes — General specifications*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1968 apply.

## 4 Designation

Fibre ropes shall be designated by the following:

- the words “fibre rope”;
- the number of this International Standard;
- the construction or type of the rope (see Clause 6);
- the reference number of the rope;
- the materials from which the rope is made;
- the level of performance of the rope: fibre rope or higher-strength (hs) fibre rope.

EXAMPLE 1 Designation of a 3-strand hawser-laid rope, reference number 20 (type A), corresponding to a linear density of 194 ktex, made of polyester/polyolefin dual fibre:

**Fibre rope ISO 10556 - A - 20 - polyester/polyolefin**

EXAMPLE 2 Designation of a 12-strand braided rope, reference number 20 (type T), corresponding to a linear density of 221 ktex, made of higher-strength polyester/polyolefin dual fibre:

**Fibre rope ISO 10556 - T - 20 - polyester/polyolefin (hs)**

## 5 Materials

### 5.1 Fibres

**5.1.1 Polyester:** the polyester portion of the rope shall be a continuous multifilament, heat- and light-resistant fibre of industrial (high tenacity) grade.

**5.1.2 Polyolefin:** the polyolefin portion of the rope shall be of suitable tenacity to meet all the requirements of this International Standard.

NOTE Polyolefin can be polypropylene, or a mixture of polypropylene and polyethylene with a minimum of 15 % and a maximum of 50 % of polyethylene.

### 5.2 Yarns

**5.2.1** The cover yarns of each strand of fibre ropes shall be made with polyester fibres covering a polyolefin core and shall contain a minimum of 40 % by mass of polyester fibre (see Table 1).

NOTE When interior yarns are used, they may consist of 100 % polyolefin fibres.

**5.2.2** All the yarns used in higher-strength fibre ropes shall be made with polyester fibres covering a polyolefin core and shall contain a minimum of 40 % by mass of polyester fibre (see Table 2).

## 6 General requirements

**6.1** Polyester/polyolefin dual-fibre ropes shall be constructed in one of the following ways:


- type A: 3-strand hawser-laid rope (see Figure 1);
- type L: 8-strand braided rope (see Figure 2);
- type T: 12-strand braided rope (see Figure 3).



Figure 1 — Shape of a 3-strand hawser-laid rope (type A)



Figure 2 — Shape of an 8-strand braided rope (type L)



<sup>a</sup> One-plait pitch.

Figure 3 — Shape of a 12-strand braided rope (type T)

**6.2** Construction, manufacture, lay, labelling, packaging, invoicing and delivery lengths shall conform to ISO 9554.

## 7 Physical properties

The linear density and minimum breaking force shall conform to Tables 1 and 2.

Table 1 — Fibre ropes: 3-strand hawser-laid rope (type A), 8-strand braided rope (type L) and 12-strand braided rope (type T) of polyester/polyolefin dual fibres

Reference number <sup>a</sup>	Linear density <sup>bc</sup>		Minimum breaking force <sup>de</sup>	
	Nominal ktex	Tolerance %	kN	
			Unspliced ropes	Ropes with eye-spliced terminations
6	17,5	±10	6,8	6,1
8	31,0		11,9	10,7
10	48,5	±8	18,2	16,4
12	69,9		25,7	23,1
14	95,1	±5	34,7	31,2
16	124		44,8	40,3
18	157		56,1	50,5
20	194		68,7	61,8
22	235		82,1	73,9
24	279		96,3	86,7
26	328		113	102
28	380		130	117
30	437		148	133
32	497		167	150
36	629		210	189
40	776		257	231
44	939		308	277
48	1 110		364	328
52	1 320		424	382
56	1 520		489	440
60	1 750		558	502
64	1 990		631	568
68	2 250	707	636	
72	2 520	789	710	
80	3 110	963	867	
88	3 750	1 160	1 040	
96	4 470	1 370	1 230	
104	5 260	1 590	1 430	
112	6 050	1 840	1 660	
120	6 980	2 100	1 890	
128	7 950	2 370	2 130	
136	8 950	2 660	2 390	
144	10 100	2 970	2 670	

Table 1 (continued)

Reference number <sup>a</sup>	Linear density <sup>bc</sup>		Minimum breaking force <sup>de</sup>	
	Nominal ktex	Tolerance %	kN	
			Unspliced ropes	Ropes with eye-spliced terminations
152	11 300	±5	3 290	2 960
160	12 500		3 630	3 270

<sup>a</sup> The reference number corresponds to the approximate diameter, in millimetres.

<sup>b</sup> The linear density, in kilotex, corresponds to the net mass per length of the rope, expressed in grams per metre or in kilograms per kilometre.

<sup>c</sup> The linear density is obtained under reference tension and is measured as specified in ISO 2307.

<sup>d</sup> The breaking forces relate to new, dry and wet ropes.

<sup>e</sup> A force determined by the test methods specified in ISO 2307 is not necessarily an accurate indication of the force at which that rope might break in other circumstances and situations. The type and quality of termination, the rate of force application, prior conditioning and previous force applications to the rope can significantly influence the breaking force. A rope bent around a post, capstan, pulley or sheave may break at a significantly lower force. A knot or other distortion in a rope may significantly reduce the breaking force.

Table 2 — Higher-strength fibre ropes: 3-strand hawser-laid rope (type A), 8-strand braided rope (type L) and 12-strand braided rope (type T) of polyester/polyolefin dual fibres

Reference number <sup>a</sup>	Linear density <sup>bc</sup>		Minimum breaking force <sup>de</sup>	
	Nominal ktex	Tolerance %	kN	
			Unspliced ropes	Ropes with eye-spliced terminations
6	19,9	±10	7,56	6,80
8	35,4		13,2	11,9
10	55,3	±8	20,2	18,2
12	79,6		28,6	25,7
14	108	±5	38,5	34,7
16	142		49,8	44,8
18	179		62,3	56,1
20	221		76,3	68,7
22	268		91,2	82,1
24	319		107	96
26	374		125	113
28	434		144	130
30	498		164	148
32	566		186	167
36	717		233	210
40	885		285	257
44	1 070		342	308