
**Resilient floor coverings —
Specification for rubber sheet floor
coverings with backing**

*Revêtements de sol résilients — Spécifications pour les revêtements de
sol en caoutchouc avec dossier*

STANDARDSISO.COM : Click to view the full PDF of ISO 10575:2012



STANDARDSISO.COM : Click to view the full PDF of ISO 10575:2012



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10575 was prepared by Technical Committee ISO/TC 219, *Floor coverings*.

STANDARDSISO.COM : Click to view the full PDF of ISO 10575:2012

STANDARDSISO.COM : Click to view the full PDF of ISO 10575:2012

Resilient floor coverings — Specification for rubber sheet floor coverings with backing

1 Scope

This International Standard specifies the characteristics of rubber sheet floor coverings with backing.

This International Standard includes a classification system based on intensity of use, which shows where resilient floor coverings should provide satisfactory service.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-B02, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test*

ISO 4649:2010, *Rubber, vulcanized or thermoplastic — Determination of abrasion resistance using a rotating cylindrical drum device*

ISO 4918, *Resilient, textile and laminate floor coverings — Castor chair test*

ISO 7619-1, *Rubber, vulcanized or thermoplastic — Determination of indentation hardness — Part 1: Durometer method (Shore hardness)*

ISO 23999, *Resilient floor coverings — Determination of dimensional stability and curling after exposure to heat*

ISO 24340, *Resilient floor coverings — Determination of thickness of layers*

ISO 24341, *Resilient and textile floor coverings — Determination of length, width and straightness of sheet*

ISO 24343-1, *Resilient and laminate floor coverings — Determination of indentation and residual indentation — Part 1: Residual indentation*

ISO 24344, *Resilient floor coverings — Determination of flexibility and deflection*

ISO 24346, *Resilient floor coverings — Determination of overall thickness*

ASTM D883, *Standard Terminology Relating to Plastics*

ASTM D1566, *Standard Terminology Relating to Rubber*

ASTM D3389, *Standard Test Method for Coated Fabrics Abrasion Resistance (Rotary Platform Abrader)*

ASTM F1515, *Standard Test Method for Measuring Light Stability of Resilient Flooring by Colour Change*

EN 431, *Resilient floor coverings — Determination of peel resistance*

EN 663, *Resilient floor coverings — Determination of conventional pattern depths*

3 Terms and definitions

3.1

rubber material

polymeric binder in the rubber sheet floor covering with backing satisfying the definition of rubber in ASTM D1566, and having been vulcanized such that it became thermoset as defined in ASTM D883

3.2

relieved

having a permanent multi-level surface produced by mechanical means, with a minimal differential in height of 0,25 mm

4 Categories of rubber sheet floor coverings with backing

Rubber sheet floor coverings covered by this International Standard shall be categorized as:

- Category A: Homogeneous rubber sheet floor covering with backing — Floor covering based on natural and/or synthetic rubber with one or more layers of the same composition and colour, patterned throughout its thickness with either fibrous or foamed backing.
- Category B: Heterogeneous rubber sheet floor covering with backing — Floor covering based on natural and/or synthetic rubber consisting of a wear layer and other compact layers which differ in composition and/or design and can contain a reinforcement with either fibrous, foamed or other backing.
- Category C: Rubber sheet floor covering with backing with a decorative layer — Floor covering based on natural and/or synthetic rubber consisting of a decorative layer and other compact layer which differ in composition and/or design and can contain a reinforcement with either fibrous, foamed or other backing.

The thickness of the decorative layer shall at least reach the values given in Table 2. These values are based on the relationship of the appearance retaining after removing a specified thickness and the abrasion value measured.

The floor covering may have smooth, embossed or relieved pattern wearing surfaces.

5 Requirements

All rubber floor sheet with backing shall conform to the appropriate general requirements specified in Table 1, when tested in accordance with the test methods given therein.





Table 1 — General minimum requirements

Characteristic		Requirements		Test method
Overall thickness; Tolerance on nominal total gauge mm		average	Individual results	ISO 24346
	relieved	Nominal value ± 0,20 mm	Nominal value ± 0,25 mm	
	smooth or embossed	Nominal value ± 0,20 mm	Nominal value ± 0,25 mm	
Width		not less than specified		ISO 24341
Length		not less than specified		ISO 24341
Thickness of wear layer		not less than specified		ISO 24340
Dimensional stability		tolerance allowed 0,4 %		ISO 23999
Flexibility: diameter of mandrel 20 mm		no cracking		ISO 24344 Method A
Residual indentation		≤ 0,25 mm		ISO 24343-1
Abrasion resistance of wear layer		≤ 250 mm ³		ISO 4649:2010, Method A, vertical load (5 ± 0,1) N
	or	< 1 g		ASTM D3389 H18/500 g
Peel resistance		Mean value ≥ 50 N/50 mm or rupture in the foam		EN 431
Colour fastness to artificial light ^a		6 minimum on blue wool scale ≥ 3 on grey scale		ISO 105-B02 Method 3
	or	ΔE not greater than 8,0 after 300 h exposure		ASTM F1515
^a Expose a full size test specimen. Store a further test specimen in the dark, which will constitute the reference standard for assessment of colour change.				

6 Classification



The classification scheme for resilient floor coverings is described in ISO 10874. The requirements for rubber sheet floor coverings with backing in accordance with this scheme are specified in Table 2.

Table 2 — Classification minimum requirements

Class	Symbol	Level of use	Overall thickness nominal value (mm)		Minimum thickness of wear layer Category B, C	Relation PD ^a /TL ^b Category C EN 663	Resistance to castor chair for smooth or embossed pattern ISO 4918	Hardness of wear layer ISO 7619-1 Shore A
			Reliefed pattern	Smooth or embossed				
21		domestic moderate	2,5	2,5	1,0	≥ 0,6	No requirement	≥ 60
22		domestic general/medium						
23		domestic heavy	3,2	3,5	1,0	≥ 0,6	No requirement	≥ 60
31		commercial moderate						
32		commercial general	3,5	3,5	1,0	≥ 0,8	No disturbance to the surface other than slight change in appearance and no delamination shall occur after 25 000 cycles	≥ 75
33		commercial heavy						
34		commercial very heavy	3,5	3,5	1,0	≥ 0,8	No disturbance to the surface other than slight change in appearance and no delamination shall occur after 25 000 cycles	≥ 75
41		light industrial moderate						

STANDARDSISO.COM : Click to view the full PDF of ISO 10575:2012

Table 2 (continued)

Class	Symbol	Level of use	Overall thickness nominal value (mm)		Minimum thickness of wear layer Category B, C	Relation PD ^a /TL ^b Category C EN 663	Resistance to castor chair for smooth or embossed pattern ISO 4918	Hardness of wear layer ISO 7619-1 Shore A
			Relieved pattern	Smooth or embossed				
42		light industrial general		3,5	1,0	≥ 0,8	No disturbance to the surface other than slight change in appearance and no delamination shall occur after 25 000 cycles	≥ 75
43		light industrial heavy						

^a PD = Pattern depth in mm.

^b TL = Thickness loss in mm, calculated according to the formula below (EN 663).

STANDARDSISO.COM : Click to view the full PDF of ISO 10575:2012

$$TL = \frac{m_L}{\rho \cdot A_a}$$

where:

TL is thickness loss in mm;

m_L is weight loss in mg;

ρ is density in mg/mm³ (ISO 23996);

A_a is abraded area in mm² ($A_a = 3\,200\text{ mm}^2$, Taber-Test ASTM D3389).

7 Marking, labelling and packaging

Rubber sheet floor covering with backing and/or their packaging shall be marked as follows:

- a) number and date of this International Standard, i.e. ISO 10575:2012;
- b) manufacturer's or supplier's identification;
- c) product name;
- d) colour/pattern, and batch number if applicable;
- e) classes/symbols appropriate for the product.

STANDARDSISO.COM : Click to view the full PDF of ISO 10575:2012

Annex A (informative)

Optional properties

Where the following properties are required for specific applications, the floor covering should be tested in accordance with the appropriate methods:

- electrical resistance (see EN 1081 and ASTM F150);
- electrostatic propensity/static dissipation (see EN 1815);
- effect of stains/resistance to chemicals (see ISO 26987);
- cigarette resistance (see EN 1399): In general use, a rubber floor covering, depending on the colour and/or pattern, is expected to have the following rating when tested in accordance with EN 1399: Method A, stubbed cigarettes: rating 4 or higher; Method B, burning cigarettes: rating 3 or higher;
- reaction to fire; determination of the burning behaviour using a radiant heat source (see ISO 9239 and ASTM E648);
- reaction to fire; ignitability when subject to direct impingement of flame (ISO 11925-2);
- reaction to fire; specific optical density of smoke generated (ASTM E662).