
**Micaceous iron oxide pigments for
paints — Specifications and test methods**

*Pigments d'oxyde de fer micacé pour peintures — Spécifications
et méthodes d'essai*

STANDARDSISO.COM : Click to view the full PDF of ISO 10601:2007



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 10601:2007

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification	2
5 Required characteristics and their tolerances	2
6 Sampling	3
7 Assessment of thin-flake content	3
8 Test report	4

STANDARDSISO.COM : Click to view the full PDF of ISO 10601:2007

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10601 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 2, *Pigments and extenders*.

This second edition cancels and replaces the first edition (ISO 10601:1993), which has been technically revised.

The main technical changes are:

- a) the description of the grades has been changed and the grade "non-lamellar" deleted;
- b) the requirements for the residue on sieve have been changed.

Introduction

Micaceous iron oxide pigments were previously included in ISO 1248 (classified in the colour group “grey with metallic sheen”) but are explicitly excluded from the revised edition published in 2006. In this revised edition of ISO 10601, the requirements for micaceous iron oxide pigment have been defined more clearly and relate to an essentially lamellar particle shape.

Micaceous iron oxide pigments can vary in composition, particle size range, and particle shape depending on whether they are produced synthetically or, if a refined natural oxide, on the location where the ore was mined.

The primary use of micaceous iron oxide is in protective coatings for steelwork, and for optimum performance the pigment should have a high content of thin flake-like particles. The protective action is ascribed to the close packing of pigment platelets within the paint film, forming overlapping layers that lie roughly parallel to the substrate. This impedes penetration of corrosion promoters, reduces ultra-violet degradation of the binder and improves film strength. For less critical requirements, micaceous iron oxide pigment with a lower content of thin flakes may be acceptable. Therefore in this International Standard, micaceous iron oxide pigments are classified into two groups according to their thin-flake content as determined by microscopic examination (see Table 1).

For the purposes of this International Standard, pigments with a lamellar-particle content below 50 % are not considered to be “micaceous” or classified as “lamellar”.

STANDARDSISO.COM : Click to view the full PDF of ISO 10601:2007

Micaceous iron oxide pigments for paints — Specifications and test methods

1 Scope

This International Standard specifies the requirements and corresponding test methods for manufactured and natural micaceous iron oxide (MIO) pigments, in dry form, used primarily in protective coatings for steelwork.

In accordance with current practice, the general requirements for micaceous iron oxide pigments have been sub-divided to give

a) those requirements that are essential (see Table 2)

and

b) those requirements that are conditional upon prior agreement between the interested parties (see Table 3).

In certain instances, reference may be made to an agreed reference pigment.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 150, *Raw, refined and boiled linseed oil for paints and varnishes — Specifications and methods of test*

ISO 787-2, *General methods of test for pigments and extenders — Part 2: Determination of matter volatile at 105 °C*

ISO 787-3, *General methods of test for pigments and extenders — Part 3: Determination of matter soluble in water — Hot extraction method*

ISO 787-5, *General methods of test for pigments and extenders — Part 5: Determination of oil absorption value*

ISO 787-9, *General methods of test for pigments and extenders — Part 9: Determination of pH value of an aqueous suspension*

ISO 1248, *Iron oxide pigments — Specifications and methods of test*

ISO 3549, *Zinc dust pigments for paints — Specifications and test methods*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

micaceous iron oxide pigment

refined mineral (also known as specular haematite) or a manufactured product consisting essentially of iron(III) oxide, Fe₂O₃, that is grey in colour with a metallic sheen and consists essentially of particles having lamellar form

4 Classification

In this International Standard, micaceous iron oxide pigments are classified by grades according to their thin-flake content as shown in Table 1 and by types according to their residue on sieve as shown in Table 2.

Thin-flake micaceous iron oxide particles are defined as having a thickness such that they appear as sharply defined red translucent platelets when viewed under an optical microscope by transmitted light, i.e. with the light source behind the specimen under examination (see test method in Clause 7).

Table 1 — Lamellar classification

Grade	Thin-flake content %
A	> 65
B	50 to 65

5 Required characteristics and their tolerances

For micaceous iron oxide pigments complying with this International Standard, the essential requirements are specified in Tables 1 and 2 and the conditional requirements are referred to in Table 3.

The reference pigment and the conditional requirements set out in Table 3 shall be the subject of agreement between the interested parties.

The reference pigment shall comply with the requirements given in Table 1 (grade A or B) and Table 2 (type 1, 2 or 3).

Table 2 — Essential requirements

Characteristic	Requirement for MIO of type			Test method
	1	2	3	
Iron content, expressed as iron(III) oxide (Fe ₂ O ₃) (determined on the pigment after drying at 105 °C)	% (by mass)	min. 85		ISO 1248 ^a
Matter volatile at 105 °C	% (by mass)	max. 0,5		ISO 787-2
Matter soluble in water (hot-extraction method)	% (by mass)	max. 0,5		ISO 787-3
Residue on sieve, % (by mass)	63 µm	max. 5	> 5 but ≤ 15	ISO 3549
	105 µm	max. 0,1	> 15 but ≤ 35 max. 0,1	

^a The use of 60 ml of 37 % (by mass) hydrochloric acid, ρ approximately 1,19 g/ml, and 0,5 g of potassium chlorate is recommended to facilitate dissolution of the sample.

Table 3 — Conditional requirements

Characteristic	Requirement	Test method
pH of aqueous suspension	Shall not differ by more than 1 pH unit from that of the agreed reference pigment	ISO 787-9
Oil absorption value	Shall not differ by more than ± 15 % from that of the agreed reference pigment	ISO 787-5
Total calcium, expressed as calcium oxide, % (by mass)	To be agreed between the interested parties	ISO 1248

6 Sampling

Take a representative sample of the product to be tested, as described in ISO 15528.

7 Assessment of thin-flake content

7.1 Reagent

7.1.1 **Refined linseed oil**, complying with the requirements of ISO 150.

7.2 Apparatus

7.2.1 **Glass microscope slide**, approximately 25 mm × 75 mm × 1 mm, and cover slip.

7.2.2 **Glass rod**, approximately 100 mm long and 5 mm in diameter, with rounded end.

7.2.3 **Optical microscope**, capable of × 200 magnification, with a × 20 objective lens and fitted with high-intensity sub-stage illumination.