

---

---

**Gas cylinders — Compatibility of cylinder  
and valve materials with gas contents —**

Part 1:  
**Metallic materials**

*Bouteilles à gaz — Compatibilité des matériaux des bouteilles et des  
robinets avec les contenus gazeux —*

*Partie 1: Matériaux métalliques*

STANDARDSISO.COM : Click to view the full PDF of ISO 11114-1:2012



STANDARDSISO.COM : Click to view the full PDF of ISO 11114-1:2012



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

**Contents**

Page

Foreword .....	iv
Introduction.....	v
<b>1</b> <b>Scope</b> .....	<b>1</b>
<b>2</b> <b>Normative references</b> .....	<b>1</b>
<b>3</b> <b>Terms and definitions</b> .....	<b>2</b>
<b>4</b> <b>Materials</b> .....	<b>2</b>
<b>4.1</b> <b>General</b> .....	<b>2</b>
<b>4.2</b> <b>Cylinder materials</b> .....	<b>3</b>
<b>4.3</b> <b>Valve materials</b> .....	<b>3</b>
<b>5</b> <b>Compatibility criteria</b> .....	<b>3</b>
<b>5.1</b> <b>General</b> .....	<b>3</b>
<b>5.2</b> <b>Corrosion</b> .....	<b>4</b>
<b>5.3</b> <b>Hydrogen embrittlement phenomenon</b> .....	<b>5</b>
<b>5.4</b> <b>Generation of dangerous products</b> .....	<b>5</b>
<b>5.5</b> <b>Violent reactions (e.g. ignition)</b> .....	<b>5</b>
<b>5.6</b> <b>Stress corrosion cracking</b> .....	<b>5</b>
<b>6</b> <b>Material compatibility</b> .....	<b>5</b>
<b>6.1</b> <b>Table of compatibility for single gases (see Table 1)</b> .....	<b>5</b>
<b>6.2</b> <b>Compatibility for gas mixtures</b> .....	<b>5</b>
<b>6.3</b> <b>Using Table 1</b> .....	<b>6</b>
<b>Annex A</b> (informative) <b>Gas/materials NQSAB compatibility code</b> .....	<b>33</b>
<b>Bibliography</b> .....	<b>47</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 11114-1 was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 23, *Transportable gas cylinders*, in collaboration with ISO Technical Committee ISO/TC 58, *Gas cylinders*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 11114-1:1997), which has been technically revised. The main changes resulting from the revision of this part of ISO 11114 are

- the term “not recommended” has been replaced by “not acceptable”,
- the text has been clarified,
- a requirement for gas mixtures has been introduced.

ISO 11114 consists of the following parts, under the general title *Gas cylinders — Compatibility of cylinder and valve materials with gas contents*:

- *Part 1: Metallic materials*
- *Part 2: Non-metallic materials*
- *Part 3: Autogenous ignition test for non-metallic materials in oxygen atmosphere*
- *Part 4: Test methods for selecting metallic materials resistant to hydrogen embrittlement*

## Introduction

Industrial, medical and special gases (e.g. high-purity gases, calibration gases) can be transported or stored in gas cylinders. An essential requirement of the material from which such gas cylinders and their valves are manufactured is compatibility with the gas content.

Compatibility of cylinder materials with gas content has been established over many years by practical application and experience. Existing national and international regulations and standards do not fully cover this aspect.

This part of ISO 11114 is based on current international experience and knowledge.

Where there is any conflict between this International Standard and any applicable regulation, the regulation always takes precedence.

This part of ISO 11114 has been written to be in conformity with the UN Recommendations on the Transport of Dangerous Goods: Model Regulations. When published it will be submitted to the UN Sub Committee of Experts on the Transport of Dangerous Goods with a request that it be included in the Model Regulations.

STANDARDSISO.COM : Click to view the full PDF of ISO 11114-1:2012

[STANDARDSISO.COM](http://STANDARDSISO.COM) : Click to view the full PDF of ISO 11114-1:2012

# Gas cylinders — Compatibility of cylinder and valve materials with gas contents —

## Part 1: Metallic materials

### 1 Scope

This part of ISO 11114 provides requirements for the selection of safe combinations of metallic cylinder and valve materials and cylinder gas content.

The compatibility data given is related to single gases and to gas mixtures.

Seamless metallic, welded metallic and composite gas cylinders and their valves, used to contain compressed, liquefied and dissolved gases, are considered.

**NOTE** In this part of ISO 11114 the term “cylinder” refers to transportable pressure receptacles, which also include tubes and pressure drums.

Aspects such as the quality of delivered gas product are not considered.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9809-1, *Gas cylinders — Refillable seamless steel gas cylinders — Design, construction and testing — Part 1: Quenched and tempered steel cylinders with tensile strength less than 1 100 MPa*

ISO 10156, *Gases and gas mixtures — Determination of fire potential and oxidizing ability for the selection of cylinder valve outlets*

ISO 10297, *Transportable gas cylinders — Cylinder valves — Specification and type testing*

ISO 11114-2, *Gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 2: Non-metallic materials*

ISO 11114-3, *Gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 3: Autogenous ignition test for non-metallic materials in oxygen atmosphere*

ISO 11120, *Gas cylinders — Refillable seamless steel tubes for compressed gas transport of water capacity between 150 l and 3 000 l — Design, construction and testing*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

**3.1 competent person**  
person who has the necessary technical knowledge, experience and authority to assess and approve materials for use with gases and to define any special conditions of use that are necessary

**3.2 acceptable**  
**A**  
material/gas combination that is safe under normal conditions of use, provided that any indicated non-compatibility risks are taken into account

NOTE Low levels of impurities can affect the acceptability of some single gases or gas mixtures.

**3.3 not acceptable**  
**N**  
material/single gas combination that is not safe under all normal conditions of use

NOTE For gas mixtures special conditions may apply (see 6.2 and Table 1).

**3.4 dry**  
state in which there is no free water in a cylinder under any service conditions, including at the highest expected operating pressure and at the lowest expected operating temperature

NOTE For compressed gases at, for example, 200 bar and  $-20\text{ }^{\circ}\text{C}$ , the maximum moisture content is not to exceed 5 ppmV, to avoid condensation of free water. For other temperatures and pressures, the maximum moisture content needed to avoid condensation of water will be different.

**3.5 wet**  
state in which the conditions as defined for **dry** (3.4) are not met

**3.6 gas mixture**  
combination of different single gases deliberately mixed in specified proportions

**3.7 single gas**  
gas which does not contain deliberately added content of another gas or gases

### 4 Materials

#### 4.1 General

The compatibility of most materials used to manufacture gas cylinders and valves is identified in this part of ISO 11114.

Other materials whose compatibility is not identified in this part of ISO 11114 may be used if all compatibility aspects have been considered and validated by a competent person.

## 4.2 Cylinder materials

The most commonly used metallic materials for cylinders are (among others) carbon manganese steel, chromium molybdenum steel, chromium molybdenum nickel steel, stainless steel and aluminium alloys, as specified in the following International Standards:

- aluminium, ISO 7866 and ISO 11118;
- steel, ISO 4706, ISO 9328-5, ISO 9809-1, ISO 9809-2, ISO 9809-3, ISO 9809-4, ISO 11118 and ISO 11120;
- aluminium alloys and stainless steel, ISO 6361-2 and ISO 15510.

## 4.3 Valve materials

### 4.3.1 General

The most commonly used metallic materials for valve bodies and internal gas wetted parts are brass and other similar copper-based alloys, carbon steel, stainless steel, nickel and nickel alloys, Cu–Be (2 %) and aluminium alloys.

### 4.3.2 Particular considerations

**4.3.2.1** In special cases, non-compatible materials may be used for non-oxidizing gases if suitably plated, protected or coated. This may only be done if all compatibility aspects have been considered and validated by a competent person for the entire life of the valve.

**4.3.2.2** Special precautions, in accordance with ISO 11114-3 (which addresses testing, not precautions per se), shall be taken for oxidizing gases as specified in ISO 10156. In this case, non-compatible materials are *not acceptable* (see 3.3) for use in valves, even if plated, protected or coated.

**4.3.2.3** For cylinder valves, compatibility in wet conditions shall be considered because of the high risk of contamination by atmospheric moisture and an airborne contaminant.

NOTE Reference is made in this part of ISO 11114 to stainless steels by their commonly used AISI identification numbers, e.g. 304. For information, the equivalent grades according to EN 10088-1 are as follows:

304	1.4301
304L	1.4306 and 1.4307
316	1.4401
316L	1.4404

## 5 Compatibility criteria

### 5.1 General

Compatibility between a gas and the cylinder/valve material is affected by chemical reactions and physical influences, which can be classified into five categories:

- corrosion;
- stress corrosion cracking;
- hydrogen embrittlement;

- generation of dangerous products through chemical reaction;
- violent reactions, such as ignition.

Non-metallic components (valve sealing, gland packing, O-ring, etc.) shall be in accordance with ISO 11114-2.

Sealing or lubricating materials (when used) at the valve stem shall be compatible with the gas content.

NOTE Annex A gives the gas/materials NQSAB compatibility codes, for information.

## 5.2 Corrosion

Many types of corrosion mechanisms can occur due to the presence of the gas, as outlined in 5.2.1 to 5.2.3.

### 5.2.1 Corrosion in dry conditions

This corrosion is affected by chemical attack by a dry gas on the cylinder material. The result is a reduction of the cylinder wall thickness. This type of corrosion is not very common, because the rate of dry corrosion is very low at ambient temperature.

### 5.2.2 Corrosion in wet conditions

This corrosion is the most common type of corrosion, which only occurs in a gas cylinder due to the presence of free water or aqueous solutions. However with some hygroscopic gases (e.g. HCl, Cl<sub>2</sub>) corrosion would occur even if the water content were less than the saturation value. Therefore, some gas/material combinations are not recommended, even if inert in the theoretical dry conditions. It is thus very important to prevent any water ingress into gas cylinders. The most common sources of or reasons for water ingress are

- a) the customer, by retro-diffusion/backfilling or when the cylinder is empty, by air entry, if the valve is not closed,
- b) ineffective drying following hydraulic testing, and
- c) during filling.

In some cases it is very difficult to completely prevent water ingress — particularly when the gas is hygroscopic (e.g. HCl, Cl<sub>2</sub>). In cases where the filler cannot guarantee the dryness of gas and cylinder, a cylinder material which is compatible with the wet gas shall be used, even if the dry gas is not corrosive.

There are several different types of “wet corrosion” in alloys:

- a) general corrosion leading to the reduction of the wall thickness, e.g. by acid gases (CO<sub>2</sub>, SO<sub>2</sub>) or oxidizing gases (O<sub>2</sub>, Cl<sub>2</sub>);
- b) localized corrosion, e.g. pitting corrosion or grain boundary attack.

Additionally, some gases, even inert ones, when hydrolysed could lead to the production of corrosive products.

### 5.2.3 Corrosion by impurities

Gases which themselves are inert (non-corrosive) can cause corrosion due to the presence of impurities. Pollution of gases can occur, during filling, during use or if the initial product is not properly purified.

The most common pollutants are

- a) atmospheric air, in which case the harmful impurities can be moisture (see also 5.2.2) and oxygen (e.g. in liquefied ammonia);

- b) aggressive products contained in some gases, e.g. H<sub>2</sub>S in natural gas;
- c) aggressive traces (acid, mercury, etc.) remaining from the manufacturing process of some gases.

The materials compatible with the impurities shall be used if the presence of these impurities cannot be prevented and if the corresponding corrosion rate is unacceptable for the intended application.

### 5.3 Hydrogen embrittlement phenomenon

Embrittlement caused by hydrogen can occur at ambient temperature in the case of certain gases and under service conditions which stress the cylinder or valve material.

This type of stress cracking phenomenon can, under certain conditions, lead to the failure of gas cylinders and/or valve components containing hydrogen, mixtures of hydrogen and other gases.

### 5.4 Generation of dangerous products

In some cases reactions of a gas with a metallic material can lead to the generation of dangerous products. Examples are the possible reactions of C<sub>2</sub>H<sub>2</sub> with copper alloys containing more than 65 % copper and of CH<sub>3</sub>Cl in aluminium alloy cylinders.

### 5.5 Violent reactions (e.g. ignition)

In principle, violent reactions of gas/metallic material are not very common at ambient temperatures, because high activation energies are necessary to initiate such reactions. In the case where a combination of non-metallic and metallic materials is used, e.g. for valves, this type of reaction can occur with some gases (e.g. O<sub>2</sub>, Cl<sub>2</sub>).

### 5.6 Stress corrosion cracking

Stress corrosion cracking can occur in many metallic materials subjected to stress, moisture and a contaminant at the same time. Stress corrosion cracking can, under certain conditions, lead to the failure of the gas cylinder or valve and/or its components (e.g. ammonia in contact with copper alloy valves or carbon monoxide/carbon dioxide mixtures in steel cylinders).

## 6 Material compatibility

### 6.1 Table of compatibility for single gases (see Table 1)

Before any gas/cylinder/valve combination is chosen a careful study of all the *key compatibility characteristics* given in Table 1 shall be made. Particular attention shall be paid to any restrictions, which shall be applied to acceptable materials.

NOTE The gases are generally listed in the table in English alphabetical order.

### 6.2 Compatibility for gas mixtures

Any gas mixtures containing single gases that are all compatible with a given material shall be considered as being compatible with this material.

For gas mixtures containing gases causing embrittlement (see 5.3, and Table A.3, groups 2 and 11) the risk of hydrogen embrittlement only occurs if the partial pressure of the gas is greater than 5 MPa (50 bar) and the stress level of the cylinder material is high enough. Some International Standards, such as ISO 11114-4, specify test methods for selecting appropriate steels with a maximum UTS (ultimate tensile strength) greater than 950 MPa.

NOTE In a gas mixture, the partial pressure for hydrogen sulphide and methyl mercaptan is reduced to 0,25 MPa (2,5 bar) at a maximum UTS of 950 MPa.

For non-compatibility of some halogenated gases with aluminium alloys, the maximum acceptable content is given in Table 1. The level of moisture can affect the acceptability of such mixtures.

### 6.3 Using Table 1

#### 6.3.1 Conventions and numbers

In Table 1, **bold face** type indicates that the material is commonly used under normal service conditions:

- A = acceptable (see 3.2);
- N = not acceptable (see 3.3).

If there is no UN number listed for a gas (or liquid), the gas has no official UN number but may be shipped using a generic NOS (not otherwise specified) number.

EXAMPLE Compressed gas, flammable, NOS, UN 1954.

#### 6.3.2 Abbreviations for materials

- CS Carbon steels used for the manufacture of cylinder valve bodies
- NS Carbon steels heat treated by normalization that are used for the manufacture of seamless and welded cylinders
- QTS Alloy steels that are treated by quenching and tempering and that are used for the manufacture of seamless steel cylinders
- SS Austenitic type stainless steels used for the manufacture of seamless and welded cylinders and some valve bodies and valve components
- AA Aluminium alloys specified in ISO 7866 when used for the manufacture of seamless cylinders. For aluminium valve bodies, alloys not specified in ISO 7866 may also be used
- B Brass and other copper alloys used for the manufacture of cylinder valves
- Ni Nickel alloys used for the manufacture of cylinders, valves and valve components
- Cu Copper
- ASB Aluminium silicon bronze

Table 1 — Gas/material compatibility

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material						
					Cylinder		Valve (body and components)				
					A	N	A	N	A	N	
1	(UN 1001) (UN 3374)	ACETYLENE	C <sub>2</sub> H <sub>2</sub>	Ability to form explosive acetylides with certain metals, including copper and copper alloys. Use <65 % Cu and copper alloy. This also applies to mixtures of more than 1 % C <sub>2</sub> H <sub>2</sub> . The acceptable limit of the silver content of alloys should preferably be 43 % (by mass) but in no case exceeding 50 %.	NS		B		B		B (Cu >65 %)
2	(UN 1005)	AMMONIA	NH <sub>3</sub>	Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric contaminant. This applies to all gases and mixtures containing even traces of NH <sub>3</sub> .	NS		CS		CS		Cu-Be (2 %)
3	(UN 1006)	ARGON	Ar	No reaction with any common materials in dry or wet conditions.	NS		B		B		
4	(UN 2188)	ARSINE	AsH <sub>3</sub>	Because of risk of hydrogen embrittlement: — QTS are limited to a maximum ultimate tensile strength of 950 MPa; — SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition. NOTE Some SS alloys can be sensitive to hydrogen embrittlement. See special conditions for mixtures given in 6.2.	NS		CS		CS		
					QTS		SS		SS		
					AA		AA		AA		
					SS		SS		SS		
					SS		AA		AA		
					NS		B		B		
					QTS		CS		CS		
					AA		SS		SS		
					SS		AA		AA		
					NS		SS		SS		
					AA		AA		AA		
					SS		Ni		Ni		
					NS		CS		CS		
					QTS		SS		SS		
					AA		AA		AA		B
					SS		Ni		Ni		

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder		Valve (body and components)			
					A	N	A	N	A	N
5	(UN 1741)	BORON TRICHLORIDE	BCl <sub>3</sub>	Hydrolyses to hydrogen chloride in contact with moisture. In wet conditions, see specific risk of hydrogen chloride compatibility, i.e. severe corrosion of most of the materials and risk of hydrogen embrittlement. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA	CS SS Ni	AA B		
6	(UN 1008)	BORON TRIFLUORIDE	BF <sub>3</sub>	Hydrolyses to hydrogen fluoride in contact with moisture. In wet conditions, see specific risk of hydrogen fluoride compatibility, i.e. severe corrosion of most of the materials and risk of hydrogen embrittlement. Mixtures containing less than 0,1 % BF <sub>3</sub> may be filled into AA cylinders.	NS QTS SS Ni	AA	CS SS Ni	AA B		
7	(UN 1974)	BROMOCHLORODIFLUOROMETHANE	CBrClF <sub>2</sub> (R12B1)	No reaction with any common materials when dry, but in the presence of water corrosion may occur.	NS QTS AA SS		B CS SS AA			
8	(UN 1009)	BROMOTRIFLUOROMETHANE	CBrF <sub>3</sub> (R13B1)	No reaction with any common materials when dry, but in the presence of water corrosion may occur.	NS QTS AA SS		B CS SS AA			
9	(UN 2419)	BROMOTRIFLUOROETHYLENE	C <sub>2</sub> BrF <sub>3</sub>	No reaction with any common materials when dry, but in the presence of water corrosion may occur.	NS QTS AA SS		B CS SS AA			
10	(UN 1010)	BUTADIENE-1,3	H <sub>2</sub> C:CHCH:CH <sub>2</sub>	No reaction with any common materials. See 5.2.3 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA			

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder		Valve (body and components)			
					A	N	A	A	N	N
11	(UN 1010)	BUTADIENE-1,2	$H_2C:C:CHCH_3$	No reaction with any common materials. See 5.2.3 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA			
12	(UN 1011)	BUTANE	$C_4H_{10}$	No reaction with common materials. See 5.2.3 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA			
13	(UN 1012)	BUTENE-1	$CH_3CH_2CH:CH_2$	No reaction with any common materials. See 5.2.3 for the effect of impurities in wet conditions.	NS QTS AA SS		CS SS AA			B
14	(UN 1012)	BUTENE-2 (CIS)	$CH_3CHCHCH_3$	No reaction with any common materials. See 5.2.3 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA			
15	(UN 1012)	BUTENE-2 (TRANS)	$CH_3CHCHCH_3$	No reaction with any common materials. See 5.2.3 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA			
16	(UN 1013)	CARBON DIOXIDE	$CO_2$	No reaction with common materials when dry. Forms acidic carbonic in the presence of water; corrosive for NS, QTS and CS. Risk (for NS and QTS) of stress corrosion cracking in presence of CO (see carbon monoxide) and water.	NS QTS AA SS		B CS SS AA			

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
17	(UN 1016)	CARBON MONOXIDE	CO	Risk of formation of toxic metal carbonyls. Highly sensitive to any traces of moisture [ $>5$ ppmV at 20 MPa (200 bar)], in the presence of $\text{CO}_2$ ( $>5$ ppmV). Industrial grades of carbon monoxide normally contain traces of $\text{CO}_2$ . This can result in risk of stress corrosion cracking, in the case of QTS, CS and NS cylinders if used at the normal service stress levels. Experience shows that this risk is eliminated if the fill pressure at $15^\circ\text{C}$ is less than 50 % of the cylinder working pressure. For details, see [9] in the Bibliography. For QTS, CS, and NS steels this risk of stress corrosion cracking shall be considered for mixtures containing down to 0,1 % CO. NOTE AA and SS are not affected by this stress corrosion cracking phenomenon.	NS QTS AA SS		B CS SS AA	
18	(UN 1982)	TETRAFLUORMETHANE (CARBON TETRAFLUORIDE)	$\text{CF}_4$ (R14)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	NS QTS AA SS		B CS SS AA	
19	(UN 2204)	CARBONYL SULPHIDE	COS	Risk of formation of toxic metal carbonyls at temperature $> 100^\circ\text{C}$ . Highly sensitive to any traces of moisture ( $>5$ ppmV), in the presence of $\text{CO}_2$ ( $>5$ ppmV); industrial grades of carbonyl sulphide normally contain traces of $\text{CO}_2$ . This results in a risk of stress corrosion cracking, in the case of QTS, NS and CS. See also CO (No.17).	NS QTS AA SS		B CS SS AA	
20	(UN 1017)	CHLORINE	$\text{Cl}_2$	Hydrolyses to hypochlorous acid and to hydrogen chloride in contact with moisture. In wet conditions, see specific risk of hydrogen chloride compatibility, i.e. severe corrosion of most of the materials and risk of hydrogen embrittlement. The service life of brass valves strongly depends on the operating service conditions.	NS QTS SS	AA	B CS SS Ni ASB	AA

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder		Valve (body and components)			
					A	N	A	A	N	N
21	(UN 1018)	CHLORODIFLUOROMETHANE	CHClF <sub>2</sub> (R22)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	NS QTS AA SS		B CS SS AA ASB			
23	(UN 1020)	CHLOROPENTAFLUOROETHANE	C <sub>2</sub> ClF <sub>5</sub> (R115)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	NS QTS AA SS		B CS SS AA			
24	(UN 1021)	CHLOROTETRAFLUOROETHANE	CClF <sub>2</sub> CHF <sub>2</sub> (R124)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	NS QTS AA SS		B CS SS AA			
25	(UN 1983)	CHLOROTRIFLUOROETHANE	CH <sub>2</sub> ClCF <sub>3</sub> (R133a)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	NS QTS AA SS		B CS SS AA			
26	(UN 1082)	CHLOROTRIFLUOROETHYLENE	C <sub>2</sub> ClF <sub>3</sub> (R1113)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	NS QTS AA SS		B CS SS AA			
27	(UN 1022)	CHLOROTRIFLUOROMETHANE	CClF <sub>3</sub> (R13)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	NS QTS AA SS		B CS SS AA			
28	(UN 1027)	CYCLOPROPANE	C <sub>3</sub> H <sub>6</sub>	No reaction with any common materials.	NS QTS AA SS		B CS SS AA			

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
29	(UN 1957)	DEUTERIUM	D <sub>2</sub>	<p>Because of risk of hydrogen embrittlement:</p> <ul style="list-style-type: none"> <li>— QTS are limited to a maximum ultimate tensile strength of 950 MPa;</li> <li>— SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition.</li> </ul> <p>NOTE Some SS alloys can be sensitive to hydrogen embrittlement. See special conditions for mixtures given in 6.2. Nickel is not acceptable for bursting disks and other components. Risk of embrittlement due to the presence of mercury from certain production processes has to be considered, especially with AA.</p>	QTS NS AA SS		B CS AA SS	
30	(UN 1941)	DIBROMODIFLUOROMETHANE	CB <sub>2</sub> F <sub>2</sub> (R12B2)	<p>No reaction with any common materials when dry, but in the presence of water corrosion can occur.</p>	QTS NS AA SS		B CS AA SS	
31	(See 6.3)	DIBROMOTETRAFLUOROETHANE	C <sub>2</sub> Br <sub>2</sub> F <sub>4</sub>	<p>No reaction with any common materials when dry, but in the presence of water corrosion can occur.</p>	QTS NS AA SS		B CS AA SS	

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder		Valve (body and components)			
					A	N	A	A	N	N
32	(UN 1911)	DIBORANE	B <sub>2</sub> H <sub>6</sub>	<p>Because of risk of hydrogen embrittlement:</p> <ul style="list-style-type: none"> <li>— QTS are limited to a maximum ultimate tensile strength of 950 MPa;</li> <li>— SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition.</li> </ul> <p>NOTE Some SS alloys can be sensitive to hydrogen embrittlement. See special conditions for mixtures given in 6.2.</p>	QTS		B			
					NS		SS			
					AA		CS			
					SS		Ni			
33	(UN 1028)	DICHLORODIFLUOROMETHANE	CCl <sub>2</sub> F <sub>2</sub> (R12)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	QTS		B			
					NS		CS			
					AA		AA			
					SS		SS			
34	(UN 1029)	DICHLOROFLUOROMETHANE	CHCl <sub>2</sub> F (R21)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	QTS		B			
					NS		CS			
					AA		AA			
					SS		SS			
35	(UN 2189)	DICHLOROSILANE	SiH <sub>2</sub> Cl <sub>2</sub>	Hydrolyses to hydrogen chloride in contact with moisture. In wet conditions, see specific risk of hydrogen chloride compatibility, i.e. severe corrosion of most materials and risk of hydrogen embrittlement. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	QTS	AA	SS	SS	AA	AA
					NS		CS	CS		B
					SS		Ni	Ni		
					Ni					
36	(UN 1958)	DICHLOROTETRAFLUOROETHANE	C <sub>2</sub> Cl <sub>2</sub> F <sub>4</sub> (R114)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	QTS		B			
					NS		CS	CS		
					AA		AA	AA		
					SS		SS	SS		

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder		Valve (body and components)			
					A	N	A	A	N	N
37	(UN 1026)	CYANOGEN	$C_2N_2$	In the presence of water, pitting corrosion can occur. Pitting corrosion can be minimized by using SS alloys such as 316. Risk of stress corrosion cracking with brass (and other copper alloys) due to atmospheric moisture, whatever the concentration.	NS QTS AA SS		Ni CS AA SS			B
38	(UN 2517)	1-CHLORO-1,1-DIFLUOROETHANE	$CH_3CClF_2$ (R142b)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	QTS NS AA SS		B CS AA SS			
39	(UN 1030)	1,1-DIFLUOROETHANE	$CH_3CHF_2$ (R152a)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	QTS NS AA SS		B CS AA SS			
40	(UN 1959)	1,1-DIFLUOROETHYLENE	$C_2H_2F_2$ (R1132a)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	QTS NS AA SS		B CS AA SS			
41	(UN 1032)	DIMETHYLAMINE	$(CH_3)_2NH$	Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric moisture, whatever the concentration.	QTS NS AA		CS SS AA			B
42	(UN 1033)	DIMETHYL ETHER	$(CH_3)_2O$	No reaction with any common materials.	NS QTS AA SS		B CS AA SS			

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder		Valve (body and components)			
					A	N	A	A	N	N
43	(UN; see 6.3)	DISILANE	Si <sub>2</sub> H <sub>6</sub>	<p>Because of risk of hydrogen embrittlement:</p> <ul style="list-style-type: none"> <li>— QTS are limited to a maximum ultimate tensile strength of 950 MPa;</li> <li>— SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition.</li> </ul> <p>NOTE Some SS alloys can be sensitive to hydrogen embrittlement. See special conditions for mixtures given in 6.2. No reaction with any common materials.</p>	NS AA QTS SS		B CS SS AA			
44	(UN 1035)	ETHANE	C <sub>2</sub> H <sub>6</sub>	No reaction with any common materials.	QTS AA NS SS		B CS AA SS			
45	(UN 1036)	ETHYLAMINE	C <sub>2</sub> H <sub>5</sub> NH <sub>2</sub>	Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric moisture, whatever the concentration.	QTS NS AA SS		SS CS AA		B	
46	(UN 1037)	ETHYL CHLORIDE	C <sub>2</sub> H <sub>5</sub> Cl (R160)	No reaction with any common materials when dry, but in the presence of water corrosion can occur. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	QTS NS SS	AA	B SS CS		AA	
47	(UN 1962)	ETHYLENE	C <sub>2</sub> H <sub>4</sub>	No reaction with any common materials.	QTS AA NS SS		B CS AA SS			
48	(UN 1040)	ETHYLENE OXIDE	C <sub>2</sub> H <sub>4</sub> O	Ethylene oxide polymerizes. Ethylene oxide polymerization increases in the presence of moisture, rust and other contaminants. Use dry and clean cylinders. Copper is not acceptable.	QTS NS AA SS		B CS AA SS			

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder		Valve (body and components)			
					A	N	A	N	A	N
49	(UN 1045)	FLUORINE	F <sub>2</sub>	Hydrolyses to hydrogen fluoride in contact with moisture. In wet conditions, see specific risk of hydrogen fluoride compatibility, i.e. severe corrosion of most of the materials and risk of hydrogen embrittlement. Risk of violent reaction with AA, whatever the concentration. Recommended materials are also Ni alloy and nickel.	QTS NS SS	AA	B CS SS Ni	AA	AA	
50	(UN 2453)	FLUOROETHANE	C <sub>2</sub> H <sub>6</sub> F (R161)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	QTS NS AA SS		B CS AA SS			
51	(UN 2454)	FLUOROMETHANE	CH <sub>3</sub> F (R41)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	QTS NS AA SS		B CS AA SS			
52	(UN 1984)	TRIFLUOROMETHANE	CHF <sub>3</sub> (R23)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	QTS NS AA SS		B CS AA SS			
53	(UN 2192)	GERMANE	GeH <sub>4</sub>	Because of risk of hydrogen embrittlement: — QTS are limited to a maximum ultimate tensile strength of 950 MPa; — SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition.  NOTE Some SS alloys can be sensitive to hydrogen embrittlement. See special conditions for mixtures in 6.2.	QTS NS AA SS		B CS SS AA			

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
54	(UN 1046)	HELIUM	He	No reaction with any common materials.	NS QTS		B CS SS AA	
55	(UN 2193)	HEXAFLUOROETHANE	C <sub>2</sub> F <sub>6</sub> (R116)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	NS QTS		B CS SS AA	
56	(UN 1858)	HEXAFLUOROPROPENE	C <sub>3</sub> F <sub>6</sub> (R1216)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	NS QTS		B CS SS AA	

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
57	(UN 1049)	HYDROGEN	H <sub>2</sub>	<p>Because of risk of hydrogen embrittlement:</p> <ul style="list-style-type: none"> <li>— QTS are limited to a maximum ultimate tensile strength of 950 MPa;</li> <li>— for seamless steel cylinders made to ISO 9809-1 or ISO 11120 from Cr-Mo quenched and tempered steels: unless they are validated by appropriate testing according to ISO 11114-4, and with a hydrogen partial pressure above 5 MPa (50 bar), the maximum UTS of the steel shall not exceed 950 MPa;</li> <li>— SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition.</li> </ul> <p>NOTE Some SS alloys can be sensitive to hydrogen embrittlement.</p> <p>See special conditions for mixtures given in 6.2.</p> <p>Nickel is not acceptable for bursting disks and other components.</p> <p>Risk of embrittlement due to the presence of mercury from certain production processes has to be considered, especially with AA.</p>	NS <b>QTS</b> AA SS		B CS SS AA Cu-Be (2%)	

STANDARDSISO.COM : Click to visit www.iso.org

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material				
					Cylinder		Valve (body and components)		
					A	N	A	A	N
58	(UN 1048)	HYDROGEN BROMIDE	HBr	<p>This compound is highly hygroscopic and corrosive in wet conditions with most of the materials except some high corrosion resistant nickel alloys (e.g. Hastelloy C). QTS are limited to a maximum ultimate tensile strength of 950 MPa. This limitation also applies to mixtures containing the gas stored at a total pressure at 15 °C greater than half the normal service pressure of the cylinder.</p> <p>However, experience shows that a cylinder can be safely used without any specific strength limitation requirements, providing the maximum working pressure at 15 °C in the cylinder is less than one-fifth of the test pressure (TP/5), in order to maintain a low stress level in the cylinder material.</p> <p>SS shall not be used for valve diaphragms or springs except if the failure of such components does not result in an unsafe situation.</p> <p>Mixtures of dry gas not exceeding 0,1% of this gas may be filled into AA cylinders.</p>	NS QTS SS Ni	AA	CS SS Ni	B AA	

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder		Valve (body and components)			
					A	N	A	A	N	N
59	(UN 1050)	HYDROGEN CHLORIDE	HCl	This compound is highly hygroscopic and corrosive in wet conditions with most of the materials except some high corrosion resistant nickel alloys (e.g. Hastelloy C). QTS are limited to a maximum ultimate tensile strength of 950 MPa. This limitation also applies to mixtures containing this gas and stored at a total pressure at 15 °C greater than half the normal service pressure of the cylinder. However experience shows that a cylinder can be safely used without any specific strength limitation requirements, providing the maximum working pressure at 15 °C in the cylinder is less than one-fifth of the test pressure (TP/5), in order to maintain a low stress level in the cylinder material. SS shall not be used for valve diaphragm and springs except if the failure of such components does not result in an unsafe situation. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA	CS SS Ni	CS SS Ni	AA B	
60	(UN 1613)	HYDROGEN CYANIDE	HCN	This compound is highly hygroscopic. Risk of corrosion in wet conditions, depending on type of alloy.	NS QTS AA SS		B CS SS AA			

STANDARDSISO.COM : Click to Buy Full PDF ISO 11114-1:2012

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
61	(UN 1052)	HYDROGEN FLUORIDE	HF	<p>This compound is highly hygroscopic and corrosive in wet conditions with most of the materials except some high corrosion resistant nickel alloys (e.g. Hastelloy C). QTS are limited to a maximum ultimate tensile strength of 950 MPa. This limitation also applies to mixtures containing the gas stored at a total pressure at 15 °C greater than half the normal service pressure of the cylinder.</p> <p>However, experience shows that a cylinder can be safely used without any specific strength limitation requirements, providing the maximum pressure at 15 °C in the cylinder is less than one-fifth of the test pressure (TP/5), in order to maintain a low stress level in the cylinder material.</p> <p>SS shall not be used for valve diaphragms or springs except if the failure of such components does not result in an unsafe situation.</p> <p>Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.</p>	NS QTS SS Ni	AA	CS SS Ni	AA B

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material						
					Cylinder		Valve (body and components)				
					A	N	A	A	N	N	
62	(UN 2197)	HYDROGEN IODIDE	HI	This compound is highly hygroscopic and corrosive in wet conditions with most of the materials, except some high corrosion resistant nickel alloys (e.g. Hastelloy C). QTS are limited to a maximum ultimate tensile strength of 950 MPa. This limitation also applies to mixtures containing this gas and stored at a total pressure at 15 °C greater than half the normal service pressure of the cylinder.  However, experience shows that a cylinder can be safely used without any specific strength limitation requirements, providing the maximum pressure at 15 °C in the cylinder is less than one-fifth of the test pressure (TP/5), in order to maintain a low stress level in the cylinder material.  SS shall not be used for valve diaphragm and springs except if the failure of such components does not result in an unsafe situation.  Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA	CS SS Ni	AA B			

STANDARDSISO.COM : Click to Buy ISO 11114-1:2012

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder		Valve (body and components)			
					A	N	A	A	N	N
63	(UN 1053)	HYDROGEN SULPHIDE	H <sub>2</sub> S	<p>— In the presence of water pitting corrosion may occur. Pitting corrosion can be minimized by using SS alloys such as 316.</p> <p>— In wet conditions risk of stress corrosion cracking for QTS. Risk of hydrogen embrittlement with NS, QTS.</p> <p>— SS shall not be used for springs or diaphragms except if the failure of such components does not result in an unsafe situation because of possibility of hydrogen embrittlement.</p> <p>— For mixtures with higher partial pressure than the one defined in 6.2 and stored at a total pressure greater than 50 % of the normal service pressure of the cylinder, NS, and QTS at a limited strength shall be used (see 6.2).</p> <p>— Nickel is not acceptable for bursting disks and components.</p>	NS QTS AA SS		CS SS AA			B
64	(UN 1969)	ISOBUTANE	CH(CH <sub>3</sub> ) <sub>3</sub>	<p>No reaction with any common materials; however, in wet conditions risk of corrosion from impurities shall be considered.</p>	NS QTS AA SS		B CS SS AA			
65	(UN 1055)	ISOBUTYLENE	CH <sub>2</sub> C(CH <sub>3</sub> ) <sub>2</sub>	<p>No reaction with any common materials; however, in wet conditions risk of corrosion from impurities shall be considered.</p>	NS QTS SS AA		B CS SS AA			
66	(UN 1056)	KRYPTON	Kr	<p>No reaction with any common materials in dry or wet conditions.</p>	NS QTS AA SS		B CS SS AA			

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material							
					Cylinder		Valve (body and components)					
					A	N	A	A	N	N		
67	(UN 1971)	METHANE	CH <sub>4</sub>	No reaction with any common materials; however, in wet conditions risk of corrosion from impurities such as traces of CO, H <sub>2</sub> S, CO <sub>2</sub> shall be considered (see CO, H <sub>2</sub> S, CO <sub>2</sub> compatibility). NOTE For natural gas see also specific compatibility requirements in ISO 11439.	NS		B					
68	(See 6.3)	PROPYLENE	C <sub>3</sub> H <sub>4</sub>	May contain traces of acetylene. The ability to form explosive acetylides has to be considered. If the C <sub>2</sub> H <sub>2</sub> content exceeds 1 % see C <sub>2</sub> H <sub>2</sub> .	NS		B	CS	SS	AA		
22	(UN 1063)	METHYL CHLORIDE	CH <sub>3</sub> Cl (R40)	In the presence of water, corrosion may occur. Mixtures of dry gas containing not more than 0,1 % of this gas may be filled into AA cylinders.	NS	AA	B	CS	SS		AA	
69	(UN 1062)	METHYL BROMIDE	CH <sub>3</sub> Br (R40B1)	In the presence of water pitting corrosion may occur. Pitting corrosion can be minimized by using SS alloys such as 316. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS	AA	B	CS	SS		AA	
					QTS							
					AA							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA
					QTS							
					SS							
					NS	AA	B	CS	SS			AA

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
70	(UN 1064)	METHYL MERCAPTAN	CH <sub>3</sub> SH	<p>— In the presence of water, pitting corrosion can occur. Pitting corrosion can be minimized by using SS alloys such as 316.</p> <p>— In wet conditions risk of stress corrosion cracking for QTS.</p> <p>— Risk of hydrogen embrittlement with NS, QTS and some SS.</p> <p>— SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition.</p> <p>NOTE Some SS alloys can be sensitive to hydrogen embrittlement.</p> <p>— For mixtures with higher partial pressure than the one defined in 6.2, stored at a total pressure greater than 50 % the normal service pressure of the cylinder, NS, and QTS are limited to a maximum strength of 950 MPa.</p> <p>— Nickel is not acceptable for bursting disks and components.</p>	NS QTS AA SS		B CS SS AA	
71	(See 6.3)	METHYL SILANE	CH <sub>3</sub> SiH <sub>3</sub>	<p>— QTS are limited to a maximum ultimate tensile strength of 950 MPa.</p> <p>— SS shall not be used for springs or diaphragms, except if the failure of components does not result in an unsafe situation.</p> <p>— Risk of corrosion by impurities in wet conditions shall be considered, e.g. contamination by sulphuric acid from some manufacturing processes.</p>	NS QTS AA SS		B CS SS AA	

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder		Valve (body and components)			
					A	N	A	A	N	N
72	(UN 1061)	METHYLAMINE	CH <sub>3</sub> NH <sub>2</sub>	Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric moisture. This applies to all gases and mixtures containing even traces of CH <sub>3</sub> NH <sub>2</sub> .	NS QTS AA SS Ni		CS SS AA Ni			B
73	(UN 1065)	NEON	Ne	No reaction with any common materials in dry or wet conditions.	NS QTS AA SS		B CS SS AA			
74	(UN 1660)	NITRIC OXIDE	NO	In the presence of water, pitting corrosion can occur. Pitting corrosion can be minimized by using SS alloys such as 316. Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric moisture. This applies to all mixtures containing even traces of NO.	NS QTS AA SS		CS SS		B AA	
75	(UN 1066)	NITROGEN	N <sub>2</sub>	No reaction with any common materials in dry or wet conditions.	NS QTS AA SS		B CS SS AA			
76	(UN 1067)	NITROGEN DIOXIDE	NO <sub>2</sub>	In the presence of water, pitting corrosion can occur. Pitting corrosion can be minimized by using SS alloys such as 316. Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric moisture. This applies to all mixtures containing even traces of NO <sub>2</sub> .	NS QTS AA SS		CS SS		B AA	

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder		Valve (body and components)			
					A	N	A	A	N	N
77	(UN 1070)	NITROUS OXIDE	N <sub>2</sub> O	Risk of stress corrosion cracking for brass and other copper alloy highly stressed components (for any concentration). The potential risk of violent reaction (ignition), especially for valves, shall be considered at the design stage in accordance with ISO 11114-2, ISO 11114-3 and ISO 10297.	NS QTS AA SS		B CS SS AA			
78	(UN 2451)	NITROGEN TRIFLUORIDE	NF <sub>3</sub>	No reaction with any common materials when dry. Becomes a strong oxidizer when decomposed.	NS QTS SS AA		B CS SS			
79	(UN 2422)	OCTOFLUOROBUT-2-ENE	C <sub>4</sub> F <sub>8</sub>	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	NS QTS AA SS		B CS SS AA			
80	(UN 1976)	OCTAFLUOROCYCLOBUTANE	C <sub>4</sub> F <sub>8</sub> (RC318)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	NS QTS AA SS		B CS SS AA			
81	(UN 2424)	OCTAFLUOROPROPANE	C <sub>3</sub> F <sub>8</sub> (R218)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	NS QTS AA SS		B CS SS AA			

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder		Valve (body and components)			
					A	N	A	N	A	N
82	(UN 1072)	OXYGEN	O <sub>2</sub>	In the presence of water, NS, QTS and CS are corroded. Water ingress in cylinders should be avoided, e.g. by use of cylinder valves with RPV (residual pressure valve). The potential risk of violent reaction (ignition), especially for valves, shall be considered at the design stage in accordance with ISO 11114-2, ISO 11114-3 and ISO 10297. Cylinder valves shall be subject to testing to establish their suitability for oxygen service and their resistance to ignition (see ISO 11114-2, ISO 11114-3 and ISO 10297). Design assessment by a competent person is recommended before using SS for springs and other internal gas wetted components, unless ignition does not create safety issues.	NS QTS AA SS		B CS SS		AA	
83	(UN 1076)	PHOSGENE	COCl <sub>2</sub>	In wet conditions, phosgene is corrosive with most materials, particularly aluminium alloys (hydrolyses to HCl). Mixtures of dry gas containing not more than 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS	AA	B CS SS Ni		AA	
84	(UN 2199)	PHOSPHINE	PH <sub>3</sub>	Because of risk of hydrogen embrittlement: — QTS are limited to a maximum ultimate tensile strength of 950 MPa; — SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition. NOTE Some SS alloys can be sensitive to hydrogen embrittlement. See special conditions for mixtures given in 6.2.	NS QTS AA SS		B CS SS AA			

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder		Valve (body and components)			
					A	N	A	A	N	N
85	(UN 1978)	PROPANE	C <sub>3</sub> H <sub>8</sub>	No reaction with any common materials; however, in wet conditions the risk of corrosion from impurities shall be considered.	NS QTS AA SS		B CS SS AA			
86	(UN 2200)	PROPADIENE	C <sub>3</sub> H <sub>4</sub>	No reaction with any common materials; however, in wet conditions the risk of corrosion from impurities shall be considered.	NS QTS AA SS		B CS SS AA			
87	(UN 1077)	PROPYLENE	C <sub>3</sub> H <sub>6</sub>	No reaction with any common materials; however, in wet conditions the risk of corrosion from impurities shall be considered.	NS QTS AA SS		B CS SS AA			Cu
88	(UN 1280)	PROPYLENE OXIDE	C <sub>3</sub> H <sub>6</sub> O	Propylene oxide polymerizes. The rate of polymerization increases in the presence of moisture, rust and other contaminants. Use a clean, dry cylinder. Copper is not acceptable.	NS QTS AA SS	Cu	B CS SS AA			Cu
89	(UN 2203)	SILANE	SiH <sub>4</sub>	— The filling ratio shall be limited to 320 g/L for steels with tensile strengths above 950 MPa. — SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition.  NOTE Some SS alloys can be sensitive to hydrogen embrittlement. See special conditions for mixtures given in 6.2. Risk of corrosion by impurities in wet conditions shall be considered, e.g. contamination by sulphuric acid from some manufacturing processes.	NS QTS SS AA		B CS SS AA			

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder		Valve (body and components)			
					A	N	A	A	N	N
90	(UN 1818)	SILICON TETRACHLORIDE	SiCl <sub>4</sub>	Hydrolyses to hydrogen chloride in contact with moisture. In wet conditions, see specific risk of hydrogen chloride compatibility, i.e. severe corrosion of most materials. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS	AA	CS B SS Ni	AA	AA	
91	(UN 1859)	SILICON TETRAFLUORIDE	SiF <sub>4</sub>	Hydrolyses to hydrogen fluoride in contact with moisture. In wet conditions, see specific risk of hydrogen fluoride compatibility, i.e. severe corrosion of most materials. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS	AA	CS B SS Ni	AA	AA	
92	(UN 1079)	SULPHUR DIOXIDE	SO <sub>2</sub>	Highly hygroscopic. Sulphur dioxide hydrolyses in presence of water to produce sulphurous acid, which is highly corrosive to steel. In the presence of water, pitting corrosion can occur. Pitting corrosion can be minimized by using SS alloys such as 316. B might suffer stress corrosion cracking, in long-term wet conditions.	NS QTS AA SS		B CS SS AA Ni			
93	(UN 1080)	SULPHUR HEXAFLUORIDE	SF <sub>6</sub>	No reaction with any common materials.	NS QTS AA SS		B CS SS AA			
94	(UN 2418)	SULPHUR TETRAFLUORIDE	SF <sub>4</sub>	In wet conditions, sulphur tetrafluoride is highly corrosive. SS alloys such as 316 and Nickel alloys may be used. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS	AA	B CS SS Ni	AA	AA	
95	(UN 1081)	TETRAFLUOROETHYLENE	C <sub>2</sub> F <sub>4</sub> (R1114)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	NS QTS AA SS		B CS SS AA			

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder		Valve (body and components)			
					A	N	A	A	N	N
96	(UN 1295)	TRICHLOROSILANE	SiHCl <sub>3</sub>	Hydrolyses to hydrogen chloride in contact with moisture. In wet conditions, see specific risk of hydrogen chloride compatibility, i.e. severe corrosion of most of the materials. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS	AA	B CS SS Ni	AA	AA	
97	(See 6.3)	TRICHLOROTRIFLUOROETHANE	C <sub>2</sub> Cl <sub>3</sub> F <sub>3</sub> (R113)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	NS QTS AA SS		B CS SS AA Ni			
98	(UN 2035)	1,1,1-TRIFLUOROETHANE	CH <sub>3</sub> CF <sub>3</sub> (R143a)	No reaction with any common materials when dry, but in the presence of water corrosion can occur.	NS QTS AA SS		B CS SS AA			
99	(UN 1083)	TRIMETHYLAMINE	(CH <sub>3</sub> ) <sub>3</sub> N	Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric moisture. This applies to all gases and mixtures containing even traces of NH <sub>3</sub> .	NS QTS AA SS Ni		CS SS AA Ni	B		
100	(UN 2196)	TUNGSTEN HEXAFLUORIDE	WF <sub>6</sub>	Hydrolyses to hydrogen fluoride in contact with moisture. In wet conditions, see specific risk of hydrogen fluoride compatibility, i.e. severe corrosion of most materials and risk of hydrogen embrittlement. Due to their highly corrosive-resistant nature, nickel-based alloys and nickel-plated valves are recommended.	NS QTS SS Ni	AA	CS SS Ni	AA	AA	
101	(UN 1085)	VINYL BROMIDE	C <sub>2</sub> H <sub>3</sub> Br (R1140B1)	Risk of corrosion in wet conditions. Some C <sub>2</sub> H <sub>2</sub> contamination could be present.	NS QTS SS	AA	B CS SS Ni	AA	AA	

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material					
					Cylinder			Valve (body and components)		
					A	N	AA	A	N	AA
102	(UN 1086)	VINYL CHLORIDE	C <sub>2</sub> H <sub>3</sub> Cl (R1140)	Risk of corrosion in wet conditions. Some C <sub>2</sub> H <sub>2</sub> contamination could be present.	NS	AA	AA	B	AA	AA
103	(UN 1860)	VINYL FLUORIDE	C <sub>2</sub> H <sub>3</sub> F (R1141)	Risk of corrosion in wet conditions. Some C <sub>2</sub> H <sub>2</sub> contamination could be present.	NS	AA	AA	B	AA	AA
104	(UN 2036)	XENON	Xe	No reaction with any common materials in dry or wet conditions.	NS	AA	AA	B	AA	AA
					QTS			CS		
					SS			SS		
					AA			AA		

STANDARDSISO.COM . Click to view the full PDF of ISO 11114-1:2012

## Annex A (informative)

### Gas/materials NQSAB compatibility code

#### A.1 General

A five-digit code allows a rating of the compatibility of each gas with five different classes of materials for use with gas cylinders and cylinder valves. This is termed the NQSAB code, where “N” represents normalized steels and carbon steels, “Q” quenched and tempered steels, “S” stainless steels, “A” aluminium alloys and “B” brass and other copper alloys, and nickel alloys. The degree of compatibility is identified by replacing the letter with the appropriate digit as described in A.2.

A.3 presents the NQSAB code itself, and in A.4 the gases covered in this part of ISO 11114 are divided into 11 groups, depending on their compatibility with cylinder and valve materials.

#### A.2 Material classes and compatibility identification

##### A.2.1 Normalized steels and carbon steels (N)

- 0 Not acceptable.
- 1 Acceptable but check Table 1, key compatibility characteristics.
- 9 Acceptable but check Table 1, key compatibility characteristics, to avoid hydrogen embrittlement.

##### A.2.2 Quenched and tempered steels (Q)

- 0 Not acceptable.
- 1 Acceptable but check Table 1, key compatibility characteristics.
- 9 Acceptable but check Table 1, key compatibility characteristics, to avoid hydrogen embrittlement.

##### A.2.3 Stainless steels (S)

- 0 Not acceptable.
- 1 Acceptable for gas cylinder but check Table 1, key compatibility characteristics.
- 2 Pitting corrosion can be minimized by using stainless steel alloys such as 316.
- 9 Hydrogen embrittlement can be minimized by using stainless steel alloys such as 316.

##### A.2.4 Aluminium alloys (A)

- 0 Not acceptable but some mixtures of dry gases may be filled into AA; check Table 1, key compatibility characteristics.
- 1 Acceptable but check Table 1, key compatibility characteristics.

### A.2.5 Brass and other copper alloys (B)

- 0 Not acceptable.
- 1 Acceptable to be used but check Table 1, key compatibility characteristics.
- 3 Use brass or other copper alloys containing less than 65 % Cu.

### A.3 NQSAB code

The NQSAB code for each gas is given in Table A.1. For gases where the compatibility rating 2, 3 or 9 are specified, refer also to Table 1.

Table A.1 — List of gases with corresponding NQSAB compatibility code

Name and gas number	Formula	N	Q	S	A	B
1 ACETYLENE	$C_2H_2$	1	1	1	1	3
2 AMMONIA	$NH_3$	1	1	1	1	0
3 ARGON	Ar	1	1	1	1	1
4 ARSINE	$AsH_3$	9	9	9	1	1
5 BORON TRICHLORIDE	$BCl_3$	1	1	2	0	0
6 BORON TRIFLUORIDE	$BF_3$	1	1	2	0	0
7 BROMOCHLORODIFLUOROMETHANE	$CBrClF_2$ (R12B1)	1	1	1	1	1
8 BROMOTRIFLUOROMETHANE	$CBrF_3$ (R13B1)	1	1	1	1	1
9 BROMOTRIFLUOROETHYLENE	$C_2BrF_3$	1	1	1	1	1

Table A.1 (continued)

Name and gas number	Formula	N	Q	S	A	B
10 BUTADIENE-1,3	$H_2C:CHCH:CH_2$	1	1	1	1	1
11 BUTADIENE-1,2	$H_2C:C:CHCH_3$	1	1	1	1	1
12 BUTANE	$C_4H_{10}$	1	1	1	1	1
13 BUTENE-1	$CH_3CH_2CH:CH_2$	1	1	1	1	1
14 BUTENE-2 (CIS)	$CH_3CH:CHCH_3$	1	1	1	1	1
15 BUTENE-2 (TRANS)	$CH_3CH:CHCH_3$	1	1	1	1	1
16 CARBON DIOXIDE	$CO_2$	1	1	1	1	1
17 CARBON MONOXIDE	$CO$	1	1	1	1	1
18 TETRAFLUOROMETHANE (CARBON TETRAFLUORIDE)	$CF_4$	1	1	1	1	1
19 CARBONYL SULPHIDE	$COS$	1	1	1	1	1
20 CHLORINE	$Cl_2$	1	1	2	0	1
21 CHLORODIFLUOROMETHANE	$CHClF_2$ (R22)	1	1	1	1	1
22 METHYL CHLORIDE (CHLOROMETHANE)	$CH_3Cl$ (R40)	1	1	1	0	1
23 CHLOROPENTAFLUOROETHANE	$C_2ClF_5$ (R115)	1	1	1	1	1
24 CHLOROTETRAFLUOROETHANE	$CClF_2-CHF_2$	1	1	1	1	1
25 CHLOROTRIFLUOROETHANE	$CH_2ClCF_3$ (R133a)	1	1	1	1	1

Table A.1 (continued)

Name and gas number	Formula	N	Q	S	A	B
26 CHLOROTRIFLUOROETHYLENE	$C_2ClF_3$ (R1113)	1	1	1	1	1
27 CHLOROTRIFLUOROMETHANE	$CClF_3$ (R13)	1	1	1	1	1
28 CYCLOPROPANE	$C_3H_6$	1	1	1	1	1
29 DEUTERIUM	$D_2$	9	9	9	1	1
30 DIBROMODIFLUOROMETHANE	$CBr_2F_2$ (R12B2)	1	1	1	1	1
31 DIBROMOTETRAFLUOROETHANE	$C_2Br_2F_4$ (R114B2)	1	1	1	1	1
32 DIBORANE	$B_2H_6$	9	9	9	1	1
33 DICHLORODIFLUOROMETHANE	$CCl_2F_2$ (R12)	1	1	1	1	1
34 DICHLOROFLUOROMETHANE	$CHCl_2F$ (R21)	1	1	1	1	1
35 DICHLOROSILANE	$SiH_2Cl_2$	1	1	2	0	0
36 DICHLOROTETRAFLUOROETHANE	$C_2Cl_2F_4$ (R114)	1	1	1	1	1
37 CYANOGEN	$C_2N_2$	1	1	2	1	0
38 1-CHLORO-1,1-DIFLUOROETHANE (1,1-(DIFLUORO-1 CHLOROETHANE))	$CH_3CClF_2$ (R142b)	1	1	1	1	1
39 1,1-DIFLUOROETHANE	$CH_3CHF_2$ (R152a)	1	1	1	1	1
40 1,1-DIFLUOROETHYLENE	$C_2H_2F_2$ (R1132a)	1	1	1	1	1
41 DIMETHYL AMINE	$(CH_3)_2NH$	1	1	1	1	0
42 DIMETHYL ETHER	$(CH_3)_2O$	1	1	1	1	1

Table A.1 (continued)

Name and gas number	Formula	N	Q	S	A	B
43 DISILANE	$\text{Si}_2\text{H}_6$	9	9	9	1	1
44 ETHANE	$\text{C}_2\text{H}_6$	1	1	1	1	1
45 ETHYLAMINE	$\text{C}_2\text{H}_5\text{NH}_2$	1	1	1	1	0
46 ETHYL CHLORIDE	$\text{C}_2\text{H}_5\text{Cl}$ (R160)	1	1	1	0	1
47 ETHYLENE	$\text{C}_2\text{H}_4$	1	1	1	1	1
48 ETHYLENE OXIDE	$\text{C}_2\text{H}_4\text{O}$	1	1	1	1	1
49 FLUORINE	$\text{F}_2$	1	1	2	0	1
50 FLUOROETHANE	$\text{C}_2\text{H}_5\text{F}$ (R161)	1	1	1	1	1
51 FLUOROMETHANE	$\text{CH}_3\text{F}$ (R41)	1	1	1	1	1
52 TRIFLUOROMETHANE	$\text{CHF}_3$ (R23)	1	1	1	1	1
53 GERMANE	$\text{GeH}_4$	9	9	9	1	1
54 HELIUM	He	1	1	1	1	1
55 HEXAFLUROETHANE	$\text{C}_2\text{F}_6$ (R116)	1	1	1	1	1
56 HEXAFLUOROPROPENE	$\text{C}_3\text{F}_6$ (R1216)	1	1	1	1	1