
**Rubber hoses and hose assemblies —
Compact wire-braid-reinforced
hydraulic types for oil-based or water-
based fluids — Specification**

*Tuyaux et flexibles en caoutchouc — Types hydrauliques compacts
avec armature de fils métalliques tressés pour fluides à base d'huile
ou à base d'eau — Spécifications*

STANDARDSISO.COM : Click to view the full PDF of ISO 11237:2017



STANDARDSISO.COM : Click to view the full PDF of ISO 11237:2017



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification	2
5 Materials and construction	2
5.1 Hoses	2
5.2 Hose assemblies	2
6 Dimensions	2
6.1 Hose diameters and cover thickness	2
6.2 Concentricity	3
6.3 Hose cover thickness	3
7 Performance requirements	3
7.1 General	3
7.2 Change in length requirements	4
7.3 Hydrostatic requirements	4
7.4 Minimum bend radius	5
7.5 Resistance to impulse	5
7.5.1 Oil-based fluid impulse test	5
7.5.2 Water-based fluid impulse test	6
7.5.3 Optional impulse test	6
7.6 Leakage of hose assemblies	6
7.7 Cold flexibility	6
7.8 Adhesion between components	6
7.9 Vacuum resistance	7
7.10 Fluid resistance	7
7.10.1 General	7
7.10.2 Oil resistance	7
7.10.3 Water resistance	7
7.11 Ozone resistance	7
7.12 Visual examination	8
8 Marking	8
8.1 Hoses	8
8.2 Hose assemblies	8
9 Recommendations for length of supplied hoses and tolerances on lengths of hose assemblies	8
Annex A (normative) Type and routine testing of production hoses	9
Annex B (informative) Periodic testing of production hoses	10
Annex C (informative) Recommendations for lengths of supplied hoses and length tolerances for hose assemblies	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Rubber and plastics hoses and hose assemblies*.

This second edition cancels and replaces the first edition (ISO 11237:2010), which has been technically revised.

The main changes compared to the previous edition are as follows:

- [Clause 1](#) has been updated to be more precise;
- [Clause 2](#) has been updated; ISO 4672 has been deleted and replaced by ISO 10619-2 and ISO 10619-1 has been added;
- [8.1](#) has been amended, year of publication of a standard shall be included in the marking if previous edition is used;
- [Clause 9](#) has been added to cite [Annex C](#).

Rubber hoses and hose assemblies — Compact wire-braid-reinforced hydraulic types for oil-based or water-based fluids — Specification

1 Scope

This document specifies requirements for five types of compact, wire-braid-reinforced hose and hose assembly of nominal size from 5 to 31,5.

They are suitable for use with

- oil-based hydraulic fluids HH, HL, HM, HR and HV as defined in ISO 6743-4 at temperatures ranging from -40 °C to $+100\text{ °C}$;
- water-based fluids HFC, HFAC, HFAS and HFB as defined in ISO 6743-4 at temperatures ranging from 0 °C to $+60\text{ °C}$;
- water at temperatures ranging from 0 °C to $+60\text{ °C}$.

This document does not include requirements for end fittings. It is limited to requirements for hoses and hose assemblies.

NOTE It is the responsibility of the user, in consultation with the hose manufacturer, to establish the compatibility of the hose with the fluid to be used.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1307, *Rubber and plastics hoses — Hose sizes, minimum and maximum inside diameters, and tolerances on cut-to-length hoses*

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 1817, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids*

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies*

ISO 6605, *Hydraulic fluid power — Hoses and hose assemblies — Test methods*

ISO 6743-4, *Lubricants, industrial oils and related products (class L) — Classification — Part 4: Family H (Hydraulic systems)*

ISO 6803, *Rubber or plastics hoses and hose assemblies — Hydraulic-pressure impulse test without flexing*

ISO 7233, *Rubber and plastics hoses and hose assemblies — Determination of resistance to vacuum*

ISO 7326:2016, *Rubber and plastics hoses — Assessment of ozone resistance under static conditions*

ISO 8033:2016, *Rubber and plastics hoses — Determination of adhesion between components*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 11237:2017(E)

ISO 10619-1:2011, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 1: Bending tests at ambient temperature*

ISO 10619-2:2011, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 2: Bending tests at sub-ambient temperatures*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Classification

Five types of hose are specified, distinguished by their construction, working pressure and minimum bend radius. These hoses have thin covers designed to permit fitting assembly without the removal of the cover or a portion of the cover.

- a) Type 1SC: Hoses with a single braid of wire reinforcement.
- b) Type 2SC: Hoses with two braids of wire reinforcement.
- c) Type R16S: Hoses with one or two braids of wire reinforcement.
- d) Type R17: 21 MPa (210 bar) constant pressure hoses with one or two braids of wire reinforcement.
- e) Type R19: 28 MPa (280 bar) constant pressure hoses with one or two braids of wire reinforcement.

NOTE Types R16S, R17 and R19 are not subjected to the vacuum resistance tests.

5 Materials and construction

5.1 Hoses

Hoses shall consist of a rubber lining resistant to oil- or water-based hydraulic fluids, one or two layers of high-tensile steel wire and a weather- and oil-resistant rubber cover.

5.2 Hose assemblies

Hose assemblies shall be manufactured using hoses conforming to the requirements of this document.

Hose assemblies shall be manufactured only with those hose fittings whose correct functioning has been verified in accordance with [7.2](#), [7.3](#), [7.5](#), [7.6](#) and [7.7](#). The manufacturer's instructions shall be followed for the preparation and fabrication of hose assemblies.

6 Dimensions

6.1 Hose diameters and cover thickness

When measured in accordance with ISO 4671, the hose diameters shall conform to the values given in [Table 1](#) and the cover thickness to [6.3](#).

Table 1 — Dimensions of hoses

Nominal size ^a	All types		Type 1SC			Type 2SC			Type R16S		Type R17		Type R19	
	Inside diameter		Diameter over wire		Outside diameter of hose	Diameter over wire		Outside diameter of hose	Diameter over wire	Outside diameter of hose	Diameter over wire	Outside diameter of hose	Diameter over wire	Outside diameter of hose
	mm		mm		mm	mm		mm	mm	mm	mm	mm	mm	mm
	min.	max.	min.	max.	max.	min.	max.	max.	max.	max.	max.	max.	max.	max.
5	4,6	5,4	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	10,1	11,6	10,8	12,7
6,3	6,1	6,9	9,6	10,8	13,5	10,6	11,7	14,2	12,3	14,5	11,0	13,2	12,4	14,4
8	7,7	8,5	10,9	12,1	14,5	12,1	13,3	16,0	13,3	15,8	13,0	15,0	14,2	16,3
10	9,3	10,1	12,7	14,5	16,9	14,4	15,6	18,3	15,9	18,8	15,0	17,0	16,0	18,0
12,5	12,3	13,5	15,9	18,1	20,4	17,5	19,1	21,5	19,1	22,0	18,8	21,1	20,4	22,6
16	15,5	16,7	19,8	21,0	23,0	20,5	22,3	24,7	22,5	25,4	23,6	25,9	25,9	27,5
19	18,6	19,8	23,2	24,4	26,7	24,6	26,4	28,6	26,3	29,0	27,7	30,3	29,7	32,5
25	25,0	26,4	30,7	31,9	34,9	32,5	34,3	36,6	34,0	36,6	35,6	38,6	N/A	N/A
31,5	31,4	33,0	37,8	39,0	42,2	39,3	41,7	44,3	41,9	44,3	N/A	N/A	N/A	N/A

N/A = Not available.

^a Nominal sizes are in accordance with ISO 1307.

6.2 Concentricity

When measured in accordance with ISO 4671, the concentricity of hoses shall conform to the values given in [Table 2](#).

Table 2 — Concentricity of hoses (all types)

Nominal size	Maximum variation in wall thickness mm	
	Between inside diameter and outside diameter	Between inside diameter and reinforcement diameter
Up to and including 6,3	0,8	0,5
Over 6,3 and up to and including 19	1,0	0,6
Over 19	1,3	0,8

6.3 Hose cover thickness

When measured in accordance with ISO 4671, the cover thickness of all types of hose shall lie in the range 0,8 mm to 1,5 mm.

7 Performance requirements

7.1 General

The requirements for type and routine testing are given in [Annex A](#) and recommendations for periodic testing in [Annex B](#).

7.2 Change in length requirements

When determined in accordance with ISO 1402 or ISO 6605, the change in length of hoses at the maximum working pressure shall not exceed +2 % to -4 %. Maximum working pressure values are given in [Table 3](#).

Table 3 — Maximum working pressure

Nominal size	Type							
	1SC		2SC/R16S		R17		R19	
	Maximum working pressure							
	MPa	bar	MPa	bar	MPa	bar	MPa	bar
5	N/A		N/A		21	210	28	280
6,3	22,5	225	40	400	21	210	28	280
8	21,5	215	35	350	21	210	28	280
10	18	180	33	330	21	210	28	280
12,5	16	160	27,5	275	21	210	28	280
16	13	130	25	250	21	210	28	280
19	10,5	105	21,5	215	21	210	28	280
25	8,8	88	16,5	165	21	210	N/A	
31,5	6,3	63	12,5	125	N/A		N/A	

N/A = Not available.
NOTE 1 MPa = 10 bar.

7.3 Hydrostatic requirements

When determined in accordance with ISO 1402 or ISO 6605, the proof pressure (see [Table 4](#)) and the minimum burst pressure (see [Table 5](#)) of hoses and hose assemblies shall conform to the values in the respective tables.

Table 4 — Proof pressure

Nominal size	Type							
	1SC		2SC/R16S		R17		R19	
	Proof pressure							
	MPa	bar	MPa	bar	MPa	bar	MPa	bar
5	N/A		N/A		42	420	56	560
6,3	45	450	80	800	42	420	56	560
8	43	430	70	700	42	420	56	560
10	36	360	66	660	42	420	56	560
12,5	32	320	55	550	42	420	56	560
16	26	260	50	500	42	420	56	560
19	21	210	43	430	42	420	56	560
25	17,6	176	33	330	42	420	N/A	
31,5	12,5	125	25	250	N/A		N/A	

N/A = Not available.
NOTE 1 MPa = 10 bar.

Table 5 — Minimum burst pressure

Nominal size	Type							
	1SC		2SC/R16S		R17		R19	
	Minimum burst pressure							
	MPa	bar	MPa	bar	MPa	bar	MPa	bar
5	N/A		N/A		84	840	112	1 120
6,3	90	900	160	1 600	84	840	112	1 120
8	86	860	140	1 400	84	840	112	1 120
10	72	720	132	1 320	84	840	112	1 120
12,5	64	640	110	1 100	84	840	112	1 120
16	52	520	100	1 000	84	840	112	1 120
19	42	420	86	860	84	840	112	1 120
25	35,2	352	66	660	84	840	N/A	
31,5	25	250	50	500	N/A		N/A	

N/A = Not available.
NOTE 1 MPa = 10 bar.

7.4 Minimum bend radius

Use a test piece having a length at least four times the minimum bend radius. Measure the hose outside diameter with callipers in the straight-lay position before bending the hose. Bend the hose through 180° to the minimum bend radius (see [Table 6](#)) and measure the flatness with the callipers.

When the hose is bent to the minimum bend radius given in [Table 6](#), measured in accordance with ISO 10619-1:2011, Method A1, the flatness shall not exceed 10 % of the original outside diameter.

Table 6 — Minimum bend radius

Nominal size	Minimum bend radius mm				
	Type 1SC	Type 2SC	Type R16S	Type R17	Type R19
5	N/A	N/A	N/A	45	45
6,3	75	75	50	50	50
8	85	85	55	55	55
10	90	90	65	65	65
12,5	130	130	90	90	90
16	150	170	100	100	100
19	180	200	120	120	120
25	230	250	150	150	N/A
31,5	250	280	210	N/A	N/A

N/A = Not available.

7.5 Resistance to impulse

7.5.1 Oil-based fluid impulse test

The impulse test shall be in accordance with ISO 6803 or ISO 6605. The test fluid temperature shall be 100 °C.

For type 1SC hoses, when tested at an impulse pressure equal to 125 % of the maximum working pressure, the hose shall withstand a minimum of 150 000 impulse cycles.

For type 2SC, R16S, R17 and R19 hoses, when tested at an impulse pressure equal to 133 % of the maximum working pressure, the hose shall withstand a minimum of 200 000 impulse cycles.

There shall be no leakage or other evidence of failure before reaching the specified number of cycles.

This test shall be considered a destructive test and the test piece shall be discarded after the test.

7.5.2 Water-based fluid impulse test

The impulse test shall be in accordance with ISO 6803 or ISO 6605. The test fluid temperature shall be 60 °C. The test fluid used shall be HFC, HFAE, HFAS or HFB as defined in ISO 6743-4.

For type 1SC hoses, when tested at an impulse pressure equal to 125 % of the maximum working pressure, the hose shall withstand a minimum of 150 000 impulse cycles.

For type 2SC, R16, R17 and R19 hoses, when tested at an impulse pressure equal to 133 % of the maximum working pressure, the hose shall withstand a minimum of 200 000 impulse cycles.

There shall be no leakage or other evidence of failure before reaching the specified number of cycles.

This test shall be considered a destructive test and the test piece shall be discarded after the test.

7.5.3 Optional impulse test

The following test may be used to maximize tester efficiency:

- a) oven-age assemblies filled with one of the water-based fluids specified in [7.5.2](#) for 120 h at 60 °C;
- b) impulse-test the aged assemblies using an oil-based hydraulic fluid at a temperature of 100 °C.

For type 1SC hoses, when tested at an impulse pressure equal to 125 % of the maximum working pressure, the hose shall withstand a minimum of 150 000 impulse cycles.

For type 2SC, R16S, R17 and R19 hoses, when tested at an impulse pressure equal to 133 % of the maximum working pressure, the hose shall withstand a minimum of 200 000 impulse cycles.

There shall be no leakage or other evidence of failure before reaching the specified number of cycles.

This test shall be considered a destructive test and the test piece shall be discarded after the test.

7.6 Leakage of hose assemblies

When tested in accordance with ISO 1402 or ISO 6605, there shall be no leakage or other evidence of failure. This test shall be considered a destructive test and the test piece shall be discarded after the test.

7.7 Cold flexibility

When tested in accordance with ISO 10619-2:2011, Method B, at a temperature of -40 °C, there shall be no cracking of the lining or cover. The test piece shall not leak or crack when subjected to a proof pressure test in accordance with ISO 1402 or ISO 6605 after regaining ambient temperature.

7.8 Adhesion between components

When determined in accordance with ISO 8033, the adhesion between lining and reinforcement and between cover and reinforcement shall be not less than 2,5 kN/m for type 1SC and 2SC hoses and not less than 1,8 kN/m for type R16S, R17 and R19 hoses.

Test pieces shall be type 5 for lining and reinforcement and type 2 or type 6 for cover and reinforcement as described in ISO 8033:2016, 6.1 and 6.3.

7.9 Vacuum resistance

When tested in accordance with ISO 7233, hoses and hose assemblies shall conform to the maximum values given in [Table 7](#).

Table 7 — Degree of vacuum

Nominal size	Type			
	Type 1SC		Type 2SC	
	Negative gauge pressure			
	MPa	bar	MPa	bar
6,3	0,08	0,80	0,095	0,95
8	0,08	0,80	0,095	0,95
10	0,08	0,80	0,095	0,95
12,5	0,08	0,80	0,095	0,95
16	0,08	0,80	0,095	0,95
19	0,08	0,80	N/A	
25	0,08	0,80	N/A	
31,5	0,08	0,80	N/A	

N/A = Not applicable.

NOTE There is no vacuum resistance requirement for types R16S, R17 and R19.

7.10 Fluid resistance

7.10.1 General

The fluid resistance tests shall be carried out on moulded sheets of lining and cover compound having a minimum thickness of 2 mm and of cure state equivalent to that of the hose.

7.10.2 Oil resistance

When determined in accordance with ISO 1817 by immersion in oil No. 3 for 168 h at a temperature of 100 °C, the percentage change in volume of the lining shall be between 0 % and +25 % for type 1SC and 2SC hoses and between 0 % and +100 % for type R16S, R17 and R19 hoses (i.e. shrinkage is not permissible).

When determined in accordance with ISO 1817 by immersion in oil No. 3 for 168 h at a temperature of 70 °C, the percentage change in volume of the cover shall, for all types of hose, be between 0 % and +100 % (i.e. shrinkage is not permissible).

7.10.3 Water resistance

When determined in accordance with ISO 1817 by immersion in distilled water for 168 h at a temperature of 60 °C, the percentage change in volume of the lining shall, for all types of hose, be between 0 % and +30 % (i.e. shrinkage is not permissible).

When tested in accordance with ISO 1817 by immersion in oil No. 3 for 168 h at a temperature of 70 °C, the percentage change in volume of the cover shall, for all types of hose, be between 0 % and +100 %.

7.11 Ozone resistance

For all hose types, when tested in accordance with ISO 7326:2016, Method 1 or 2, depending on the nominal size of the hose, no cracking or deterioration of the cover shall be visible under ×2 magnification.

7.12 Visual examination

Hose shall be examined for visible defects in the outer cover and to verify that the hose identification is correct and has been properly marked. Hose assemblies shall, in addition, be inspected to verify that the correct fittings are fitted.

8 Marking

8.1 Hoses

Hoses meeting the requirements of this document shall be marked at least once every 760 mm with at least the following information:

- a) the manufacturer's name or identification, e.g. XXX;
- b) a reference to this document, i.e. ISO 11237;
- c) the type, e.g. 1SC;
- d) the nominal size, e.g. 16;
- e) the maximum working pressure, in megapascal with additional in bars with the units indicated, e.g. 22,5 MPa (225 bar);
- f) the quarter and last two digits of the year of manufacture, e.g. 2Q17 (other date-coding methods indicating, for instance, the day or month and year of manufacture are allowed as long as they are clear to the user).

For item b), the hose manufacturer shall use the latest publication of this document, otherwise the year of publication shall be included in the marking.

EXAMPLE XXX/ISO 11237/1SC/16/22,5 MPa (225 bar)/2Q17.

8.2 Hose assemblies

Hose assemblies meeting the requirements of this document shall be marked with at least the following information:

- a) the manufacturer's name or identification, e.g. XXX;
- b) the maximum working pressure of the assembly, in megapascals and in bars, or in either, with the units indicated, e.g. 22,5 MPa (225 bar);

NOTE The maximum working pressure of a hose assembly is equal to the maximum working pressure of the component having the lowest maximum working pressure.

- c) two digits indicating the month of assembly followed by a slash and the last two digits of the year of assembly, e.g. 06/17 (other date-coding methods indicating, for instance, the day or month and year of manufacture are allowed as long as they are clear to the user, e.g. 11/12/17).

EXAMPLE XXX/22,5 MPa (225 bar)/06/17.

9 Recommendations for length of supplied hoses and tolerances on lengths of hose assemblies

The length of supplied hoses and hose assemblies shall be the subject of agreement between the manufacturer and the purchaser. However, recommendations for length of supplied hoses and tolerances on length of hose assemblies are given in [Annex C](#).