

Second edition
2018-02

AMENDMENT 1
2021-02

**Plastics piping systems for renovation
of underground non-pressure
drainage and sewerage networks —**

Part 4:
Lining with cured-in-place pipes

**AMENDMENT 1: Updated definitions,
marking requirements and procedure
for alternative expression of flexural
test results**

*Systèmes de canalisations en plastique pour la rénovation des réseaux
de branchements et de collecteurs d'assainissement enterrés sans
pression —*

Partie 4: Tubage continu par tubes polymérisés sur place

*AMENDEMENT 1: Actualisation des définitions, des exigences
de marquage, et de la procédure pour une autre expression des
propriétés de flexion*



STANDARDSISO.COM : Click to view the full PDF of ISO 11296-4:2018/Amd 1:2021



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 8, *Rehabilitation of pipeline systems*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 155, *Plastics piping systems and ducting systems*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

A list of all parts in the ISO 11296 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

STANDARDSISO.COM : Click to view the full PDF of ISO 11296-4:2018/Amd 1:2021

Plastics piping systems for renovation of underground non-pressure drainage and sewerage networks —

Part 4: Lining with cured-in-place pipes

AMENDMENT 1: Updated definitions, marking requirements and procedure for alternative expression of flexural test results

Normative references

Replace the references to ISO 178:2010+A1:2013, ISO 7685:1998, ISO 10467:–1), ISO 10468 and ISO 14125:1998+A1:2011 with the following:

ISO 178:2019, *Plastics — Determination of flexural properties*

ISO 7685:2019, *Glass-reinforced thermosetting plastics (GRP) pipes — Determination of initial ring stiffness*

ISO 10467:2018, *Plastics piping systems for pressure and non-pressure drainage and sewerage — Glass-reinforced thermosetting plastics (GRP) systems based on unsaturated polyester (UP) resin*

ISO 10468, *Glass-reinforced thermosetting plastics (GRP) pipes — Determination of the ring creep properties under wet or dry conditions*

ISO 14125:1998, *Fibre-reinforced plastic composites — Determination of flexural properties*

Delete ISO 7684 from the list.

Delete footnote 1).

Terms and definitions

Replace 3.1.2, 3.1.3, 3.1.4, 3.1.12 and 3.1.15 with the following:

**3.1.2
carrier material**

porous component of the *lining tube* (3.1.11), which carries the liquid *resin system* (3.1.16) during insertion into the pipe being renovated and forms part of the installed lining system once the resin has been cured

**3.1.3
CIPP product**

cured-in-place pipe of a particular design, produced from a *lining tube* (3.1.11) of specified materials, with a wall structure which is uniquely defined for each diameter/wall thickness combination, and which is impregnated with a specific *resin system* (3.1.16) and installed by a specific process

**3.1.4
CIPP unit**

specific cured-in-place pipe produced from a continuous *lining tube* (3.1.11), which has been impregnated in one process and installed as a single length

**3.1.12
nominal CIPP “M” stage wall thickness**

one of a range of discrete *lining tube* (3.1.11) wall thicknesses dictated by the sum of the thicknesses of the individual layers of materials used for tube construction at the “M” stage, excluding any internal or external membranes

Note 1 to entry: This term is expressed using the symbol $e_{n,M}$ (see 4.1).

**3.1.15
reinforcement**

fibres incorporated in the *lining tube* (3.1.11) which enhance the dimensional stability of the lining tube and/or the structural properties of the cured *composite* (3.1.6)

Note 1 to entry: The reinforcement can be incorporated in the carrier material (3.1.1), constitute the carrier material, or can be a separate layer.

Add the following new term and definition after 3.1.21:

**3.1.22
nominal CIPP “I” stage wall thickness**

one of a range of discrete *CIPP product* (3.1.3) wall thicknesses at the “I” stage, dictated by the sum of the thicknesses of the individual layers of materials used for *lining tube* (3.1.11) construction, excluding any internal or external membranes

Note 1 to entry: This term is expressed using the symbol $e_{n,I}$ (see 4.1).

4.1

Add the following new symbols:

$e_{n,I}$	nominal CIPP “I” stage wall thickness
$e_{n,M}$	nominal CIPP “M” stage wall thickness
EI	section bending stiffness per unit length of the pipe wall
EI_c	apparent section bending stiffness of a curved 3-point test piece before correction for curvature
M	section moment capacity per unit length of the pipe wall
M_c	apparent section moment capacity of a curved 3-point test piece before correction for curvature

4.2

Replace the description of PPTA with:

PPTA Poly(p-phenylene terephthalamide)

Add the following new abbreviated term:

PP Polypropylene

5.1, Table 1

In the row “Carrier material/reinforcement”, replace the term “PPTA” with “PPTA aramid”, and replace the reference “ISO 10467:—” with “ISO 10467”.

5.4

Replace the entire text of the subclause with the following:

Where the manufacturer elects to mark the lining tube with nominal CIPP “M” stage wall thickness, see 5.8, the thickness of the lining tube shall be measured by a method documented in the manufacturer’s quality plan. The thicknesses of any membranes shall be deducted.

The total nominal CIPP “M” stage wall thickness may be determined as the sum of the similarly measured thicknesses of individual layers of material.

NOTE 1 Such measurement is possible only where the lining tube is marked before impregnation with the resin system.

NOTE 2 The “I” stage wall thickness achieved (see 8.4.3) depends not only on the “M” stage thickness, but also on the volume, rheology and curing characteristics of the resin system used, the internal dimensions and condition of the pipe to be lined, and details of the installation process applied.

Where the manufacturer elects to mark the lining tube with nominal CIPP “I” stage wall thickness, see 5.8, this thickness shall represent the minimum value of the mean thickness, $e_{c,m}$, of the composite achieved when the lining tube is installed by a prescribed process in a circular pipe of internal diameter equal to the declared nominal outside diameter, d_n , of the lining tube.

In all cases, the perimeter of the lining tube should be dimensioned such that when installed, it forms a close fit to the existing sewer wall or as otherwise required by the design. The manufactured length and thickness of the lining tube should include allowances for any longitudinal and circumferential stretch during installation.

5.8

Replace the third paragraph with the following:

For compliance with ISO 11296-1:2018, 5.8 d), the dimension marked shall be either the nominal CIPP "M" stage wall thickness, $e_{n,M}$, or nominal CIPP "I" stage wall thickness, $e_{n,I}$, making clear which is intended.

6.8

Replace the second and third paragraphs with the following:

For compliance with ISO 11296-1:2018, 6.8 c), the dimensions marked shall be the nominal inside diameter of the lateral pipe, and, where applicable, also of the main pipe that the lateral connection collar is designed to fit.

For compliance with ISO 11296-1:2018, 6.8 d), the dimension marked shall be either the nominal CIPP "M" stage wall thickness, $e_{n,M}$, or nominal CIPP "I" stage wall thickness, $e_{n,I}$, making clear which is intended.

In the fourth paragraph, replace the opening words "As specified in..." with "For compliance with..."

8.1

In the final paragraph, delete "+A1:2011" after "ISO 14125:1998".

8.5.2, Table 5

In the final column of the first row, replace "7685:1998" with "7685:2019".

8.5.2, Table 6

In the final column of the first row, replace "ISO 7684 with extrapolation according to ISO 10468" with "ISO 10468".

9.4.2

In the NOTE, replace "pre-liner" with "preliner".

Annex A, Table A.1

In footnote a, replace the reference to "ISO 10467:—, 4.3.1. a)" with "ISO 10467:2018, 4.3.1. a)".

Annex B

Throughout this Annex, replace all instances of “ISO 178:2010+A1:2013” with “ISO 178:2019”, and all instances of “ISO 14125:1998+A1:2011” with “ISO 14125:1998”. The cited clause and table numbers remain valid for these replacement dated references.

B.5.5

Replace the entire text of the subclause with the following:

Where the mean composite thickness, $e_{c,m}$, cannot easily be determined, for example, due to uncertainty about thickness of membranes or any excess neat resin layer, or where, as in the case of structured-wall reinforced liners, the apparent flexural modulus, E_f , is itself a function of wall thickness, the flexural characteristics of the liner pipe wall may alternatively or additionally be expressed as section bending stiffness, EI , and section moment capacity, M , per unit length of the wall.

For flat test pieces, section moment capacity and section bending stiffness are independent of thickness and given simply by Formulae (B.12) and (B.13):

$$M = \frac{(F/b) \cdot L}{4} \quad (\text{B.12})$$

$$EI = \frac{(F/s) \cdot L^3}{48b} \quad (\text{B.13})$$

The relevant value of (F/s) to be used in Formula (B.13) is the steepest slope of the initial load-deflection curve.

For curved test pieces, the apparent section moment capacity, M_c , and apparent section bending stiffness, EI_c , are obtained by substituting true span L_2 (see Figure B.1) for L in Formula (B.12) and Formula (B.13) respectively. An adequate estimate of L_2 for this purpose is given as a function of the mean total thickness, h_m , of the test piece by Formula (B.14):

$$L_2 = \frac{L}{1 - \left[\frac{2r + h_m}{d_n - h_m} \right]} \quad (\text{B.14})$$

If the nominal outside diameter, d_n , of the liner pipe from which the test piece is cut is not known, the expression $[d_n - h_m]$ in Formula (B.14) may be substituted by $[2R_1 + h_m]$, where inside radius R_1 is obtained by measurement of the test piece in accordance with B.4.3 b).

The apparent values of section moment capacity and bending stiffness of curved test pieces can then be converted to equivalent values for flat test pieces by Formulae (B.15) and (B.16):

$$M = \frac{M_c}{C_\sigma} \quad (\text{B.15})$$

$$EI = \frac{EI_c}{C_E} \quad (\text{B.16})$$