

---

---

**Paints and varnishes — Determination of  
resistance to cyclic corrosion conditions —**

Part 2:

**Wet (salt fog)/dry/humidity/UV light**

*Peintures et vernis — Détermination de la résistance aux conditions de  
corrosion cyclique —*

*Partie 2: Brouillard salin/sécheresse/humidité/lumière UV*



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 11997-2:2000

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.ch](mailto:copyright@iso.ch)  
Web [www.iso.ch](http://www.iso.ch)

Printed in Switzerland

**Contents**

	Page
1 Scope .....	1
2 Normative references .....	1
3 Principle .....	2
4 Required supplementary information .....	2
5 Salt fog test solution .....	2
6 Apparatus .....	2
7 Sampling .....	3
8 Test panels .....	3
9 Procedure .....	3
10 Examination of test panels .....	4
11 Precision .....	4
12 Test report .....	4
 <b>Annex</b>	
A Required supplementary information.....	5

STANDARDSISO.COM : Click to view the full PDF of ISO 11997-2:2000

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 11997 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 11997-2 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

ISO 11997 consists of the following parts, under the general title *Paints and varnishes — Determination of resistance to cyclic corrosion conditions*:

- Part 1: *Wet (salt fog)/dry/humidity*
- Part 2: *Wet (salt fog)/dry/humidity/UV light*

Annex A forms a normative part of this part of ISO 11997.

## Introduction

Coatings of paints, varnishes and similar materials are exposed to cyclic wet and dry corrosion and UV exposure conditions using specified salt solutions in cabinets in order to simulate, in the laboratory, processes occurring in aggressive outdoor conditions. Generally, valid correlations between such outdoor weathering and laboratory testing cannot be expected because of the large number of factors influencing the breakdown process. Certain relationships can only be expected if the effect on the coating of the important parameters (e.g. nature of the pollutant, spectral distribution of the incident irradiance in the relevant photochemical region, temperature of the specimen, type and cycle of wetting and relative humidity) is known. In contrast to outdoor weathering, laboratory testing in a cabinet is performed with a reduced number of variables, which can be controlled and therefore the effects are more reproducible.

The method described may give a means of checking that the quality of a paint or paint system is being maintained. The method is intended to provide a more realistic simulation of these factors than is found in traditional tests with continuous exposure to a static set of corrosive conditions. The method has been found to be useful in comparing the cyclic salt spray resistance of different coatings. It is most useful in providing relevant ratings for a series of coated panels exhibiting significant differences in cyclic salt spray/UV exposure resistance tested at the same time and to the same test cycle.

The cycle specified in this part of ISO 11997 has been found useful for air-drying industrial maintenance coatings on steel; other cycles may be used as required.

This part of ISO 11997 is equivalent to ASTM D 5894-96, *Standard Practice for Cyclic Salt Fog/UV exposure of Painted Metal (Alternating Exposures in a Fog/Dry Cabinet and a UV/Condensation Cabinet)*.

STANDARDSISO.COM : Click to view the full PDF of ISO 11997-2:2000

STANDARDSISO.COM : Click to view the full PDF of ISO 11997-2:2000

# Paints and varnishes — Determination of resistance to cyclic corrosion conditions —

## Part 2: Wet (salt fog)/dry/humidity/UV light

### 1 Scope

This part of ISO 11997 is one of a series of standards dealing with the sampling and testing of paints, varnishes and related products.

It specifies a test method of determining resistance of coatings to a defined cycle of wet (salt fog)/dry/humidity/UV light conditions using a specified solution.

### 2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 11997. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 11997 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 1513, *Paints and varnishes — Examination and preparation of samples for testing.*

ISO 1514, *Paints and varnishes — Standard panels for testing.*

ISO 2808, *Paints and varnishes — Determination of film thickness.*

ISO 3270, *Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing.*

ISO 3696, *Water for analytical laboratory use — Specification and test methods.*

ISO 4628-1, *Paints and varnishes — Evaluation of degradation of paint coatings — Designation of intensity, quantity and size of common types of defect — Part 1: General principles and rating schemes.*

ISO 4628-2, *Paints and varnishes — Evaluation of degradation of paint coatings — Designation of intensity, quantity and size of common types of defect — Part 2: Designation of degree of blistering.*

ISO 4628-3, *Paints and varnishes — Evaluation of degradation of paint coatings — Designation of intensity, quantity and size of common types of defect — Part 3: Designation of degree of rusting.*

ISO 4628-4, *Paints and varnishes — Evaluation of degradation of paint coatings — Designation of intensity, quantity and size of common types of defect — Part 4: Designation of degree of cracking.*

ISO 4628-5, *Paints and varnishes — Evaluation of degradation of paint coatings — Designation of intensity, quantity and size of common types of defect — Part 5: Designation of degree of flaking.*

ISO 11507, *Paints and varnishes — Exposure of coatings to artificial weathering — Exposure to fluorescent UV and water.*

ISO 11997-1, *Paints and varnishes — Determination of resistance to cyclic corrosion conditions — Part 1: Wet (salt fog)/dry/humidity.*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling.*

### 3 Principle

A coated test panel is exposed to a cyclic wet (salt fog), drying, humidity and UV light test schedule and the effects of exposure are evaluated by criteria agreed in advance between the interested parties, these criteria usually being of a subjective nature.

### 4 Required supplementary information

For any particular application, the test method specified in this part of ISO 11997 needs to be completed by supplementary information. The items of supplementary information are given in annex A.

### 5 Salt fog test solution

**5.1** Prepare the spray solution by dissolving sodium chloride and ammonium sulfate in water of at least grade 2 quality as defined in ISO 3696 to give a solution with  $c(\text{NaCl}) = (0,5 \pm 0,01) \text{ g/l}$  and  $c[(\text{NH}_4)_2\text{SO}_4] = (3,5 \pm 0,01) \text{ g/l}$ .

**5.2** The salts shall be white and comply with the purity requirements given in Table 1.

**Table 1 — Purity of salt**

Impurity	Maximum mass percentage of impurity % (calculated on the dry salt)
Total	0,5
Iodide	0,1
Copper	0,001
Nickel	0,001

**5.3** Filter the solution before placing it in the reservoir of the cabinet, in order to remove any solid matter which might block the apertures of the spraying device.

### 6 Apparatus

Ordinary laboratory apparatus and glassware, together with the following:

**6.1 Artificial weathering cabinet**, conforming to the requirements of ISO 11507, fitted with UVA 340 lamps and set to repeat a test cycle consisting of 4 h light (UV) at 60 °C and 4 h condensation at 50 °C, unless otherwise specified.

**6.2 Cyclic corrosion cabinet**, conforming to the requirements of ISO 11997-1, set to repeat a test cycle consisting of 60 min salt fog at  $(23 \pm 2) \text{ °C}$  and 60 min dry at  $(35 \pm 2) \text{ °C}$ , unless otherwise specified. The salt fog deposition rate shall be 1 ml/h to 2 ml/h, when collected over a continuous 24 h period (see ISO 11997-1).

If the cabinet (6.1 or 6.2) has been used for a spray test, or for any other purpose, using a solution differing from that specified for the current test cycle, then it shall be thoroughly cleaned before use.

## 7 Sampling

Take a representative sample of the product to be tested (or of each product in the case of a multi-coat system), as described in ISO 15528.

Examine and prepare each sample for testing, as described in ISO 1513.

## 8 Test panels

### 8.1 Material and dimensions

Unless otherwise specified or agreed, the test panels shall be of burnished steel complying with ISO 1514, and of minimum dimensions 150 mm × 70 mm × 0,3 mm.

### 8.2 Preparation and coating of panels

Unless otherwise specified, prepare each test panel in accordance with ISO 1514 and then coat it by the specified method with the product or system under test.

Unless otherwise specified, the back and edges of the panel shall be coated with the product or system under test.

If the coating on the back and edges of the panel differs from that of the product under test, it shall have a corrosion resistance greater than that of the product under test.

### 8.3 Drying and conditioning

Dry (or stove) and age (if applicable) each coated test panel for the specified time under the specified conditions, and then, unless otherwise specified, condition them at a temperature and relative humidity as defined in ISO 3270 for at least 16 h, with free circulation of air and without exposing them to direct sunlight. The test procedure shall then be carried out as soon as possible.

### 8.4 Thickness of coating

Determine the thickness, in micrometres, of the dried coating by one of the non-destructive procedures described in ISO 2808.

### 8.5 Scribing of panels

If specified, make a straight scribe through the coating to the substrate as described in ISO 11997-1.

## 9 Procedure

**9.1** Carry out the determination in triplicate, unless otherwise agreed.

**9.2** Expose at least one control specimen of similar composition and known durability with every test.

**NOTE** It is recommended that two control specimens, one of lower and one of higher durability, be included with each series of test panels.

**9.3** Unless otherwise specified, set up the cabinets as described in clause 6 and allow equilibrium to be established. Always start the exposure in the artificial weathering cabinet.

**9.4** Arrange the panels in the artificial weathering cabinet (6.1) and expose for 168 h.