
**Geosynthetics — Static puncture test
(CBR test)**

Géosynthétiques — Essai de poinçonnement statique (essai CBR)

STANDARDSISO.COM : Click to view the full PDF of ISO 12236:2006



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 12236:2006

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions.....	1
4 Principle	2
5 Apparatus	3
6 Specimens	4
7 Conditioning.....	4
8 Procedure	5
9 Recording, calculation and expression of results	6
9.1 Recording of data	6
9.2 Calculation and expression of results.....	6
10 Test report	6

STANDARDSISO.COM : Click to view the full PDF of ISO 12236:2006

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 12236 was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 189, *Geosynthetics* in collaboration with Technical Committee ISO/TC 221, *Geosynthetics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 12236:1996), which has been technically revised.

STANDARDSISO.COM : Click to view the PDF file ISO 12236:2006

Geosynthetics — Static puncture test (CBR test)

1 Scope

This International Standard specifies a method for the determination of the puncture resistance by measuring the force required to push a flat-ended plunger through geosynthetics.

The test is normally carried out on dry specimens conditioned in the specified atmosphere.

The test is applicable to most types of products, but not to materials with apertures greater than 10 mm.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the cited edition applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 554, *Standard atmospheres for conditioning and/or testing — Specifications*

ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system*

ISO 9862, *Geosynthetics — Sampling and preparation of test specimens*

ISO 10320, *Geosynthetics — Identification on site*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

plunger force

F

force as the plunger is pushed onto and through the specimen at a constant rate of displacement

See Figure 1.

NOTE The plunger force is expressed in kilonewtons.

3.2

push-through force

F_p

maximum plunger force recorded for each single test

See Figure 1.

NOTE The push-through force is expressed in kilonewtons.

3.3 displacement

h
distance the plunger has travelled starting from a preload of 20 N

See Figure 1.


NOTE The displacement is measured in millimetres.

3.4 push-through displacement

h_p
displacement at maximum recorded force F_p

See Figure 1.

NOTE The push-through displacement is measured in millimetres.



Key

- h displacement, in mm
- F plunger force, in kN
- F_p push-through force, in kN
- h_p push-through displacement, in mm

Figure 1 — Example of a typical curve — Plunger force versus plunger displacement

4 Principle

The specimen is clamped between two steel rings. A plunger is advanced at a constant rate on the centre of the specimen and perpendicularly to it. The push-through force, push-through displacement and force-displacement curve are recorded.

5 Apparatus

5.1 Testing machine.


The testing machine shall be of class 1 or class 0 in accordance with ISO 7500-1 and shall be capable of the following:

- a constant rate of displacement of (50 ± 5) mm/min;
- recording force and displacement;
- providing an autographic read-out of force and displacement.

5.2 Plunger.

A stainless steel plunger with a diameter of $(50 \pm 0,5)$ mm is used. The radius of the leading edge of the plunger shall be $(2,5 \pm 0,2)$ mm (see Figure 2).

Dimensions in millimetres




NOTE This figure is not to scale.

Figure 2 — Plunger

5.3 Clamping system.

The clamping system shall prevent slippage or cutting of the specimens. The internal diameter of the clamping rings shall be $(150 \pm 0,5)$ mm. Examples of a clamping system and a guide block are shown in Figure 3 and Figure 4. The surfaces should be arranged so that the distance between the inner diameter of the ring and the gripping zone (i.e. start of serration, corrugations, etc.) does not exceed 7 mm.



- Key**
- | | | | |
|---|----------------|---|----------------------------|
| 1 | load cell | 5 | specimen |
| 2 | cross head | 6 | support frame or CBR mould |
| 3 | plunger | 7 | rounded inside edges |
| 4 | clamping rings | | |

Figure 3 — Example of clamping system device

6 Specimens

Five specimens shall be tested. Take specimens at random from the sample in accordance with ISO 9862.

If the material to be tested is known to have different characteristics on the two faces (e.g. physical characteristics or as a consequence of the manufacturing process), then the complete test shall be carried out separately on each face.


7 Conditioning

The test specimens shall be conditioned in the standard atmosphere for testing (20 ± 2) °C and (65 ± 5) % relative humidity as defined in ISO 554.

The specimens can be considered to be conditioned when the change in mass, in successive weightings made at intervals of not less than 2 h, does not exceed 0,25 % of the mass of the test specimen.

Conditioning and/or testing in the standard atmosphere may only be omitted when it can be shown that results obtained for the same specific type of product (both structure and polymer type) are not affected by changes in the atmosphere exceeding the limits. This information shall be included in the test report.

Dimensions in millimetres

**Key**


1 upper clamping ring	5 guide block
2 specimen	6 screw
3 tube	7 lower clamping ring
4 clamping aid	

NOTE 1 This figure is not to scale.

NOTE 2 Number of screws to suit the clamping rings being used.

a) Example of guide block used

Dimensions in millimetres



NOTE This figure is not to scale.

b) Example of details of serrated surfaces**Figure 4 — Examples of guide block and details of serrated surfaces****8 Procedure**

Secure a specimen between the clamping rings of the clamping system (see Figure 3), e.g. by using a guide block [see Figure 4 a)]. Place the specimen and clamping system in the testing machine.

Advance the plunger (see Figure 2) onto and through the specimen at a rate of (50 ± 5) mm/min and start recording the displacement at preload of 20 N.

Repeat the procedure on the remaining specimens.