
**Glass in building — Laminated glass and
laminated safety glass —**

Part 6:
Appearance

*Verre dans la construction — Verre feuilleté et verre feuilleté de
sécurité —*

Partie 6: Aspect

STANDARDSISO.COM : Click to view the full PDF of ISO 12543-6:2011



STANDARDSISO.COM : Click to view the full PDF of ISO 12543-6:2011



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 12543-6 was prepared by Technical Committee ISO/TC 160, *Glass in building*, Subcommittee SC 1, *Product considerations*.

This second edition cancels and replaces the first edition (ISO 12543-6:1998), which has been technically revised.

ISO 12543 consists of the following parts, under the general title *Glass in building — Laminated glass and laminated safety glass*:

- *Part 1: Definitions and description of component parts*
- *Part 2: Laminated safety glass*
- *Part 3: Laminated glass*
- *Part 4: Test methods for durability*
- *Part 5: Dimensions and edge finishing*
- *Part 6: Appearance*

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 12543-6:2017

Glass in building — Laminated glass and laminated safety glass —

Part 6: Appearance

1 Scope

This part of ISO 12543 specifies defects of finished sizes and test methods with regard to the appearance of laminated glass when looking through the glass.

NOTE Special attention is paid to acceptability criteria in the vision area.

This part of ISO 12543 is applicable to finished sizes at the time of supply.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 12543-1, *Glass in building — Laminated glass and laminated safety glass — Part 1: Definitions and description of component parts*

ISO 12543-5, *Glass in building — Laminated glass and laminated safety glass — Part 5: Dimensions and edge finishing*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 12543-1 and the following apply.

3.1

spot defect

type of defect that includes opaque spots, bubbles and foreign bodies

3.2

linear defect

type of defect that includes foreign bodies and scratches or grazes

3.3

other defect

glass defect, such as vents and interlayer defects, such as creases, shrinkage and streaks

3.4

opaque spot

visible defect in the laminated glass

EXAMPLES Tin marks and inclusions in the glass or interlayer.

3.5

bubble

usually air, in the glass or interlayer

3.6

foreign body

unwanted item introduced into the laminated glass during manufacture

3.7

scratch

linear damage to the outside surface of the laminated glass

3.8

graze

damage to the outside surface of the laminated glass

3.9

vent

sharp-tipped fissure or crack running into the glass from an edge

3.10

crease

distortion introduced into the interlayer by folds visible after manufacture

3.11

streak due to interlayer inhomogeneity

distortion in the interlayer, caused by manufacturing defects in the interlayer, which are visible after manufacture


3.12

edge area

perimeter of the pane, which is generally contained within the glazing system

NOTE For pane sizes that are less than 5 m², the width of the edge area as given in Figure 1 is 15 mm. The width of the edge area is increased to 20 mm for pane sizes that are greater than 5 m².

STANDARDSONLINE.COM : Click to view the full PDF of ISO 12543-6:2011

**Key**

- | | | | |
|---|--------------------|-----|----------------|
| 1 | width of edge area | L | width of pane |
| 2 | edge area | H | height of pane |
| 3 | vision area | | |

Figure 1 — Areas to be examined on finished sizes ready for glazing

3.13**vision area**

main area of the glass that excludes the edge area

4 Principle

The laminated glass is put in a vertical position, in front of and parallel to a matt grey screen, and is lit by diffuse daylight or equivalent.

The laminated glass is visually inspected perpendicularly at a distance of 2 m from the glass, with the matt screen on the other side of the glass.

Any visible defects that are disturbing shall be marked.

5 Defects in the edge area for framed edges

When inspected according to the test method given in Clause 9, defects which do not exceed 5 mm in diameter or 5 % to the edge area are permitted.

6 Vents

Vents are not permitted.

7 Creases and streaks

These are not allowed in the visual area.

8 Defects in the vision area

8.1 Spot defects in the vision area

When inspected according to the test method given in Clause 9, the admissibility of spot defects depends on the following:

- size of the defect;
- frequency of the defect;
- size of the pane;
- number of panes as components of a laminated glass.

The number of permissible defects in a pane shall be in accordance with Table 1.

Defects less than 0,5 mm shall not be considered.

Defects greater than 3 mm shall not be permitted.

NOTE Admissibility of spot defects in laminated glass is independent of the individual glass thickness.

Table 1 — Permissible spot defects in the vision area

Size of defect <i>d</i> mm		0,5 < <i>d</i> ≤ 1,0	1,0 < <i>d</i> ≤ 3,0			
		for all sizes	<i>A</i> ≤ 1	1 < <i>A</i> ≤ 2	2 < <i>A</i> ≤ 8	<i>A</i> > 8
Size of pane <i>A</i> m ²						
Number or density of permissible defects	2 panes	no limitation; however, no accumulation of defects	1	2	1/m ²	1,2/m ²
	3 panes		2	3	1,5/m ²	1,8/m ²
	4 panes		3	4	2/m ²	2,4/m ²
	≥5 panes		4	5	2,5/m ²	3/m ²

NOTE An accumulation of defects occurs if four or more defects are at a distance of <200 mm from each other. This distance is reduced to 180 mm for laminated glass consisting of three panes, to 150 mm for laminated glass consisting of four panes and to 100 mm for laminated glass consisting of five or more panes.

The number of permissible defects in Table 1 shall be increased by one for each individual interlayer which is thicker than 2 mm.