

# INTERNATIONAL STANDARD

**ISO**  
**12757-2**

First edition  
1998-05-01

---

---

## **Ball point pens and refills —**

### **Part 2: Documentary use (DOC)**

*Stylos à pointe bille et recharges —*

*Partie 2: Utilisation documentaire (DOC)*

STANDARDSISO.COM : Click to view the full PDF of ISO 12757-2:1998



Reference number  
ISO 12757-2:1998(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 12757-2 was prepared by Technical Committee ISO/TC 10, *Technical drawings, product definition and related documentation*, Subcommittee SC 9, *Media and equipment for drawing and related documentation*.

ISO 12757 consists of the following parts, under the general title *Ball point pens and refills*:

- Part 1: *General use*
- Part 2: *Documentary use (DOC)*

© ISO 1998

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case postale 56 • CH-1211 Genève 20 • Switzerland  
Internet central@iso.ch  
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

## Introduction

This part of ISO 12757 is applicable to ball point pens for documentary use. Part 1 of ISO 12757 is applicable to ball point pens for general use.

For documentary use, some requirements, in addition to those for general use, are necessary

- a) to assure the legibility of lettering, and
- b) for the handling and storage of documents during long periods of time (these requirements are often discussed with the archivist).

An example of documentary use is the preparation of documents that are required as evidence.

Furthermore, pens which meet the requirements for documentary use produce lines which are more resistant to modification (e.g. attempts to falsify a document) than those for general use.

STANDARDSISO.COM : Click to view the full PDF of ISO 12757-2:1998

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 12757-2:1998

# Ball point pens and refills —

## Part 2: Documentary use (DOC)

### 1 Scope

This part of ISO 12757 establishes minimum quality requirements for ball point pens (refillable or non-refillable) and refills for documentary use.

Basic requirements for ball point pens for general use are given in ISO 12757-1.

### 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 12757. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 12757 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 105-A02:1993, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour.*

ISO 105-B02:1994, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test.*

ISO 12756:1998, *Drawing and writing instruments — Ball point pens and roller ball pens — Vocabulary.*

ISO 12757-1:1998, *Ball point pens and refills — Part 1: General use.*

### 3 Definitions

For the purposes of this part of ISO 12757, the definitions given in ISO 12756 apply.

### 4 Requirements

#### 4.1 General requirements

See the general requirements given in ISO 12757-1:1998 (4.1 to 4.3.4 and 4.3.7).

#### 4.2 Erasure resistance

The surface of the testing paper shall show clear evidence of damage before the line is rendered invisible when tested as specified in 6.2.1.

#### 4.3 Ethanol resistance

The line shall remain visible when tested as specified in 6.2.2.

#### 4.4 Hydrochloric acid resistance

The line shall remain visible when tested as specified in 6.2.3.

#### 4.5 Ammonium hydroxide resistance

The line shall remain visible when tested as specified in 6.2.4.

#### 4.6 Bleaching resistance

The line shall remain visible when tested as specified in 6.2.5.

#### 4.7 Water resistance

The line shall remain visible when tested as specified in 6.2.6.

#### 4.8 Light resistance

The line shall remain visible when tested as specified in 6.2.7.

### 5 Test equipment, accessories and solutions

#### 5.1 Test equipment and accessories

See ISO 12757-1.

#### 5.2 Test solutions

**5.2.1 Ethanol solution**, 50 % aqueous solution (volume fraction).

**5.2.2 Hydrochloric acid solution**, 10 % aqueous solution (mass fraction).

**5.2.3 Ammonium hydroxide solution**, 10 % aqueous solution (mass fraction).

**5.2.4 Bleaching solution**, 3 % freshly made aqueous solution of chloramin T<sup>1)</sup> (mass fraction).

### 6 Testing

#### 6.1 General test

##### 6.1.1 Sampling

See ISO 12757-1:1998, 6.1.

---

1) Standard designation: *N*-chloro-*p*-toluene sulfonamide sodium salt.

1) IUPAC designation: *N*-chloro-4-methyl-benzene sulfonamide sodium salt.

### 6.1.2 Climatic test conditions

See ISO 12757-1:1998, 6.2.

### 6.1.3 General test procedure

See ISO 12757-1:1998, 6.3.

## 6.2 Additional tests

### 6.2.1 Erasure resistance test

Keep a fresh machine-written test piece approximately 5 cm long from the sheet provided in 6.1.3 under the climatic conditions specified in 6.1.2 for 10 min (to allow to dry), then erase a portion of line with the eraser specified in ISO 12757-1:1998, 5.3. Examine the surface of the erased section of the paper for compliance with 4.2.

### 6.2.2 Ethanol resistance test

Keep a machine-written test piece approximately 5 cm long from the sheet provided in 6.1.3 under the climatic conditions specified in 6.1.2 for 1 h (to allow to dry), then immerse in the ethanol solution specified in 5.2 for 10 min. Remove and allow to air dry. Examine the written line of the test piece for compliance with 4.3.

### 6.2.3 Hydrochloric acid resistance test

Keep a machine-written test piece approximately 5 cm long from the sheet provided in 6.1.3 under the climatic conditions specified in 6.1.2 for 1 h (to allow to dry), then immerse in the hydrochloric acid solution specified in 5.3 for 24 h. Remove and immerse in distilled water or de-ionized water for 10 min and allow to air dry. Examine the written line of the test piece for compliance with 4.4.

### 6.2.4 Ammonium hydroxide resistance test

Keep a machine-written test piece approximately 5 cm long from the sheet provided in 6.1.3 under the climatic conditions specified in 6.1.2 for 1 h (to allow to dry), then immerse in the ammonium hydroxide solution specified in 5.4 for 24 h. Remove and immerse in distilled water or de-ionized water for 10 min and allow to air dry. Examine the written line of the test piece for compliance with 4.5.

### 6.2.5 Bleaching resistance test

Keep a machine-written test piece approximately 5 cm long from the sheet provided in 6.1.3 under the climatic conditions specified in 6.1.2 for 10 min (to allow to dry), then immerse in the bleaching solution specified in 5.5 for 5 min. Remove and immerse in distilled water or de-ionized water for 10 min and allow to air dry. Examine the written line of the test piece for compliance with 4.6.

### 6.2.6 Water resistance test

Keep a machine-written test piece approximately 5 cm long from the sheet provided in 6.1.3 under the climatic conditions specified in 6.1.2 for 2 h (to allow to dry), then immerse in distilled water or de-ionized water for 24 h. Remove and allow to air dry. Examine the written line of the test piece for compliance with 4.7.

### 6.2.7 Light resistance test

Expose a machine-written test piece approximately 5 cm long from the sheet provided in 6.1.3 to the light source of the apparatus specified in ISO 12757-1:1998, 5.5, together with the blue wool references specified in ISO 105-B02 until the contrast between the unexposed and the exposed blue wool reference 5 becomes equal to grey scale grade 4 specified in ISO 105-A02. Examine the written line of the test piece for compliance with 4.8.

## 7 Designation and marking

### 7.1 Designation

The designation of a ball point pen or refill shall comprise, in the given order, the following elements:

- a) the description block (e.g. "ball point pen" or "ball point refill");
- b) the number of this part of ISO 12757 (i.e. ISO 12757-2);
- c) the type classification code for refills (see 4.2 of ISO 12757-1:1998);
- d) the tip classification code (EF, F, M or B; see table 1 of ISO 12757-1:1998); and
- e) an additional indicator for documentary use (DOC).

### EXAMPLES

A disposable ball point pen complying with the requirements of this part of ISO 12757, with a medium sized tip (M), shall be designated as follows:

**Ball point pen ISO 12757-2 M DOC**

A ball point refill complying with the requirements of this part of ISO 12757, type B, with a broad sized tip (B), shall be designated as follows:

**Ball point refill ISO 12757-2 B B DOC**

### 7.2 Marking

For identification, disposable ball point pens or refills shall be marked as follows:

- a) the name of the manufacturer, supplier or trademark;
- b) the designation in accordance with 7.1 [except 7.1 a), which is optional]; and
- c) the date of manufacture (year/month, in full or coded) or the batch number.

## 8 Test report

The test report shall include the following information:

- a) reference to this part of ISO 12757;
- b) the date and place of test;
- c) precise identification of the samples (see 7.2);