

---

---

**Determination of particle size distribution  
by centrifugal liquid sedimentation  
methods —**

Part 3:  
**Centrifugal X-ray method**

*Détermination de la distribution granulométrique par les méthodes de  
sédimentation centrifuge dans un liquide —*

*Partie 3: Méthode centrifuge aux rayons X*



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 13318-3:2004

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Contents

	Page
Foreword .....	iv
Introduction .....	v
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions .....	1
4 Symbols .....	1
5 Sampling .....	2
6 Principle .....	2
7 Apparatus .....	3
8 Preparation .....	4
9 Measurement procedure .....	4
10 Tests in duplicate and validation .....	4
11 Calculation of results .....	5
12 Test report .....	5
Annex A (informative) Worked example .....	6

STANDARDSISO.COM : Click to view the full PDF of ISO 13318-3:2004

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 13318-3 was prepared by Technical Committee ISO/TC 24, *Sieves, sieving and other sizing methods*, Subcommittee SC 4, *Sizing by methods other than sieving*.

ISO 13318 consists of the following parts, under the general title *Determination of particle size distribution by centrifugal liquid sedimentation methods*:

- *Part 1: General principles and guidelines*
- *Part 2: Photocentrifuge method*
- *Part 3: Centrifugal X-ray method*

STANDARDSISO.COM : Click to view the full PDF of ISO 13318-3:2004

## Introduction

The X-ray centrifuge monitors particle concentration changes at a fixed or variable radius. In some configurations, the instrument can also be used in a gravitational mode (see ISO 13317-1) and those data blended with other data determined in the centrifugal mode, thus extending the typical upper size limit above 5  $\mu\text{m}$ .

STANDARDSISO.COM : Click to view the full PDF of ISO 13318-3:2004



# Determination of particle size distribution by centrifugal liquid sedimentation methods —

## Part 3: Centrifugal X-ray method

**WARNING** — This part of ISO 13318 may involve hazardous materials operations and equipment. This part of ISO 13318 does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of the regulatory limitations prior to its use.

### 1 Scope

This part of ISO 13318 describes a method for determining the particle size distribution of homogeneous particulate material using centrifugal sedimentation in a liquid. Solids concentrations are determined by the attenuation of an X-ray beam. The resulting signal enables conversion to a particle size distribution.

The method of determining the particle size distribution described in this standard is applicable to powders which can be dispersed in liquids or powders which are present in slurry form. The typical particle size range for analysis is from 0,1  $\mu\text{m}$  to 5  $\mu\text{m}$ . The method is applicable to powders in which all particles have the same effective density, chemical composition and comparable shapes. Materials possessing elements with an atomic number greater than about 12 can be expected to produce adequate X-ray opacity. Particles should not undergo chemical or physical change in the suspension liquid. It is necessary that the particles have a higher density than that of the liquid.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 13318-1, *Determination of particle size distribution by centrifugal liquid sedimentation methods — Part 1: General principles and guidelines*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 13318-1 and the following apply.

### 4 Symbols

For the purpose of this document, the symbols of ISO 13318-1 and the following apply.

$B$	function of the atomic number of the sample elements in the beam
$C$	concentration of sample in the beam
$I_0$	transmission of the emergent X-ray beam through the suspending fluid with no particles present
$I$	transmission of the emergent X-ray beam through suspension at radius $M$ and time $t$

$D$	X-ray density [ $\log_{10} (I_0/I)$ ]
$x_{St}$	diameter of the largest particle in the X-ray beam, i.e. the Stokes diameter, expressed in micrometres
$M$	distance, expressed in centimetres, from rotation axis to measurement zone
$S$	distance, expressed in centimetres, from rotation axis to liquid-air interface of sample

## 5 Sampling

For information regarding sampling, see ISO 13318-1.

## 6 Principle

A stable, finely collimated beam of X-rays passes through a suspension containing the sample particles and is detected at a known radius. The centrifuge disc containing the sample is of known dimensions and a known amount of suspension is used so that the surface radius for the suspension can be calculated. The measured settling radius can be reduced during the analysis for the purpose of obtaining a more rapid analysis than would be possible if the radius were fixed. The mass percentage of sample present at a given time, and at a known measurement radius, is determined by calculating the ratio of

- the X-ray transmission through a clear dispersing liquid, and
- the signal with the sample present.

The Stokes diameter ( $x_{St}$ ) at measurement radius,  $M$ , and time,  $t$ , is given by the following equation:

$$x_{St} = \sqrt{\frac{18\eta \ln \frac{M}{S}}{(\rho_s - \rho_l) \omega^2 t}} \quad (1)$$

The transmission,  $I$ , of the emergent X-ray beam having passed through the suspension is proportional to the mass of powder in the beam.

$$I = I_0 \exp[-BC(r,t)] \quad (2)$$

where  $C(r,t)$  is the concentration of the sample in the beam at radius,  $r$ , and time,  $t$ .

The X-ray density,  $D$ , at measurement radius,  $r$ , and time,  $t$ , is given by the following equation:

$$D = -BC(M,t) \log_{10} e = \log_{10} (I_0 / I) \quad (3)$$

The X-ray density of the emergent beam, after correction for radial dilution effects, is proportional to the mass of sample in the beam.



## 7.2 Ancillary apparatus

The ancillary apparatus consists of

- dispersing vessel, of appropriate dimensions,
- flexible spatula, and
- ultrasonic bath or probe, a bottle shaker or high speed mechanical stirrer capable of rotating at 500 r·min<sup>-1</sup> to 1 000 r·min<sup>-1</sup>.

## 8 Preparation

### 8.1 Sample preparation

Prepare an analytical sample as described in ISO 13318-1.

Prepare an initial sample for analysis having a homogeneous concentration of about 0,2 % by volume. If this is not sufficient to give an adequate signal, it may be necessary to increase the concentration.

Carry out duplicate tests at higher concentrations in order to determine whether delayed settling is occurring. If the second test gives a significantly higher percentage of small particles, then discard these data.

### 8.2 Temperature

Measure and record the temperature of the suspension before and after analysis, in accordance with ISO 13318-1. Record the liquid viscosity and liquid density for the spin fluid or suspension at the temperature of the analysis. Maintain the temperature in accordance with ISO 13318-1.

### 8.3 Dispersion

For information regarding the dispersion, see ISO 13318-1.

## 9 Measurement procedure

Switch the instrument on 20 min before use in order to obtain stable operating signal. Determine the attenuation of the emergent X-ray beam with only the suspension liquid in the disc. To this end, inject sufficient clear suspension liquid into the disc to ensure that the X-ray beam path is below the liquid surface in order to provide the maximum X-ray transmission reading. The suspension liquid is then removed. For more precise results, a base-line scan of the entire measuring portion of the disc may be determined for subsequent correction of the corresponding suspension data.

Set the run conditions prior to analysis by keying into the computer the operating variables such as effective particle density, liquid density and liquid viscosity. Then switch the centrifuge on to the desired speed and feed the suspension into the centrifuge disc without delay and activate the timer.

## 10 Tests in duplicate and validation

### 10.1 Tests in duplicate

For information regarding duplicate tests, see ISO 13318-1.

### 10.2 Validation

For information regarding validation, see ISO 13318-1.

## 11 Calculation of results

### 11.1 Calculation of particle size

Calculate the Stokes diameters in accordance with ISO 13318-1.

### 11.2 Calculation of cumulative mass percentage

In the centrifugal X-ray method, the attenuation of the X-ray beam is directly proportional to the mass of particles in the path of the beam through the suspension and the result is presented automatically.

## 12 Test report

The report shall conform with the requirements in accordance with ISO 13318-1. Results shall typically be presented as a plot of Stokes diameter versus cumulative distribution by mass reported to the nearest 0,1 %. On graphic presentations of the plot, the diameters are placed on the abscissa and the cumulative mass percentage on the ordinate.

The report shall include

- reference to this part of ISO 13318,
- name of the testing establishment,
- date of the test,
- operator identification,
- instrument type used,
- mode of operation (e.g. fixed radius or scanning),
- test sample identification,
- sample density (and mass, if available),
- suspending liquid, its temperature, density, viscosity and, if applicable, its volume,
- dispersing agent and concentration of agent used,
- method of dispersion of the suspension, including dispersion time,
- centrifuge speed,
- any other operations not specified in this part of ISO 13318 and which might have an influence on the results.

The following instrument characteristic, typically determined by the manufacturer and pre-programmed into the equipment software, may be optionally reported if available:

- Measurement radius,  $M$  (not fixed in scanning mode)

## Annex A (informative)

### Worked example

#### A.1 General

Experimental data are presented in Table A.1. Supplementary data include the following.

The measurement radius,  $M$ , at the start of the analysis is 4,88 cm and the surface radius,  $S$ , is 4,41 cm. After 1 min, the source and detector scan towards the surface at constant speed and  $M$  decreases as  $t$  increases such that after 7 min scanning the X-ray beam is 0,2 cm below the surface.

The opacity to X-ray is determined by the count level of a scintillation counter and converted into a percentage to give the measured concentration. The example data presented here represent smoothed data taken every 15 s. In an actual analysis, the data may be taken more frequently and data smoothing may be performed automatically in some instrument configurations.

Using Equation (1), the Stokes diameter,  $x_1$ , in micrometres, at 15 s is given by

$$x_1 = \sqrt{\frac{18 \times 8,90 \times 10^{-4} \ln\left(\frac{4,88}{4,41}\right)}{(2\,500 - 1\,000) 15(50\pi)^2}} = 1,71 \quad (\text{A.1})$$

At 1 min, the Stokes diameter is 0,855  $\mu\text{m}$ . Scanning commences after 1 min and causes the measurement radius to decrease with increasing time. Subsequent diameters, expressed in micrometres, are, therefore, determined using the Stokes equation in the following form:

$$x_i = 20,80 \sqrt{\frac{\ln\left(\frac{M_i}{4,41}\right)}{t_i}} \quad (\text{A.2})$$

#### A.2 Example

ISO reference	ISO 13318-3
Testing establishment	MAL
Date	2000-11-15
Report	Quartz 123
Operator	DM
Instrument	Model X234
Operation mode	Scanning
Sample identification	Quartz A157
Material	Quartz