
**Petroleum and natural gas industries —
Completion fluids and materials —**

Part 2:

**Measurement of properties of proppants
used in hydraulic fracturing and gravel-
packing operations**

AMENDMENT 1: Addition of Annex B:
Proppand specification

*Industries du pétrole et du gaz naturel — Fluides de complétion et
matériaux —*

*Partie 2: Mesurage des propriétés des matériaux de soutènement
utilisés dans les opérations de fracturation hydraulique et de
remplissage de gravier*

*AMENDEMENT 1: Ajout de l'Annexe B: Spécifications relatives aux
matériaux de soutènement*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

 **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 13503-2:2006 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for the petroleum, petrochemical and natural gas industries*, Subcommittee SC 3, *Drilling and completion fluids, and well cements*.

STANDARDSISO.COM : Click to view the full PDF of ISO 13503-2:2006/Amd.1:2009

STANDARDSISO.COM : Click to view the full PDF of ISO 13503-2:2006/Amd 1:2009

Petroleum and natural gas industries — Completion fluids and materials —

Part 2:

Measurement of properties of proppants used in hydraulic fracturing and gravel-packing operations

AMENDMENT 1: Addition of Annex B: Proppand specification

Page 1, Clause 1

Replace the last line with the following:

The objective of this part of ISO 13503 is to provide a consistent methodology and specifications for testing performed on hydraulic fracturing and/or gravel-packing proppants.

Page 1, Clause 2

Add the date to ASTM E11 as follows:

ASTM E11-04, *Standard Specification for Wire Cloth and Sieves for Testing Purposes*

Page 28, after Annex A

Add the following Annex B.

Annex
(informative)

Proppant specifications

B.1 Fracturing proppant sizes

A minimum of 90 % of the tested proppant sample shall pass the coarse designated (or first primary) sieve and be retained on the fine designated (or second primary) sieve (i.e. 12/20, 20/40, 40/60, etc.). For 20/40 sieve sizes, a minimum of 90,0 % of the tested proppant sample shall pass the 20 mesh sieve and be retained on the 40 mesh sieve. Not over 0,1 % of the total tested proppant sample shall be larger than the first sieve size in the sieve stack specified in Table B.1 and not over 1,0 % of the total tested proppant sample shall be smaller than the last designated sieve size.

EXAMPLE For 20/40 sieve sizes, no more than 0,1 % of the total tested proppant sample shall be retained on the 16 mesh sieve (the first sieve size in the stack) and no more than 1,0 % of the total tested proppant sample shall be smaller than the 50 mesh sieve.

The median diameter and sieve distribution of each grade shall be made available.

Table B.1 — Sieve sizes

Sieve opening sizes µm	3 350/ 11 700	2 360/ 1 180	1 700/ 1 000	1 700/ 850	1 180/ 850	1 180/ 600	850/ 425	600/ 300	425/ 250	425/ 212	212/ 106
Typical proppant/ gravel pack size designation ^a	6/12	8/16	12/18	12/20	16/20	16/30	20/40	30/50	40/60	40/70	70/140
Coarse sieve ^b	4	6	8	8	12	12	16	20	30	30	50
	6	8	12	12	16	16	20	30	40	40	70
	8	10	14	14	18	18	25	35	45	45	80
Fine sieve ^c	10	12	16	16	20	20	30	40	50	50	100
	12	14	18	18	25	25	35	45	60	60	120
	14	16	20	20	30	30	40	50	70	70	140
	16	20	30	30	40	40	50	70	100	100	200
	pan	pan	pan	pan	pan	pan	pan	pan	pan	pan	pan

^a Stack of sieves in vertical order top to bottom as defined in ASTM E 11-04.

^b Coarse designated (or first primary) sieve is shaded.

^c Fine designated (or second primary) sieve is shaded.

B.2 Gravel packing sizes


A minimum of 96,0 % of the tested proppant sample shall pass the coarse designated (or first primary) sieve and be retained on the fine designated (or second primary) sieve (i.e. 12/20, 20/40, 40/60, etc.). For 20/40 sieve sizes, a minimum of 96,0 % of the tested proppant sample shall pass the 20 mesh sieve and be retained on the 40 mesh sieve. Not over 0,1 % of the total tested proppant sample shall be larger than the first sieve size in the stack specified in Table B.1 and not over 1,0 % of the total tested proppant sample shall be smaller than the last designated sieve size.

EXAMPLE A 20/40 proppant sample shall have no more than 0,1 % of the total tested proppant sample retained on the 16 mesh sieve and no more than 1,0 % of the total tested proppant sample shall be smaller than the 50 mesh sieve.

The median diameter and sieve distribution shall be made available.

B.3 Sphericity and roundness

Ceramic proppants and resin-coated ceramic proppants shall have an average sphericity of 0,7 or greater and an average roundness of 0,7 or greater. All other proppants shall have an average sphericity of 0,6 or greater and an average roundness of 0,6 or greater.



Key
 X roundness
 Y sphericity

Figure B.1 — Chart for visual estimation of sphericity and roundness

B.4 Acid solubility

The acid soluble material in proppants shall not exceed the values shown in Table B.2.

Table B.2 — Maximum acid solubility

Proppant size mesh	Maximum solubility % mass fraction
Hydraulic fracturing sand, resin coated sand, gravel packing sand proppants	
— Larger than or equal to 30/50	2,0
— Smaller than 30/50	3,0
Ceramic proppants and resin coated ceramic proppants	7,0

B.5 Maximum proppant turbidity

The turbidity of all fracturing and gravel packing proppants shall not exceed 250 FTU (NTU).

B.6 Maximum crush material

B.6.1 General

The provisions of B.6 do not apply to curable resin coated proppants. Consolidated wafers fall outside this test.

B.6.2 Gravel packing proppants

Samples of gravel packing proppant subjected to this test shall not produce average fines in excess of the fines specified in Table B.3, at a stress of 13,8 MPa (2 000 psi).

Table B.3 — Maximum fines

Proppant size mesh	Crushed material max. % mass fraction
8/16	8,0
12/20	4,0
16/30	2,0
20/40	2,0
30/50	2,0
40/60	2,0