

First edition
2003-09-15

Corrected version
2004-11-01

**Centrifugally cast steel and alloy
products —**

**Part 2:
Heat resistant materials**

Produits en acier et alliages moulés par centrifugation —

Partie 2: Aciers moulés réfractaires

STANDARDSISO.COM : Click to view the full PDF of ISO 13583-2:2003



Reference number
ISO 13583-2:2003(E)

© ISO 2003

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 13583-2:2003

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 General technical delivery conditions	1
4 Heat treatment	1
5 Chemical requirements	1
6 Mechanical properties	1
7 Supplementary requirements	4
8 Additional information	4
Annex A (informative) Mean values for 1 % elongation and creep rupture	5
Annex B (informative) Physical properties	7

STANDARDSISO.COM : Click to view the full PDF of ISO 13583-2:2003

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 13583-2 was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 11, *Steel castings*.

ISO 13583 consists of the following parts, under the general title *Centrifugally cast steel and alloy products*:

- *Part 1: General testing and tolerances*
- *Part 2: Heat resistant materials*

This corrected version of ISO 13583-2:2003 incorporates the following corrections.

Clause 2, normative reference to ISO 4990 has been updated.

Table 1, row 17, column 13 (C + N = 0,20 max.).

Table 2, row 12, column 1 (GX42NiCrWSi35-25-5).

Table 3, row 11, column 1 (GX42NiCrSiNbTi35-25).

Table A.1, row 7, column 1 (GX40NiCrSi38-18).

Table A.3, row 13, column 1 (GX42NiCrSiNbTi45-35).

Centrifugally cast steel and alloy products —

Part 2: Heat resistant materials

1 Scope

This part of ISO 13583 specifies cast steel and alloy grades for elevated temperature service pieces manufactured by centrifugal casting.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4990:2003, *Steel castings — General technical delivery requirements*

ISO 13583-1:2000, *Centrifugally cast steel and alloy products — Part 1: General testing and tolerances*

3 General technical delivery conditions

Cast steel and alloy grades specified by this International Standard shall conform to the applicable requirements of ISO 4990 and ISO 13583-1 including the supplementary requirements that are indicated in the enquiry and purchase order.

4 Heat treatment

The cast steel and alloy grades specified by this International Standard do not require heat treatment. If heat treatment is required, the treatment shall be established by mutual agreement between the manufacturer and the purchaser, and shall be specified in the purchase contract.

5 Chemical requirements

The cast steels and alloy grades shall conform to the chemical requirements listed in Table 1.

6 Mechanical properties

The cast steel and alloy grades shall conform to the requirements given in Tables 2 and 3.

Mechanical tests at room temperature and elevated temperature shall be performed if agreed upon between the manufacturer and purchaser at the time of enquiry and order.

Table 1 — Chemical composition (cast analysis % by mass)

Designation	C	Si	Mn	P max.	S max.	Cr	Ni	Mo max.	Nb	W	Co	Others
GX30CrNiSi19-9	0,25 0,35	1,30 1,80	0,50 1,50	0,03	0,03	18,0 20,0	8,0 10,0	0,5				
GX40CrNiSi25-12	0,35 0,45	1,00 2,00	0,50 1,50	0,03	0,03	24,0 26,0	11,0 13,0	0,5				
GX42CrNiSi25-20	0,38 0,45	1,00 2,00	0,50 1,50	0,03	0,03	24,0 26,0	19,0 21,0	0,5				
GX30CrNiSiNb24-24	0,25 0,35	0,70 2,00	0,50 1,50	0,03	0,03	23,0 25,0	23,0 25,0	0,5	1,20 1,80			
GX12NiCrSiNb32-21	0,08 0,15	0,50 1,50	0,50 1,50	0,03	0,03	19,0 22,0	31,0 33,0	0,5	0,60 1,30			
GX40NiCrSi38-18	0,35 0,45	1,30 2,00	0,50 1,50	0,03	0,03	17,0 19,0	36,0 39,0	0,5				
GX12NiCrSiNb35-25	0,08 0,15	0,50 1,50	0,50 1,50	0,03	0,03	24,0 27,0	34,0 37,0	0,5	0,60 1,30			
GX42NiCrSiNb35-25	0,38 0,45	0,50 1,50	0,50 1,50	0,03	0,03	24,0 27,0	34,0 37,0	0,5	0,60 1,25			
GX43NiCrSiNb35-25	0,38 0,48	1,50 2,50	0,50 1,50	0,03	0,03	24,0 27,0	34,0 37,0	0,5	0,60 1,80			
GX42NiCrSiNbTi35-25	0,38 0,45	1,00 2,00	0,50 1,50	0,03	0,03	24,0 27,0	34,0 37,0	0,5	0,60 1,80			Ti 0,06 min. ^a addition required
GX42NiCrWSi35-25-5	0,38 0,45	1,00 2,00	0,50 1,50	0,03	0,03	24,0 27,0	34,0 37,0	0,5		4,00 6,00		
GX42NiCrSiNbTi45-35	0,38 0,45	1,00 2,00	0,50 1,50	0,03	0,03	33,0 36,0	44,0 47,0	0,5	0,50 1,50			Ti 0,06 min. ^a addition required
GX45NiCrCoW35-25-15-5	0,40 0,50	1,00 2,00	0,50 1,50	0,03	0,03	24,0 26,0	33,0 37,0	0,5		4,00 6,00	14,0 16,0	
GX48NiCrWSi48-28-5	0,40 0,55	1,00 1,75	0,50 1,50	0,03	0,03	27,0 29,0	47,0 49,0	0,5		4,00 6,00		
GX48NiCrWCo48-28-5-3	0,40 0,55	1,00 1,75	0,50 1,50	0,03	0,03	27,0 29,0	47,0 49,0	0,5		4,00 6,00	2,50 3,50	
GX8NiCrNb50-50	0,1 max.	0,5 max.	0,5 max.	0,02	0,02	47,0 52,0	balance	0,5	1,40 1,70			N 0,16 max., C + N = 0,20 max. Fe 1,0 max.

^a Other micro alloying elements can be substituted for titanium. The total micro alloying elements shall be 0,06 % min.

Table 2 — Mechanical properties at room temperature

Designation	$R_{p0,2}$	R_m	A_5
	MPa ^a min.	MPa ^a min.	% min.
GX30CrNiSi19-9	230	450	15
GX40CrNiSi25-12	230	450	10
GX42CrNiSi25-20	220	450	8
GX30CrNiSiNb24-24	220	450	10
GX12NiCrSiNb32-21	170	440	20
GX40NiCrSi38-18	220	420	6
GX12NiCrSiNb35-25	175	440	20
GX42NiCrSiNb35-25	220	450	8
GX43NiCrSiNb35-25	220	450	8
GX42NiCrSiNbTi35-25	220	450	8
GX42NiCrW35-25-5	220	450	4
GX42NiCrSiNbTi45-35	250	450	5
GX45NiCrCoW35-25-15-5	250	450	5
GX48NiCrW35-25-15-5	220	400	5
GX48NiCrWCo48-28-5-3	220	400	5
GX8NiCrNb50-50	250	550	8

^a 1 N/mm² = 1 MPa.

Table 3 — Short time rupture test: minimum time to rupture of 100 hours at constant stress and temperature

Designation	Temperature °C	Stress MPa
GX30CrNiSi19-9	800	47
GX40CrNiSi25-12	900	34
GX42CrNiSi25-20	900	40
GX30CrNiSiNb24-24	900	48
GX12NiCrSiNb32-21	800	70
GX40NiCrSi38-18	900	34
GX12NiCrSiNb35-25	800	70
GX42NiCrSiNb35-25	950	40
GX43NiCrSiNb35-25	950	40
GX42NiCrSiNbTi35-25	950	42
GX42NiCrW35-25-5	950	35
GX42NiCrSiNbTi45-35	1 050	21
GX45NiCrCoW35-25-15-5	950	40
GX48NiCrW35-25-15-5	1 050	20
GX48NiCrWCo48-28-5-3	1 050	20
GX8NiCrNb50-50	900	40

7 Supplementary requirements

A list of standardized supplementary requirements for use at the option of the purchaser is included in ISO 4990 and ISO 13583-1. These supplementary requirements may be used with this specification upon agreement between the manufacturer and purchaser. These must be agreed at the time of the order and listed in the order.

8 Additional information

Additional information on the cast steels and alloy grades in this International Standard is included in Tables A.1, A.2 and A.3 and in Annex B. This information is given for guidance only and is not a requirement of this International Standard.

STANDARDSISO.COM : Click to view the full PDF of ISO 13583-2:2003

Annex A (informative)

Mean values for 1 % elongation and creep rupture

Table A.1 — Mean values of stress for 1 % elongation in 10 000 h
(mean values out of a scatter band ± 20 %)

Values in megapascals

Designation	$R_{1/10\ 000}$ at 600 °C	$R_{1/10\ 000}$ at 700 °C	$R_{1/10\ 000}$ at 800 °C	$R_{1/10\ 000}$ at 900 °C	$R_{1/10\ 000}$ at 1 000 °C	$R_{1/10\ 000}$ at 1 100 °C
GX30CrNiSi19-9	78	44	22	9		
GX40CrNiSi25-12		50	26	13	6	
GX42CrNiSi25-20		65	36	17	7	2,4
GX30CrNiSiNb24-24		80	46	22	7,5	
GX12NiCrSiNb32-21		64	36	15,5	5	
GX40NiCrSi38-18		55	32	18	7	
GX12NiCrSiNb35-25		64	36	15,5	5	
GX42NiCrSiNb35-25		80	51	28	13	3,6
GX43NiCrSiNb35-25		74	46	25	10,5	2,9
GX42 NiCrSiNbTi35-25		84	54	29	14	4
GX42NiCrW35-25-5		73	43	22	9,8	2,6
GX42NiCrSiNbTi 45-35		84	50	28	15,4	7,1
GX45NiCrCoW35-25-15-5		90	60	32	17	6
GX48NiCrW35-25-5			46	27	13	4
GX48NiCrWCo48-28-5-3		90	55	29	13,5	6
GX8NiCrNb50-50		71	38	18	6,8	

NOTE Purchasers should consider the effects of atmospheres and temperatures in service when assessing the suitability of component design and selection of grade.