
**Implants for surgery — Hydroxyapatite —
Part 2:
Coatings of hydroxyapatite**

Implants chirurgicaux — Hydroxyapatite —

Partie 2: Revêtements à base d'hydroxyapatite

STANDARDSISO.COM : Click to view the full PDF of ISO 13779-2:2000



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 13779-2:2000

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 13779 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 13779-2 was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC 1, *Materials*.

ISO 13779 consists of the following parts, under the general title *Implants for surgery — Hydroxyapatite*:

- *Part 1: Ceramic hydroxyapatite*
- *Part 2: Coatings of hydroxyapatite*
- *Part 3: Chemical analysis and characterization of crystallinity and phase purity*
- *Part 4: Determination of coating adhesion strength*

Introduction

No known surgical implant material has ever been shown to cause absolutely no adverse reactions in the human body. However, long-term clinical experience of the use of the material referred to in this part of ISO 13779 has shown that an acceptable level of biological response can be expected, if the material is used in appropriate applications.

The biological response to coatings of hydroxyapatite ceramic has been demonstrated by a history of clinical use and by laboratory studies. See Bibliography.

STANDARDSISO.COM : Click to view the full PDF of ISO 13779-2:2000

Implants for surgery — Hydroxyapatite —

Part 2: Coatings of hydroxyapatite

1 Scope

This part of ISO 13779 specifies requirements for ceramic hydroxyapatite coatings applied to metallic or non-metallic surgical implants.

This part of ISO 13779 does not apply to coatings made from glasses, glass ceramics, α - and β -calcium orthophosphate or other forms of calcium phosphate, nor does it apply to coatings in which the hydroxyapatite is present in a powder form.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 13779. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 13779 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 10993-17:—¹⁾ *Biological evaluation of medical devices — Part 17: Establishment of permissible limits and process residues using health-based risk assessment.*

ISO 13779-3:—¹⁾ *Implants for surgery — Hydroxyapatite — Part 3: Chemical analysis and characterization of crystallinity and phase purity.*

ISO 13779-4: —¹⁾ *Implants for surgery — Hydroxyapatite — Part 4: Determination of coating adhesion strength.*

3 Terms and definitions

For the purposes of this part of ISO 13779, the following terms and definitions apply.

3.1

ceramic hydroxyapatite

hydroxyapatite which has been formed into a coherent crystalline mass by subjecting it to conditions at which the crystals in the powder fuse together

1) To be published.

3.2 hydroxyapatite

chemical compound with a crystallographic structure characterized by the powder diffraction file PDF 9-432 of the International Committee for Diffraction Data ICDD, USA

NOTE The chemical formula is $\text{Ca}_5(\text{OH})(\text{PO}_4)_3$.

3.3 coating

hydroxyapatite which has been deposited onto the surface of a metallic or non-metallic substrate, either by means of a thermal spray process which produces a ceramic-type coating, or by means of a solution based technique which may deposit hydroxyapatite directly or may require thermal or other treatment to convert it into a crystalline form

4 Requirements

4.1 Chemical analysis

The content of calcium and phosphorus of the hydroxyapatite ceramic coating shall be determined in accordance with ISO 13779-3. The calcium to phosphorus ratio, Ca/P, shall have a value in the range of 1,67 to 1,76 for the atomic ratio. This shall be determined as specified in ISO 13779-3.

4.2 Trace elements

The limits of specific trace elements for ceramic hydroxyapatite are given in Table 1.

The maximum allowable limit for metals having adverse biological reactions is a total of 50 mg/kg. The trace element levels shall be determined as specified in ISO 13779-3.

Assessment of the risk posed by other chemical impurities shall be carried out in accordance with ISO 10993-17.

Table 1 — Limits of specific trace elements

Trace element	Maximum limit mg/kg
Arsenic	3
Cadmium	5
Mercury	5
Lead	30

4.3 Crystalline content

The content of crystalline hydroxyapatite shall be not less than 45 %. The maximum allowable level of other crystalline phases shall be 5 %, with the balance being amorphous.

The quantitative determination of the content of the hydroxyapatite crystalline phase and of other crystalline phases shall be carried out in accordance with ISO 13779-3.

4.4 Adhesion to substrate

The adhesion to the substrate material shall be determined in accordance with the method described in ISO 13779-4 and shall have a value for adhesion strength of not less than 15 MPa.

Bibliography

- [1] ISO 5961:1985, *Water quality — Determination of cadmium — Flame atomic absorption spectrometric methods.*
- [2] ISO 8288:1986, *Water quality — Determination of cobalt, nickel, copper, zinc, cadmium and lead — Flame atomic absorption spectrometric method.*
- [3] ASTM C 633-79:1985, *Standard test method for adhesion or cohesion strength of flame sprayed coatings.*
- [4] ASTM F 1609:1995, *Standard specification for calcium phosphate coatings for implantable materials.*
- [5] ASTM F 1185:1988, *Standard specification for composition of ceramic hydroxyapatite for surgical implants.*
- [6] ASTM F 1501:1995, *Standard test method for tension testing of calcium phosphate coatings.*
- [7] BS 5350 Part C15:1982, *Standard test method for adhesion of coatings using a compressive method.*
- [8] NF S 94-065, *Materials for surgical implants — Determination of arsenic, mercury, cadmium and lead on coating based on phosphate of calcium.*
- [9] NF S 94-066, *Materials for surgical implants — Quantitative determination of the Ca/P ratio of calcium phosphate.*
- [10] NF S 94-067, *Materials for surgical implants — Qualitative and quantitative determination of the foreign phases present in calcium phosphate based powders, deposits and ceramics.*
- [11] NF S 94-068, *Materials for surgical implants — Determination of the crystallinity and apparent size of the apatite crystallites of hydroxyapatite based powders, deposits and ceramics.*
- [12] NF S 94-071, *Materials for surgical implants — Determination of the surface finish of coatings used for biomedical applications.*
- [13] NF S 94-072, *Materials for surgical implants — Determination of tensile adherence of phosphocalcic materials for biomedical applications.*
- [14] JIS H 8666, *Thermal sprayed ceramic coatings.*
- [15] ICDD cards 9-432, 9-348, 9-169, 25-1137, 37-1497, 9-80, 9-77, 14-1475, 5-586 X-ray diffraction standards for hydroxyapatite, α -tricalcium orthophosphate, β -tricalcium orthophosphate, tetracalcium phosphate, calcium oxide, monetite, brushite, aragonite, calcite.
- [16] *Hydroxyapatite Ceramic — A Decade of Experience in Hip Arthroplasty*, Symposium at Royal College of Surgeons of England, London, November 1995.
- [17] K. de GROOT *et al.*, *J. Biomed. Mater. Res.*, **21**, pp. 1375ff, 1987.
- [18] A. MORONI *et al.*, Bone Ingrowth Analysis and Interface Evaluation of Hydroxyapatite Coated Versus Uncoated Titanium Porous Bone Implants, in *Bioceramics*, T Yamamuro, T Kokubo, T Nakamura (eds.), Vol. 5, Kobunshi Kankokai, Kyoto, 1992 pp. 299-305.
- [19] CPAT KLEIN *et al.*, Stability of calcium phosphate ceramics and plasma-sprayed coating, in *An Introduction to Bioceramics*, L. Hench and J. Wilson (eds.), World Scientific, 1993 pages 199-221.
- [20] S.D. COOK *et al.*, Hydroxylapatite Coated Titanium for Orthopaedic Implant Applications, *Clin. Orthop. Rel. Res.*, **232**, pp. 225-243, 1988.

- [21] G.W. HASTINGS *et al.*, Hydroxyapatite coatings for biomaterials — A report of a multi-centre investigation, in *Bioceramics* 7, Ö.H. Andersson, R.P. Happonen, A. Yli-Urpo (eds.), Butterworth-Heinemann, Oxford, 1994, pp. 207-213.
- [22] A.M. TUDOR *et al.*, The analysis of biomedical hydroxyapatite powders and hydroxyapatite coatings on metallic implants by near-IR Fourier Transform raman spectroscopy. *Spectrochim, Acta*, **49A**, 4/6, pp. 675-680, 1993.
- [23] A. MEROLLI, P. TRANQUILLI, LEALI. Crystallinity of the coating directs the *in vivo* response to hydroxyapatite in the rabbit, in *Bioceramics* 7, Ö.H. Andersson, R.P. Happonen, A. Yli-Urpo (eds.) Butterworth-Heinemann, Oxford, 1994, pp, 223-228.
- [24] R.G.T. GEESINK and M.T. MANLEY (eds.). *Hydroxyapatite coatings in orthopaedic surgery*, Raven Press, New York 1993.
- [25] Hideki AOKI, *Medical Applications of Hydroxyapatite*. Ishiyaku Euro America, Tokyo, 1994.

STANDARDSISO.COM : Click to view the full PDF of ISO 13779-2:2000