

INTERNATIONAL STANDARD

ISO 139

Second edition
2005-01-15

AMENDMENT 1
2011-07-01

Textiles — Standard atmospheres for conditioning and testing

AMENDMENT 1

Textiles — Atmosphères normales de conditionnement et d'essai
AMENDEMENT 1

STANDARDSISO.COM : Click to view the full PDF of ISO 139:2005/Amd 1:2011



Reference number
ISO 139:2005/Amd.1:2011(E)

© ISO 2011

STANDARDSISO.COM : Click to view the full PDF of ISO 139:2005/Amd 1:2011



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 139:2005 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 24, *Conditioning atmospheres and physical tests for textile fabrics*.

STANDARDSISO.COM : Click to view the full PDF of ISO 139:2005/Amd 1:2017

Textiles — Standard atmospheres for conditioning and testing

AMENDMENT 1

Page 1, Clause 2

Insert a definition of “rapid conditioning” as follows:

2.8

rapid conditioning

accelerated conditioning

system that permits specimens to reach equilibrium with the standard atmosphere for testing textiles at a significantly faster rate than if the specimens are exposed to the atmosphere in a static state

Page 2, Clause 3

Replace Clause 3 with the following text.

3 Requirements

3.1 Standard atmosphere

The standard atmosphere shall have a temperature of 20,0 °C and a relative humidity of 65,0 %.

3.2 Alternative standard atmospheres

The alternative, but not equivalent, atmosphere (3.2.1 or 3.2.2) may only be used if the parties involved agree on its use, and the alternative atmosphere used shall be reported.

3.2.1 Specific standard atmosphere

The specific standard atmosphere shall have a temperature of 23,0 °C and a relative humidity of 50,0 %.

3.2.2 Tropical standard atmosphere

The tropical standard atmosphere shall have a temperature of 27,0 °C and a relative humidity of 65,0 %.

3.3 Tolerance zone for the standard atmosphere and the alternative standard atmospheres

The tolerance for temperature is $\pm 2,0$ °C.

The tolerance for relative humidity is $\pm 4,0$ %.

NOTE For a control of standard atmospheres, see Annex A.

Page 3, Subclause 5.4

Replace the second paragraph with the following text.

Unless otherwise specified, the textile should be considered to be in equilibrium when successive weighings show no progressive change in mass greater than 0,25 %.

In the case of the standard atmosphere in a conditioned laboratory, successive weighing should be done on the textile at intervals of 2 h.

However, where accelerated conditioning systems are used, a shorter interval of 2 min to 10 min should be used.

STANDARDSISO.COM : Click to view the full PDF of ISO 139:2005/Amd 1:2011