

---

---

**Plastics piping and ducting systems —  
Thermoplastics pipes — Determination of  
ring flexibility**

*Systèmes de canalisations et de gaines en matières plastiques —  
Tubes en matières thermoplastiques — Détermination de la flexibilité  
annulaire*

STANDARDSISO.COM : Click to view the full PDF of ISO 13968:2008



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 13968:2008



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 13968 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories — Test methods and basic specifications*.

This second edition cancels and replaces the first edition (ISO 13968:1997), which has been technically revised.

[STANDARDSISO.COM](http://STANDARDSISO.COM) : Click to view the full PDF of ISO 13968:2008

# Plastics piping and ducting systems — Thermoplastics pipes — Determination of ring flexibility

## 1 Scope

This International Standard specifies a method for testing the ring flexibility of a thermoplastics pipe having a circular cross-section.

The method enables determination of the deflection, and necessary force, at which physical damage, if any, occurs within the specified diametric deflection.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9969, *Thermoplastics pipes — Determination of ring stiffness*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1

#### ring flexibility

ability of a pipe to resist ring diametric deflection without loss of structural integrity

[EN 13476-1:2007, 3.1.2.10]

## 4 Principle

The ring flexibility of a pipe is tested by measuring the force and the deflection while deflecting a ring section from the pipe diametrically at a constant speed until at least the specified deflection is achieved or prior fracture has occurred.

Each test piece is monitored during testing and subsequently inspected for signs of several specific types of mechanical failure.

**NOTE** It is assumed that the following test parameters are set by the standard making reference to this International Standard:

- a) if appropriate, a greater length of the test pieces than the length specified in ISO 9969, see Clause 6;
- b) the deflection, if appropriate, see 8.1.

## 5 Apparatus

**5.1 Compression testing machine**, as specified in ISO 9969, but capable of producing at least the specified diametric deflection of the test piece at the applicable speed (see ISO 9969:2007, Table 1).

**5.2 Dimensional and force measuring devices**, conforming to ISO 9969, but capable of measuring diametric deflections up to at least the specified deflection and the corresponding compressive forces.

## 6 Test pieces

Prepare three test pieces from a single pipe, as specified in ISO 9969, and designate them a, b, and c respectively. The referring standard may specify longer test pieces than defined in ISO 9969.

## 7 Conditioning

Condition the test pieces as specified in ISO 9969.

## 8 Procedure

**8.1** Conduct the test in accordance with the procedure given in ISO 9969, but continue compression while measuring the change in either inside diameter or outside diameter until the specified deflection has been achieved. Unless otherwise specified in the referring standard, the deflection shall be 30 % of the outside diameter.

During the compression, monitor for signs of failure (see 8.2), until either the specified deflection has been reached or the test piece has failed, whichever occurs first.

If desired, the deflection may be continued after a failure has occurred or the specified deflection has been reached in order to determine other properties of the pipe.

**8.2** For each test piece, prepare a force/deflection graph, and inspect and record the type and the position of each event [a) to e)] with respect to the corresponding force and deflection.

- a) Inspect the force/deflection graph for compliance to the requirements in the referring standard.
- b) Check for any cracking or crazing in any part of the wall structure.
- c) Check for any wall delamination.
- d) Check for any permanent buckling in any part of the structure of the pipe wall.
- e) Make any other observation as specified in the referring standard.

Whitening of the pipe shall not be considered as an indication of one of the above-mentioned mechanical failures.

## 9 Test report

The test report shall include at least the following information:

- a) a reference to this International Standard and to the referring standard;
- b) the identification of the thermoplastics pipe, including:
  - 1) manufacturer,
  - 2) type of pipe,
  - 3) dimensions,
  - 4) production date,
  - 5) lengths of test pieces,
  - 6) mass per metre length of the pipe;
- c) the test temperature;
- d) the force/deflection graph for each test piece;
- e) where appropriate, the force and deflection at which any of the events specified in 8.2 occurred;
- f) the deflection and force at the maximum point, if a maximum occurred;
- g) any factors which may have affected the results, such as any incidents or any operating details not specified in this International Standard;
- h) the date of test.

STANDARDSISO.COM : Click to view the full PDF of ISO 13968:2008

## Bibliography

- [1] EN 13476-1:2007, *Plastics piping systems for non-pressure underground drainage and sewerage — Structured-wall piping systems of unplasticized poly(vinyl chloride) (PVC-U), polypropylene (PP) and polyethylene (PE) — Part 1: General requirements and performance characteristics*

STANDARDSISO.COM : Click to view the full PDF of ISO 13968:2008