
Welding consumables — Solid wire electrodes, tubular cored electrodes and electrode/flux combinations for submerged arc welding of non alloy and fine grain steels — Classification

Produits consommables pour le soudage — Fils-électrodes pleins, fils-électrodes fourrés et couples fils-flux pour le soudage à l'arc sous flux des aciers non alliés et à grains fins — Classification

STANDARDSISO.COM : Click to view the full PDF of ISO 14171:2010



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 14171:2010



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Classification	2
4 Symbols and requirements	3
4.1 Symbol for the process.....	3
4.2 Symbol for tensile properties.....	3
4.2.1 Multi-run technique	3
4.2.2 Two-run technique	4
4.3 Symbol for the impact properties of all-weld metal or two-run welded joint.....	4
4.4 Symbol for type of welding flux	5
4.5 Symbol for the chemical composition	6
4.5.1 Solid wire electrodes.....	6
4.5.2 Tubular cored electrode/flux combinations.....	6
4.6 Symbol for hydrogen content of deposited metal	14
5 Mechanical tests	14
5.1 Multi-run technique	14
5.2 Two-run technique	16
6 Chemical analysis	16
7 Rounding procedure	17
8 Retest.....	17
9 Technical delivery conditions	17
10 Examples of designation	18

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 14171 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

This second edition cancels and replaces the first edition (ISO 14171:2002), which has been technically revised.

Requests for official interpretations of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 3 via your national standards body. A complete listing of these bodies can be found at www.iso.org.

Introduction

This International Standard recognizes that there are two somewhat different approaches in the global market to classifying a given electrode/flux combination, and allows for either or both to be used, to suit a particular market need. Application of either type of classification designation (or of both where suitable) identifies a product as classified in accordance with this International Standard.

This International Standard provides a classification system for the designation of solid wire electrodes in terms of their chemical composition, tubular cored electrodes in terms of the deposit composition obtained with a particular submerged arc flux and, where required, electrode/flux combinations in terms of the yield strength, tensile strength and elongation of the all-weld metal deposit. The ratio of yield to tensile strength of weld metal is generally higher than that of parent material. Users should note that matching weld metal yield strength to parent material yield strength does not necessarily ensure that the weld metal tensile strength matches that of the parent material. Thus, where the application of the material requires matching tensile strengths, selection of the consumable should be made by reference to column 3 of Table 1A or 1B, as appropriate.

Although combinations of electrodes and fluxes supplied by individual companies may have the same classification, the individual wire electrodes and fluxes from different companies are not interchangeable unless verified in accordance with this International Standard.

The mechanical properties of all-weld metal test specimens used to classify the electrode/flux combinations vary from those obtained in production joints because of differences in welding procedures such as electrode size and parent material composition.

STANDARDSISO.COM : Click to view the full PDF of ISO 14171:2010

STANDARDSISO.COM : Click to view the full PDF of ISO 14171:2010

Welding consumables — Solid wire electrodes, tubular cored electrodes and electrode/flux combinations for submerged arc welding of non alloy and fine grain steels — Classification

1 Scope

This International Standard specifies requirements for the classification of electrode/flux combinations and weld metal in the as-welded condition and in the post-weld heat-treated condition for submerged arc welding of non alloy and fine grain steels with a minimum yield strength of up to 500 MPa or a minimum tensile strength of up to 570 MPa. One flux can be classified with different solid wire electrodes and tubular cored electrodes. The solid wire electrode is also classified separately based on chemical composition.

This International Standard is a combined specification providing for classification utilizing a system based upon the yield strength and the average impact energy for weld metal of 47 J, or utilizing a system based upon the tensile strength and the average impact energy for weld metal of 27 J.

- a) Clauses, subclauses, and tables which carry the suffix letter “A” are applicable only to electrode/flux combinations and wire electrodes classified using the system based upon the yield strength and the average impact energy for weld metal of 47 J, in accordance with this International Standard.
- b) Clauses, subclauses, and tables which carry the suffix letter “B” are applicable only to electrode/flux combinations and wire electrodes classified using the system based upon the tensile strength and the average impact energy for weld metal of 27 J, in accordance with this International Standard.
- c) Clauses, subclauses, and tables which do not have either the suffix letter “A” or the suffix letter “B” are applicable to all electrode/flux combinations and wire electrodes classified in accordance with this International Standard.

Fluxes for the single-run and two-run techniques are classified on the basis of the two-run technique.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 3690, *Welding and allied processes — Determination of hydrogen content in arc weld metal*

ISO 6847, *Welding consumables — Deposition of a weld metal pad for chemical analysis*

ISO 13916, *Welding — Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature*

ISO 14174, *Welding consumables — Fluxes for submerged arc welding and electroslag welding — Classification*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 15792-1:2000, *Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys*

ISO 15792-2:2000, *Welding consumables — Test methods — Part 2: Preparation of single-run and two-run technique test specimens in steel*

ISO 80000-1:2009, *Quantities and units — Part 1:General*

3 Classification

Classification designations are based upon two approaches to indicate the tensile properties and the impact properties of the weld metal obtained with a given electrode/flux combination. The two designation approaches include additional symbols for some other classification requirements, but not all, as is clear from the following clauses. In most cases, a given commercial product can be classified in accordance with both systems. Then either or both classification designations can be used for the product.

A solid wire electrode shall be classified in accordance with its chemical composition as given in Table 4A or 4B.

An all-weld metal deposit from a tubular cored electrode shall be classified in accordance with the all-weld metal composition, as given in Table 5A or 5B, obtained with a particular flux.

When the solid wire electrode or tubular cored electrode is classified in combination with a flux for submerged arc welding, the classification shall be prefixed with a symbol in accordance with Clause 4 as appropriate.

The electrode/flux classification includes weld metal properties obtained with a manufacturer's specific electrode/flux combination as given below. A wire electrode may be separately classified with the symbol for its chemical composition in Table 4A or 4B.

3A Classification by yield strength and 47 J impact energy

The classification is divided into five mandatory parts and an optional sixth part:

- 1) the first part gives a symbol indicating the process to be identified;
- 2) the second part gives a symbol indicating the strength and elongation of all-weld metal for multi-run technique or the strength of the parent material used in classification for the two-run technique (see Table 1A or 2A);

3B Classification by tensile strength and 27 J impact energy

The classification is divided into five mandatory parts and an optional sixth part:

- 1) the first part gives a symbol indicating the process to be identified;
- 2) the second part gives a symbol indicating the strength and elongation of all-weld metal in either the as-welded or post-weld heat-treated condition for a multi-run technique or the specified minimum tensile strength of the parent material or the weld metal used in classification for the two-run technique (see Table 1B or 2B);

- 3) the third part gives a symbol indicating the impact properties of all-weld metal or welded joint (see Table 3);
 - 4) the fourth part gives a symbol indicating the type of flux used in accordance with ISO 14174 (see 4.4);
 - 5) the fifth part gives a symbol indicating the chemical composition of the solid wire electrode used (see Table 4A) or the chemical composition of the all-weld metal obtained with a tubular cored electrode/flux combination (see Table 5A);
 - 6) the sixth part gives an optional symbol indicating the diffusible hydrogen content of the weld metal obtained in accordance with ISO 3690 (see Table 6).
- 3) the third part gives a symbol indicating the impact properties of all-weld metal or welded joint in the same condition as specified for the tensile strength (see Table 3). The letter "U" after this designator indicates that the deposit meets an average optional requirement of 47 J at the designated Charpy test temperature;
 - 4) the fourth part gives a symbol indicating the type of flux used in accordance with ISO 14174 (see 4.4);
 - 5) the fifth part gives a symbol indicating the chemical composition of the solid wire electrode used (see Table 4B) or the chemical composition of the all-weld metal obtained with a tubular cored electrode/flux combination (see Table 5B);
 - 6) the sixth part gives an optional symbol indicating the diffusible hydrogen content of the weld metal obtained in accordance with ISO 3690 (see Table 6).

4 Symbols and requirements

4.1 Symbol for the process

The symbol for an electrode/flux combination used in the submerged arc welding process shall be the letter S at the beginning of the designation.

4.2 Symbol for tensile properties

4.2.1 Multi-run technique

4.2.1A Classification by yield strength and 47 J impact energy

For products suitable for multi-run welding, the symbols in Table 1A indicate yield strength, tensile strength and elongation of the all-weld metal in the as-welded condition determined in accordance with 5.1A.

4.2.1B Classification by tensile strength and 27 J impact energy

For products suitable for multi-run welding, the symbols in Table 1B indicate yield strength, tensile strength and elongation of the all-weld metal in the as-welded condition or in the post-weld heat-treated condition determined in accordance with 5.1B.

Table 1A — Symbols for tensile properties by multi-run technique
(Classification by yield strength and 47 J impact energy)

Symbol	Minimum yield strength ^a MPa	Tensile strength MPa	Minimum elongation ^b %
35	355	440 to 570	22
38	380	470 to 600	20
42	420	500 to 640	20
46	460	530 to 680	20
50	500	560 to 720	18

^a For yield strength the lower yield strength, R_{eL} , is used when yielding occurs, otherwise the 0,2 % proof strength, $R_{p0,2}$, is used.

^b Gauge length is equal to five times the test specimen diameter.

Table 1B — Symbols for tensile properties by multi-run technique
(Classification by tensile strength and 27 J impact energy)

Symbol ^a	Minimum yield strength ^b MPa	Tensile strength MPa	Minimum elongation ^c %
43X	330	430 to 600	20
49X	390	490 to 670	18
55X	460	550 to 740	17
57X	490	570 to 770	17

^a X is "A" or "P", where "A" indicates testing in the as-welded condition and "P" indicates testing in the post-weld heat-treated condition.

^b For yield strength, the 0,2 % proof strength, $R_{p0,2}$, is used.

^c Gauge length is equal to five times the test specimen diameter.

4.2.2 Two-run technique

For products suitable for two-run welding, the symbols in Table 2A or 2B indicate the minimum tensile strength of the welded joint in relation to the specified minimum strength of the parent material used in two-run welding tests satisfactorily completed in accordance with 5.2.

Table 2A — Symbols for tensile properties by two-run technique
(Classification by yield strength and 47 J impact energy)

Symbol	Minimum parent material yield strength MPa	Minimum tensile strength of the welded joint MPa
2T	275	370
3T	355	470
4T	420	520
5T	500	600

Table 2B — Symbols for tensile properties by two-run technique
(Classification by tensile strength and 27 J impact energy)

Symbol	Minimum tensile strength of the parent material and of the welded joint MPa
43S	430
49S	490
55S	550
57S	570

4.3 Symbol for the impact properties of all-weld metal or two-run welded joint

The symbols in Table 3 indicate the temperature at which an impact energy of 47 J or 27 J is achieved under the conditions given in Clause 5.

4.3A Classification by yield strength and 47 J impact energy

Three test specimens shall be tested. Only one individual value may be lower than 47 J but not lower than 32 J.

4.3B Classification by tensile strength and 27 J impact energy

Five test specimens shall be tested. The lowest and highest values obtained shall be disregarded. Two of the three remaining values shall be greater than the specified 27 J level, one of the three may be lower, but shall not be less than 20 J. The average of the three remaining values shall be at least 27 J.

The addition of the optional symbol U, immediately after the symbol for condition of heat treatment, indicates that the supplemental requirement of 47 J impact energy at the normal 27 J impact test temperature has also been satisfied. For the 47 J impact requirement, the number of specimens tested and values obtained shall meet the requirement of 4.3A.

When an all-weld metal or a welded joint has been classified for a certain temperature, it automatically covers any higher temperature in Table 3.

Table 3 — Symbols for impact properties of all-weld metal or welded joint

Symbol	Temperature for minimum average impact energy of 47 J ^a or 27 J ^b
	°C
Z	No requirements
A ^a or Y ^b	+20
0	0
2	-20
3	-30
4	-40
5	-50
6	-60
7	-70
8	-80
9	-90
10	-100
^a	See 4.3A.
^b	See 4.3B.

4.4 Symbol for type of welding flux

The symbol for welding flux type shall be in accordance with ISO 14174.

4.5 Symbol for the chemical composition

4.5.1 Solid wire electrodes

The symbols in Tables 4A and 4B indicate the chemical composition of the solid wire electrode and include an indication of characteristic alloying elements.

The symbol for a wire electrode used in the submerged arc welding process shall be the letters S or SU at the beginning of the wire electrode designation.

NOTE The chemical composition of the weld metal is dependent on the chemical composition of the wire electrode and the metallurgical behaviour of the flux (see ISO 14174).

4.5.2 Tubular cored electrode/flux combinations

The symbols in Tables 5A and 5B indicate the chemical composition of the all-weld metal obtained with a tubular cored electrode/flux combination and include an indication of characteristic alloying elements.

The symbol for all-weld metal obtained with a tubular cored electrode used in the submerged arc welding process shall be the letters T or TU at the beginning of the wire electrode designation.

In cases of dispute, the sample for all-weld metal deposit shall be in accordance with ISO 6847.

STANDARDSISO.COM : Click to view the full PDF of ISO 14171:2010

Table 4A — Chemical composition of solid wire electrodes for submerged arc welding
(Classification by yield strength and 47 J impact energy)

Symbol	Chemical composition, % (by mass) ^{abc}										
	C	Si	Mn	P	S	Mo	Ni	Cr	Cu		
S1	0,05 to 0,15	0,15	0,35 to 0,60	0,025	0,025	0,15	0,15	0,15	0,30		
S2	0,07 to 0,15	0,15	0,80 to 1,30	0,025	0,025	0,15	0,15	0,15	0,30		
S3	0,07 to 0,15	0,15	1,30 to 1,75	0,025	0,025	0,15	0,15	0,15	0,30		
S4	0,07 to 0,15	0,15	1,75 to 2,25	0,025	0,025	0,15	0,15	0,15	0,30		
S1Si	0,07 to 0,15	0,15 to 0,40	0,35 to 0,60	0,025	0,025	0,15	0,15	0,15	0,30		
S2Si	0,07 to 0,15	0,15 to 0,40	0,80 to 1,30	0,025	0,025	0,15	0,15	0,15	0,30		
S2Si2	0,07 to 0,15	0,40 to 0,60	0,80 to 1,30	0,025	0,025	0,15	0,15	0,15	0,30		
S3Si	0,07 to 0,15	0,15 to 0,40	1,30 to 1,85	0,025	0,025	0,15	0,15	0,15	0,30		
S4Si	0,07 to 0,15	0,15 to 0,40	1,85 to 2,25	0,025	0,025	0,15	0,15	0,15	0,30		
S1Mo	0,05 to 0,15	0,05 to 0,25	0,35 to 0,60	0,025	0,025	0,45 to 0,65	0,15	0,15	0,30		
S2Mo	0,07 to 0,15	0,05 to 0,25	0,80 to 1,30	0,025	0,025	0,45 to 0,65	0,15	0,15	0,30		
S2MoTiB ^d	0,05 to 0,15	0,15 to 0,35	1,00 to 1,35	0,025	0,025	0,40 to 0,65	—	—	0,30		
S3Mo	0,07 to 0,15	0,05 to 0,25	1,30 to 1,75	0,025	0,025	0,45 to 0,65	0,15	0,15	0,30		
S4Mo	0,07 to 0,15	0,05 to 0,25	1,75 to 2,25	0,025	0,025	0,45 to 0,65	0,15	0,15	0,30		
S2Ni1	0,07 to 0,15	0,05 to 0,25	0,80 to 1,30	0,020	0,020	0,15	0,80 to 1,20	0,15	0,30		
S2Ni1,5	0,07 to 0,15	0,05 to 0,25	0,80 to 1,30	0,020	0,020	0,15	1,20 to 1,80	0,15	0,30		
S2Ni2	0,07 to 0,15	0,05 to 0,25	0,80 to 1,30	0,020	0,020	0,15	1,80 to 2,40	0,15	0,30		
S2Ni3	0,07 to 0,15	0,05 to 0,25	0,80 to 1,30	0,020	0,020	0,15	2,80 to 3,70	0,15	0,30		
S2Ni1Mo	0,07 to 0,15	0,05 to 0,25	0,80 to 1,30	0,020	0,020	0,45 to 0,65	0,80 to 1,20	0,20	0,30		
S3Ni1,5	0,07 to 0,15	0,05 to 0,25	1,30 to 1,70	0,020	0,020	0,15	1,20 to 1,80	0,20	0,30		
S3Ni1Mo	0,07 to 0,15	0,05 to 0,25	1,30 to 1,80	0,020	0,020	0,45 to 0,65	0,80 to 1,20	0,20	0,30		
S3Ni1Mo0,2	0,07 to 0,15	0,10 to 0,35	1,20 to 1,60	0,015	0,015	0,15 to 0,30	0,80 to 1,2	0,15	0,30		
S3Ni1,5Mo	0,07 to 0,15	0,05 to 0,25	1,20 to 1,80	0,020	0,020	0,30 to 0,50	1,20 to 1,80	0,20	0,30		

Table 4A (continued)

Symbol	Chemical composition, % (by mass) ^{abc}									
	C	Si	Mn	P	S	Mo	Ni	Cr	Cu	
S2Ni1Cu	0,08 to 0,12	0,15 to 0,35	0,70 to 1,20	0,020	0,020	0,15	0,65 to 0,90	0,40	0,40 to 0,65	
S3Ni1Cu	0,05 to 0,15	0,15 to 0,40	1,20 to 1,70	0,025	0,025	0,15	0,60 to 1,20	0,15	0,30 to 0,60	
SZ ^c	Any other agreed composition									

a Finished product chemical composition, Cu inclusive of a copper coating, ≤0,30 % (by mass), Al ≤0,030 % (by mass).

b Single values are maxima.

c Consumables for which the chemical composition is not listed shall be symbolized similarly and prefixed by the letters SZ. The chemical composition ranges are not specified and it is possible that two electrodes with the same Z classification are not interchangeable.

d Ti: 0,10 % (by mass) to 0,20 % (by mass), B: 0,005 % (by mass) to 0,020 % (by mass).

STANDARDS1.COM : Click to view the full PDF of ISO 14171:2010

Table 4B — Chemical composition of solid wire electrodes for submerged arc welding
(Classification by tensile strength and 27 J impact energy)

Symbol	Chemical composition, % (by mass) ^{abc}										
	C	Si	Mn	P	S	Mo	Ni	Cr	Cu		
SU11	0,15	0,15	0,20 to 0,90	0,025	0,025	0,15	0,15	0,15	0,40		
SU12	0,15	0,10 to 0,60	0,20 to 0,90	0,025	0,025	0,15	0,15	0,15	0,40		
SU21	0,05 to 0,15	0,10 to 0,35	0,80 to 1,25	0,025	0,025	0,15	0,15	0,15	0,40		
SU22	0,15	0,15	0,80 to 1,40	0,025	0,025	0,15	0,15	0,15	0,40		
SU23	0,18	0,15 to 0,60	0,80 to 1,40	0,025	0,025	0,15	0,15	0,15	0,40		
SU24 ^d	0,06 to 0,19	0,35 to 0,75	0,90 to 1,40	0,025	0,025	0,15	0,15	0,15	0,40		
SU25	0,06 to 0,16	0,35 to 0,75	0,90 to 1,40	0,030	0,030	0,15	0,15	0,15	0,40		
SU31	0,06 to 0,15	0,80 to 1,15	1,40 to 1,85	0,030	0,030	0,15	0,15	0,15	0,40		
SU32	0,15	0,05 to 0,60	1,30 to 1,90	0,025	0,025	0,15	0,15	0,15	0,40		
SU33	0,15	0,15	1,30 to 1,90	0,025	0,025	0,15	0,15	0,15	0,40		
SU41	0,20	0,15	1,60 to 2,30	0,025	0,025	0,15	0,15	0,15	0,40		
SU42	0,15	0,15 to 0,65	1,50 to 2,30	0,025	0,025	0,15	0,15	0,15	0,40		
SU51	0,15	0,15	2,20 to 2,80	0,025	0,025	0,15	0,15	0,15	0,40		
SU1M3	0,15	0,25	0,20 to 1,00	0,025	0,025	0,40 to 0,65	0,15	0,15	0,40		
SU1M3TiB ^e	0,05 to 0,15	0,20	0,65 to 1,00	0,025	0,025	0,45 to 0,65	0,15	0,15	0,35		
SU2M1	0,15	0,25	0,80 to 1,40	0,025	0,025	0,15 to 0,40	0,15	0,15	0,40		
SU3M1	0,15	0,25	1,30 to 1,90	0,025	0,025	0,15 to 0,40	0,15	0,15	0,40		
SU2M3	0,17	0,25	0,80 to 1,40	0,025	0,025	0,40 to 0,65	0,15	0,15	0,40		
SU2M3TiB ^e	0,05 to 0,17	0,20	0,95 to 1,35	0,025	0,025	0,40 to 0,65	0,15	0,15	0,35		
SU3M3	0,17	0,25	1,20 to 1,90	0,025	0,025	0,40 to 0,65	0,15	0,15	0,40		
SU4M1	0,15	0,25	1,60 to 2,30	0,025	0,025	0,15 to 0,40	0,15	0,15	0,40		
SU4M3	0,17	0,25	1,60 to 2,30	0,025	0,025	0,40 to 0,65	0,15	0,15	0,40		
SU4M31	0,05 to 0,15	0,50 to 0,80	1,60 to 2,10	0,025	0,025	0,40 to 0,60	0,15	0,15	0,40		

Table 4B (continued)

Symbol	Chemical composition, % (by mass) ^{abc}										
	C	Si	Mn	P	S	Mo	Ni	Cr	Cu		
SU5M3	0,15	0,25	2,20 to 2,80	0,025	0,025	0,40 to 0,65	0,15	0,15			
SUN2	0,15	0,30	0,75 to 1,40	0,020	0,020	0,15	0,75 to 1,25	0,20			
SUN21	0,12	0,40 to 0,80	0,80 to 1,40	0,020	0,020	0,15	0,75 to 1,25	0,20			
SUN3	0,15	0,25	0,80 to 1,40	0,020	0,020	0,15	1,20 to 1,80	0,20			
SUN31	0,15	0,25	1,30 to 1,90	0,020	0,020	0,15	1,20 to 1,80	0,20			
SUN5	0,15	0,30	0,75 to 1,40	0,020	0,020	0,15	1,80 to 2,90	0,20			
SUN7	0,15	0,30	0,60 to 1,40	0,020	0,020	0,15	2,40 to 3,80	0,20			
SUCC	0,15	0,30	0,80 to 1,90	0,030	0,030	0,15	0,15	0,30 to 0,60			
SUNCC1	0,12	0,20 to 0,35	0,35 to 0,65	0,025	0,030	0,15	0,40 to 0,80	0,50 to 0,80			
SUNCC3	0,15	0,30	0,80 to 1,90	0,030	0,030	0,15	0,05 to 0,80	0,50 to 0,80			
SUN1M3	0,10 to 0,18	0,20	1,70 to 2,40	0,025	0,025	0,40 to 0,65	0,40 to 0,80	0,20			
SUN2M1	0,12	0,05 to 0,30	1,20 to 1,60	0,020	0,020	0,10 to 0,30	0,75 to 1,25	0,20			
SUN2M3	0,15	0,25	0,80 to 1,40	0,020	0,020	0,40 to 0,65	0,80 to 1,20	0,20			
SUN2M31	0,15	0,25	1,30 to 1,90	0,020	0,020	0,40 to 0,65	0,80 to 1,20	0,20			
SUN2M32	0,15	0,25	1,60 to 2,30	0,020	0,020	0,40 to 0,65	0,80 to 1,20	0,20			
SUN3M3	0,15	0,25	0,80 to 1,40	0,020	0,020	0,40 to 0,65	1,20 to 1,80	0,20			
SUN3M31	0,15	0,25	1,30 to 1,90	0,020	0,020	0,40 to 0,65	1,20 to 1,80	0,20			
SUN4M1	0,12 to 0,19	0,10 to 0,30	0,60 to 1,00	0,015	0,030	0,10 to 0,30	1,60 to 2,10	0,20			
SUZ ^c	Any other agreed composition ^d										

a The electrode shall be analysed for the specific elements for which values are shown in this table. If the presence of other elements is indicated, in the course of this work, the amount of those elements shall be determined to ensure that their total (excluding iron) does not exceed 0,50 % (by mass).

b Single values are maxima.

c Consumables for which the chemical composition is not listed shall be symbolized similarly and prefixed by the letters SUZ. The chemical composition ranges are not specified and it is possible that two electrodes with the same Z classification are not interchangeable.

d Ti: 0,03 % (by mass) to 0,17 % (by mass).

e Ti: 0,05 % (by mass) to 0,30 % (by mass) and B: 0,005 % (by mass) to 0,030 % (by mass).

Table 5A — All-weld metal classification symbols for tubular cored electrode/flux combinations
(Classification by yield strength and 47 J impact energy)

Symbol	Chemical composition, % (by mass) ^{abc}					
	Mn	Ni	Mo	Cu		
T2	1,4	—	—	—	0,3	
T3	1,4 to 2,0	—	—	—	0,3	
T2Mo	1,4	—	0,3 to 0,6	—	0,3	
T3Mo	1,4 to 2,0	—	0,3 to 0,6	—	0,3	
T2Ni1	1,4	0,6 to 1,2	—	—	0,3	
T2Ni1,5	1,6	1,2 to 1,8	—	—	0,3	
T2Ni2	1,4	1,8 to 2,6	—	—	0,3	
T2Ni3	1,4	2,6 to 3,8	—	—	0,3	
T3Ni1	1,4 to 2,0	0,6 to 1,2	—	—	0,3	
T2Ni1Mo	1,4	0,6 to 1,2	0,3 to 0,6	—	0,3	
T2Ni1Cu	1,4	0,8 to 1,2	—	—	0,3 to 0,6	
TZ ^c	Any other agreed composition					

a If not specified Mo: ≤ 0,2 % (by mass), Ni: ≤ 0,5 % (by mass), Cr: ≤ 0,2 % (by mass), V: ≤ 0,08 % (by mass), Nb: ≤ 0,05 % (by mass), C: 0,03 % (by mass) to 0,15 % (by mass), Si: ≤ 0,8 % (by mass), S: ≤ 0,025 % (by mass), P: ≤ 0,025 % (by mass).

b Single values are maxima.

c Consumables for which the chemical composition is not listed shall be symbolized similarly and prefixed by the letters TZ. The chemical composition ranges are not specified and it is possible that two electrodes with the same Z classification are not interchangeable.

Table 5B — All-weld metal classification symbols for tubular cored electrode/flux combinations
(Classification by tensile strength and 27 J impact energy)

Symbol	Chemical composition, % (by mass) ^{abc}												
	C	Mn	Si	S	P	Cr	Ni	Mo	Cu	other			
TU3M	0,15	1,80	0,90	0,035	0,035	—	—	—	0,35	—	—	—	—
TU2M3	0,12	1,00	0,80	0,030	0,030	—	—	0,40 to 0,65	0,35	—	—	—	—
TU2M31	0,12	1,40	0,80	0,030	0,030	—	—	0,40 to 0,65	0,35	—	—	—	—
TU4M3	0,15	2,10	0,80	0,030	0,030	—	—	0,40 to 0,65	0,35	—	—	—	—
TU3M3	0,15	1,60	0,80	0,030	0,030	—	—	0,40 to 0,65	0,35	—	—	—	—
TUN2	0,12 ^c	1,60 ^d	0,80	0,025	0,030	0,15	0,75 to 1,10	0,35	0,35	—	—	Ti + V + Zr: 0,05	—
TUN5	0,12 ^c	1,60 ^d	0,80	0,025	0,030	—	2,00 to 2,90	—	0,35	—	—	—	—
TUN7	0,12	1,60	0,80	0,025	0,030	0,15	2,80 to 3,80	—	0,35	—	—	—	—
TUN4M1	0,14	1,60	0,80	0,025	0,030	—	1,40 to 2,10	0,10 to 0,35	0,35	—	—	—	—
TUN2M1	0,12	1,60	0,80	0,025	0,030	—	0,70 to 1,10	0,10 to 0,35	0,35	—	—	—	—
TUN3M2	0,12	0,70 to 1,50	0,80	0,030	0,030	0,15	0,90 to 1,70	0,55	0,35	—	—	—	—
TUN1M3	0,17	1,25 to 2,25	0,80	0,030	0,030	—	0,40 to 0,80	0,40 to 0,65	0,35	—	—	—	—
TUN2M3	0,17	1,25 to 2,25	0,80	0,030	0,030	—	0,70 to 1,10	0,40 to 0,65	0,35	—	—	—	—
TUN1C2	0,17	1,60	0,80	0,035	0,030	0,60	0,40 to 0,80	0,25	0,35	—	—	Ti + V + Zr: 0,03	—
TUN5C2M3	0,17	1,20 to 1,80	0,80	0,020	0,020	0,65	2,00 to 2,80	0,30 to 0,80	0,50	—	—	—	—
TUN4C2M3	0,14	0,80 to 1,85	0,80	0,020	0,030	0,65	1,50 to 2,25	0,60	0,40	—	—	—	—
TUN3	0,10	0,60 to 1,60	0,80	0,030	0,030	0,15	1,25 to 2,00	0,35	0,30	—	—	Ti + V + Zr: 0,03	—
TUN4M2	0,10	0,90 to 1,80	0,80	0,020	0,020	0,35	1,40 to 2,10	0,25 to 0,65	0,30	—	—	Ti + V + Zr: 0,03	—
TUN4M3	0,10	0,90 to 1,80	0,80	0,020	0,020	0,65	1,80 to 2,60	0,20 to 0,70	0,30	—	—	Ti + V + Zr: 0,03	—
TUN5M3	0,10	1,30 to 2,25	0,80	0,020	0,020	0,80	2,00 to 2,80	0,30 to 0,80	0,30	—	—	Ti + V + Zr: 0,03	—

Table 5B (continued)

Symbol	Chemical composition, % (by mass) ^{abc}											other
	C	Mn	Si	S	P	Cr	Ni	Mo	Cu			
TUN4M21	0,12	1,60 to 2,50	0,50	0,015	0,015	0,40	1,40 to 2,10	0,20 to 0,50	0,30			Ti: 0,03 V: 0,02 Zr: 0,02
TUN4M4	0,12	1,60 to 2,50	0,50	0,015	0,015	0,40	1,40 to 2,10	0,70 to 1,00	0,30			Ti: 0,03 V: 0,02 Zr: 0,02
TUNCC	0,12	0,50 to 1,60	0,80	0,030	0,035	0,45 to 0,70	0,40 to 0,80	—	0,30 to 0,75			—
TUZ ^c	Any other agreed composition											

a The weld metal shall be analysed for the specific elements for which values are shown in this table. If the presence of other elements is indicated in the course of this work, the amount of those elements shall be determined to ensure that their total (excluding iron) does not exceed 0,50 % (by mass).

b Single values are maxima.

c Consumables for which the chemical composition is not listed shall be symbolized similarly and prefixed by the letters TUZ. The chemical composition ranges are not specified and it is possible that two electrodes with the same Z classification are not interchangeable.

d Manganese in the N2 and N5 designated weld metals may be 1,80 % (by mass) maximum when the carbon is restricted to 0,10 % (by mass) maximum.

4.6 Symbol for hydrogen content of deposited metal

The symbols in Table 6 indicate the deposited metal hydrogen content determined in accordance with the method given in ISO 3690.

Table 6 — Symbol for hydrogen content of deposited metal

Symbol	Hydrogen content ml/100 g deposited metal, max.
H5	5
H10	10
H15	15

When a hydrogen symbol in accordance with Table 6 is included in the classification, the manufacturer shall state in their literature what restrictions need to be placed on the conditions of storage and redrying, and on current, arc voltage, electrode extension, and polarity to remain within the limit for that symbol.

5 Mechanical tests

5.1 Multi-run technique

5.1A Welding conditions in the classification by yield strength and 47 J impact energy

Tensile and impact tests shall be carried out on weld metal in the as-welded condition using an all-weld metal test assembly type 1.3 in accordance with ISO 15792-1:2000 using 4,0 mm or nearest commercially available diameter wire electrodes.

Welding conditions (single wire welding) and details of the test assembly shall be selected from Table 7A.

Preheating is not required; welding may start from room temperature.

The interpass temperature shall be measured using temperature indicator crayons, surface thermometers or thermocouples (see ISO 13916).

5.1B Welding conditions in the classification by tensile strength and 27 J impact energy

Tensile and impact tests shall be carried out on weld metal in the as-welded condition or in the post-weld heat-treated condition using an all-weld metal test assembly type 1.4 in accordance with ISO 15792-1:2000 using 4,0 mm or nearest commercially available diameter wire electrodes.

Welding conditions (single wire welding) and details of the test assembly shall be selected from Table 7B. Solid wire diameters not specified and all tubular cored electrodes shall be welded based on the manufacturer's recommendations.

The interpass temperature shall be measured using temperature indicator crayons, surface thermometers or thermocouples (see ISO 13916).

The interpass temperature shall not exceed the interpass temperature range indicated in Table 7B. If, after any pass, the interpass temperature range is exceeded, the test assembly shall be cooled in air to a temperature within the indicated range. If the interpass temperature is below the indicated interpass temperature range, the test assembly shall be reheated into the interpass temperature range.

The interpass temperature shall not exceed the interpass temperature range indicated in Table 7A. If, after any pass, the interpass temperature range is exceeded, the test assembly shall be cooled in air to a temperature within the indicated range. If the interpass temperature is below the indicated interpass temperature range, the test assembly shall be reheated into the interpass temperature range.

Test assemblies made with electrodes classified in the post-weld heat-treated condition shall be heat-treated at $620\text{ °C} \pm 15\text{ °C}$ for 60 min to 75 min. The furnace shall be at a temperature no higher than 315 °C when the test assembly is placed in it. The heating rate, from that point to the $620\text{ °C} \pm 15\text{ °C}$ holding temperature, shall not exceed 220 °C/h . When the holding time has been completed, the assembly shall be allowed to cool in the furnace to a temperature below 315 °C at a rate not exceeding 195 °C/h . The assembly may be removed from the furnace at any temperature below 315 °C and allowed to cool in still air to room temperature.

Table 7A — Welding conditions for multi-run single solid wire welding
(Classification by yield strength and 47 J impact energy)

Conditions ^a	Solid wire electrode diameter ^b		Tubular cored electrode diameter ^b	
	mm		mm	
	2,8 to 3,2	4,0	3,0 to 3,2	4,8
Type of current	d.c. ^c			
Length of weld deposit, mm	≥ 350			
Welding current, A	440 ± 20	580 ± 20	480 ± 20	550 ± 20
Welding voltage, V	27 ± 2	29 ± 2	30 ± 2	
Welding speed, mm/min	400 ± 50	550 ± 50	450 ± 50	
Interpass temperature range, °C (no preheat)	150 ± 25			
Electrode extension, mm	30 ± 5			
^a	A.c. or d.c., either polarity, may be used. The reference method shall be as recommended by the manufacturer.			
^b	Diameters not specified are to be welded following the recommendations of the electrode manufacturer.			
^c	Direct current welding polarity shall follow the recommendation of the manufacturer.			

Table 7B — Welding conditions for multi-run single solid wire welding
(Classification by tensile strength and 27 J impact energy)

Conditions ^a	Wire electrode diameter mm					
	3,2	4	4,8	3,2	4	4,8
Type of current	d.c.e.p.			a.c.		
Length of weld deposit, mm	≥200			≥200		
Welding current, A	450 ± 50	500 ± 50	600 ± 50	450 ± 50	500 ± 50	600 ± 50
Welding voltage, V	28 ± 2	30 ± 2	32 ± 2	30 ± 2	32 ± 2	34 ± 2
Welding speed, mm/min	350 ± 20	400 ± 20	450 ± 20	350 ± 20	400 ± 20	450 ± 20
Preheat temperature, °C	b	Room temperature			Room temperature	
	c	≥100			≥100	
Interpass temperature range, °C	150 ± 15			150 ± 15		
Electrode extension, mm	30 ± 5			30 ± 5		
^a A.c. or d.c., either polarity (e.p.), may be used. The reference method shall be as recommended by the manufacturer. ^b For SU0, SU11, SU12, SU21, SU22, SU23, SU24, SU25, SU31, SU32, SU33, SU41, SU42, SU51. ^c For symbols other than those in footnote b.						

5.2 Two-run technique

Tensile and impact tests and any required retests shall be carried out on weld metal in the as-welded condition using a test assembly type 2.5 in accordance with ISO 15792-2:2000 using a 4,0 mm solid or tubular cored electrode or the nearest commercially available diameter. Welding conditions shall be within the range recommended by the manufacturer and shall be recorded to demonstrate compliance with this International Standard.

For an electrode/flux combination of a given specified minimum tensile strength, the specified minimum tensile strength of the parent material used for the classification test shall not exceed the specified minimum tensile strength of the tubular cored electrode/flux combination by more than 50 MPa.

6 Chemical analysis

Chemical analysis shall be performed on specimens of the solid wire electrode and all-weld metal deposits from tubular electrodes.

For solid wire electrodes where the chemical composition does not change during production, the analysis of the product being processed, or the raw material itself, or a report of the ladle analysis of the raw material can be substituted.

For tubular cored electrode/flux combinations, chemical analysis is performed on any suitable all-weld metal test specimen. The reference method is described in ISO 6847.

Any analytical technique can be used, but in cases of dispute, reference shall be made to established published methods.