
**Plastics — Polyketone (PK) moulding and
extrusion materials —**

**Part 2:
Preparation of test specimens and
determination of properties**

Plastiques — Polycétone (PK) pour moulage et extrusion —

Partie 2: Préparation des éprouvettes et détermination des propriétés

STANDARDSISO.COM : Click to view the full PDF of ISO 15526-2:2000



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 15526-2:2000

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 734 10 79
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 15526 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 15526-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

ISO 15526 consists of the following parts, under the general title *Plastics — Polyketone (PK) moulding and extrusion materials*:

- *Part 1: Designation system and basis for specifications*
- *Part 2: Preparation of test specimens and determination of properties*

STANDARDSISO.COM : Click to view the full PDF of ISO 15526-2:2000

Plastics — Polyketone (PK) moulding and extrusion materials —

Part 2:

Preparation of test specimens and determination of properties

1 Scope

This part of ISO 15526 specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of polyketone moulding and extrusion materials. Requirements for handling test material and for conditioning both the test material before moulding and the specimens before testing are given here.

Procedures and conditions for the preparation of test specimens and procedures for measuring properties of the materials from which these specimens are made are given. Properties and test methods which are suitable and necessary to characterize polyketone moulding and extrusion materials are listed.

The properties have been selected from the general test methods in, ISO 10350:1993. Other test methods in wide use for or of particular significance to these moulding and extrusion materials are also included in this part of ISO 15526, as are the designatory properties specified in part 1.

In order to obtain reproducible and comparable test results, it is necessary to use the methods of preparation and conditioning, the specimen dimensions and the test procedures specified herein. Values determined will not necessarily be identical to those obtained using specimens of different dimensions or prepared using different procedures.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 15526. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 15526 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 62:1999, *Plastics — Determination of water absorption.*

ISO 75-1:1993, *Plastics — Determination of temperature of deflection under load — Part 1: General test method.*

ISO 75-2:1993, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite.*

ISO 178:1993, *Plastics — Determination of flexural properties.*

ISO 179-1:—¹⁾, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test.*

ISO 291:1997, *Plastics — Standard atmospheres for conditioning and testing.*

ISO 294-1:1996, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens.*

ISO 527-1:1993, *Plastics — Determination of tensile properties — Part 1: General principles.*

1) To be published. (Revision of ISO 179:1993)

ISO 527-2:1993, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics.*

ISO 1133:1997, *Plastics — Determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastics.*

ISO 1183:1987, *Plastics — Methods for determining the density and relative density of non-cellular plastics.*

ISO 2818:1994, *Plastics — Preparation of test specimens by machining.*

ISO 3146:2000, *Plastics — Determination of melting behaviour (melting temperature or melting range) of semi-crystalline polymers by capillary tube and polarizing-microscope methods.*

ISO 3167:1993, *Plastics — Multipurpose test specimens.*

ISO 3451-4:1998, *Plastics — Determination of ash — Part 4: Polyamides.*

ISO 4589-2:1996, *Plastics — Determination of burning behaviour by oxygen index — Part 2: Ambient-temperature test.*

ISO 6603-2:—²⁾, *Plastics — Determination of puncture impact behaviour of rigid plastics — Part 2: Instrumented impact testing.*

ISO 10350:1993³⁾, *Plastics — Acquisition and presentation of comparable single-point data.*

ISO 11359-2:1999, *Plastics — Thermomechanical analysis (TMA) — Part 2: Determination of coefficient of linear thermal expansion and glass transition temperature.*

ISO 15512:1999, *Plastics — Determination of water content.*

ISO 15526-1:2000, *Plastics — Polyketone (PK) moulding and extrusion materials — Part 1: Designation system and basis for specifications.*

IEC 60093:1980, *Methods of test for volume resistivity and surface resistivity of solid electrical insulating materials.*

IEC 60112:1979, *Method for determining the comparative and the proof tracking indices of solid insulating materials under moist conditions.*

IEC 60243-1:1998, *Electrical strength of insulating materials — Test methods — Part 1: Tests at power frequencies.*

IEC 60250:1969, *Recommended methods for the determination of the permittivity and dielectric dissipation factor of electrical insulating materials at power, audio and radio frequencies including metre wavelengths.*

IEC 60296:1982, *Specification for unused mineral insulating oils for transformers and switchgear.*

IEC 60695-11-10:1999, *Fire hazard testing — Part 11-10: Test flames — 50 W horizontal and vertical flame test methods.*

IEC 61006:1991, *Methods of test for the determination of the glass transition temperature of electrical insulating materials.*

2) To be published. (Revision of ISO 6603-2:1989)

3) ISO 10350:1993 is the normative reference, even though it has been replaced by ISO 10350-1:1998.

3 Preparation of test specimens

3.1 General

It is essential that specimens are always prepared by the same procedure (injection moulding), using the same processing conditions.

3.2 Treatment of the material before moulding

Before processing, the moisture content of the material sample shall not exceed 0,2 % by mass. If the moisture level exceeds this limit, the sample shall be dried in accordance with the manufacturer's instructions until the moisture content is below the limit.

3.3 Injection moulding

Specimens shall be prepared in accordance with ISO 294-1 using the conditions specified in Table 1.

Table 1 — Injection-moulding conditions

Designation code for composition ^a	Material		Moulding conditions					
	Designation code for melting temperature ^a	Filler content	Melt temperature	Mould temperature	Average injection velocity	Hold pressure	Hold pressure time	Total cycle time
		%	°C	°C	mm/s	MPa	s	s
PK-EP	210	0 to 50	235	80	200 ± 100	70 ± 10	15 ± 5	≤ 35
	220		245					
	230		255					
	240		265					
	250		275					
PK-E	260		275					

^a See ISO 15526-1.

4 Conditioning of test specimens

After moulding, test specimens shall be conditioned in accordance with ISO 291 for between 48 h and 96 h at 23 °C ± 2 °C and (50 ± 5) % relative humidity.

5 Determination of properties

In the determination of properties and the presentation of data, the standards, supplementary instructions and notes given in ISO 10350:1993 shall be applied. All tests shall be carried out in the standard atmosphere of 23 °C ± 2 °C and (50 ± 5) % relative humidity unless specifically stated otherwise in the tables which follow.

Table 2 is compiled from ISO 10350:1993, and the properties listed are those which are appropriate to polyketone moulding and extrusion materials. These properties are those considered useful for comparisons of data generated for different thermoplastics.

Table 3 contains those properties, not found specifically in Table 2, which are in wide use or of particular significance in the practical characterization of polyketone moulding and extrusion materials.

Table 2 — General properties and test conditions (selected from ISO 10350)

Property	Unit	Standard	Specimen type (dimensions in mm)	Test conditions and supplementary instructions	
Rheological properties					
Melt mass-flow rate	g/10 min	ISO 1133	Moulding compound	Use one of the test temperatures and loads given in Table 4 of ISO 15526-1 ^a	
Melt volume-flow rate	cm ³ /10 min				
Mechanical properties					
Tensile modulus	MPa	ISO 527-1 ISO 527-2	See ISO 3167	Test speed 1 mm/min	
Yield stress	MPa			Test speed 50 mm/min	
Yield strain	%				
Nominal strain at break	%				
Stress at 50 % strain	MPa				
Stress at break	MPa				Test speed 5 mm/min. Only to be quoted if stress at 50 % strain cannot be obtained at 50 mm/min
Strain at break	%				
Flexural modulus	MPa	ISO 178	80 × 10 × 4	Test speed 2 mm/min	
Flexural strength	MPa				
Charpy impact strength	kJ/m ²	ISO 179-1	80 × 10 × 4	Method 1eU (edgewise impact)	
Charpy notched impact strength	kJ/m ²		80 × 10 × 4 V-notch, r = 0,25	Method 1eA (edgewise impact)	
Thermal properties					
Melting temperature	°C	ISO 3146	Moulding compound	Method C (DSC or DTA). Use 10 °C/min.	
Glass transition temperature	°C	IEC 61006	Moulding compound	Method A (DSC or DTA). Use 10 °C/min.	
Temperature of deflection under load	°C	ISO 75-1 ISO 75-2	80 × 10 × 4 flatwise	0,45 MPa and 1,8 MPa	
Flammability	mm/min	IEC 60695-11-10	125 × 13 × 3	Method A — linear burning rate of horizontal specimens	
	s			Method B (vertical) a) afterflame time b) afterglow time	
Electrical properties					
Relative permittivity	—	IEC 60250	≥ 80 × ≥ 80 × 1	Frequency 100Hz and 1 MHz (compensate for electrode edge effect)	
Dissipation factor	—				
Volume resistivity	Ω · m	IEC 60093		Voltage 100 V	
Surface resistivity	Ω				
Electric strength	kV/mm	IEC 60243-1	≥ 80 × ≥ 80 × 4	Use 25 mm/75 mm coaxial-cylinder electrode configuration. Immerse in IEC 60296 transformer oil. Use short time (rapid rise) test.	
Comparative tracking index	—	IEC 60112	≥ 15 × ≥ 15 × 4	Use solution A	
Other properties					
Water absorption	%	ISO 62	Thickness ≤ 1	Saturation value in water at 23 °C	
				Saturation value at 23 °C and 50 % relative humidity	
Density	kg/m ³	ISO 1183	10 × 10 × 4	Use part of centre of multipurpose specimen	

^a The melt density of unfilled grades is about 1 000 kg/min³ to 1 100 kg/m³ (depending on composition and temperature).