

INTERNATIONAL STANDARD

ISO 1567

Third edition
1999-02-15

AMENDMENT 1
2003-09-01

Dentistry — Denture base polymers

AMENDMENT 1

Art dentaire — Polymères pour base de prothèses dentaires

AMENDEMENT 1

STANDARDSISO.COM : Click to view the full PDF of ISO 1567:1999/Amd 1:2003



Reference number
ISO 1567:1999/Amd.1:2003(E)

© ISO 2003

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 1567:1999/Amd 1:2003

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 1567:1999 was prepared by Technical Committee ISO/TC 106, *Dentistry*, Subcommittee SC 2, *Prosthetic materials*.

Dentistry — Denture base polymers

AMENDMENT 1

Page 1, Scope

Add to paragraph 1.1

Furthermore, it applies to denture base polymers for which the manufacturer claims that the material is a high impact polymer. It also specifies the requirement and the test method to be used.

Page 1, Normative references

Add the following reference:

ISO 179:1993, *Plastics — Determination of Charpy impact strength*

Page 4, subclause 5.1.3

First line, delete Type 1 class 2 and Type 2 class 2.

Page 5, subclause 5.2.10

Last paragraph, last line after 0,2 % add "mass fraction".

After subclause 5.2.12 add the following subclause:

5.2.13 Impact strength

When the manufacturer claims that the material is a high impact polymer, the impact strength shall not be less than 2,0 kJ/m² when tested in accordance with 8.9.

Page 14, subclause 8.5.3.5.2.5

Before 5.2.7 and 5.2.8 add "requirements of".

Page 16, subclause 8.7.3.3.2

Replace 8.7.3.1.1.1 with 8.7.3.1.1.

Page 22, subclause 8.8.5.4

Second paragraph replace two with three to read: "If at least three of the".

After subclause 8.8.5.5 add the following subclause:

8.9 Impact strength

8.9.1 Materials

This consists of two specimen plates, freshly formed and processed in accordance with the manufacturer's instructions, each from a separate mix. Use the material, the apparatus (8.5.1.1) and the mould (8.5.1.1.2) (except that the dimensions of the plates shall be (50 ± 2) mm long, (50 ± 2) mm wide and $(4 \pm 0,2)$ mm in height).

8.9.2 Apparatus

8.9.2.1 See 8.5.3.2.1, 8.5.3.2.2 and 8.5.3.2.4.

8.9.2.2 **Standard metallographic grinding papers**, progressively finer grades using a grain size of approximately $26 \mu\text{m}$ (600 FEPA) for the final finishing stage.


8.9.2.3 **Containers of water**, for storing the specimen strips at $(23 \pm 2)^\circ\text{C}$ and $(37 \pm 1)^\circ\text{C}$ for pre-test conditioning.

8.9.2.4 **Pendulum impact testing machine**, conforming to ISO 179:1993. A test capacity of 0,5 J is suitable.

8.9.3 Procedure

Within (24 ± 2) h of the beginning of the curing cycle of the denture base polymer, cut each plate lengthways into seven to eight equal strips, (50 ± 2) mm long (l), $(6 \pm 0,2)$ mm wide (w) and $(4 \pm 0,2)$ mm in height (h). Machine the strips in a milling machine (8.5.3.2.2) on the edges and equally from both moulded surfaces so that the dimensions remain slightly oversized. Take care to avoid overheating the specimen strips. Wet-grind all faces and edges smooth and flat with metallographic grinding papers (8.9.2.2).


Cut a notch (type A) (see Figure 4) in the middle of each specimen strip as described in ISO 179:1993. Cut the notch edgewise to a depth of $(1,2 \pm 0,1)$ mm leaving a residual depth beneath the notch of $(4,8 \pm 0,1)$ mm. The radius of the notch base (tip) shall be $(0,25 \pm 0,05)$ mm (see Figure 5).



a Direction of blow.

b See Figure 5.

Figure 4 — Charpy edgewise impact test, with single-notched specimen



Radius of notch base $r_n = (0,25 \pm 0,05)$ mm.

Figure 5 — Part of single-notched specimen strip with type A notch

Measure and record, the height, h , [nominal $(4 \pm 0,2)$ mm] of each specimen strip near the notch and the residual depth, b , [nominal $(4,8 \pm 0,1)$ mm] beneath the notch using a measuring instrument (8.2.1.5 or 8.5.3.2.4). Use only specimen strips which are of good quality and fall within the correct size range.

Store 12 selected specimen strips in the container of water at (37 ± 1) °C for $7 d \pm 2 h$. Condition the specimen strips in the container of water at (23 ± 2) °C for (60 ± 15) min prior to testing. After conditioning, remove a specimen strip from the water and place it on the specimen supports of the testing apparatus (8.9.2.4). Set the specimen supports at a separation of $(40,0 \pm 0,2)$ mm. Place the specimen strip with the notch facing away from the point of impact of the pendulum. Ensure that the specimen strip is centred with regard to the position of the notch and the point of impact of the pendulum. As soon as possible after removing each separate specimen strip from the water bath, release the pendulum in order to fracture the specimen. Record the value of energy absorbed, J_1 .

Re-zero the instrument and allow the pendulum to swing again with no specimen strip in place. (The energy recorded, J_2 , gives an indication of the friction in the system.)

8.9.4 Calculation and expression of results

Calculate the impact strength of notched specimen, a , in kilojoules per square metre (kJ/m^2) using the formula:

$$\frac{(J_1 - J_2) \times 10^3}{bh}$$

where

J_1 is the value of energy, in joules, absorbed by the specimen strip;

J_2 is the friction energy, in joules, of the system;

h is the height, in millimetres, of the specimen strip;

b is the depth, in millimetres, behind the notch.

8.9.5 Pass/fail determination of impact strength

If results obtained for at least nine of the twelve specimen strips conform to the requirement stated in 5.2.13, the material fulfils the requirement of a high impact denture base polymer.

If five or fewer of the twelve specimen strips conform to the requirement stated in 5.2.13, the polymer fails.

If only six to eight of the twelve specimen strips conform to the requirement stated in 5.2.13, repeat the test.

If at least ten of the second series of specimen strips conform to the requirement stated in 5.2.13, the polymer passes.

8.9.6 Expression of results

Report the number of specimens evaluated, all results for impact strength with the number of specimens conforming to 5.2.13 and whether the material passes.

Page 22,

After subclause 9.2.1 k) add the following item:

- l) the term "high impact" if the manufacturer wishes to claim that the material is a high impact polymer. If claimed, the polymer shall conform to the requirement of 5.2.13 when tested in accordance with 8.9.

Page 23,

After subclause 9.2.2 k) add the following item:

- l) the term "high impact" if the manufacturer wishes to claim that the material is a high impact polymer. If claimed, the polymer shall conform to the requirement of 5.2.13 when tested in accordance with 8.9.

Page 24,

After subclause 9.3 m) add the following item.

- n) the term "high impact" if the manufacturer wishes to claim that the material is a high impact polymer. If claimed, the polymer shall conform to the requirement of 5.2.13 when tested in accordance with 8.9.