
**Plastics piping systems for hot and cold
water installations — Crosslinked
polyethylene (PE-X) —**

**Part 5:
Fitness for purpose of the system**

*Systèmes de canalisations en plastique pour les installations d'eau
chaude et froide — Polyéthylène réticulé (PE-X) —*

Partie 5: Aptitude à l'emploi du système



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 15875-5:2003

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 15875-5 was prepared by the European Committee for Standardization (CEN) in collaboration with Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 2, *Plastics pipes and fittings for water supplies*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

Throughout the text of this document, read “...this European Standard...” to mean “...this International Standard...”.

ISO 15875 consists of the following parts, under the general title *Plastics piping systems for hot and cold water installations — Crosslinked polyethylene (PE-X)*:

- *Part 1: General*
- *Part 2: Pipes*
- *Part 3: Fittings*
- *Part 5: Fitness for purpose of the system*
- *Part 7: Guidance for the assessment of conformity* [Technical Specification]

Contents

Foreword.....	v
Introduction	vii
1 Scope	1
2 Normative references	1
3 Terms and definitions, symbols and abbreviated terms	2
4 Fitness for purpose of the joints and the piping system.....	2
4.1 General.....	2
4.2 Internal pressure test	3
4.3 Bending test	3
4.4 Pull-out test	4
4.5 Thermal cycling test	5
4.6 Pressure cycling test.....	5
4.7 Leaktightness under vacuum	6
Bibliography	7

STANDARDSISO.COM : Click to view the full PDF of ISO 15875-5:2003

Foreword

This document (EN ISO 15875-5:2003) has been prepared by Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems", the secretariat of which is held by NEN, in collaboration with Technical Committee ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2004, and conflicting national standards shall be withdrawn at the latest by December 2005.

NOTE 1 This draft was submitted for CEN enquiry as prEN 12318-5:1996.

This standard is part of a System Standard for plastics piping systems of a particular material for a specified application. There are a number of such System Standards.

System Standards are based on the results of the work undertaken in ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids", which is a Technical Committee of the International Organization for Standardization (ISO).

They are supported by separate standards on test methods to which references are made throughout the System Standard.

The System Standards are consistent with general standards on functional requirements and recommended practices for installation.

EN ISO 15875 consists of the following Parts ¹⁾, under the general title *Plastics piping systems for hot and cold water installations — Crosslinked Polyethylene (PE-X)*

- Part 1: General
- Part 2: Pipes
- Part 3: Fittings
- Part 5: Fitness for purpose of the system (the present standard)
- Part 7: Guidance for the assessment of conformity (intended to be published as CEN ISO/TS 15875-7).

This Part of EN ISO 15874:2003 includes a Bibliography.

At the date of publication of this standard, System Standards for piping systems of other plastics materials used for the same application are the following:

EN ISO 15874, *Plastics piping systems for hot and cold water installations — Polypropylene (PP)* (ISO 15874:2003)

EN ISO 15876, *Plastics piping systems for hot and cold water installations — Polybutylene (PB)* (ISO 15876:2003)

EN ISO 15877, *Plastics piping systems for hot and cold water installations — Chlorinated poly(vinyl chloride) (PVC-C)* (ISO 15877:2003)

For pipes and fittings which have conformed to the relevant national standard before 1st November, 2003, as shown by the manufacturer or by a certification body, the national standard may continue to apply until 30th November, 2005.

1) This System Standard does not incorporate a Part 4 *Ancillary equipment* or a Part 6: *Guidance for installation*. For ancillary equipment separate standards can apply. Guidance on installation of plastics piping systems made from different materials intended to be used for hot and cold water installations is given by ENV 12108 ^[1].

ISO 15875-5:2003(E)

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

STANDARDSISO.COM : Click to view the full PDF of ISO 15875-5:2003

Introduction

The System Standard, of which this is Part 5, specifies the requirements for a piping system and its components when made from crosslinked polyethylene (PE-X). The piping system is intended to be used for hot and cold water installations.

In respect of potential adverse effects on the quality of water intended for human consumption, caused by the product covered by EN ISO 15875;

- This standard provides no information as to whether the product may be used without restriction in any of the Member States of the EU or EFTA;
- It should be noted that, while awaiting the adoption of verifiable European criteria, existing national regulations concerning the use and/or the characteristics of this product remain in force.

Requirements and test methods for components of the piping system are specified in Part 1, 2 and 3 of this System Standard. Part 7 (CEN ISO/TS 15875-7) gives guidance for the assessment of conformity.

This Part of EN ISO 15875 specifies the characteristics of fitness for purpose of the piping systems.

STANDARDSISO.COM : Click to view the full PDF of ISO 15875-5:2003

1 Scope

This Part of EN ISO 15875 specifies the characteristics of the fitness for purpose of crosslinked polyethylene (PE-X) piping systems, intended to be used for hot and cold water installations within buildings for the conveyance of water whether or not intended for human consumption (domestic systems) and for heating systems, under design pressures and temperatures according to the class of application (see Table 1 of EN ISO 15875-1:2003).

This standard covers a range of service conditions (application classes) and design pressure classes. For values of T_D , T_{max} and T_{mal} in excess of those in Table 1 of Part 1, this standard does not apply.

NOTE It is the responsibility of the purchaser or specifier to make the appropriate selections from these aspects, taking into account their particular requirements and any relevant national regulations and installation practices or codes.

It also specifies the test parameters for the test methods referred to in this standard.

In conjunction with the other parts of EN ISO 15875:2003 (see Foreword) it is applicable to PE-X pipes, fittings, their joints and to joints with components of other plastics and non-plastics materials intended to be used for hot and cold water installations.

2 Normative references

This standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to, or revisions of, any of these publications apply to this standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 712, *Thermoplastics piping systems — End-load bearing mechanical joints between pressure pipes and fittings — Test method for resistance to pull-out under constant longitudinal force*

EN 713, *Plastics piping systems — Mechanical joints between fittings and polyolefin pressure pipes — Test method for leaktightness under internal pressure of assemblies subjected to bending*

EN 921, *Plastics piping systems — Thermoplastics pipes — Determination of resistance to internal pressure at constant temperature*

EN 12293, *Plastics piping systems — Thermoplastics pipes and fittings for hot and cold water — Test method for the resistance of mounted assemblies to temperature cycling*

EN 12294, *Plastics piping systems — Systems for hot and cold water — Test method for leaktightness under vacuum*

EN 12295, *Plastics piping systems — Thermoplastics pipes and associated fittings for hot and cold water — Test method for resistance of joints to pressure cycling*

EN ISO 15875-1:2003, *Plastics piping system for hot and cold water installations — Crosslinked polyethylene (PE-X) — Part 1: General (ISO 15875-1:2003)*

EN ISO 15875-2:2003, *Plastics piping system for hot and cold water installations — Crosslinked polyethylene (PE-X) — Part 2: Pipes (ISO 15875-2:2003)*

3 Terms and definitions, symbols and abbreviated terms

For the purpose of this standard, the terms and definitions, symbols and abbreviated terms given in EN ISO 15875-1:2003 apply.

4 Fitness for purpose of the joints and the piping system

4.1 General

When tested in accordance with the applicable test methods as specified in Table 1, using the indicated parameters given in 4.2 to 4.7, as applicable, the joints and the piping system shall have characteristics conforming to the requirements given in the applicable clauses.

For the tests described the fittings shall be connected to the pipe with which they are intended to be used.

Table 1 specifies the tests applicable for each different type of jointing system covered by this standard.

Table 1 — Joint tests

Test	Jointing system ^a		Test parameters	Test method
	EF	M		
Internal pressure test	Y	Y	Shall conform to 4.2	EN 921
Bending test	N	Y	Shall conform to 4.3	EN 713
Pull-out test	N	Y	Shall conform to 4.4	EN 712
Thermal cycling test	Y	Y	Shall conform to 4.5	EN 12293
Pressure cycling test	N	Y	Shall conform to 4.6	EN 12295
Vacuum test	N	Y	Shall conform to 4.7	EN 12294
^a EF : Electrofusion joint M : Mechanical joint Y : denotes test applicable N : denotes test not applicable				

4.2 Internal pressure test

When tested in accordance with EN 921 using the test parameters given in Table 2 for the relevant classes the joint assemblies shall not leak.

The test pressure, p_J , for a given time to failure and test temperature shall be determined by the following equation:

$$p_J = p_D \times \frac{\sigma_P}{\sigma_{DP}}$$

where

- p_J is the hydrostatic test pressure, in bars, to be applied to the joint assembly during the test period;
- σ_P are the hydrostatic stress values, in megapascals, of the pipe material corresponding to time to failure/test temperature points given in Table 2;
- σ_{DP} are the design stress values, in megapascals, for the pipe material as determined for each class and listed in Table A.2 of EN ISO 15875-2:2003;
- p_D is the design pressure of 4 bar, 6 bar, 8 bar or 10 bar, as applicable.

Table 2 — Derivation of test pressure p_J

	Application class			
	Class 1	Class 2	Class 4	Class 5
Max. Design temperature, T_{max}, in °C	80	80	70	90
Design stress of pipe material, σ_{DP}, in MPa	3,85	3,54	4,00	3,24
Test temperature ^a, T_{test}, in °C	95 ^a	95 ^a	80	95
Test duration, t, in h	1000	1000	1000	1000
Hydrostatic stress of pipe material, σ_P, in MPa	4,4	4,4	5,2	4,4
Test pressure, p_J, in bars, for a design pressure, p_D , of:				
4 bar	5,8 ^b	5,8 ^b	6,9 ^b	5,8 ^b
6 bar	6,9	7,5	7,8	8,2
8 bar	9,2	10,0	10,4	10,9
10 bar	11,5	12,5	13,0	13,6
Number of test pieces	3	3	3	3
^a Generally the highest test temperature is taken to be ($T_{max} + 10$) °C with an upper limit of 95 °C. However to match existing test facilities the highest test temperature for classes 1 and 2 is also set at 95 °C. The hydrostatic stresses given correspond to the given test temperatures. ^b The 20 °C, 10 bar, 50 years, cold water requirement, being higher, determines this value (see clause 4 of EN ISO 15875-1:2003).				

In special circumstances, if joint tests according to this clause cause leaks resulting from deformations induced by differential elongation, a test pressure may be determined from the stress and creep data (relative to a design period of 50 years) for the different materials used.

4.3 Bending test

When tested in accordance with EN 713 to the applicable pressure for the 20 °C, 1 h condition given in Table 3, using a bending radius equal to the minimum radius of bending for the pipes as recommended by the system supplier, the joint assembly shall not leak.

This test is only applicable to pipes of nominal diameter greater than or equal to 32 mm.

Table 3 — Test parameters for bending test

	Application class			
	Class 1	Class 2	Class 4	Class 5
Max. design temperature, T_{max} , in °C	80	80	70	90
Design stress of pipe material, σ_{DP} , in MPa	3,85	3,54	4,00	3,24
Test temperature, T_{test} , in °C	20	20	20	20
Test duration, t , in h	1	1	1	1
Hydrostatic stress of pipe material, σ_p , in MPa	12	12	12	12
Test pressure, p_j , in bars, for a design pressure, p_D , of:				
4 bar	15,8 ^a	15,8 ^a	15,8 ^a	15,8 ^a
6 bar	18,7	20,4	18,0	22,3
8 bar	25,0	27,2	24,0	29,7
10 bar	31,2	33,9	30,0	37,1
Number of test pieces	3	3	3	3

^a The 20 °C, 10 bar, 50 years, cold water requirement, being higher, determines this value (see clause 4 of EN ISO 15875-1:2003).

4.4 Pull-out test

When tested in accordance with EN 712 using the parameters given in Table 4, the joint assemblies shall withstand the pull-out force, without being separated.

The force, F , shall be calculated from the following equation:

$$F = \frac{\pi}{4} \times d_n^2 \times p_D$$

where:

- F is the force, expressed in newtons (N);
- d_n is the nominal outside diameter of the pipe, expressed in millimetres (mm);
- p_D is the design pressure of 4, 6, 8 or 10 bar, as applicable, expressed in megapascals. In the case of the classification 'All classes' the design pressure shall be 10 bar, expressed in megapascals (MPa).

Table 4 — Test parameters for pull-out test

	All application classes	Application class			
		Class 1	Class 2	Class 4	Class 5
Max design temperature, T_{max} , in °C	—	80	80	70	90
Test temperature, in °C	23	90	90	80	95
Test period, in h	1	1	1	1	1
Pull-out force, in N	$1,5 \times F$	F	F	F	F
Number of test pieces	3	3	3	3	3