

---

---

**Instrumentation for use in association with  
non-active surgical implants — General  
requirements**

*Instrumentation à utiliser en association avec les implants chirurgicaux non  
actifs — Exigences générales*

STANDARDSISO.COM : Click to view the full PDF of ISO 16061:2000



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 16061:2000

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 734 10 79  
E-mail [copyright@iso.ch](mailto:copyright@iso.ch)  
Web [www.iso.ch](http://www.iso.ch)

Printed in Switzerland

## Contents

	Page
Foreword.....	iv
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions .....	2
4 Intended performance .....	2
5 Design attributes.....	2
6 Selection of materials.....	3
7 Design evaluation .....	3
7.1 General.....	3
7.2 Pre-clinical evaluation.....	3
7.3 Clinical evaluation .....	3
8 Manufacture.....	3
9 Sterilization.....	4
9.1 Products supplied sterile .....	4
9.2 Products provided non-sterile.....	4
10 Packaging .....	4
10.1 Protection from damage in storage and transport.....	4
10.2 Maintenance of sterility in transit.....	4
11 Information to be supplied by the manufacturer .....	4
11.1 General.....	4
11.2 Instruments with measuring function.....	4
11.3 Restrictions in combinations.....	5
11.4 Marking on instruments .....	5
11.5 Instructions for use .....	5
11.6 Instruments intended for single use.....	5
<b>Annex A (informative) Examples of typical instrument applications, together with materials found acceptable for instrument manufacture .....</b>	<b>6</b>
<b>Bibliography .....</b>	<b>18</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 16061 was prepared by Technical Committee ISO/TC 150, *Implants for surgery*.

Annex A of this International Standard is for information only.

STANDARDSISO.COM : Click to view the full PDF of ISO 16061:2000

# Instrumentation for use in association with non-active surgical implants — General requirements

## 1 Scope

This International Standard specifies general requirements for instruments to be used in association with non-active surgical implants. These requirements apply to instruments when they are manufactured and when they are resupplied after refurbishment.

This International Standard applies to instruments which may be connected to power-driven systems, but does not apply to the power-driven systems themselves.

With regard to safety, this International Standard gives requirements for intended performance, design attributes, selection of materials, design evaluation, manufacture, sterilization, packaging and information to be supplied by the manufacturer.

This International Standard is not applicable to instruments associated with dental implants, transendodontic and transradicular implants and ophthalmic implants.

NOTE References to standards for non-active surgical implants are listed in the Bibliography.

## 2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 11134, *Sterilization of health care products — Requirements for validation and routine control — Industrial moist heat sterilization.*

ISO 11135, *Medical devices — Validation and routine control of ethylene oxide sterilization.*

ISO 11137, *Sterilization of health care products — Requirements for validation and routine control — Radiation sterilization.*

ISO 11607, *Packaging for terminally sterilized medical devices.*

ISO 14155, *Clinical investigation of medical devices.*

ISO 14971-1, *Medical devices — Risk management — Part 1: Application of risk analysis.*

ISO 15223, *Medical devices — Symbols to be used with medical device labels, labelling and information to be supplied.*

EN 556:1994 + A1:1998, *Sterilization of medical devices — Requirements for terminally-sterilized medical devices to be labelled "Sterile"*.

EN 1041:1998, *Information supplied by the manufacturer with medical devices*.

### 3 Terms and definitions

For the purposes of this International Standard, the following terms and definitions apply.

#### 3.1

**associated instrument**  
**instrument**

non-active medical device intended for use during surgical procedures related to a specific non-active surgical implant

#### 3.2

**resupplied instrument**

instrument or set of instruments that has been returned to the manufacturer and has been reissued

### 4 Intended performance

The intended performance of an instrument shall be described and documented by addressing the following:

- a) functional characteristics;
- b) intended conditions of use.

NOTE Account should be taken of:

- published standards;
- published clinical and scientific literature;
- validated test results.

The extent to which the intended performance of an instrument has been achieved shall be determined (see clause 7).

### 5 Design attributes

The development of the design attributes of an instrument to meet the performance intended by the manufacturer shall take into account at least the following:

- a) physical, mechanical and chemical properties of the instrument materials (see clauses 6 and 7);
- b) microbiological and particulate contamination levels (see clauses 7, 9 and 10);
- c) ease of use, cleaning and maintenance (see clause 7);
- d) potential deterioration of the material characteristics due to sterilization and storage (see clauses 6, 7 and 8);
- e) effects of contact between the instrument and body, the implant and other instruments (see clause 7);
- f) shape and dimensions of the instrument, including their possible effects on the body (see clause 7);

- g) wear characteristics of materials and the effect of wear and wear products on the instrument and the body (see clauses 6 and 7);
- h) insertion, removal and interconnecting parts (see clause 7);
- i) extent of fluid leakage and/or diffusion of substances into or out of instruments (see clauses 6 and 7);
- j) accuracy and stability of instruments with a measuring function (see clauses 7 and 8);
- k) ability of the instrument or fragment of instrument to be located by means of an external imaging device (see 11.5).

## 6 Selection of materials

Materials for the manufacture of instruments shall be selected with regard to the properties required for the intended purpose, taking into account the effects of manufacture, handling, sterilization and storage (see clause 7).

The suitability of a given material for a particular application shall be demonstrated by either:

- a) evaluating in accordance with clause 7; or
- b) by selection from the materials found suitable by proven clinical use in similar applications.

NOTE Annex A lists some of the materials that have been found acceptable in certain applications.

## 7 Design evaluation

### 7.1 General

Instruments shall be evaluated in association with the implant they are designed for, in order to demonstrate that the intended performance (see clause 4) is achieved. Safety shall be demonstrated by pre-clinical evaluation and by carrying out a risk analysis in accordance with ISO 14971-1.

NOTE In certain circumstances a clinical evaluation can also be required.

### 7.2 Pre-clinical evaluation

If pre-clinical testing of instruments is required, the testing shall simulate conditions of intended use.

### 7.3 Clinical evaluation

If a clinical evaluation is required, it shall be conducted using the associated implant under the intended conditions of use. Where a clinical investigation is carried out, it shall be managed in accordance with ISO 14155.

## 8 Manufacture

Instruments shall be manufactured to specifications in accordance with the required design attributes (see clause 5).

NOTE 1 The application of quality systems as described in EN 46001 and EN 46002 may be appropriate.

NOTE 2 The design specification for re-supplied instruments need not necessarily be the same as the original, provided that the requirements of this International Standard are met.

## 9 Sterilization

### 9.1 Products supplied sterile

Instruments which are labelled "STERILE" shall comply with EN 556.

Sterilization processes shall be validated and routinely controlled.

If instruments are to be sterilized by ethylene oxide, ISO 11135 applies,

If instruments are to be sterilized by irradiation, ISO 11137 applies,

If instruments are to be sterilized by steam, ISO 11134 applies.

### 9.2 Products provided non-sterile

For instruments which are supplied non-sterile, the manufacturer shall specify at least one appropriate sterilization method such that the functional safety of the product is not adversely affected. If multiple sterilizations are not allowed, this shall be stated (see 11.6).

## 10 Packaging

### 10.1 Protection from damage in storage and transport

For each instrument, the packaging shall be designed so that, under conditions specified by the manufacturer for storage, transport and handling (including control of temperature, humidity and ambient pressure, if applicable), it protects against damage and deterioration and does not adversely affect the intended performance of the instrument.

NOTE Possible test methods are specified in IEC 60068-2-27, IEC 60068-2-32, IEC 60068-2-32 AMD 2 and/or IEC 104/49/CDV.

### 10.2 Maintenance of sterility in transit

Instruments labelled "STERILE" shall be packed such that they remain sterile under normal storage, transport and handling conditions, unless the protective package is damaged or opened.

The packaging shall conform to ISO 11607.

## 11 Information to be supplied by the manufacturer

### 11.1 General

Information supplied with instruments by manufacturers shall be in accordance with EN 1041:1998, with the exception of 4.3. All packages shall bear a label which indicates the full contents. If the label does not list the full contents of the package, a contents list shall be enclosed. If symbols are to be used, they shall be in accordance with ISO 15223.

### 11.2 Instruments with measuring function

The limits of accuracy of instruments having a measuring function shall be indicated by a marking on the device and/or label, instruction leaflet or manual.

NOTE This requirement does not apply to gauges used for component size selection and GO/ NO GO determination.

### 11.3 Restrictions in combinations

If the instrument is intended to be used in combination with other instruments, devices or equipment, restrictions in the use of the combination shall be indicated on the label or in the instruction leaflet or the manual.

### 11.4 Marking on instruments

Instruments shall be marked with the following:

- manufacturer's name or trademark;
- batch code or serial number, where appropriate;
- catalogue/article number, where appropriate, and/or size indication if needed for safe selection or use.

If the marking would affect the intended performance, or the instrument is too small to be legibly marked, the information required shall be given on the label.

### 11.5 Instructions for use

If the instrument cannot be used safely without instructions for use, these shall be provided. It shall be indicated whether the instrument or any fragment thereof may be located by means of an external imaging device, and with what kind of such device.

### 11.6 Instruments intended for single use

Instruments intended for single use only shall be labelled either "For single use only" or by a symbol in accordance with ISO 15223.

STANDARDSISO.COM : Click to view the full PDF of ISO 16061:2000

**Annex A**  
(informative)

**Examples of typical instrument applications, together with materials found acceptable for instrument manufacture**

**A.1 Invasive applications**

**A.1.1 Instruments with cutting edges**

- scissors;
- needles;
- knives;
- cannulae;
- chisels;
- drill bits;
- gouges;
- broaches;
- curettes;
- sawblades;
- burrs;
- reamers;
- trepans.

**A.1.2 Instruments used as guides**

- cannulae;
- saw guides;
- drill guides.
- aiming devices

**A.1.3 Instruments having implant contact**

- punches;
- extractors;

- introducers;
- impactors;
- pullers;
- trial implants;
- drive connections.

#### **A.1.4 Instruments having passive contact**

- retractors;
- location guides;
- spreaders;
- sizers;
- forceps;
- measuring devices;
- holders;
- trial implants;
- location pins.

#### **A.1.5 Miscellaneous**

- vents;
- brushes;
- restrictors.

### **A.2 Non-invasive applications**

- external alignment guides;
- handles.

### **A.3 Materials for invasive applications**

#### **A.3.1 Instruments with cutting edges**

##### **A.3.1.1 Stainless steel**

See Tables A.1, A.2, A.3 and A.4.

ISO 5832-1, *Implants for surgery — Metallic materials — Part 1: Wrought stainless steel.*

ISO 5832-9, *Implants for surgery — Metallic materials — Part 9: Wrought high nitrogen stainless steel.*

#### A.3.1.2 Cobalt/chromium alloys

ISO 5832-4, *Implants for surgery — Metallic materials — Part 4: Cobalt-chromium-molybdenum casting alloy.*

ISO 5832-5, *Implants for surgery — Metallic materials — Part 5: Wrought cobalt-chromium-tungsten-nickel alloy.*

ISO 5832-6, *Implants for surgery — Metallic materials — Part 6: Wrought cobalt-nickel-chromium-molybdenum alloy.*

ISO 5832-7, *Implants for surgery — Metallic materials — Part 7: Forgeable and cold-formed cobalt-chromium-nickel-molybdenum-iron alloy.*

ISO 5832-8, *Implants for surgery — Metallic materials — Part 8: Wrought cobalt-nickel-chromium-molybdenum-tungsten-iron alloy.*

ISO 5832-12, *Implants for surgery — Metallic materials — Part 12: Wrought cobalt-chromium-molybdenum alloy.*

#### A.3.1.3 Non-metallic

- silicon carbide;
- tungsten carbide.

#### A.3.1.4 Coatings

- titanium nitride;
- titanium carbide;
- silicon carbide;
- chromium-based.

### A.3.2 Instruments used as guides

#### A.3.2.1 Stainless steels

See Tables A.1, A.2, A.3 and A.4.

ISO 5832-1, *Implants for surgery — Metallic materials — Part 1: Wrought stainless steel.*

ISO 5832-9, *Implants for surgery — Metallic materials — Part 9: Wrought high nitrogen stainless steel.*

#### A.3.2.2 Cobalt/chromium alloys

ISO 5832-4, *Implants for surgery — Metallic materials — Part 4: Cobalt — chromium-molybdenum casting alloy.*

ISO 5832-5, *Implants for surgery — Metallic materials — Part 5: Wrought cobalt-chromium-tungsten-nickel alloy.*

ISO 5832-6, *Implants for surgery — Metallic materials — Part 6: Wrought cobalt-nickel-chromium-molybdenum alloy.*

ISO 5832-7, *Implants for surgery — Metallic materials — Part 7: Forgeable and cold-formed cobalt-chromium-nickel-molybdenum-iron alloy.*

ISO 5832-8, *Implants for surgery — Metallic materials — Part 8: Wrought cobalt-nickel-chromium-molybdenum-tungsten-iron alloy.*

ISO 5832-12, *Implants for surgery — Metallic materials — Part 12: Wrought cobalt-chromium-molybdenum alloy.*

### A.3.2.3 Titanium / titanium alloys

ISO 5832-2, *Implants for surgery — Metallic materials — Part 2: Unalloyed titanium.*

ISO 5832-3, *Implants for surgery — Metallic materials — Part 3: Wrought titanium 6-aluminium 4-vanadium alloy.*

ISO 5832-11, *Implants for surgery — Metallic materials — Part 11: Wrought titanium 6-aluminium 7-niobium alloy.*

## A.3.3 Instruments having implant contact

### A.3.3.1 Stainless steel

See Tables A.1, A.2, A.3 and A.4.

ISO 5832-1, *Implants for surgery — Metallic materials — Part 1: Wrought stainless steel.*

ISO 5832-9, *Implants for surgery — Metallic materials — Part 9: Wrought high nitrogen stainless steel.*

### A.3.3.2 Cobalt/chromium alloys

ISO 5832-4, *Implants for surgery — Metallic materials — Part 4: Cobalt — chromium-molybdenum casting alloy.*

ISO 5832-5, *Implants for surgery — Metallic materials — Part 5: Wrought cobalt-chromium-tungsten-nickel alloy.*

ISO 5832-6, *Implants for surgery — Metallic materials — Part 6: Wrought cobalt-nickel-chromium-molybdenum alloy.*

ISO 5832-7, *Implants for surgery — Metallic materials — Part 7: Forgeable and cold-formed cobalt-chromium-nickel-molybdenum-iron alloy.*

ISO 5832-8, *Implants for surgery — Metallic materials — Part 8: Wrought cobalt-nickel-chromium-molybdenum-tungsten-iron alloy.*

ISO 5832-12, *Implants for surgery — Metallic materials — Part 12: Wrought cobalt-chromium-molybdenum alloy.*

### A.3.3.3 Titanium/titanium alloys

ISO 5832-2, *Implants for surgery — Metallic materials — Part 2: Unalloyed titanium.*

ISO 5832-3, *Implants for surgery — Metallic materials — Part 3: Wrought titanium 6-aluminium 4-vanadium alloy.*

ISO 5832-11, *Implants for surgery — Metallic materials — Part 11: Wrought titanium 6-aluminium 7-niobium alloy.*

### A.3.3.4 Polymers

— polyacetal [Delrin<sup>1</sup>), Celcon<sup>1</sup>];

---

1) Delrin, Celcon, Ultem, Canvesit and Tufnol are examples of suitable products available commercially. This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of these products.

- polyetheramide [Ultem<sup>1</sup>];
- oxide resins;
- polycarbonate (see NOTE 1);
- polyester resins;
- polysulfone (see NOTE 1);
- silicone rubbers;
- polyethylene (see NOTE 2);
- polyurethane;
- polypropylene;
- polyamides (e.g. nylon);
- polyaryletherketone (PAEK);
- cotton-reinforced phenolformaldehyde [Canvesit<sup>1</sup>].

NOTE 1 These polymers can exhibit cracking if exposed to lipids

NOTE 2 Some methods of resterilization of polyethylene may affect mechanical properties and dimensional stability.

### A.3.4 Instruments having passive tissue contact

#### A.3.4.1 Stainless steels

See Tables A.1, A.2, A.3 and A.4.

ISO 5832-1, *Implants for surgery — Metallic materials — Part 1: Wrought stainless steel.*

ISO 5832-9, *Implants for surgery — Metallic materials — Part 9: Wrought high nitrogen stainless steel.*

#### A.3.4.2 Cobalt/chromium alloys

ISO 5832-4, *Implants for surgery — Metallic materials — Part 4: Cobalt — chromium-molybdenum casting alloy.*

ISO 5832-5, *Implants for surgery — Metallic materials — Part 5: Wrought cobalt-chromium-tungsten-nickel alloy.*

ISO 5832-6, *Implants for surgery — Metallic materials — Part 6: Wrought cobalt-nickel-chromium-molybdenum alloy.*

ISO 5832-7, *Implants for surgery — Metallic materials — Part 7: Forgeable and cold-formed cobalt-chromium-nickel-molybdenum-iron alloy.*

ISO 5832-8, *Implants for surgery — Metallic materials — Part 8: Wrought cobalt-nickel-chromium-molybdenum-tungsten-iron alloy.*

ISO 5832-12, *Implants for surgery — Metallic materials — Part 12: Wrought cobalt-chromium-molybdenum alloy.*

**A.3.4.3 Titanium/titanium alloys**

ISO 5832-2, *Implants for surgery — Metallic materials — Part 2: Unalloyed titanium.*

ISO 5832-3, *Implants for surgery — Metallic materials — Part 3: Wrought titanium 6-aluminium 4-vanadium alloy.*

ISO 5832-11, *Implants for surgery — Metallic materials — Part 11: Wrought titanium 6-aluminium 7-niobium alloy.*

**A.3.4.4 Aluminium alloys**

Aluminium should be anodized in accordance with EN 2101, *Aerospace series — Chromic acid anodizing of aluminium and wrought aluminium alloys.*

EN 2100, *Aerospace series — Aluminium alloy AL-P2014A T4511 — Extruded bars and sections a or D < or = 200 mm.*

EN 2127, *Aerospace series — Aluminium alloy AL-P7075-T73511 — Extruded bars and sections a or D < or = 100 mm.*

EN 2128, *Aerospace series — Aluminium alloy AL-P7075-T7351 — Drawn bars 6 mm < or = a or D < or = 75 mm.*

EN 2318, *Aerospace series — Aluminium alloy AL-P2024 -T3511 — Extruded bars and sections 1,2 mm < or = a or D < or = 150 mm.*

EN 2326, *Aerospace series — Aluminium alloy AL-P6082-T6 — Extruded bars and sections a or D < or = 200 mm.*

EN 2384, *Aerospace series — Aluminium alloy AL-P2014A T6511 — Extruded bars and sections a or D < or = 150 mm.*

**A.3.4.5 Polymers**

- polyacetal [Celcon<sup>1</sup>];
- polyetheramide [Ultem<sup>1</sup>];
- oxide resins;
- polycarbonate (see NOTE 1 under A.3.3.4);
- polyester resins;
- polysulfone (see NOTE 1 under A.3.3.4);
- silicone rubbers;
- polyethylene (see NOTE 2 under A.3.3.4);
- polyurethane;
- polypropylene;
- polyamides (e.g. nylon);
- polyaryletherketone (PAEK);
- cotton-reinforced phenolformaldehyde [Canvesit<sup>1</sup>].

### A.3.5 Miscellaneous

#### A.3.5.1 Vents

- plasticized PVC.

#### A.3.5.2 Brushes

- polyamide (e.g. nylon).

#### A.3.5.3 Restrictors

- polyethylene;
- polypropylene;
- polyurethanes.

### A.4 Materials for non-invasive applications

NOTE All materials standardized under ISO 5832-1 to ISO 5832-12 apply.

#### A.4.1 Stainless steel

See Tables A.1, A.2, A.3 and A.4

#### A.4.2 Aluminium alloys

Aluminium alloys should be anodized in accordance with EN 2101, *Aerospace series — Chromic acid anodizing of aluminium and wrought aluminium alloys*.

EN 2100, *Aerospace series — Aluminium alloy AL-P2014A T4511 — Extruded bars and sections a or D < or = 200 mm.*

EN 2127, *Aerospace series — Aluminium alloy AL-P7075-T73511 — Extruded bars and sections a or D < or = 100 mm.*

EN 2128, *Aerospace series — Aluminium alloy AL-P7075-T7351 — Drawn bars 6 mm < or = a or D < or = 75 mm.*

EN 2318, *Aerospace series — Aluminium alloy AL-P2024 -T3511 — Extruded bars and sections 1,2 mm a or D < or = 150 mm.*

EN 2326, *Aerospace series — Aluminium alloy AL-P6082-T6 — Extruded bars and sections a or D < or = 200 mm.*

EN 2384, *Aerospace series — Aluminium alloy AL-P2014A T6511 — Extruded bars and sections a or D < or = 150 mm.*

#### A.4.3 Polymers

- polyacetal [Delrin<sup>1</sup>], Celcon<sup>1</sup>];
- polyetheramide [Ultem<sup>1</sup>];
- oxide resins;

- polycarbonate (see NOTE 1 under A.3.3.4);
- polyester resins;
- polysulfone (see NOTE 1 under A.3.3.4);
- silicone rubbers;
- polyethylene (see NOTE 2 under A.3.3.4);
- polyurethane;
- polypropylene;
- polyamides (e.g. nylon);
- polyaryletherketone (PAEK);
- cotton-reinforced phenolformaldehyde [Canvesit<sup>1</sup>];
- linen-reinforced phenolformaldehyde [Tufnol<sup>1</sup>].

STANDARDSISO.COM : Click to view the full PDF of ISO 16061:2000

Table A.1 — Austenitic stainless steels

Steel grade in accordance with:			Chemical composition %								
ISO 7153-1 ref. letter	ISO 4957	AISI	C max.	Si max.	Mn max.	P max.	S	Cr	Mo	Ni	
M	—	304	0,07	1	2	0,045	0,03 max.	17 to 19	—	8 to 11	
N	—	303	0,12	1	2	0,060	0,15 to 0,35	17 to 19	0,7	8 to 10	
O	—	—	0,15	1	2	0,045	0,03 max.	16 to 18	—	6 to 8	
P	—	316	0,07	1	2	0,045	0,03 max.	16,5 to 18,5	2 to 2,5	10,5 to 13,5	

STANDARDSISO.COM · Click to view the full PDF of ISO 16061:2000

Table A.2 — Martensitic stainless steel

Steel grade in accordance with:			Chemical composition %									
ISO 7153-1 ref. letter	ISO 4957	AISI	C max.	Si max.	Mn max.	P max.	S	Cr	Mo	Ni	Other elements	
A	—	410	0,09 to 0,15	1	1	0,04	0,03 max.	11,5 to 13,5	—	1 max.	—	
B	27	420 A	0,16 to 0,25	1	1	0,04	0,03 max.	12 to 14	—	1 max.	—	
C	28	420 B	0,26 to 0,35	1	1	0,04	0,03 max.	12 to 14	—	1 max.	—	
D	—	420 C	0,42 to 0,50	1	1	0,04	0,03 max.	12,5 to 14,5	—	1 max.	—	
E	—	—	0,47 to 0,57	0,5	1	0,030	0,03 max.	13,7 to 15,2	—	0,5 max.	—	
F	—	—	0,60 to 0,70	0,5	1	0,030	0,03 max.	12 to 13,5	—	0,5 max.	—	
G	—	—	0,65 to 0,75	1	1	0,04	0,03 max.	12 to 14	0,5	1 max.	—	
H	—	—	0,35 to 0,40	1	1	0,045	0,03 max.	14 to 15	0,4 to 0,6	—	V 0,1 to 0,15	
I	—	—	0,42 to 0,55	1	1	0,045	0,03 max.	12 to 15	0,45 to 0,90	—	V 0,1 to 0,15	
K	30	—	0,33 to 0,43	1	1	0,03	0,03 max.	15 to 17	1,0 to 1,5	1 max.	—	
—	—	431	0,20 max.	1	1	0,04	0,03 max.	15 to 17	—	1,0 to 1,5	—	
R	—	440B	0,85 to 0,95	1	1	0,045	0,03 max.	17 to 19	0,9 to 1,3	—	V 0,07 to 0,12	
—	—	440A	0,60 to 0,75	1	1	0,040	0,03 max.	16 to 18	0,75 max.	—	—	
—	—	440 F	0,95 to 1,20	1	1,25	0,06	0,15 to 0,27	16 to 18	—	0,5 max.	Cu 0,6 max.	