

INTERNATIONAL STANDARD

ISO
1637

Second edition
1987-06-01



INTERNATIONAL ORGANIZATION FOR STANDARDIZATION
ORGANISATION INTERNATIONALE DE NORMALISATION
МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ

Wrought copper and copper alloy rod and bar — Technical conditions of delivery

Barres en cuivre et en alliages de cuivre corroyés — Conditions techniques de livraison

STANDARDSISO.COM : Click to view the full PDF of ISO 1637:1987

Reference number
ISO 1637:1987 (E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 1637 was prepared by Technical Committee ISO/TC 26, *Copper and copper alloys*.

This second edition cancels and replaces the first edition (ISO 1637 : 1974), of which it constitutes a technical revision.

Users should note that all International Standards undergo revision from time to time and that any reference made herein to any other International Standard implies its latest edition, unless otherwise stated.

Wrought copper and copper alloy rod and bar — Technical conditions of delivery

1 Scope and field of application

This International Standard specifies the technical conditions of delivery of wrought copper and copper alloy rod and bar, currently available in commercial quantities.

For the purpose of this International Standard, the definitions for copper and copper alloys in ISO 197-1 and for rod and bar in ISO 197-3 as well as the principles for designation in ISO 1190-1 and ISO 1190-2 apply.

For technical conditions of delivery for wire, see ISO 1638.

2 References

2.1 Definitions

ISO 197, *Copper and copper alloys — Terms and definitions*

- Part 1 : *Materials.*
- Part 3 : *Wrought products.*

2.2 Designations

ISO 1190, *Copper and copper alloys — Code of designation*

- Part 1 : *Designation of materials.*
- Part 2 : *Designation of tempers.*

2.3 Chemical composition

ISO 426, *Wrought copper-zinc alloys — Chemical composition and forms of wrought products*

- Part 1 : *Non-leaded and special copper-zinc alloys.*
- Part 2 : *Leaded copper-zinc alloys.*

ISO 427, *Wrought copper-tin alloys — Chemical composition and forms of wrought products.*

ISO 428, *Wrought copper-aluminium alloys — Chemical composition and forms of wrought products.*

ISO 429, *Wrought copper-nickel alloys — Chemical composition and forms of wrought products.*

ISO 430, *Wrought copper-nickel-zinc alloys — Chemical composition and forms of wrought products.*

ISO 1187, *Special wrought copper alloys — Chemical composition and forms of wrought products.*

ISO 1336, *Wrought coppers (having minimum copper content of 97,5 %) — Chemical composition and forms of wrought products.*

ISO 1337, *Wrought coppers (having minimum copper content of 99,85 %) — Chemical composition and forms of wrought products.*

2.4 Technical conditions of delivery

ISO 1638, *Wrought copper and copper alloy wire — Technical conditions of delivery.*

2.5 Methods of test

2.5.1 Sampling

ISO 4739, *Wrought copper and copper alloy products — Selection and preparation of specimens and test pieces for mechanical testing.*

2.5.2 Tensile testing

ISO 6892, *Metallic materials — Tensile testing.*

2.5.3 Hardness testing

ISO 6506, *Metallic materials — Hardness test — Brinell test.*

ISO 6507, *Metallic materials — Hardness test — Vickers test*
— Part 1 : HV 5 to HV 100.

ISO 6508, *Metallic materials — Hardness test — Rockwell test (scales A — B — C — D — E — F — G — H — K).*

2.5.4 Stress corrosion testing

ISO 196, *Wrought copper and copper alloys — Detection of residual stress — Mercury(I) nitrate test.*

ISO 6957, *Copper and copper alloys — Ammonia test for stress corrosion resistance.¹⁾*

1) At present at the stage of draft.

2.6 Dimensional tolerances

ISO 3488, *Wrought copper and copper alloys — Extruded round, square or hexagonal bars — Dimensions and tolerances.*

ISO 3489, *Wrought copper and copper alloys — Drawn round bars — All minus tolerances on diameter and form tolerances.*

ISO 3490, *Wrought copper and copper alloys — Drawn hexagonal bars — All minus tolerances on width across flats and form tolerances.*

ISO 3491, *Wrought copper and copper alloys — Drawn square bars — All minus tolerances on width across flats and form tolerances.*

ISO 6958, *Wrought copper and copper alloys — Drawn rectangular bars — Dimensions and tolerances.*

ISO 7756, *Wrought copper and copper alloys — Drawn round bars — Symmetric plus and minus tolerances on diameter and form tolerances.*

ISO 7757, *Wrought copper and copper alloys — Drawn hexagonal bars — Symmetric plus and minus tolerances on width across flats and form tolerances.*

ISO 7758, *Wrought copper and copper alloys — Drawn square bars — Symmetric plus and minus tolerances on width across flats and form tolerances.*

3 Ordering information

The purchaser shall state on his inquiry and order the following information :

- a) quantity;
- b) designation of the material and temper required (see table 2);
- c) the mandatory mechanical properties : tensile strength, hardness (see 4.2);
- d) dimensions, i.e.
 - diameter, width across flats, thickness, width,
 - length;
- e) in case of hardness, whether Vickers, Brinell or Rockwell hardness is mandatory;
- f) the tests to be carried out, including those to be agreed upon.

4 Requirements

4.1 Chemical composition

The chemical composition shall comply with the requirements as specified in the International Standards referred to in table 1.

Table 1 — Chemical composition

| Material | Chemical composition in accordance with |
|---------------------------|---|
| Coppers | ISO 1336, ISO 1337 |
| Copper-zinc alloys | ISO 426-1 and ISO 426-2 |
| Copper-tin alloys | ISO 427 |
| Copper-aluminium alloys | ISO 428 |
| Copper-nickel alloys | ISO 429 |
| Copper-nickel-zinc alloys | ISO 430 |
| Special copper alloys | ISO 1187 |

4.2 Mandatory mechanical properties

4.2.1 This International Standard embodies the principle that either

- tensile strength and elongation or
- hardness

are generally sufficient to define the condition of the material. Exact conversion between tensile strength and hardness is not possible.

At the option of the purchaser, mandatory properties of the material may be either

- tensile strength and elongation or
- hardness,

but not both.

In case of hardness, it shall be indicated whether the Vickers or Brinell or the Rockwell hardness test method is mandatory.

If mandatory properties are not specified by the purchaser, the supplier may choose to meet either

- tensile strength and elongation or
- hardness.

4.2.2 Mechanical properties are given in table 2.

Values shown in brackets are given for information only.

The elongation values listed are valid :

- a) for diameter, width across flats, thickness over 2,5 mm based on gauge length $5,65 \sqrt{S_0} \cong A_5$
- b) for diameter, width across flats, thickness from 0,10 up to 2,5 mm based on
 - either a gauge length $11,3 \sqrt{S_0} \cong A_{10}$,
 - or a fixed gauge length of 50 mm $\cong A_{50}$.

Rods and bars having dimensions outside the given ranges may not comply with the properties given in table 2.

4.2.3 Subject to agreement between the purchaser and the supplier, copper-zinc alloy rod and bar may be supplied in the stress-relieved condition and be subject to the stress corrosion test. Test pieces subjected to this test shall not crack.

Should a lot of material fail the test, the supplier shall have the option to restress relieve the lot and to resubmit it to all relevant tests.

4.3 Dimensions and tolerances

For rod and bar, the tolerances specified in table 2 apply :

Table 2 – Tolerances applicable to rod and bar

| Cross-section | Tolerance | International Standard |
|---------------------|----------------------|------------------------|
| Round (extruded) | Plus/minus | ISO 3488 |
| Round (drawn) | All minus | ISO 3489 |
| | Plus/minus symmetric | ISO 7756 |
| Square (drawn) | All minus | ISO 3491 |
| | Plus/minus symmetric | ISO 7758 |
| Hexagonal (drawn) | All minus | ISO 3490 |
| | Plus/minus symmetric | ISO 7757 |
| Rectangular (drawn) | Plus/minus symmetric | ISO 6958 |

4.4 Surface quality

The rods and bars shall be clean, sound and free from injurious defects. Discoloration which is characteristic of hot working or proper heat treatment shall not be cause for rejection. A superficial film or residual light lubricant is normally present and is permissible, unless otherwise specified.

5 Methods of test

5.1 Sampling

Selection and preparation of test specimens and test pieces for mechanical testing shall be carried out in accordance with ISO 4739.

The lot size shall be subject to the agreement between supplier and purchaser.

If not otherwise specified, the rate of sampling for plate, sheet and strip shall be one test piece per lot for each of the tests referred to in 5.2 to 5.7, as appropriate.

5.2 Tensile testing

The test shall be made in accordance with ISO 6892.

5.3 Hardness testing

5.3.1 Vickers

The test shall be made in accordance with ISO 6507-1.

5.3.2 Brinell hardness

The test shall be made in accordance with ISO 6506.

5.3.3 Rockwell hardness

The test shall be made in accordance with ISO 6508.

5.4 Stress corrosion test

If required, the test is only carried out on copper-zinc alloys as listed in table 3.

The method shall be the mercury(II) nitrate test according to ISO 196. By agreement between supplier and purchaser, an ammonia test according to ISO 6957 may be specified instead of the mercury(II) nitrate test.

5.5 Retests

5.5.1 If both of the two test pieces which were originally taken from a lot fail to meet the specification for any reason, the lot shall be deemed not to comply with this International Standard.

5.5.2 If one of the two test pieces taken originally from the lot fails to meet the specification for any reason, two further test pieces shall be taken. One of these two test pieces shall be taken from the rod or bar from which the failed test piece was originally taken, unless that rod or bar has been withdrawn from the lot by the supplier. The other test piece shall be taken from another sample from the same lot. All appropriate tests shall be carried out.

5.5.3 Should both of the new test pieces pass the tests, the lot represented by the test pieces shall be deemed to comply with this International Standard. Should either of the additional test pieces fail, then the lot represented by the test pieces shall be deemed not to comply with this International Standard.

Table 3 – Mandatory mechanical properties

| Temper | Dimensions (mm) | | | Mechanical properties | | | | | Hardness | | |
|--|-----------------------------------|------------|----------|---|--|-----------------------------|------------------------------|------------------------------|--------------|------------|--------------|
| | Diameter or distance across flats | Rectangles | | Tensile strength R_m N/mm ² min. | Proof stress $R_{p0,2}$ N/mm ² min. | Elongation | | | Vickers HV10 | Brinell HB | Rockwell HRB |
| | | Thickness | Width | | | A ₅ % min. | A ₁₀ % min. | A ₅₀ % min. | | | |
| Coppers (Cu min. 99,85 %) : Cu-ETP, Cu-FRHC, Cu-FRTP, Cu-OF, Cu-HCP, Cu-DLP, Cu-DHP | | | | | | | | | | | |
| M | — | — | — | Without specified properties | | | | | | | |
| O | min. 6 | 3 to 35 | max. 150 | max. 250 | — | 35 | 30 | 32 | max. 65 | — | — |
| HB | 6 to 40 | 3 to 25 | max. 150 | 250 | (160) | 15 | 12 | 15 | min. 65 | min. 60- | — |
| HD | 6 to 18 | 6 to 10 | max. 100 | 290 | (250) | 5 | — | 5 | min. 90 | min. 80 | min. 48 |
| Coppers (Cu min. 97,5 %) : CuS, CuS(P), CuTe, CuTe(P), CuPb1 | | | | | | | | | | | |
| HB | 6 to 50 | — | — | 250 | 200 | 7 | 5 | 5 | min. 80 | min. 75 | min. 25 |
| CuCr1 | | | | | | | | | | | |
| TF | 6 to 80 | 6 to 50 | max. 150 | 370 | (260) | 18 | — | 20 | min. 120 | min. 110 | min. 70 |
| TH | 6 to 50 | 6 to 18 | max. 50 | 440 | (350) | 10 | — | 12 | min. 145 | min. 130 | min. 80 |
| TL | 6 to 30 | — | — | 500 | (440) | 5 | — | 7 | min. 160 | min. 145 | min. 85 |
| CuZn37 | | | | | | | | | | | |
| O | 10 to 40 | — | — | 290 | — | 45 | 40 | 45 | max. 100 | max. 90 | max. 60 |
| HB | 10 to 40 | — | — | 370 | — | 27 | 22 | 27 | min. 100 | min. 90 | min. 60 |
| HC | 10 to 40 | — | — | 440 | — | 14 | 11 | 14 | min. 135 | min. 120 | min. 75 |
| CuZn40 | | | | | | | | | | | |
| M | — | — | — | Without specified properties | | | | | | | |
| O | 10 to 40 | — | — | 340 | — | 35 | 30 | 35 | max. 125 | max. 110 | max. 70 |
| HB | 10 to 40 | — | — | 390 | — | 20 | 17 | 20 | min. 125 | min. 110 | min. 70 |
| CuZn38Sn1 | | | | | | | | | | | |
| M | 6 to 80 | — | — | Without specified properties | | | | | | | |
| HB | 6 to 50 | 2 to 25 | max. 100 | 400 | (180) | 20 | 15 | 20 | min. 120 | min. 110 | min. 70 |
| HD | 6 to 30 | 2 to 25 | 2 to 50 | 460 | (310) | 13 | 10 | 13 | min. 150 | min. 130 | min. 80 |
| CuZn37Sn1Pb1 | | | | | | | | | | | |
| M | 6 to 80 | — | — | Without specified properties | | | | | | | |
| HB | 6 to 18 | 2 to 50 | max. 100 | 420 | (200) | 15 | 12 | 15 | min. 140 | min. 125 | min. 76 |
| | 18 to 40 | 2 to 50 | max. 100 | 400 | (180) | 18 | 15 | 18 | min. 120 | min. 110 | min. 67 |
| | Over 40 | 2 to 50 | max. 100 | 360 | (160) | 20 | 18 | 20 | min. 110 | min. 100 | min. 62 |
| CuZn37Mn2AlSi | | | | | | | | | | | |
| M | 6 to 80 | — | — | Without specified properties | | | | | | | |
| HB | 6 to 18 | — | — | 600 | (300) | 12 | — | 12 | min. 160 | — | min. 84 |
| | 18 to 40 | — | — | 550 | (270) | 15 | — | 15 | min. 140 | — | min. 76 |
| CuZn39AlFeMn | | | | | | | | | | | |
| M | 6 to 80 | — | — | Without specified properties | | | | | | | |
| HB | 6 to 18 | — | — | 460 | (270) | 12 | 10 | 12 | min. 150 | min. 135 | min. 80 |
| | 18 to 40 | — | — | 440 | (250) | 15 | 12 | 15 | min. 140 | min. 120 | min. 75 |
| | 40 to 50 | — | — | 440 | (210) | 18 | 15 | 18 | min. 120 | min. 110 | min. 65 |
| HC | 6 to 40 | — | — | 540 | (290) | 12 | 10 | 12 | min. 150 | min. 135 | min. 80 |

Table 3 — Mandatory mechanical properties (continued)

| Temper | Dimensions (mm) | | | Mechanical properties | | | | | Hardness | | |
|--------------------------------------|-----------------------------------|------------|-------|---|--|--------------------|-----------------------|-----------------------|--------------|------------|--------------|
| | Diameter or distance across flats | Rectangles | | Tensile strength R_m N/mm ² min. | Proof stress $R_{p0.2}$ N/mm ² min. | Elongation | | | Vickers HV10 | Brinell HB | Rockwell HRB |
| | | Thickness | Width | | | A_5 % min. | A_{10} % min. | A_{50} % min. | | | |
| CuZn34Pb2 | | | | | | | | | | | |
| M | — | — | — | Without specified properties | | | | | | | |
| HA | 6 to 40 | — | — | 350 | (220) | 25 | 22 | 25 | min. 90 | min. 85 | min. 50 |
| HB | 6 to 40 | — | — | 400 | (290) | 20 | 16 | 20 | min. 130 | min. 125 | min. 70 |
| CuZn36Pb3 | | | | | | | | | | | |
| M | — | — | — | Without specified properties | | | | | | | |
| O | 6 to 50 | 2 to 25 | 150 | 330 | — | 25 | 22 | 25 | min. 105 | min. 100 | min. 45 |
| HB | 6 to 10 | — | — | 400 | (180) | 7 | — | — | — | — | — |
| | 10 to 30 | — | — | 380 | (160) | 10 | — | — | min. 107 | min. 94 | min. 60 |
| | 30 to 50 | — | — | 350 | (140) | 15 | — | — | min. 99 | min. 87 | min. 55 |
| HD | Up to 6 | — | — | 550 | (310) | — | — | — | — | — | — |
| | 6 to 12 | — | — | 480 | (240) | 6 | — | — | — | — | — |
| CuZn40Pb/CuZn39Pb1 | | | | | | | | | | | |
| M | 6 to 80 | — | — | Without specified properties | | | | | | | |
| HB | 6 to 40 | 2 to 6 | — | 380 | — | 25 | 20 | 25 | min. 90 | min. 85 | min. 50 |
| HD | 6 to 18 | 2 to 4 | — | 460 | 330 | 10 | 7 | 10 | min. 130 | min. 125 | min. 70 |
| CuZn38Pb2/CuZn40Pb2/CuZn39Pb3 | | | | | | | | | | | |
| M | 6 to 80 | — | — | Without specified properties | | | | | | | |
| HB | 6 to 40 | 2 to 6 | — | 400 | (210) | 18 | 15 | 18 | min. 120 | min. 110 | min. 65 |
| HD | 6 to 18 | 2 to 4 | — | 460 | (360) | 12 | 7 | 12 | min. 130 | min. 125 | min. 70 |
| CuZn38Pb4 | | | | | | | | | | | |
| M | 6 to 80 | — | — | Without specified properties | | | | | | | |
| HB | 6 to 18 | 2 to 6 | — | 420 | — | 15 | 12 | 15 | min. 110 | min. 95 | min. 65 |
| | 18 to 40 | 2 to 6 | — | 400 | — | 18 | 15 | 18 | min. 110 | min. 95 | min. 65 |
| CuSn5 | | | | | | | | | | | |
| HA | 6 to 18 | — | — | 485 | — | — | — | 13 | min. 150 | — | min. 80 |
| | 18 to 30 | — | — | 415 | — | — | — | 15 | min. 148 | — | min. 79 |
| HB | 6 to 18 | — | — | 480 | — | 13 | — | — | — | — | |
| HE | 6 to 10 | — | — | 700 | — | 5 | — | — | — | — | — |
| | 10 to 18 | — | — | 620 | — | 9 | — | — | — | — | — |
| CuSn6 | | | | | | | | | | | |
| HA | 6 to 40 | — | — | 400 | — | 33 | — | — | — | — | — |
| HB | 6 to 18 | — | — | 500 | — | 15 | — | — | — | — | — |
| HD | 6 to 10 | — | — | 580 | — | 7 | — | — | — | — | — |
| CuSn8 | | | | | | | | | | | |
| HA | 6 to 40 | — | — | 450 | — | 35 | — | — | — | — | — |
| HB | 6 to 18 | — | — | 530 | — | 15 | — | — | — | — | — |
| HD | 6 to 10 | — | — | 600 | — | 8 | — | — | — | — | — |

Table 3 – Mandatory mechanical properties (continued)

| Temper | Dimensions (mm) | | | Mechanical properties | | | | | Hardness | | |
|------------------------|-----------------------------------|------------|-------|---|--|--------------------|-----------------------|-----------------------|--------------|------------|--------------|
| | Diameter or distance across flats | Rectangles | | Tensile strength R_m N/mm ² min. | Proof stress $R_{p0,2}$ N/mm ² min. | Elongation | | | Vickers HV10 | Brinell HB | Rockwell HRB |
| | | Thickness | Width | | | A_5 % min. | A_{10} % min. | A_{50} % min. | | | |
| CuAl7Si2 | | | | | | | | | | | |
| HB | 6 to 18 | — | — | 520 | (270) | 15 | — | 15 | min. 160 | min. 140 | min. 84 |
| | 18 to 40 | — | — | 520 | (270) | 18 | — | 18 | min. 140 | min. 120 | min. 75 |
| | Over 40 | — | — | 520 | (240) | 20 | — | 20 | min. 130 | min. 115 | min. 72 |
| CuAl8Fe3 | | | | | | | | | | | |
| HB | 10 to 80 | — | — | 470 | (200) | 25 | — | 30 | min. 120 | min. 110 | min. 65 |
| CuAl9Mn2 | | | | | | | | | | | |
| M | 6 to 80 | — | — | Without specified properties | | | | | | | |
| HA | 6 to 80 | — | — | 490 | (200) | 25 | — | 25 | min. 100 | min. 95 | min. 65 |
| HB | 6 to 50 | — | — | 590 | (250) | 15 | — | 15 | min. 135 | min. 130 | min. 75 |
| CuAl9Ni3Fe2 | | | | | | | | | | | |
| M | 6 to 50 | — | — | 490 | (180) | 22 | — | — | — | — | — |
| CuAl10Fe3 | | | | | | | | | | | |
| M | 6 to 80 | — | — | Without specified properties | | | | | | | |
| HB | 6 to 80 | — | — | 590 | (250) | 12 | — | 15 | min. 135 | min. 125 | min. 75 |
| CuAl10Ni5Fe4 | | | | | | | | | | | |
| M | 6 to 80 | — | — | Without specified properties | | | | | | | |
| HB | 6 to 50 | — | — | 700 | (380) | 10 | — | 12 | min. 170 | min. 150 | min. 85 |
| CuNi30Mn1Fe | | | | | | | | | | | |
| O | min. 6 | — | — | max. 400 | (120) | 35 | — | 35 | max. 120 | max. 115 | max. 70 |
| HB | 6 to 18 | — | — | 420 | (300) | 14 | — | 14 | min. 110 | min. 105 | min. 65 |
| CuNi18Zn19Pb1 | | | | | | | | | | | |
| HB | 3 to 18 | — | — | 430 | (290) | 25 | 20 | 25 | min. 110 | min. 105 | min. 55 |
| HC | 3 to 10 | — | — | 530 | (420) | 6 | — | 6 | min. 140 | min. 130 | min. 75 |
| CuNi10Zn28Pb1 | | | | | | | | | | | |
| HB | 3 to 18 | — | — | 410 | (240) | 23 | 18 | 23 | min. 110 | min. 105 | min. 55 |
| HC | 3 to 10 | — | — | 490 | (370) | 8 | 5 | 8 | min. 145 | min. 135 | min. 75 |
| CuBe2/CuBe2Pb | | | | | | | | | | | |
| TB | 6 to 65 | — | — | 420 | (140) | 35 | — | 35 | min. 90 | — | min. 45 |
| TD | 6 to 50 | — | — | 600 | (520) | 10 | — | 10 | min. 180 | — | min. 90 |
| TF | 6 to 65 | — | — | 1 150 | (1 000) | — | — | — | min. 350 | — | min. C36 |
| TH | 6 to 50 | — | — | 1 210 | (1 030) | — | — | — | min. 360 | — | min. C38 |
| CuCo2Be/CuNi2Be | | | | | | | | | | | |
| TB | 6 to 65 | — | — | 240 | (140) | 20 | — | 20 | min. 70 | — | min. 20 |
| TD | 6 to 50 | — | — | 450 | (380) | 10 | — | 10 | min. 130 | — | min. 60 |
| TF | 6 to 65 | — | — | 660 | (550) | 10 | — | 10 | min. 200 | — | min. 90 |
| TH | 6 to 50 | — | — | 740 | (650) | 8 | — | 8 | min. 220 | — | min. 95 |

Table 3 – Mandatory mechanical properties (concluded)

| Temper | Dimensions (mm) | | | Mechanical properties | | | | | Hardness | | |
|-----------------|-----------------------------------|------------|---------|---|--|--------------------|-----------------------|-----------------------|--------------|------------|--------------|
| | Diameter or distance across flats | Rectangles | | Tensile strength R_m N/mm ² min. | Proof stress $R_{p0,2}$ N/mm ² min. | Elongation | | | Vickers HV10 | Brinell HB | Rockwell HRB |
| | | Thickness | Width | | | A_5 % min. | A_{10} % min. | A_{50} % min. | | | |
| CuNi1Si | | | | | | | | | | | |
| TD | 6 to 30 | — | — | 410 | (290) | 9 | — | 9 | min. 110 | min. 100 | min. 65 |
| TH | 6 to 30 | — | — | 590 | (540) | 12 | — | 12 | min. 160 | min. 150 | min. 85 |
| CuNi2Si | | | | | | | | | | | |
| TD | 6 to 30 | — | — | 410 | (340) | 8 | — | 8 | min. 140 | min. 130 | min. 80 |
| TH | 6 to 30 | — | — | 640 | (590) | 10 | — | 10 | min. 170 | min. 160 | min. 90 |
| CuSi1 | | | | | | | | | | | |
| O | 6 to 50 | 6 to 50 | 6 to 50 | 280 | — | — | — | 30 | min. 90 | — | min. 50 |
| HA | 6 to 50 | 6 to 50 | 6 to 50 | 380 | — | — | — | 17 | min. 160 | — | min. 84 |
| HB | 6 to 50 | 6 to 12 | 6 to 50 | 450 | — | — | — | 15 | min. 170 | — | min. 86 |
| HC | 6 to 30 | 6 to 12 | 6 to 50 | 520 | — | — | — | 13 | min. 175 | — | min. 88 |
| CuSi3Mn1 | | | | | | | | | | | |
| O | 6 to 50 | — | — | max. 490 | (100) | 40 | — | 40 | max. 120 | max. 110 | max. 70 |
| HB | 6 to 50 | — | — | 490 | (340) | 12 | — | 12 | min. 130 | min. 120 | min. 75 |

STANDARDSISO.COM : Click to view the full PDF of ISO 1637:1987