

First edition
2012-06-01

AMENDMENT 1
2014-04-01

**Plastics piping systems for the supply
of gaseous fuels - Unplasticized
polyamide (PA-U) piping systems
with fusion jointing and mechanical
jointing —**

**Part 3:
Fittings**

AMENDMENT 1

*Systèmes de canalisations en matières plastiques pour la distribution
de combustibles gazeux — Systèmes de canalisations en polyamide
non plastifié (PA-U) avec assemblages par soudage et assemblages
mécaniques —*

Partie 3: Raccords

AMENDEMENT 1



Reference number
ISO 16486-3:2012/Amd.1:2014(E)

© ISO 2014

STANDARDSISO.COM : Click to view the full PDF of ISO 16486-3:2012/Amd 1:2014



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 16486-3:2012 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 4, *Plastics pipes and fittings for the supply of gaseous fuels*.

STANDARDSISO.COM : Click to view the full PDF of ISO 16486-3:2012/Amd.1:2014

STANDARDSISO.COM : Click to view the full PDF of ISO 16486-3:2012/Amd 1:2014

Plastics piping systems for the supply of gaseous fuels - Unplasticized polyamide (PA-U) piping systems with fusion jointing and mechanical jointing —

Part 3: Fittings

AMENDMENT 1

Page 6, 6.2.1, [Table 1](#)

Replace the existing table with the following one:

Table 1 — Electrofusion socket dimensions

Dimensions in millimetres

Nominal diameter d_n	Depth of penetration		Fusion zone $L_{2,min}$
	$L_{1,min}$	$L_{1,max}$	
20	25	41	10
25	25	41	10
32	25	44	10
40	25	49	12
50	28	55	15
63	31	63	19
75	35	70	22
90	40	79	26
110	53	82	32
125	58	87	36
140	62	92	40
160	68	98	46
180	74	105	52
200	80	112	57
225	88	120	64
250	95	129	71

Page 8, 6.3, Figure 2

Replace the existing key with the following one:

Key

D_1 mean outside diameter of fusion end piece^a

D_2 bore comprising minimum diameter of flow channel through body of fitting^b

E body wall thickness of fitting^c

E_1 fusion face wall thickness^d

L_1 cut-back length of fusion end piece^e

L_2 tubular length of fusion end piece^f

a D_1 is measured in any plane parallel to the plane of the entrance face at a distance $L_2/2$.

b The measurement of this diameter does not include the fusion bead (if present).

c It comprises the thickness measured at any point of the wall of the fitting.

d It is measured at any point at a maximum distance of L_1 (cut-back length) from the entrance face and shall be equal to the pipe wall thickness and tolerance to which it is intended to be butt fused.

e It comprises the initial depth of the spigot end necessary for butt fusion or reweld and may be obtained by joining a length of pipe to the spigot end of the fitting provided the wall thickness of the pipe is equal to E_1 for its entire length.

f It comprises the initial length of the fusion end piece and shall allow the following (in any combination): the use of clamps required in the case of butt fusion; assembly with an electrofusion fitting.

STANDARDSISO.COM : Click to view the full PDF of ISO 16486-3:2012/Amd 1:2014