
**Building construction — Determination of
the staining of porous substrates by
sealants used in joints —**

Part 1:
Test with compression

*Construction immobilière — Détermination du tachage des supports
poreux par les mastics utilisés dans les joints —*

Partie 1: Essai avec compression



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 16938-1:2008



COPYRIGHT PROTECTED DOCUMENT

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16938-1 was prepared by Technical Committee ISO/TC 59, *Building construction*, Subcommittee SC 8, *Jointing products*.

ISO 16938 consists of the following parts, under the general title *Building construction — Determination of the staining of porous substrates by sealants used in joints*:

- *Part 1: Test with compression*
- *Part 2: Test without compression*

STANDARDSISO.COM : Click to view the full PDF of ISO 16938-1:2008

Building construction — Determination of the staining of porous substrates by sealants used in joints —

Part 1: Test with compression

1 Scope

This part of ISO 16938 specifies a method for determining the staining of porous substrates (e.g. marble, limestone, sandstone or granite) by sealants used in building construction. The method evaluates the likelihood of a sealant causing an early stain on a porous substrate due to exudation of materials from the sealant. The outcome of the test is specific to the tested sealant and tested substrate and cannot be extrapolated to other sealant formulations or other porous substrates. During this accelerated test, if the sealant does not stain or discolour the substrates, it does not mean that the tested sealant will not stain or discolour the tested porous substrate over a longer time period. Experience in various countries with similar test methods has shown that the compression of test specimens further accelerates the occurrence of staining.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4892-1, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance*

ISO 4892-2:2006, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps*

ISO 4892-3, *Plastics — Methods of exposure to laboratory light sources — Part 3: Fluorescent UV lamps*

ISO 6927, *Building construction — Jointing products — Sealants — Vocabulary*

ISO 11431:2002, *Building construction — Jointing products — Determination of adhesion/cohesion properties of sealants after exposure to heat, water and artificial light through glass*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6927 apply.

4 Principle

This method measures the visible staining attributed to joint sealants on porous substrates that is a result of the conditioning specified.

A sealant is applied and cured between two pieces of porous substrate. The test specimens are compressed and then subjected to heat aging and/or cold aging and/or aging in actinic radiation accelerated weathering equipment. After aging, the test specimens are evaluated and visible staining is recorded on the exterior surface and in the interior of the substrate after visual inspection of changes in surface appearance and measurements of maximum and minimum stain width and stain penetration.

5 Apparatus

5.1 Substrate materials, for the preparation of each test specimen; two substrate pieces of the same material are required with dimensions as shown in Figure 1.

5.2 Spacers, for the preparation of the test specimens, of cross-section 12 mm × 12 mm, with non-adherent surface (see Figure 1).

NOTE If the spacers are made of a material to which the sealant adheres, their surfaces should be made non-adherent, e.g. by a thin wax coating.

5.3 Non-adherent substrate, for the preparation of test specimens, e.g. polyethylene (PE) film, preferably on the advice of the sealant manufacturer.

5.4 Masking tape, suitable for covering the tested surface of the substrates (see Figure 1) to prevent sealant contamination during specimen preparation.

5.5 Ventilated convection-type oven, capable of being maintained at $(70 \pm 2) ^\circ\text{C}$.

5.6 Refrigerated enclosure, capable of being maintained at $(-20 \pm 2) ^\circ\text{C}$.

5.7 Clamps or other device, for maintaining the specimen under compression (see Table 1).

5.8 Actinic radiation accelerated aging apparatus.

Fluorescent ultraviolet radiation/condensation test apparatus or xenon light test apparatus shall be employed as actinic radiation accelerated aging apparatus.

NOTE Test results can differ between the exposure to fluorescent ultraviolet radiation/condensation and xenon light because of differences in the spectral power distribution of the radiation source and differences in the exposure conditions a) to d). See 8.2.4.


5.8.1 Fluorescent ultraviolet radiation/condensation test apparatus, fitted with fluorescent UVA-340 lamps having their peak emission at 343 nm, capable of exposing the test specimens to radiation under controlled conditions of temperature and moisture or water, complying with the requirements of ISO 4892-3. Standard practices for operating such accelerated weathering chambers are described in ISO 4892-1. The target value for irradiance at 340 nm shall be $(0,77 \pm 0,02) \text{ W/m}^2$ at $60 ^\circ\text{C}$.

5.8.2 Xenon light test apparatus, fitted with xenon light source with daylight filter, capable of exposing the test specimens to radiation under controlled conditions of temperature and water, complying with the requirements of ISO 4892-2:2006, Table 3, Method A (cycle 1 or 2). Irradiance at the surface of the test specimens between the wavelength of 290 nm and 800 nm shall be $(550 \pm 75) \text{ W/m}^2$. Irradiance below 300 nm shall not exceed 1 W/m^2 .

5.9 Black standard thermometer, complying with the requirements of ISO 4892-1. All temperatures reported in this part of ISO 16938 for the UV exposure apparatus are measured with the black standard thermometer. Black panel thermometer may also be used. Under given operating conditions, they tend to indicate lower temperatures than the black standard thermometer. The temperature difference between the measurements will depend on the test temperature, but can be up to $10 ^\circ\text{C}$.

5.10 Measuring device, scaled in half millimetres.

Dimensions in millimetres

**Key**

- 1 substrate
- 2 sealant
- 3 spacer
- 4 tested surface
- 5 tooled surface

Figure 1 — Test specimen assembly

6 Preparation of test specimens

Four test specimens for each sealant and each aging method shall be prepared.

For each test specimen, two substrate materials (5.1) and two spacers (5.2) shall be assembled (see Figure 1) and set up on the non-adherent substrate (5.3).

The instructions of the sealant manufacturer concerning, for instance, whether a primer is to be used, and the mixing procedure for multi-component sealants, shall be followed.

The following procedure shall be used for specimen preparation:

- a) the sealant and the substrate materials (5.1) shall be brought to (23 ± 2) °C;
- b) the tested surface of both substrate materials shall be placed in the same plane as the tooled surface of the sealant (see Figure 1).
- c) masking tape (5.4) shall be applied on the tested surfaces of the substrate materials to prevent sealant contamination during specimen preparation;
- d) the hollow volume formed by the substrate materials and spacers (5.2) shall be filled with the sealant (avoiding the formation of air bubbles);
- e) the sealant shall be pressed to the inner surfaces of the substrate materials;
- f) the sealant surface shall be trimmed so that it is flush with the masking tapes on the faces of the substrate materials and spacers;
- g) immediately following application and tooling of the sealant, the masking tape shall be removed;
- h) the test specimens shall be set on edge on one of the substrate materials and the non-adherent substrate removed as soon as possible; the specimens shall remain in this position with the spacers in place for another 48 h to allow curing or optimum drying of the sealant.

7 Conditioning

The test specimens shall be conditioned for 28 d at (23 ± 2) °C and (50 ± 5) % relative humidity.

8 Test procedure

8.1 Compression

All test specimens shall be compressed by a percentage equal to the movement capability for the sealant under test. This compression shall be 7,5 %, 12,5 %, 20 % or 25 % or any other compression as agreed by the concerned parties. The sealant shall be held at this compression (see Table 1) using suitable clamps (5.7).

Table 1 — Correspondence of movement capability, compression and joint width after compression

Movement capability (%)	Compression (%)	Joint width after compression (mm)
7,5	7,5	11,1
12,5	12,5	10,5
20	20	9,6
25	25	9,0

8.2 Aging procedures

8.2.1 General

One or more of the following aging procedures (8.2.2, 8.2.3, 8.2.4) shall be carried out as agreed between the concerned parties.

8.2.2 Heat aging

Four of the compressed specimens shall be placed in an oven (5.5) at (70 ± 2) °C. Remove two specimens after 14 d and the other two specimens after 28 d.

8.2.3 Cold aging

Four of the compressed specimens shall be placed in a refrigerated enclosure (5.6) at (-20 ± 2) °C. Remove two specimens after 14 d and the other two specimens after 28 d.

8.2.4 Actinic radiation aging

As agreed between the concerned parties, the test specimens shall be exposed to actinic radiation according to one of the following aging procedures:

- UV fluorescent radiation condensation apparatus (5.8.1) with wet exposure condition [see a)];
- xenon lamp test apparatus (5.8.2) with wet exposure condition [see b)];
- UV fluorescent radiation condensation apparatus (5.8.1) with dry exposure condition [see c)];
- xenon lamp test apparatus (5.8.2) with dry exposure condition [see d)].

Four of the compressed specimens shall be placed in the actinic radiation exposure apparatus, with the tested surface perpendicularly facing the radiation source. Two specimens shall be removed after 14 d and the other two specimens after 28 d.

Wet exposure.

- a) In the UV fluorescent radiation/condensation test apparatus the sealant surface shall be held 50 mm from the radiation source. The cycle of the UV fluorescent radiation/condensation test apparatus shall be set to 8 h UV radiation at (60 ± 2) °C, and 4 h condensation at (50 ± 2) °C.
- b) In the xenon-lamp test apparatus, the specimens shall be exposed to cycles of dry periods with radiation followed by wet periods (water spray or immersion) as defined in ISO 11431:2002, 8.2.2 (automatic cycling) or 8.2.3 (manual cycling).

Dry exposure.

- c) In the UV fluorescent radiation/condensation test apparatus, the sealant surface shall be held 50 mm from the radiation source. The UV fluorescent radiation/condensation test apparatus shall be set to UV radiation at (60 ± 2) °C.
- d) In the xenon-lamp test apparatus, the specimens shall be exposed dry to radiation for a period of 500 h at a temperature of (65 ± 2) °C as measured on the black standard thermometer (5.9).

9 Detection of staining

9.1 General

After aging, the compression on the test specimens shall be released and the specimens shall be conditioned at (23 ± 2) °C and (50 ± 5) % relative humidity for one day.

9.2 Detection at the surface of the substrate


The substrates shall be examined to determine if the sealant caused the tested surface to change in appearance in any way. If so, the maximum and minimum dimensions of the stain width on the tested surface of the substrate shall be measured to the nearest 0,5 mm, using the measurement device (5.10) (see Figure 2), and recorded.

9.3 Detection in the depth of the substrate

The substrates shall be broken perpendicular to the joint within the area of maximum stain width. If no staining can be observed on the tested substrate surface, the substrates shall be broken in half. The bulk of the substrate shall be examined to determine if the sealant has caused any discoloration of the substrate itself. The maximum and minimum of the stain penetration into the bulk substrate (see Figure 3) at the centre of the sealant joint (6 mm depth) shall be recorded to the nearest 0,5 mm, using the measurement device (5.10).


9.4 Expression of results

The minimum and maximum measurements of stain width and penetration of each of the two specimens shall be determined for each of the test conditions (see Figure 4 for an example worksheet).



- Key**
- 1 substrate materials
 - 2 minimum stain width
 - 3 maximum stain width

Figure 2 — Determination of minimum and maximum stain width



- Key**
- 1 minimum stain penetration
 - 2 maximum stain penetration

Figure 3 — Determination of minimum and maximum stain penetration

For some sealant formulations, the ease and reliability of the detection of staining may be improved by inspecting the test specimen in a dark room under illumination with a short-wave length UV lamp.

Sometimes the detection of hydrophobic staining may be improved by wetting the substrates with water. Some sealants may stain the substrates completely, resulting in a uniform discolouration of the substrates and making the detection of the stain difficult. In this situation, it may be helpful to compare the substrate surface to an unexposed control.

Exposure	Specimen	Substrate	Duration			
			14 days		28 days	
			Minimum stain width	Maximum stain width	Minimum stain width	Maximum stain width
70 °C	1	A	2	8	4	15
		B	3	5	8	12
	2	A	4	6	9	10
		B	2	4	5	9
	Report		2	8	4	15
−20 °C	1	A				
		B				
	2	A				
		B				
	Report					
Xenon (wet exposure)	1	A				
		B				
	2	A				
		B				
	Report					

Figure 4 — Example worksheet for determination of reportable maximum and minimum stain width and penetration

10 Test report

The test report shall include the following information:

- a) name of test laboratory, number and date of test report;
- b) reference to this part of ISO 16938, i.e. ISO 16938-1:2008;
- c) name, type (chemical family) and colour of sealant;
- d) batch of sealant from which the test specimens were produced, if possible;
- e) compression used;
- f) substrate material, substrate source (place of origin) and tested surface finish;
- g) name, type and batch of primer from which the test specimens were produced, if applicable;
- h) details of test procedure, as agreed between the concerned parties, namely:
 - 1) the specific aging procedures employed, i.e. heat aging, and/or cold aging, and/or actinic radiation aging (8.2.2 and/or 8.2.3 and/or 8.2.4);
 - 2) the type of actinic radiation aging procedure employed [i), ii), iii), or iv]):
 - i) UV fluorescent radiation condensation apparatus (5.8.1) with wet exposure condition;
 - ii) xenon lamp test apparatus (5.8.2) with wet exposure condition;
 - iii) UV fluorescent radiation condensation apparatus (5.8.1) with dry exposure condition;
 - iv) xenon lamp test apparatus (5.8.2) with dry exposure condition;