

INTERNATIONAL
STANDARD

ISO
17236

IULTCS/IUP
43

First edition
2002-12-15

**Leather — Physical and mechanical
tests — Determination of extension set**

*Cuir — Essais physiques et mécaniques — Détermination de
la déformabilité*

STANDARDSISO.COM : Click to view the full PDF of ISO 17236:2002



Reference number
ISO 17236:2002(E)
IULTCS/IUP 43

© ISO 2002

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 17236:2002

© ISO 2002

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

| | Page |
|---|------|
| Foreword..... | iv |
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Principle | 1 |
| 4 Apparatus | 1 |
| 5 Sampling and sample preparation | 1 |
| 6 Procedure | 2 |
| 7 Expression of results | 2 |
| 8 Test report | 3 |

STANDARDSISO.COM : Click to view the full PDF of ISO 17236:2002

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17236 was prepared by the Physical Test Commission of the International Union of Leather Technologists and Chemists Societies (IUP Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement). It is based on IUP 43 which was published in *J. Soc. Leather Tech. Chem.* **84**, p. 399, (2000) and confirmed as an official method in March 2001.

STANDARDSISO.COM : Click to view the PDF of ISO 17236:2002

Leather — Physical and mechanical tests — Determination of extension set

1 Scope

This International Standard specifies a method for determining the extension set of leather. It is intended for use on upholstery leather but is applicable to all flexible leathers.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418 *Leather - Chemical, physical and mechanical and fastness tests - Sampling location*

ISO 2419 *Leather - Physical and mechanical tests - Sample preparation and conditioning*

ISO 2589 *Leather - Physical and mechanical tests - Determination of thickness*

ISO 7500-1 *Metallic materials - Verification of static uniaxial testing machines - Part 1: Tension/compression testing machines - Verification and calibration of the force-measuring system*

3 Principle

A test piece is repeatedly extended at a specified rate until the forces reach a predetermined level and the permanent extension is calculated as a percentage of the original length.

4 Apparatus

4.1 Tensile testing machine, having a force range appropriate to the specimen under test and consisting of a means of recording the force (4.1.1) and jaws that operate at a uniform speed of separation of $50 \text{ mm} \pm 5 \text{ mm/min}$.

4.1.1 Means of recording the force, to an accuracy as specified by Class 2 of ISO 7500-1.

4.1.2 Jaws, minimum length 30 mm in the direction of the applied load, designed to apply constant clamping by mechanical or pneumatic means. The texture and design of the inside faces of the jaws shall be such that at the maximum load attained in the test the test piece does not slip at either jaw.

4.2 Thickness gauge, as specified in ISO 2589.

4.3 Press knife, the inner wall of which is a rectangle $250 \text{ mm} \pm 5 \text{ mm} \times 10,0 \text{ mm} \pm 0,5 \text{ mm}$, conforming to the requirements of ISO 2419.

4.4 Ruler, reading to 0,5 mm.

4.5 Stopwatch, reading to 1 s.

5 Sampling and sample preparation

5.1 Sample in accordance with ISO 2418.

5.2 Cut six test pieces by applying the press knife (4.3) to the grain surface. Cut three test pieces with the longer edge parallel to the backbone and three with the longer edge perpendicular to the backbone.

NOTE 1 In the case of small skins, the number of test pieces may have to be reduced because of the size of the test piece.

NOTE 2 If there is a requirement for more than two hides or skins to be tested in one batch, then only one test piece in each direction need be taken from each hide or skin, provided that the overall total is not less than three test pieces in each direction.

5.3 Condition the test pieces in accordance with ISO 2419.

5.4 Measure the thickness in accordance with ISO 2589.

6 Procedure

6.1 Mark a line $35 \text{ mm} \pm 5 \text{ mm}$ from each short edge of the test piece with the line parallel to the short edges.

6.2 Using the ruler measure the distance, L_0 , between the two lines to the nearest 1 mm.

6.3 Set the jaws of the tensile testing machine (4.1) 200 mm apart. Clamp the test piece in the jaws such that the short edges of the test piece are parallel to the edges of the jaws, and about 25 mm of the test piece is clamped in each jaw. When the test piece is clamped its grain surface shall lie in one plane.

6.4 Run the tensile test machine until a load of $20,0 \text{ N} \pm 0,5 \text{ N}$ is reached. Immediately this load is reached stop the crosshead and keep the crosshead stopped in that position for $10 \text{ s} \pm 1 \text{ s}$.

NOTE Stopping the crosshead keeps the sample under load although relaxation of the test piece means that the load will fall slightly.

6.5 Return the crosshead to its start position as rapidly as possible.

6.6 Repeat 6.4 to 6.5 so that the test piece is subjected to a total of 5 extension cycles.

NOTE The cycling of the tensile test machine may be carried out manually using the stopwatch for timing or it may be by programming the load and timing into the tensile test machine.

6.7 Remove the test piece from the tensile test machine immediately after the final load cycle (6.4). Start the stopwatch and lay the test piece on a flat surface with the lines applied as described in 6.1 uppermost. $60 \text{ s} \pm 5 \text{ s}$ after removing the test piece from the tensile tester, measure the distance, L_1 , between the lines to the nearest 1 mm.

6.8 Repeat 6.1 to 6.7 for other test pieces.

6.9 If there is slippage of the test piece at either jaw reject the result and repeat the determination with a new test piece.

7 Expression of results

The percentage extension set, E_s , shall be calculated using the formula:

$$E_s = \frac{(L_1 - L_0) \times 100}{L_0}$$

where:

L_1 is the final distance between the marks, in millimetres measured as described in 6.7

L_0 is the initial distance between the marks, in millimetres measured as described in 6.2