
**Ships and marine technology —
Ceramic weld backing for marine use**

Navires et technologie maritime — Soutien de soudures en céramique

STANDARDSISO.COM : Click to view the full PDF of ISO 17683:2014



STANDARDSISO.COM : Click to view the full PDF of ISO 17683:2014



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Classification	1
5 Dimensions and appearance	2
5.1 General	2
5.2 Dimensions	2
5.3 Appearance	2
6 Performance and test	2
6.1 Moisture absorption rate	2
6.2 Refractoriness	3
6.3 Chemical composition	3
6.4 Adhesive aluminium foil tape	3
6.5 Metal cases	3
7 Type approval test	4
7.1 General	4
7.2 Test items	4
7.3 Acceptance criteria	4
8 Acceptance test	4
8.1 Test items	4
8.2 Acceptance criteria	4
9 Marking, packaging, and storage	5
9.1 Marking	5
9.2 Packaging	5
9.3 Storage	5

STANDARDSISO.COM · Click to view the full PDF of ISO 17683:2014

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 8, *Ships and marine technology*, Subcommittee SC 8, *Ship design*.

STANDARDSISO.COM : Click to view the full PDF of ISO 17683:2014

Ships and marine technology — Ceramic weld backing for marine use

1 Scope

This International Standard specifies the classification, dimension and appearance, performance, and test methods for ceramic weld backing. It also specifies marking, packaging, and storage.

This International Standard is applicable to designing, manufacturing, testing, and accepting ceramic weld backing that are to be used in the double side form with single side weld, such as arc welding, gas welding, vertical gas welding, and submerged arc welding, and the shaping structural steel welding end for carbon steel, stainless steel, aluminium alloy, copper alloy, and so on.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 528, *Refractory products — Determination of pyrometric cone equivalent (refractoriness)*

ISO 29862, *Self adhesive tapes — Determination of peel adhesion properties*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

ceramic weld backing block

ceramic block with certain geometric shape manufactured by inorganic material

3.2

moisture absorption rate

W_a

ratio of the weight of water vapour absorbed on the surface of ceramic weld backing block to the weight of the dried sample, with certain temperature, humidity, and time

3.3

adhesive aluminium foil tape

strip of aluminium foil coated with pressure-sensitive adhesive and covered with release paper

3.4

metal case

case which is made of low carbon steel, and used for combining ceramic weld backing blocks

4 Classification

According to the fixed method, ceramic weld backing is classified as follows:

- a) type I — ceramic weld backing with adhesive aluminium foil tape;
- b) type II — ceramic weld backing with metal cases.

5 Dimensions and appearance

5.1 General

For inspection of its dimensions and appearance, six strips of ceramic weld backing shall be randomly selected. Each one of the samples shall meet the requirements in 5.2 and 5.3.

5.2 Dimensions

5.2.1 The tolerance of thickness for ceramic weld backing block shall be $\pm 0,5$ mm of its thickness.

5.2.2 The length tolerance for a strip of ceramic weld backing shall be -10 mm to $+20$ mm of its length.

5.2.3 The centreline tolerance for ceramic weld backing block with moulding groove shall be $\pm 1,0$ mm.

5.2.4 The angle tolerances of a triangular or trapezoidal ceramic weld backing block shall be $\pm 2^\circ$.

5.3 Appearance

5.3.1 Defects, such as damage and rounded corners, are not allowed for the joints between ceramic weld backing blocks other than rounded corners made by the mould itself.

5.3.2 Within the area of the groove of the ceramic weld backing blocks and 2 mm on either side of them, mould sticking grain shall not be larger than 0,5 mm and the defect of the pit and damages shall not be more than 0,5 mm on the surface of the ceramic weld backing blocks.

6 Performance and test

6.1 Moisture absorption rate

6.1.1 The moisture absorption rate shall be measured as follows.

- a) Randomly select three samples among the ceramic weld backing blocks. The dust on their surface shall be blown clear. Lay the samples on a tray, then put into an oven of constant temperature and humidity together.
- b) Switch on the power of the oven and adjust the humidity to (95 ± 3) % and the temperature to (25 ± 2) °C.
- c) Keep the samples and tray in the oven for 4 h, then take the samples out of the oven, weigh all samples, and record the weights as m_2 separately with an accuracy of 0,001 g.
- d) Lay the samples on the tray, then place into the oven of constant temperature. Switch on the power of the oven, adjust the temperature to 200 °C, and keep for 2 h.
- e) Take the samples out of the oven and keep it in the dryer until it cools down to the room temperature. Weigh all samples by an analytical balance, and record the weights as m_1 separately with an accuracy of 0,001 g.
- f) The moisture absorption rate for each sample shall be calculated in accordance with Formula (1).

$$W_a = \frac{m_2 - m_1}{m_1} \times 100 \% \quad (1)$$

where

W_a is the value of the moisture absorption rate (%);

m_1 is the weight of dried sample (g);

m_2 is the weight of sample which has absorbed water vapour sufficiently (g).

g) Calculate the average value of the three samples.

6.1.2 The average value of the moisture absorption rate shall be less than 0,35 %.

6.2 Refractoriness

6.2.1 The refractoriness should be determined according to the welding method and melting point for the metal to be welded.

6.2.2 Randomly select one ceramic weld backing block. The test of the refractoriness shall be conducted according to ISO 528.

6.3 Chemical composition

6.3.1 The content of sulfur and phosphorus in the ceramic weld backing shall be analysed by an appropriate method and shall be less than 0,1 %.

6.3.2 The content of boron in the ceramic weld backing shall be analysed by an appropriate method and shall be less than 0,01 %.

6.3.3 Any analytical technique can be used, but in case of dispute, reference shall be made to established, published methods.

6.4 Adhesive aluminium foil tape

6.4.1 Randomly select one strip of type I ceramic weld backing for the adhesive aluminium foil tape test.

6.4.2 The peeling strength of adhesive aluminium foil tape shall be determined in accordance with ISO 29862 and shall be more than 12 N/25 mm.

6.5 Metal cases

6.5.1 Randomly select one strip of type II ceramic weld backing for the metal cases test.

6.5.2 Erect the strip of ceramic weld backing, and there is no loose between the ceramic weld backing and metal cases.

7 Type approval test

7.1 General

The type approval test shall be carried out under one of the following situations:

- a) initial production;
- b) upon reproduction or re-manufacturing, after being suspended from production for half a year or more, or production for 4 y continuously;
- c) whenever the manufacturing technique which could affect the performance or quality of the products, or its ingredient and raw material, is changed significantly.

7.2 Test items

The following tests for type approval shall be carried out, in addition to the items required in [5.2](#) and [5.3](#):

- a) moisture absorption rate (see [6.1](#));
- b) refractoriness (see [6.2](#));
- c) chemical composition (see [6.3](#));
- d) adhesive aluminium foil tape (for type I) (see [6.4](#));
- e) metal cases (for type II) (see [6.5](#)).

7.3 Acceptance criteria

If the samples meet all test requirements, the batch of ceramic weld backing will be deemed to have passed the type test. However, if the samples fail to meet any of the test requirements, additional double of samples shall be tested. If the additional samples pass all test requirements, the batch of ceramic weld backing will be deemed to have passed the type test. Otherwise, the batch of ceramic weld backing will be deemed to have failed the type test.

8 Acceptance test

8.1 Test items

Prior to delivery of the batch of ceramic weld backing blocks, the manufacturer shall test every batch of ceramic weld backing block for the following items:

- a) dimensions and tolerances (see [5.2](#));
- b) appearance (see [5.3](#));
- c) moisture absorption rate (see [6.1](#));
- d) chemical composition (see [6.3](#)).

8.2 Acceptance criteria

With the same lot of raw materials, ingredients, and manufacturing technique, the ceramic weld backing can be inspected as one batch which should not be more than 500 000 m. If less than 500 000 m, the products should be treated as a batch.