INTERNATIONAL STANDARD

ISO 17885

First edition
2015-09-01

AMENDMENT 1
2016-08-15

Plastics piping systems — Mechanical fittings for pressure piping systems — Specifications

AMENDMENT 1

Systèmes de canalisations en plastiques — Raccords mécaniques pour les canalisations sous pression — Spécifications

AMENDEMENT 1

Reference number
ISO 17885:2015/Amd.1:2016(E)

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

Amendment 1 to ISO 17885:2015 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 4, *Plastics pipes and fittings for the supply of gaseous fuels*.

Plastics piping systems — Mechanical fittings for pressure piping systems — Specifications

AMENDMENT 1

Page 30-31, Annex C, Table C.1

Replace the existing table with the following:

Table C.1 — Test pressure of materials and fittings bodies

Material	Test temperature	Test duration	σ_{tF}	MRS	σ_s
	°C	h	MPa	MPa	MPa
ABS	20	1	24,8	12,5	8,0
	70	1 000	3,1	12,5	8,0
ECTFE	20	40	26,0	18,4	14,3
	80	170	8,0	18,4	14,3
PA 11 160	20	1 000	19,0	16	8,0
	80	165	10,0	16	8,0
PA 11 180	20	1 000	20,0	18	9,0
	80	165	11,5	18	9,0
PA 12 160	20	1 000	19,0	16	8,0
	80	165	10,0	16	8,0
PA 12 180	20	1 000	20,0	18	9,0
	80	165	11,5	18	9,0
PA 12-GF30	20	1	50,0	20	12,5
	60	1 000	20,0	20	12,5
PA 12-GF50	20	1	50,0	20	12,5
	60	1 000	20,0	20	12,5
PA 12-GF65	20	1	50,0	20	12,5
	60	1 000	20,0	20	12,5
PB	20	1	15,5	12,5	10,0
	95	1 000	6,0	12,5	10,0
PE 80	20	1	11,3	8	6,3
	80	1 000	4,0	8	6,3
PE 100	20	1	13,3	10	8,0
	80	1 000	5,0	10	8,0
PE-RT – Type 1	20	1	9,9	8	6,3
	95	1 000	3,4	8	6,3
PE-RT – Type 2	20	1	10,8	8	6,3
	95	1 000	3,6	8	6,3
PE-X	20	1	11,0	8	6,3
	95	1 000	4,4	8	6,3

[a] Valid for design coefficient C = 1,6. For other design coefficients, a different design stress σ_s is used. See ISO 16422.[15]

Table C.1 *(continued)*

Material	Test temperature	Test duration	σ_{tF}	MRS	σ_s
	°C	h	MPa	MPa	MPa
POM-C	20	1	31,5	10	6,3
	60	1 000	5,985	10	6,3
POM-H	20	1	39,69	10	6,3
	60	1 000	9,45	10	6,3
PP-B	20	1	15,75	8	6,3
	95	1 000	2,52	8	6,3
PP-H	20	1	20,79	10	6,3
	95	1 000	3,465	10	6,3
PP-R	20	1	15,75	8	6,3
	95	1 000	3,465	8	6,3
PP-RCT	20	1	15,0	11,2	9,0
	95	1 000	3,8	11,2	9,0
PPSU	20	1	57,1	32	22,4
	95	1 000	21,3	32	22,4
PSU	20	1	66,0	16	11,2
	95	1 000	9,7	16	11,2
PVC-C	20	1	43,0	20	10,0
	60	1 000	16,5	20	10,0
PVC-HI	20	1	30,0	25	10,0
	60	1 000	9,0	25	10,0
PVC-O 315	20	10	40,8	31,5	20,0[a]
	60	1 000	19,2	31,5	20,0[a]
PVC-O 355	20	10	46,0	35,5	22,0[a]
	60	1 000	22,0	35,5	22,0[a]
PVC-O 400	20	10	52,0	40,0	25,0[a]
	60	1 000	25,0	40,0	25,0[a]
PVC-O 450	20	10	60,0	45,0	28,0[a]
	60	1 000	29,0	45,0	28,0[a]
PVC-O 500	20	10	65,0	50,0	32,0[a]
	60	1 000	32,0	50,0	32,0[a]
PVC-U	20	1	42,0	25	10,0
	60	1 000	10,0	25	10,0
PVDF	20	1	32,6	25	16,0
	95	1 000	11,5	25	16,0

[a] Valid for design coefficient C = 1,6. For other design coefficients, a different design stress σ_s is used. See ISO 16422.[15]