

Third edition  
2000-12-15

**AMENDMENT 2**  
2013-04-01

---

---

## Plastics — Determination of Izod impact strength

### AMENDMENT 2: Precision data

*Plastiques — Détermination de la résistance au choc Izod*

*AMENDEMENT 2: Données de fidélité*

STANDARDSISO.COM : Click to view the full PDF of ISO 180:2000/Amd 2:2013



Reference number  
ISO 180:2000/Amd.2:2013(E)

© ISO 2013

STANDARDSISO.COM : Click to view the full PDF of ISO 180:2000/Amd 2:2013



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 2 to ISO 180:2000 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 2, *Mechanical properties*.

STANDARDSISO.COM : Click to view the full PDF of ISO 180:2000/Amd 2:2013

# Plastics — Determination of Izod impact strength

## AMENDMENT 2: Precision data

*Page 8, Clause 9*

Replace the paragraph with: “See Annex A.”.

*Page 10, Clause 10*

Add, at the end of the clause, the following new Annex A:

STANDARDSISO.COM : Click to view the full PDF of ISO 180:2000/Amd 2:2013

## Annex A (informative)

### Precision statement

**A.1** Table A.1 is based on a round-robin test involving six laboratories and three materials. All of the test samples were prepared and distributed by one source, except for notching, which was the responsibility of the laboratories involved. Notches were then verified by the laboratory responsible for specimen distribution. Each “test result” was the average of ten individual determinations. Each laboratory obtained and reported one test result for each material on two consecutive days. Test results are labelled according to laboratory and day (e.g. A1, A2, B1 and B2). Data from laboratory F were significantly different than data from the others; for this reason, they were excluded from the analysis and not reported.

**A.2** Table A.2 contains statistical results output from ASTM E691.

**CAUTION** — Due to the limited number of laboratories and materials, the following explanations of  $r$  and  $R$  (see A.3) are only intended to present a meaningful way of considering the approximate precision of the test method. The data in table A.2 should not be rigorously applied to the acceptance or rejection of material, as those data are specific to the round robin and might not be representative of other lots, conditions, materials or laboratories.

**A.3** The concepts of “ $r$ ” and “ $R$ ” in Table A.2: if  $s_r$  and  $s_R$  have been calculated from a large enough body of data, and for test results that were from one test determination, then:

- a) repeatability: two test results obtained within one laboratory shall be judged not equivalent if they differ by more than the  $r$  value for that material.  $r$  is the interval representing the critical difference between two test results for the same material, obtained by the same operator using the same equipment in the same laboratory.
- b) reproducibility: two test results obtained by different laboratories shall be judged not equivalent if they differ by more than the  $R$  value for that material.  $R$  is the interval representing the critical difference between two test results for the same material, obtained by different operators using different equipment in different laboratories.

Any judgement in accordance with A.3 above would have approximately 95 % (0,95) probability of being correct.

**Table A.1 — Data for two consecutive days, notched impact strength**

Notched impact strength in kilojoule per square metre (kJ/m<sup>2</sup>)

Laboratory/day	ABS		PBT		PBT GF30	
	Average	Std. dev.	Average	Std. dev.	Average	Std. dev.
A1	22,32	1,72	5,96	2,48	11,13	1,53
A2	22,46	0,64	6,46	0,96	11,31	0,84
	–	–	–	–	–	–
B1	20,70	0,32	4,81	0,37	10,12	0,62
B2	21,08	0,44	4,59	0,16	10,41	0,46
	–	–	–	–	–	–
C1	20,27	0,35	4,37	0,29	9,19	0,36
C2	19,97	0,27	4,11	0,13	8,93	0,31
	–	–	–	–	–	–
D1	20,57	0,41	5,09	0,12	9,85	0,52

**Table A.1** (continued)

D2	20,54	0,46	5,16	0,06	10,06	0,64
	–	–	–	–	–	–
E1	21,59	0,85	7,73	0,38	12,00	1,23
E2	20,59	0,56	7,61	0,28	11,96	1,61
	–	–	–	–	–	–
Average	21,01	–	5,59	–	10,50	–

**Table A.2 — Precision, notched impact strength**Notched impact strength in kilojoule per square metre (kJ/m<sup>2</sup>)

Material	Average	$s_r$	$s_R$	$r$	$R$
<b>ABS</b>	21,01	0,35	0,89	0,99	2,49
<b>PBT</b>	5,59	0,20	1,38	0,55	3,86
<b>PBT GF30</b>	10,50	0,15	1,14	0,42	3,19

$s_r$  = standard deviation within laboratory

$s_R$  = standard deviation between laboratories

$r$  = 95 % repeatability limit = 2,8  $s_r$

$R$  = 95 % reproducibility limit = 2,8  $s_R$

Page 10, Clause 10

At the end of the clause and the new Annex A, add the following new Bibliography:

## Bibliography

- [1] ASTM E691-11, *Standard Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method*

STANDARDSISO.COM : Click to view the full PDF of ISO 180:2000/Amd 2:2013