

---

---

**Plastics piping systems — Multilayer  
piping systems for outdoor gas  
installations — Specifications for  
systems**

*Systèmes de canalisations en plastique — Tubes multicouches  
destinés à l'alimentation en gaz à l'extérieur des bâtiments —  
Spécifications pour les systèmes*

STANDARDSISO.COM : Click to view the PDF of ISO 18225:2007



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 18225:2007



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

**Contents**

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>2</b>
<b>4 Pipes</b> .....	<b>6</b>
<b>5 Fittings</b> .....	<b>12</b>
<b>6 Fitness for purpose of the system</b> .....	<b>12</b>
<b>7 Marking and documentation</b> .....	<b>13</b>
<b>Annex A (normative) List of reference product standards</b> .....	<b>14</b>
<b>Annex B (normative) Testing resistance to gas constituents</b> .....	<b>15</b>
<b>Annex C (normative) Testing resistance to weathering of outer layer of M-pipes</b> .....	<b>16</b>
<b>Bibliography</b> .....	<b>18</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 18225 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 4, *Plastics pipes and fittings for the supply of gaseous fuels*.

STANDARDSISO.COM : Click to view the full PDF of ISO 18225:2007

## Introduction

The test methods used in this International Standard have been developed by ISO TC 138/SC 5 as far as possible. However, not all the required methods were in the SC 5 standards development work programme at the time of publication of this International Standard, so they have been placed in its annexes. When those methods are developed for other International Standards, these annexes will be redundant.

For multilayer pipe construction — consisting of a layer of a reference standard material, an adhesive and a non-stress designed layer — Procedure I and the relevant product standards are required to be followed for all aspects, excepting for those of delamination and — if applicable — oxygen permeation.

For example, layers can have the following purposes:

- the ability to withstand pressure;
- the ability to realize interlayer adhesion;
- the ability to block or greatly diminish incoming UV light and/or sunlight;
- the ability to mechanically protect the outside layer;
- the ability to control longitudinal expansion;
- the ability to give the multilayer pipe a colour (inside or outside layer).

Moreover, some characteristics can be combined in one layer.

[STANDARDSISO.COM](http://STANDARDSISO.COM) : Click to view the full PDF of ISO 18225:2007

# Plastics piping systems — Multilayer piping systems for outdoor gas installations — Specifications for systems

## 1 Scope

This International Standard specifies general and performance requirements for multilayer pipe systems based on pipes made from thermoplastics and intended to be used for gas supply.

It gives requirements for the design of pipe systems consisting of multilayer pipes based on thermoplastics and for which at least 60 % of the wall thickness is of a polymeric material. The polymeric material used for stress design layers and all inner layers must be polyethylene (PE) and/or crosslinked polyethylene (PE-X), in accordance with Annex A. The outer layers of metal multilayer pipes must be of either PE or PE-X.

NOTE For the purposes of this International Standard, PE-RT is considered as PE, while PE-X and adhesive layers are considered as thermoplastics materials.

This International Standard is applicable to systems intended to be operated at temperatures ranging from  $-20\text{ }^{\circ}\text{C}$  to  $40\text{ }^{\circ}\text{C}$ . It is applicable to pipes in these systems having a nominal diameter up to and including 630 mm, and to the supply of gaseous fuels of categories D (natural gas) and E (LPG vapour and natural gas or LPG vapour) (see ISO 13623).

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 161-1, *Thermoplastics pipes for the conveyance of fluids — Nominal outside diameters and nominal pressures — Part 1: Metric series*

ISO 497, *Guide to the choice of series of preferred numbers and of series containing more rounded values of preferred numbers*

ISO 1167 (all parts), *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure*

ISO 3126, *Plastics pipes — Measurement of dimensions*

ISO 4437, *Buried polyethylene (PE) pipes for the supply of gaseous fuels — Metric series — Specifications*

ISO 6447, *Rubber seals — Joint rings used for gas supply pipes and fittings — Specification for material*

ISO 8085-3, *Polyethylene fittings for use with polyethylene pipes for the supply of gaseous fuels — Metric series — Specifications — Part 3: Electrofusion fittings*

ISO 9080, *Plastics piping and ducting systems — Determination of the long-term hydrostatic strength of thermoplastics materials in pipe form by extrapolation*

ISO 9969, *Thermoplastics pipes — Determination of ring stiffness*

ISO 10146, *Crosslinked polyethylene (PE-X) pipes — Effect of time and temperature on the expected strength*

## ISO 18225:2007(E)

ISO 10838-1, *Mechanical fittings for polyethylene piping systems for the supply of gaseous fuels — Part 1: Metal fittings for pipes of nominal outside diameter less than or equal to 63 mm*

ISO 12162, *Thermoplastics materials for pipes and fittings for pressure applications — Classification and designation — Overall service (design) coefficient*

ISO 13968, *Plastics piping and ducting systems — Thermoplastics pipes — Determination of ring flexibility*

ISO 14531-1, *Plastics pipes and fittings — Crosslinked polyethylene (PE-X) pipe systems for the conveyance of gaseous fuels — Metric series — Specifications — Part 1: Pipes*

ISO 14531-2, *Plastics pipes and fittings — Crosslinked polyethylene (PE-X) pipe systems for the conveyance of gaseous fuels — Metric series — Specifications — Part 2: Fittings for heat-fusion jointing*

ISO 14531-3, *Plastics pipes and fittings — Crosslinked polyethylene (PE-X) pipe systems for the conveyance of gaseous fuels — Metric series — Specifications — Part 3: Fittings for mechanical jointing (including PE-X/metal transitions)*

ISO 16871, *Plastics piping and ducting systems — Plastics pipes and fittings — Method for exposure to direct (natural) weathering*

ISO 17454, *Plastics piping systems — Multilayer pipes — Test method for the adhesion of the different layers using a pulling rig*

ISO 17456:2006, *Plastics piping systems — Multilayer pipes — Determination of long-term strength*

ISO 24033:2006, *Pipes made of raised-temperature-resistance polyethylene (PE-RT) — Effect of time and temperature on the expected strength*

EN 573-3, *Aluminium and aluminium alloys — Chemical composition and form of wrought products — Part 3: Chemical composition*

EN 12117, *Plastics piping systems — Fittings, valves and ancillaries — Determination of gaseous flow rate/pressure drop relationships*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 3.1 Structural definitions

##### 3.1.1 Construction groups

###### 3.1.1.1

###### construction group A

group comprising multilayer pipes in which all the layers considered to be designed for stress-bearing are made of polymeric materials selected from the list of reference product standards

NOTE 1 See Annex A for the list of reference product standards.

NOTE 2 For this definition, adhesives are not considered as stress-designed layers.

###### 3.1.1.2

###### construction group B

group comprising multilayer pipes in which all the layers considered to be designed for stress-bearing are made of polymeric materials selected from the list of reference product standards and which include a stress bearing metallic layer

NOTE 1 See Annex A for the list of reference product standards.

NOTE 2 For this definition, adhesives are not considered as stress-designed layers.

**3.1.2****multilayer pipe**

pipe comprised of several stress-designed layers

**3.1.3****multilayer M pipe**

multilayer pipe comprised of polymers and one metallic layer, whose pipe wall thickness consists of at least 60 % of polymer layers

**3.1.4****multilayer P pipe**

pipe comprised of more than one stress-designed polymeric layer

EXAMPLE PE/PE-X.

**3.1.5****layer**

homogeneous circumferential section of pipe wall that has chemical and/or mechanical and/or physical characteristics different from those of its immediate neighbours

**3.1.6****inner layer**

layer in contact with the conveyed fluid

**3.1.7****outer layer**

layer exposed to the outer environment

**3.1.8****embedded layer**

layer between the outer and inner layer

**3.2 Geometrical definitions****3.2.1****nominal diameter**

$d_n$

specified diameter, in millimetres, assigned to a nominal size (DN/OD or DN/ID)

**3.2.2****outside diameter**

$d_e$

outside diameter measured through its cross-section at any point of a pipe, or the fitting end of a fitting, rounded to the next greater 0,1 mm

**3.2.3****mean outside diameter**

$d_{em}$

measured length of the outer circumference of the pipe divided by  $\pi$ , rounded up to the nearest 0,1 mm

NOTE The value for  $\pi$  is taken to be 3,142.

**3.2.4****inside diameter**

$d_i$

value of the measurement of the inside diameter through its cross-section at any point of a pipe, rounded to the next greater 0,1 mm

**3.2.5**

**mean inside diameter**

$d_{im}$   
average value of a number of equally spaced measurements of inside diameter in the same cross-section of the pipe, rounded to the next greater 0,1 mm

**3.2.6**

**metal layer standard dimension ratio**

$SDR_m$   
nominal outside diameter of the metal layer of the pipe divided by the nominal wall thickness of the metal layer (DN or  $OD/e_{n,m}$ )

**3.2.7**

**wall thickness**

difference between the pipe outside diameter and the pipe inside diameter divided by two

**3.2.8**

**nominal wall thickness**

$e_n$   
wall thickness corresponding to the minimum wall thickness at any point

**3.2.9**

**total wall thickness**

$e$   
measured total wall thickness at any point around the circumference of the component, rounded up to the nearest 0,1 mm

**3.2.10**

**layer wall thickness**

$e_l$   
measured wall thickness of the layer at any point around the circumference of the component, rounded up to the nearest 0,1 mm

**3.2.11**

**minimum layer wall thickness**

$e_{lmin}$   
minimum value of the measured wall thickness of a layer at any point around the circumference of the component, rounded up to the nearest 0,1 mm

**3.3 Definitions related to pressure**

**3.3.1**

**design pressure**

$p_D$   
highest pressure related to the circumstances for which the system has been designed and intended to be used

**3.4 Materials definitions**

**3.4.1**

**virgin material**

material in a form such as granules or powder that has not been subjected to use or processing other than that required for its manufacture and to which no reprocessible or recyclable material has been added

**3.4.2**

**own reprocessible material**

material prepared from rejected unused pipes and fittings, including trimmings from the production of pipes and fittings that will be reprocessed in a manufacturer's plant after having been previously processed by the same manufacturer by a process such as moulding or extrusion and for which the complete formulation is known

**3.4.3****reference product standard**

International Standard or Draft International Standard prepared by ISO/TC 138/SC 4, applicable for non-multilayer pipes, to which this International Standard can refer for clauses related to the materials, components (e.g. fittings), and fitness for purpose of the system

**3.5 Definitions related to material characteristics****3.5.1****lower confidence limit of the predicted hydrostatic strength**

$\sigma_{LPL}$   
quantity, with the dimensions of stress, expressed in megapascals (MPa), which represents the 97,5 % lower confidence limit of the predicted hydrostatic strength for a single value at a temperature,  $T$ , and time,  $t$ , and which is expressed as

$$\sigma_{LPL} = \sigma_{(T,t,0,975)}$$

**3.5.2****minimum required strength**

MRS

value of  $\sigma_{LPL}$  at a temperature 20 °C and a time 50 years [ $\sigma_{(20,50\text{years},0,975)}$ ], rounded down to the next smaller value of the R10 series or of the R20 series conforming to ISO 3, ISO 497 and ISO 12162, depending on the value of  $\sigma_{LPL}$

**3.5.3****lower confidence limit of the predicted hydrostatic pressure**

$P_{LPL}$

quantity with the dimension of pressure that represents the 97,5 % (one-sided) lower confidence limit of the predicted hydrostatic pressure at a temperature,  $T$ , and time,  $t$

**3.5.4****minimum required pressure**

MRP

value of  $P_{LPL}$  of a pipe at a temperature of 20 °C and a time 50 years, rounded to the nearest lower value of the R10 series conforming to ISO 3 and ISO 497

**3.5.5****overall service coefficient****overall design coefficient**

$C$

overall coefficient with a value greater than 1, which takes into consideration service conditions as well as properties of the components of a piping system other than those represented in the lower confidence limit

NOTE For gas systems, a minimum  $C$  value of 2,0 is allocated by this International Standard for the calculation, see 4.2.3.

**3.6 Terms related to service conditions****3.6.1****gaseous fuel**

any fuel which is in the gaseous state at a temperature of 15 °C and a pressure of 1 bar

NOTE 1 bar = 0,1 MPa =  $10^5$  Pa; 1 MPa = 1 N/mm<sup>2</sup>.

**3.6.2****category D gaseous fuel**

category of gaseous fuel, as defined in ISO 13623, corresponding to natural gas

**3.6.3**

**category E gaseous fuel**

category of gaseous fuel, as defined in ISO 13623, corresponding to LPG (liquefied petroleum gas) vapour

**3.6.4**

**maximum operating pressure**

**MOP**

maximum pressure at which a system can be operated continuously under normal conditions

## **4 Pipes**

### **4.1 Material**

#### **4.1.1 General**

All stress-designed and inner polymeric layers shall be reference materials in accordance with Annex A. The material of the outer layer need not to be a reference material.

Materials intended for the stress-bearing layers shall conform to the material requirements of the reference product standard(s). See Annex A. The pipe manufacturer shall declare the reference material standard applicable to his product, as listed in Annex A.

#### **4.1.2 Reprocessable materials**

Clean, own-reprocessable material (except PE-X), of the same polymer type as products manufactured to the reference product standard, may be added to the virgin material of the same type.

#### **4.1.3 Metallic materials**

Aluminium materials used shall be in accordance with EN 573-3.

#### **4.1.4 Product classification and construction group**

Multilayer pipes can include polymeric or metallic layers, which may have several purposes, including the ability to withstand pressure.

For the purposes of this International Standard, multilayer pipes are classified in two construction groups, A and B. The pipe manufacturer shall declare the construction group of the multilayer pipe.

## **4.2 General characteristics**

### **4.2.1 General**

When viewed without magnification, the internal and external surfaces of pipes shall be smooth, clean and free from scoring, cavities and other surface defects that would prevent conformance with this International Standard. The ends of the pipe shall be cut cleanly and square to the axis of the pipe.

The following information is required:

- outside diameter;
- wall thickness;
- thickness of the inner layer;

- thickness of the metal layer;
- thickness of the outer layer;
- and the tolerances.

Dimensions shall be measured in accordance with ISO 3126.

#### 4.2.2 Multilayer pipe construction

The joint line of the metallic layer shall be continuously welded.

#### 4.2.3 Minimum overall service (design) coefficient and design pressure

The minimum overall service (design) coefficient is 2, as used to calculate the design pressure,  $p_D$ , taking into account the maximum operating temperature.

Design stress is determined by dividing MRS or MRP by the design coefficient.

For the calculation of the design pressure of multilayer M pipes, the design coefficient of the inner layer shall be used.

For multilayer P pipes, the design coefficient of each layer shall be taken into account.

### 4.3 Dimensions of pipes

#### 4.3.1 General

The pipes are characterised by the nominal size related to the outside diameter (OD).

The values given by ISO 161-1 shall be used.

Pipe dimensions shall be selected taking into account the fitness for purpose (see Clause 6).

#### 4.3.2 Dimensions

##### 4.3.2.1 Measurements of dimensions

The dimensions of the pipes shall be measured in accordance with ISO 3126.

##### 4.3.2.2 Mean outside diameter and out-of-roundness (ovality) and their tolerances

The mean outside diameter,  $d_{e,m}$ , and the out-of-roundness (ovality) and their tolerances shall be in accordance with Table 1.

**Table 1 — Mean outside diameters and out-of-roundness**

Dimensions in millimetres

Nominal outside diameter	$d_{em,min}$	$d_{em,max}$	Maximum of absolute out-of-roundness (ovality)		
			Grade B	Grade K	Grade N
$d_n$					
16	16,0	16,3	1,2	1,2	1,2
20	20,0	20,3	1,2	1,2	1,2
25	25,0	25,3	1,5	1,5	1,2
32	32,0	32,3	2,0	2,0	1,3
40	40,0	40,4	2,4	2,4	1,4
50	50,0	50,4	3,0	3,0	1,4
63	63,0	63,4	3,8	3,8	1,5
75	75,0	75,5	—	—	1,6
90	90,0	90,6	—	—	1,8
110	110,0	110,7	—	—	2,2
125	125,0	125,8	—	—	2,5
140	140,0	140,9	—	—	2,8
160	160,0	161,0	—	—	3,2
180	180,0	181,1	—	—	3,6
200	200,0	201,2	—	—	4,0
225	225,0	226,4	—	—	4,5
250	250,0	251,5	—	—	5,0
280	280,0	281,7	—	—	9,8
315	315,0	316,9	—	—	11,1
355	355,0	357,2	—	—	12,5
400	400,0	402,4	—	—	14,0
450	450,0	452,7	—	—	15,6
500	500,0	503,0	—	—	17,5
560	560,0	563,4	—	—	19,6
630	630,0	633,8	—	—	22,1

Measurement of out-of-roundness shall be made at the point of manufacture according to ISO 3126.

For coiled pipe with  $d_n \leq 63$  mm, grade K applies; for pipe with  $d_n \geq 75$  mm, the maximum out-of-roundness shall be specified by agreement.

If applicable, the maximum out-of-roundness of the pipes shall conform to the geometrical characteristics of the reference material standard.

**4.3.2.3 Wall thickness and tolerances**

The values of the wall thickness shall be specified by the manufacturer. For pipe dimensions in relation to fittings sizes, see Clause 5.

NOTE 1 Pipes are preferably sized such that they are compatible with standardized inserts.

NOTE 2 Layers will be measured by means of, for example, a microscope.

**4.4 Mechanical properties**

**4.4.1 Long-term hydrostatic strength**

**4.4.1.1 General**

The long-term hydrostatic strength of the multilayer pipes shall be measured or calculated, as applicable. Consequently two procedures for determining the long-term hydrostatic strength of multilayer pipes are defined:

- Procedure I: calculation method;
- Procedure II: testing of pipe construction.

For design purposes, the value of the long-term hydrostatic strength of the multilayer pipes at a time 50 years and at a temperature of 20 °C shall be determined to obtain MRS or MRP.

Evaluation shall permit the calculation of the long-term hydrostatic strength at a time of 50 years at 40°C in accordance with the scope of this International Standard and taking into account the relevant extrapolation time factors given in ISO 9080.

#### 4.4.1.2 Procedure I (calculation method)

The long-term hydrostatic strength,  $\sigma_{LTHS}$ , shall be calculated using the reference lines (see Table A.1) or from data determined in accordance with ISO 9080 for each individual pressure-bearing polymer layer in accordance with ISO 17456. The addition rule related to each pressure-bearing layer assumes complete interlayer adhesion.

For validation of this calculation, a pressure test shall be carried out at an elevated temperature of at least 80 °C for 3 000 h on a pipe of each diameter group (see Table 2). This test shall be carried out at 95 % of the calculated LPL.

NOTE Procedure I can only be used for multilayer P pipes.

#### 4.4.1.3 Procedure II (testing method)

##### 4.4.1.3.1 General

Evaluate at least one diameter (the pipe with the lowest strength) of every similar construction type in accordance with ISO 9080 for each group of dimensions as defined in Table 2.

For multilayer M pipes, the pipe with the highest  $SDR_m$  of the metal layer shall be tested.

Table 2 — Dimension groups

	Dimension group		
	1	2	3
Nominal outside diameter, $d_n$ mm	≤ 63	> 63 and < 250	≥ 250

##### 4.4.1.3.2 Pressure strength of all diameters

All diameters of similar construction type, excluding the diameter tested in accordance with 4.4.1.3.1, shall undergo a confirmation testing of 3 000 h at a temperature of at least 80 °C, or in accordance with the reference material standard and at a pressure level of 95 % of LPL.

#### 4.4.1.4 Calculation of the control points

##### 4.4.1.4.1 Procedure I — P-pipes

Failure control points for each diameter for 22 h, 165 h and 1 000 h shall be calculated at a temperature of at least 80 °C, using ISO 17456:2006, Annex A.

##### 4.4.1.4.2 Procedure II — P-pipes and M-pipes

Failure control points for each diameter for 22 h, 165 h and 1 000 h shall be calculated at a temperature of at least 80 °C, using the 95 % value of the  $P_{LPL}$  line of the fully tested diameter.

**4.4.2 Resistance to RCP**

Any pipe product used for the transport of gaseous fuels shall be resistant to the phenomenon known as *rapid crack propagation* (RCP) in the intended service conditions. Multilayer pipe constructions shall comply with the following.

- a) The pipe shall have an RCP critical pressure  $\geq 1,5 \times \text{MOP}$ . The test shall be carried out on a pipe with a wall thickness equal to the maximum wall thickness of the production range.
- b) RCP shall be tested if pipes are intended to be used under the following conditions:
  - 1) in distribution systems with an MOP > 0, 1 bar and  $d_n \geq 250$  mm;
  - 2) in distribution systems with an MOP > 4 bar and  $d_n \geq 90$  mm;
  - 3) for RCP relating to PE and PE-X, according to ISO 4437 and ISO 14531-1, for test methods in accordance with ISO 13477 (S4 test) or ISO 13478 (Full Scale Test) and the conditions under which they are performed.

For severe service conditions (e.g. sub-zero temperatures) RCP testing is also recommended to establish the critical pressure at service temperature.

**4.4.3 Strength of the weld line of M pipe**

The strength of the weld line is covered by the control points for the resistance-to-inner-water-pressure test carried out according to ISO 17456.

**4.4.4 Resistance to slow crack growth of the outer layer (cone test) for M pipes**

When tested according to ISO 13480, the crack growth rate of the material of the outer layer shall be less than 10 mm/day.

Testing shall be carried out on pipe produced from material used for the outer layer.

**4.4.5 Structural performance**

**4.4.5.1 Multilayer M pipes**

The test pieces shall be tested in accordance with Table 3. When tested using the test method and parameters specified therein, the pipe shall have mechanical characteristics conforming to the requirements of Table 3.

**Table 3 — Structural performance of M pipes**

Characteristic	Requirement	Test parameters	Test method
Delamination	Adhesion force $\geq 1,5$ N/mm	In accordance with ISO 17454	ISO 17454

**4.4.5.2 Multilayer P pipes**

When tested in accordance with the test methods specified in Table 4 using the indicated parameters, the pipe shall have structural performance conforming to the requirements given in Table 4.

Table 4 — Structural performance of P pipes

Characteristic	Requirement	Test parameters		Test method
		Parameter	Value	
Integrity of the structure after deflection	$\geq 80$ % of the initial stiffness value	Deflection position of test piece	30 % of $d_{em}$ when applicable, at 0°, 45° and 90° from the upper plate	ISO 13968

For the determination of the integrity of the structure after deflection of multilayer P pipes, the following procedure shall be applied.

- Determine the initial ring stiffness of the pipe according to ISO 9969;
- Carry out the ring flexibility test according to ISO 13968;
- After a 1 h period for recovery, determine again the ring stiffness of the pipe according to ISO 9969. The ring stiffness of the multilayer P pipes shall be at least 80 % of the initial ring stiffness.

## 4.5 Physical properties

### 4.5.1 General

The applicable physical characteristics of each stress-designed and inner layer shall be checked in accordance with the corresponding clause of the reference product standard.

### 4.5.2 Additional requirements

Additional requirements for pipes and layers other than those referred to in 4.5.1 are given in Table 5.

Table 5 — Physical properties

Characteristic	Requirements	Test parameters		Test method
		Parameter	Value	
Resistance to gas constituents [M and P pipes]	No delamination	Conditioning under pressure	1 500h/23 °C, 0,4 $P_D$	Annex B
[M pipes]	No delamination	Delamination test	1,5 N/mm	ISO 17454
Oxidation induction time for outer layer (OIT)	$\geq 20$ min	Temperature	200 °C <sup>a</sup>	ISO 11357-6
Resistance to weathering (for non-black compounds only) [M pipes] <sup>b</sup>	No visible cracks at a bending strain of 3 %	Energy	$\geq 3,5$ GJ/m <sup>2</sup>	Annex C ISO 16871

<sup>a</sup> The test may be carried out at 210 °C provided that there is clear correlation with the results at 200 °C. In case of dispute the reference temperature shall be 200 °C.

<sup>b</sup> Resistance to weathering for P pipes is covered by the reference product standards.

## 5 Fittings

### 5.1 Fittings reference standards

Fittings shall comply with the performance requirements of the following standards:

- mechanical fittings, ISO 10838-1;
- electrofusion fittings, ISO 8085-3;
- PE-X electrofusion fittings, ISO 14531-2;
- mechanical fittings for PE-X, ISO 14531-3.

### 5.2 Materials

The materials from which the fitting components are made shall be such that the level of performance of these components is at least equal to that specified for the multilayer pipe connected to the fitting. ISO 10838-1 shall be used as a reference for fitting materials. Materials in contact with the multilayer pipe shall not prevent the pipe from conforming to this specification.

### 5.3 Dimensions

The values of the nominal inside diameter and the value of the nominal wall thickness and tolerances shall be provided by the supplier.

The tolerances on these values shall also be supplied.

### 5.4 Elastomeric seals

Elastomeric seals shall comply with ISO 6447.

## 6 Fitness for purpose of the system

The clauses related to the fitness of purpose of the relevant reference product standards shall be fulfilled for the respective kinds of pipe.

Fitness for purpose is described in the following International Standards:

- mechanical fittings, ISO 10838-1;
- electrofusion fittings, ISO 8085-3;
- PE-X electrofusion fittings, ISO 14531-2;
- mechanical fittings for PE-X, ISO 14531-3.

During installation of the fittings on the pipe, the aluminium layer and, in particular, the welded seam shall not be torn.

Tools and aids used for installation of the fittings shall not damage the pipe or fittings.

## 7 Marking and documentation

### 7.1 Legibility

Marking details shall be legible without magnification.

Legibility shall be maintained during storage, handling, installation and use.

### 7.2 Damage

Marking shall not initiate cracks or other types of failure in the product.

### 7.3 Minimum marking requirements

Marking details shall be in a colour that differs from that of the external pipe surface.

The marking frequency shall be at intervals not greater than 1 m.

Coils shall be sequentially marked with the length in metres which will indicate the length remaining on the coil. The marking shall include the information specified in Table 6.

Table 6 — Minimum information for marking

Information	Marking or symbol
Manufacturer or trademark	Name or symbol
Internal fluid	Gas
Design pressure	In accordance with national regulations
Dimensions	$d_n \times e_n$
Material and designation: layer construction and type of material required; description from outside to inside	e.g. PE-X-Al-PEX or PE80-PEX
Production period	Date, code (manufacturer's own reference)
Reference to this International Standard	ISO 18225

#### 7.3.1 Additional Instructions

The manufacturer shall provide clear assembly instructions containing at least the following information:

- instructions that pipe and fitting(s) belong together and are not interchangeable with other products;
- statement as to whether a coupler is fit for repeated assembly;
- if the manufacturer allows the use of a standard bending tool, a statement in the manufacturer's instructions that damage of the external coating shall be avoided if bending the pipe;
- information on gaseous flow rate/pressure drop relationship according to EN 12117;
- minimum bending radius;
- bending tools to be used;
- if a calibration tool is necessary to insert a stiffener, the manufacturer's instructions.

## Annex A (normative)

### List of reference product standards

At the time of publication of this International Standard, the reference product standards either published or under preparation are those listed in Table A1.

The list is applicable only to materials used in stress-designed layers.

Table A.1 — Reference product standards

Reference material	Reference material standard
PE	ISO 4437
PE-X	ISO 14531-1 (ISO 10146 for reference lines)
PE-RT	ISO 4437 (ISO 24033 for reference lines)