

---

---

**Welding consumables — Solid wire electrodes, solid strip electrodes, solid wires and solid rods for fusion welding of nickel and nickel alloys — Classification**

*Produits consommables pour le soudage — Fils-électrodes pleins, feuillets pleins, fils pleins et baguettes pleines pour le soudage par fusion du nickel et des alliages de nickel — Classification*

STANDARDSISO.COM : Click to view the PDF of ISO 18274:2010



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 18274:2010



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Contents

Page

Foreword .....	iv
Introduction.....	v
1 Scope .....	1
2 Normative references .....	1
3 Classification .....	1
4 Symbols and requirements .....	1
4.1 Symbols for the product form .....	1
4.2 Symbol for the chemical composition .....	2
5 Mechanical properties of the weld metal .....	9
6 Chemical analysis .....	9
7 Rounding procedure .....	9
8 Retest.....	9
9 Technical delivery conditions .....	9
10 Designation .....	9
Annex A (informative) Description of consumables classes .....	11
Annex B (informative) System for designation of welding filler metals.....	18
Annex C (informative) Corresponding national classifications and typical weld metal tensile strengths .....	19
Bibliography.....	24

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 18274 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

This second edition cancels and replaces the first edition (ISO 18274:2004), of which it constitutes a technical revision. It also incorporates the Technical Corrigenda ISO 18274:2004/Cor.1:2005 and ISO 18274:2004/Cor.2:2006.

Requests for official interpretation of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 3 via your national standards body. A complete listing of these bodies can be found at [www.iso.org](http://www.iso.org).

## Introduction

For nickel welding consumables, there is no unique relationship between the product form (solid wire electrode, solid strip electrode, solid wire or solid rod) and the welding process used (e.g. gas shielded metal arc welding, gas tungsten arc welding, plasma arc welding, submerged arc welding, strip overlay welding, laser welding or other welding processes). For this reason, the solid wire electrode, solid strip electrode, solid wire or solid rod may be classified on the basis of any of the above product forms and can be used as appropriate, for more than one of the above processes.

STANDARDSISO.COM : Click to view the full PDF of ISO 18274:2010

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 18274:2010

# Welding consumables — Solid wire electrodes, solid strip electrodes, solid wires and solid rods for fusion welding of nickel and nickel alloys — Classification

## 1 Scope

This International Standard specifies requirements for classification of solid wire electrodes, solid strip electrodes, solid wires and solid rods for fusion welding of nickel and nickel alloys. The classification of the solid wire electrodes, solid strip electrodes, solid wires and solid rods is based on their chemical composition.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 80000-1:2009, *Quantities and units — Part 1: General*

## 3 Classification

The classification is divided into two parts:

- a) the first part indicates the product form, being solid wire electrode, solid strip electrode, solid wire or solid rod, see 4.1;
- b) the second part gives a numerical symbol indicating the chemical composition of the solid wire electrode, solid strip electrode, solid wire or solid rod, see Table 1.

## 4 Symbols and requirements

### 4.1 Symbols for the product form

The symbol for the solid wire electrode, solid wire or solid rod shall be “S”. The symbol for the solid strip electrode shall be “B”.

NOTE One product form can be used for more than one welding process.

## 4.2 Symbol for the chemical composition

The initial symbol "Ni" in Table 1 identifies the welding consumable as a nickel base alloy. The following four digits indicate the chemical composition of the solid wire electrode, solid strip electrode, solid wire or solid rod, determined under conditions given in Clause 6. The first digit is an indicator of the alloy group as follows:

- 1 significant molybdenum addition without significant chromium addition (nickel-molybdenum alloys);
- 2 no significant alloy addition;
- 4 significant copper addition (nickel-copper alloys);
- 5 significant copper additions with aluminium and titanium for precipitation hardening;
- 6 significant chromium addition, with iron less than 25 % (by mass) (nickel-chromium-iron and nickel-chromium-molybdenum alloys);
- 7 same as 6, but with aluminium and titanium for precipitation hardening;
- 8 significant chromium addition, with iron more than 25 % (by mass) (nickel-iron-chromium alloys).

The remaining digits indicate the alloy composition of the welding consumable. A description of common uses of each welding consumable alloy is given in Annex A. The basis of the system of designation is described in Annex B.

NOTE In addition, the chemical symbol can be used.

STANDARDSISO.COM : Click to view the full PDF of ISO 18274:2010

Table 1 — Symbols and chemical composition requirements for solid wire electrodes, solid strip electrodes, solid wires and solid rods

Alloy symbols		Chemical composition, % (by mass) <sup>a</sup>													
Numerical	Chemical	C	Mn	Fe	Si	Cu	Ni <sup>b</sup>	Co	Al	Ti	Cr	Nb <sup>c</sup>	Mo	W	Others <sup>d, e</sup>
<b>Nickel</b>															
Ni 2061	NiTi3	0,15	1,0	1,0	0,7	0,25	≥92,0	—	1,5	2,0 to 3,5	—	—	—	—	P 0,03
<b>Nickel-Copper</b>															
Ni 4060	NiCu30Mn3Ti	0,15	4,0	2,5	1,2	28,0 to 32,0	≥62,0	—	1,2	1,5 to 3,0	—	0,3	—	—	—
Ni 4061	NiCu30Mn3Nb	0,15	4,0	2,5	1,25	28,0 to 32,0	≥60,0	—	1,0	1,0	—	3,0	—	—	—
Ni 5504	NiCu25Al3Ti	0,25	1,5	2,0	1,0	≥20,0	63,0 to 70,0	—	2,0 to 4,0	0,3 to 1,0	—	—	—	—	P 0,03
<b>Nickel-Chromium</b>															
Ni 6072	NiCr44Ti	0,01 to 0,10	0,20	0,50	0,20	0,50	≥52,0	—	—	0,3 to 1,0	42,0 to 46,0	—	—	—	—
Ni 6073	NiCr38AlNbTi	0,03	0,50	1,0	0,30	0,30	≥63,0	1,0	0,75 to 1,20	0,25 to 0,75	36,0 to 39,0	0,25 to 1,00	0,50	—	P 0,02 S 0,015 B 0,003 Zr 0,02
Ni 6076	NiCr20	0,08 to 0,15	1,0	2,00	0,30	0,50	≥75,0	—	0,4	0,15 to 0,50	19,0 to 21,0	—	—	—	P 0,03
Ni 6082	NiCr20Mn3Nb	0,10	2,5 to 3,5	3,0	0,5	0,5	≥67,0	—	—	0,7	18,0 to 22,0	2,0 to 3,0	—	—	P 0,03
<b>Nickel-Chromium-Iron</b>															
Ni 6002	NiCr21Fe18Mo9	0,05 to 0,15	1,0	17,0 to 20,0	1,0	0,5	≥44,0	0,5 to 2,5	—	—	20,5 to 23,0	—	8,0 to 10,0	0,2 to 1,0	P 0,04 S 0,03
Ni 6025	NiCr25Fe10AlY	0,15 to 0,25	0,5	8,0 to 11,0	0,5	0,1	≥59,0	1,0	1,8 to 2,4	0,1 to 0,2	24,0 to 26,0	—	—	—	Y 0,05 to 0,12; Zr 0,01 to 0,10

Table 1 (continued)

Alloy symbols		Chemical composition, % (by mass) <sup>a</sup>													
Numerical	Chemical	C	Mn	Fe	Si	Cu	Ni <sup>b</sup>	Co	Al	Ti	Cr	Nb <sup>c</sup>	Mo	W	Others <sup>d, e</sup>
Ni 6030	NiCr30Fe15Mo5W	0,03	1,5	13,0 to 17,0	0,8	1,0 to 2,4	≥36,0	5,0	—	—	28,0 to 31,5	0,3 to 1,5	4,0 to 6,0	1,5 to 4,0	P 0,04 S 0,02
Ni 6043	NiCr30Fe9Nb2	0,04	3,0	7,0 to 12,0	0,5	0,30	≥54,0	—	0,50	0,5	28,0 to 31,5	1,0 to 2,5	0,50	—	—
Ni 6045	NiCr28Fe23Si3	0,05 to 0,12	1,0	21,0 to 25,0	2,5 to 3,0	0,3	≥40,0	1,0	0,30	—	26,0 to 29,0	—	—	—	P 0,020 S 0,010
Ni 6052	NiCr30Fe9	0,04	1,0	7,0 to 11,0	0,5	0,3	≥54,0	—	1,1	1,0	28,0 to 31,5	0,10	0,5	—	Al + Ti < 1,5
Ni 6054	NiCr29Fe9	0,04	1,0	7,0 to 11,0	0,50	0,30	≥51,0	0,12	1,10	1,0	28,0 to 31,5	0,5 to 1,0	0,50	—	P 0,02 S 0,015
Ni 6055	NiCr29Fe5Mo4Nb3	0,03	1,0	14,4	0,50	0,30	52,0 to 62,0	0,10	0,50	0,50	28,5 to 31,0	2,1 to 4,0	3,0 to 5,0	—	P 0,02 S 0,015 B 0,003 Zr 0,02
Ni 6062	NiCr15Fe8Nb	0,08	1,0	6,0 to 10,0	0,3	0,5	≥70,0	—	—	—	14,0 to 17,0	1,5 to 3,0	—	—	P 0,03
Ni 6176	NiCr16Fe6	0,05	0,5	5,5 to 7,5	0,5	0,1	≥76,0	0,05	—	—	15,0 to 17,0	—	—	—	—
Ni 6601	NiCr23Fe15Al	0,10	1,0	20,0	0,5	1,0	58,0 to 63,0	—	1,0 to 1,7	—	21,0 to 25,0	—	—	—	P 0,03
Ni 6693	NiCr29Fe4Al3	0,15	1,0	2,5 to 6,0	0,5	0,5	≥53,0	—	2,5 to 4,0	1,0	27,0 to 31,0	0,5 to 2,5	—	—	P 0,03 S 0,01
Ni 6701	NiCr36Fe7Nb	0,35 to 0,50	0,5 to 2,0	7,0	0,5 to 2,0	—	42,0 to 48,0	—	—	—	33,0 to 39,0	0,8 to 1,8	—	—	—
Ni 6975	NiCr25Fe13Mo6	0,03	1,0	10,0 to 17,0	1,0	0,7 to 1,2	≥47,0	—	—	0,70 to 1,50	23,0 to 26,0	—	5,0 to 7,0	—	P 0,03 S 0,03
Ni 6985	NiCr22Fe20Mo7Cu2	0,01	1,0	18,0 to 21,0	1,0	1,5 to 2,5	≥40,0	5,0	—	—	21,0 to 23,5	0,50	6,0 to 8,0	1,5	P 0,04 S 0,03

Table 1 (continued)

Alloy symbols		Chemical composition, % (by mass) <sup>a</sup>													
Numerical	Chemical	C	Mn	Fe	Si	Cu	Ni <sup>b</sup>	Co	Al	Ti	Cr	Nb <sup>c</sup>	Mo	W	Others <sup>d, e</sup>
Ni 7069	NiCr15Fe7Nb	0,08	1,0	5,0 to 9,0	0,50	0,50	≥70,0	—	0,4 to 1,0	2,0 to 2,7	14,0 to 17,0	0,70 to 1,20	—	—	P 0,03
Ni 7092	NiCr15Ti3Mn	0,08	2,0 to 2,7	8,0	0,3	0,5	≥ 67,0	—	—	2,5 to 3,5	14,0 to 17,0	—	—	—	P 0,03
Ni 7718	NiCr19Fe19Nb5Mo3	0,08	0,3	24,0	0,3	0,3	50,0 to 55,0	—	0,2 to 0,8	0,7 to 1,1	17,0 to 21,0	4,8 to 5,5	2,8 to 3,3	—	B 0,006 P 0,015
Ni 8025	NiFe30Cr29Mo	0,02	1,0 to 3,0	30,0	0,5	1,5 to 3,0	35,0 to 40,0	—	0,2	1,0	27,0 to 31,0	—	2,5 to 4,5	—	—
Ni 8065	NiFe30Cr21Mo3	0,05	1,0	≥22,0	0,5	1,5 to 3,0	38,0 to 46,0	—	0,2	0,6 to 1,2	19,5 to 23,5	—	2,5 to 3,5	—	P 0,03 S 0,03
Ni 8125	NiFe26Cr25Mo	0,02	1,0 to 3,0	30,0	0,5	1,5 to 3,0	37,0 to 42,0	—	0,2	1,0	23,0 to 27,0	—	3,5 to 7,5	—	—
<b>Nickel-Molybdenum</b>															
Ni 1001	NiMo28Fe	0,08	1,0	4,0 to 7,0	1,0	0,5	≥55,0	2,5	—	—	1,0	—	26,0 to 30,0	1,0	V 0,20 to 0,40 S 0,03
Ni 1003	NiMo17Cr7	0,04 to 0,08	1,0	5,0	1,0	0,50	≥65,0	0,20	—	—	6,0 to 8,0	—	15,0 to 18,0	0,50	V 0,50 S 0,02
Ni 1004	NiMo25Cr5Fe5	0,12	1,0	4,0 to 7,0	1,0	0,5	≥62,0	2,5	—	—	4,0 to 6,0	—	23,0 to 26,0	1,0	V 0,60 P 0,04 S 0,03
Ni 1008	NiMo19WCr	0,1	1,0	10,0	0,50	0,50	≥60,0	—	—	—	0,5 to 3,5	—	18,0 to 21,0	2,0 to 4,0	—
Ni 1009	NiMo20WCu	0,1	1,0	5,0	0,5	0,3 to 1,3	≥65,0	—	1,0	—	—	—	19,0 to 22,0	2,0 to 4,0	—
Ni 1024	NiMo25	0,03	0,80	2,0	0,80	0,50	≥59,0	1,0	0,50	—	7,0 to 9,0	—	24,0 to 26,0	—	P 0,030 S 0,015

Table 1 (continued)

Alloy symbols		Chemical composition, % (by mass) <sup>a</sup>														
Numerical	Chemical	C	Mn	Fe	Si	Cu	Ni <sup>b</sup>	Co	Al	Ti	Cr	Nb <sup>c</sup>	Mo	W	Others <sup>d, e</sup>	
Ni 1062	NiMo24Cr8Fe6	0,01	1,0	5,0 to 8,0	0,1	0,5	≥62,0	—	0,5	—	6,0 to 10,0	—	21,0 to 25,0	—	—	
Ni 1066	NiMo28	0,02	1,0	2,0	0,1	0,5	≥64,0	1,0	—	0,5	1,0	—	26,0 to 30,0	1,0	P 0,04 S 0,03	
Ni 1067	NiMo30Cr	0,01	3,0	1,0 to 3,0	0,1	0,2	≥65,0	3,0	0,5	0,2	1,0 to 3,0	0,2	27,0 to 32,0	3,0	V 0,20 P 0,03	
Ni 1069	NiMo28Fe4Cr	0,01	1,0	2,0 to 5,0	0,1	0,5	≥65,0	1,0	0,1 to 0,5	0,3	0,5 to 1,5	0,5	26,0 to 30,0	—	—	
<b>Nickel-Chromium-Molybdenum</b>																
Ni 6012	NiCr22Mo9	0,05	1,0	3,0	0,5	0,5	≥58,0	—	0,4	0,4	20,0 to 23,0	1,5	8,0 to 10,0	—	—	
Ni 6022	NiCr21Mo13Fe4W3	0,01	0,5	2,0 to 6,0	0,08	0,5	≥49,0	2,5	—	—	20,0 to 22,5	—	12,5 to 14,5	2,5 to 3,5	V 0,3	
Ni 6035	NiCr33Mo8	0,05	0,5	2,0	0,6	0,30	≥49,0	1,00	0,40	0,20	32,25 to 34,25	0,50	7,60 to 9,00	0,60	V 0,20 P 0,030 S 0,015	
Ni 6057	NiCr30Mo11	0,02	1,0	2,0	1,0	—	≥53,0	—	—	—	29,0 to 31,0	—	10,0 to 12,0	—	V 0,4 P 0,04 S 0,03	
Ni 6058	NiCr21Mo20	0,01	0,5	1,5	0,10	0,50	≥52,0	0,3	0,4	—	20,0 to 23,0	—	19,0 to 21,0	0,3	N 0,02 to 0,15 P 0,015 S 0,010	
Ni 6059	NiCr23Mo16	0,01	0,5	1,5	0,1	0,5	≥56,0	0,3	0,1 to 0,4	0,5	22,0 to 24,0	—	15,0 to 16,5	—	V 0,3	
Ni 6200	NiCr23Mo16Cu2	0,01	0,5	3,0	0,08	1,3 to 1,9	≥52,0	2,0	0,5	—	22,0 to 24,0	—	15,0 to 17,0	—	P 0,025	
Ni 6205	NiCr25Mo16	0,03	0,5	1,0	0,5	0,2	≥55,0	0,2	0,4	0,4	24,0 to 26,0	—	14,0 to 16,0	0,3	—	

Table 1 (continued)

Alloy symbols		Chemical composition, % (by mass) <sup>a</sup>													
Numerical	Chemical	C	Mn	Fe	Si	Cu	Ni <sup>b</sup>	Co	Al	Ti	Cr	Nb <sup>c</sup>	Mo	W	Others <sup>d, e</sup>
Ni 6276	NiCr15Mo16Fe6W4	0,02	1,0	4,0 to 7,0	0,08	0,5	≥50,0	2,5	—	—	14,5 to 16,5	—	15,0 to 17,0	3,0 to 4,5	V 0,35 P 0,04 S 0,03
Ni 6452	NiCr20Mo15	0,01	1,0	1,5	0,1	0,5	≥56,0	—	—	—	19,0 to 21,0	0,4	14,0 to 16,0	—	V 0,4
Ni 6455	NiCr16Mo16Ti	0,01	1,0	3,0	0,08	0,5	≥56,0	2,0	—	0,7	14,0 to 18,0	—	14,0 to 18,0	0,5	P 0,04 S 0,03
Ni 6625	NiCr22Mo9Nb	0,1	0,5	5,0	0,5	0,5	≥58,0	—	0,4	0,4	20,0 to 23,0	3,2 to 4,1	8,0 to 10,0	—	—
Ni 6650	NiCr20Fe14Mo11WN	0,03	0,5	12,0 to 16,0	0,5	0,3	≥44,0	1,0	0,05 to 0,50	—	19,0 to 21,0	0,05 to 0,50	9,5 to 12,5	0,5 to 2,5	N 0,05 to 0,20; S 0,010 V 0,30
Ni 6660	NiCr22Mo10W3	0,03	0,5	2,0	0,5	0,3	≥58,0	0,2	0,4	0,4	21,0 to 23,0	0,2	9,0 to 11,0	2,0 to 4,0	—
Ni 6686	NiCr21Mo16W4	0,01	1,0	5,0	0,08	0,5	≥49,0	—	0,5	0,25	19,0 to 23,0	—	15,0 to 17,0	3,0 to 4,4	S 0,02
Ni 7725	NiCr21Mo8Nb3Ti	0,03	0,3	≥8,0	0,20	—	55,0 to 59,0	—	0,35	1,0 to 1,7	19,0 to 22,5	2,75 to 4,00	7,0 to 9,5	—	—
<b>Nickel-Chromium-Cobalt</b>															
Ni 6160	NiCr28Co30Si3	0,02 to 0,10	1,0	3,5	2,4 to 3,0	0,5	≥30,0	27,0 to 32,0	0,40	0,2 to 0,6	26,0 to 29,0	0,3	0,7	0,5	P 0,03
Ni 6617	NiCr22Co12Mo9	0,05 to 0,15	1,0	3,0	1,0	0,5	≥44,0	10,0 to 15,0	0,8 to 1,5	0,6	20,0 to 24,0	—	8,0 to 10,0	0,5	P 0,03
Ni 7090	NiCr20Co18Ti3	0,13	1,0	1,5	1,0	0,2	≥50,0	15,0 to 18,0	1,0 to 2,0	2,0 to 3,0	18,0 to 21,0	—	—	—	f

Table 1 (continued)

Alloy symbols		Chemical composition, % (by mass) <sup>a</sup>													
Numerical	Chemical	C	Mn	Fe	Si	Cu	Ni <sup>b</sup>	Co	Al	Ti	Cr	Nb <sup>c</sup>	Mo	W	Others <sup>d, e</sup>
Ni 7263	NiCr20Co20Mo6Ti2	0,04 to 0,08	0,6	0,7	0,4	0,2	≥47,0	19,0 to 21,0	0,3 to 0,6	1,9 to 2,4	19,0 to 21,0	—	5,6 to 6,1	—	Al+Ti: 2,4 to 2,8, S ≤0,007, Ag ≤0,000 5, B ≤0,005, Bi ≤0,000 1
<b>Nickel-Chromium-Tungsten</b>															
Ni 6231	NiCr22W14Mo2	0,05 to 0,15	0,3 to 1,0	3,0	0,25 to 0,75	0,50	≥48,0	5,0	0,2 to 0,5	—	20,0 to 24,0	—	1,0 to 3,0	13,0 to 15,0	P 0,03
<b>Any other agreed composition</b>															
	Ni Z <sup>9</sup>	Any other agreed composition with a minimum nickel content greater than the minimum value for any other element													

**a** Single values for all elements are maxima except where the ≥ sign is used.

**b** Up to 1 % (by mass) of the nickel content can be cobalt unless otherwise specified. For certain applications, lower cobalt levels may be required and should be agreed between contracting parties.

**c** Up to 20 % (by mass) of the niobium content can be tantalum.

**d** The total of unspecified elements shall not exceed 0,5 % (by mass).

**e** Phosphorus 0,020 % (by mass) maximum and sulfur 0,015 % (by mass) maximum unless otherwise stated.

**f** Ag ≤ 0,000 5 % (by mass), B ≤ 0,020 % (by mass), Bi ≤ 0,000 1 % (by mass), Pb ≤ 0,002 0 % (by mass), Zr ≤ 0,15 % (by mass).

**g** Consumables for which the chemical composition is not listed shall be symbolized similarly and prefixed by the letters Ni Z. The chemical composition ranges are not specified and it is possible that two electrodes with the same Z-classification are not interchangeable.

NOTE Corresponding national classifications are shown in Annex C.

## 5 Mechanical properties of the weld metal

Mechanical properties of the weld metal are not part of the classification.

NOTE Information on typical weld metal tensile strengths, where they exist, can be found in Annex C.

## 6 Chemical analysis

Chemical analysis shall be performed on specimens of the product or the stock from which it is made. Any analytical technique can be used, but in case of dispute, reference shall be made to established published methods, agreed between the contracting parties.

NOTE 1 The shielding gas or flux can influence the chemical composition of the all-weld metal as compared to the chemical analysis of the product or stock.

NOTE 2 See Annex B.

## 7 Rounding procedure

For purposes of determining compliance with the requirements of this International Standard, the actual test values obtained shall be subjected to the rounding rules of ISO 80000-1:2009, Annex B, Rule A. If the measured values are obtained by equipment calibrated in units other than those of this International Standard, the measured values shall be converted to the units of this International Standard before rounding. If an average value is to be compared to the requirements of this International Standard, rounding shall be done only after calculating the average. In the case where the testing standard cited in the normative references of this International Standard contains instructions for rounding that conflict with the instructions of this International Standard, the rounding requirements of the testing standard shall apply. The rounded results shall fulfil the requirements of the appropriate table for the classification under test.

## 8 Retest

If any test fails to meet the requirement, that test shall be repeated twice. The results of both retests shall meet the requirement. Specimens for the retest may be taken from the original test sample or from a new test sample. For chemical analysis, retest need only be for those specific elements that failed to meet their test requirement. If the results of one or both retests fail to meet the requirement, the material under test shall be considered as not meeting the requirements of this International Standard for that classification.

In the event that, during preparation or after completion of any test, it is clearly determined that prescribed or proper procedures were not followed in preparing the weld test sample or test specimen(s), or in conducting the tests, the test shall be considered invalid, without regard to whether the test was actually completed or whether the test results met, or failed to meet, the requirement. That test shall be repeated, following proper prescribed procedures. In this case, the requirement for doubling the number of test specimens does not apply.

## 9 Technical delivery conditions

Technical delivery conditions shall meet the requirements of ISO 544 and ISO 14344.

## 10 Designation

The designation of solid wire electrodes, solid strip electrodes, solid wires and solid rods shall follow the principle given in the examples below.

## ISO 18274:2010(E)

EXAMPLE 1 A solid wire (S) for gas shielded metal arc welding having a chemical composition within the limits for the alloy symbol 6625 (NiCr22Mo9Nb) of Table 1 is designated:

**ISO 18274 – S Ni 6625**

or alternatively

**ISO 18274 – S Ni 6625 (NiCr22Mo9Nb)**

EXAMPLE 2 A solid rod (S) for gas tungsten arc welding is designated:

**ISO 18274 – S Ni 6625**

or alternatively

**ISO 18274 – S Ni 6625 (NiCr22Mo9Nb)**

EXAMPLE 3 A solid strip (B) for submerged arc or electroslag welding is designated:

**ISO 18274 – B Ni 6625**

or alternatively

**ISO 18274 – B Ni 6625 (NiCr22Mo9Nb)**

where:

ISO 18274 is the number of this International Standard;

S or B is the product form (see 4.1);

Ni 6625 is the chemical composition of the welding consumable (see Table 1);

NiCr22Mo9Nb is the optional chemical symbol of the welding consumable (see Table 1).

## Annex A (informative)

### Description and uses of welding consumable alloys

#### A.1 General

The following non-exhaustive details are included to provide an indication of the typical application for which individual classes of consumables are commonly used. More particular information on welding consumable selection, information, and techniques to be applied when using consumables depositing nickel-base alloys should be sought from the manufacturer.

#### A.2 Nickel

##### Ni 2061

Consumables of this classification are used for welding wrought and cast forms of commercially pure nickel (e.g. UNS N02200 or UNS N02201) and welding the clad side of nickel-clad steel, and surfacing of steel dissimilar metal welding.

#### A.3 Nickel-Copper

##### Ni 4060, Ni 4061

Consumables of these classifications are used for welding nickel-copper alloys (e.g. UNS N04400) to each other, welding the clad side of nickel-copper alloy-clad steel, and surfacing of steel.

##### Ni 5504

Consumables of this classification are used for welding age-hardening nickel-copper alloy (UNS N05500) to itself using gas tungsten arc welding, gas shielded metal arc welding, submerged arc welding, and plasma arc welding. The weld metal age hardens on heat treatment.

#### A.4 Nickel-Chromium

##### Ni 6072

Consumables of this classification are used for gas shielded metal arc welding and gas tungsten arc welding of 50/50 (by mass) nickel-chromium alloy, overlaying steel, cladding nickel-chromium alloy on to nickel-iron-chromium tubing, and casting repair. The weld metal is resistant to high-temperature corrosion, including fuel-ash corrosion in atmospheres containing sulfur and vanadium.

##### Ni 6073

The nominal composition of this classification is 60 Ni, 38 Cr, 0,9 Al, 0,5 Nb, where the numbers are percentages by mass. Consumables of this classification are used for overlay cladding of ferrous materials used in high-temperature applications, and welding of nickel-chromium-iron alloy having UNS number N06690 to itself and to steels. Welds made with this composition are particularly resistant to high-temperature oxidation, carburization, and sulfidation.

**Ni 6076**

Consumables of this classification are used for welding nickel-chromium-iron alloys (e.g. UNS N06600, N06075) to each other, for the clad side of joints in steel clad with nickel-chromium-iron alloy, for surfacing steel with nickel-chromium-iron weld metal, and for joining steel to nickel-base alloys using gas tungsten arc welding, gas shielded metal arc welding, submerged arc welding, and plasma arc welding.

**Ni 6082**

Consumables of this classification are used for welding nickel-chromium alloys (e.g. UNS N06075, UNS N07080), nickel-chromium-iron alloys (e.g. UNS N06600, UNS N06601), and nickel-iron-chromium alloys (e.g. UNS N08800 and UNS N08801). They are also used for cladding and for welding dissimilar metal joints. They may be used for welding nickel steels for cryogenic applications.

**A.5 Nickel-Chromium-Iron**

**Ni 6002**

Consumables of this classification are used for welding low-carbon nickel-chromium-molybdenum alloys (especially UNS N06002) for welding the clad side in steel clad with low-carbon nickel-chromium-molybdenum alloy, and for welding low-carbon nickel-chromium-molybdenum alloys to steel and other nickel-base alloys.

**Ni 6025**

Consumables of these classifications are used for welding nickel-base alloys of similar composition (e.g. UNS N06025, UNS N06603). Welds exhibit resistance to oxidation, carburization, and sulfidation and are used at temperatures up to 1 200 °C.

**Ni 6030**

Consumables of this classification are used for welding nickel-chromium-molybdenum alloy (e.g. UNS N06030) to itself, to steel, to other nickel-base alloys, and for cladding steel with nickel-chromium-molybdenum weld metal using gas tungsten arc welding, gas shielded metal arc welding, and plasma arc welding.

**Ni 6043**

Consumables of this classification are used for producing corrosion-resistant overlays on low-alloy and stainless steels. They may also be used for welding high chromium-nickel base alloys (e.g. UNS N06690) and for dissimilar metal joints.

**Ni 6045**

The nominal chemical composition of consumables of this classification is 46 Ni, 28 Cr, 23 Fe, 2,7 Si, where the numbers are percentages by mass. Filler metal of this classification is used for welding nickel-chromium-iron alloy having UNS number N06045 to itself, to steel, and to other nickel-base alloys.

**Ni 6052**

Consumables of this classification are used for welding high chromium-nickel base alloys (e.g. UNS N06690). They may also be used for producing corrosion-resistant overlays on low-alloy and stainless steels and for dissimilar metal joints.

**Ni 6054**

The nominal composition of consumables of this classification is 60 Ni, 29 Cr, 9 Fe, 0,75 Nb, where the numbers are percentages by mass. Consumables of this classification are used for welding nickel-chromium-iron alloy having UNS number N06690 to itself, to steels, and to weld overlay steels. Welds made with this composition are particularly resistant to ductility-dip cracking (DDC), and oxide inclusions.

**Ni 6055**

The nominal composition of this classification is 57 Ni, 29 Cr, 8 Fe, 4 Mo, 2,5 Nb, where the numbers are percentages by mass. Consumables of this classification are used for welding nickel-chromium-iron alloy having UNS number N06690 to itself, to steels, and to weld overlay steels. Welds made with this composition are particularly resistant to ductility-dip cracking (DDC), and oxide inclusions.

**Ni 6062**

Consumables of this classification are used for welding nickel-chromium-iron alloy (e.g. UNS N06600) to itself using gas tungsten arc welding, gas shielded metal arc welding, submerged arc welding, and plasma arc welding. The higher niobium content of these consumables is intended to minimize cracking where high welding stresses are encountered, as in thick-section base metal.

**Ni 6176**

Consumables of this classification are used for welding nickel-chromium-iron alloys (e.g. UNS N06600 and UNS N06601) for the clad side of joints in steel with nickel-chromium-iron alloy and for surfacing steel. They have good dissimilar metal welding capability. They may be used for applications at temperatures up to 980 °C but their weld metal does not exhibit optimum oxidation resistance and strength above 820 °C.

**Ni 6601**

Consumables of this classification are used for welding nickel-chromium-iron-aluminium alloy (e.g. UNS N06601) to itself and to other high-temperature compositions using gas tungsten arc welding. It is used for severe applications where the exposure temperature can exceed 1 150 °C.

**Ni 6693**

The nominal composition of consumables of this classification is 59 Ni, 29 Cr, 4 Fe, 3 Al, where the numbers are percentages by mass. Consumables of this classification are used for welding nickel-chromium-iron alloy having UNS number N06693 to itself, to steels, and to weld overlay steels. Welds made with this composition are particularly resistant to metal dusting in chemical and petrochemical applications. The alloy is resistant to carburization, sulfidation, and other high-temperature corrosion forms.

**Ni 6701**

Consumables of this classification are used for welding matching nickel-chromium-iron alloys to each other and to high-temperature alloys for application temperatures up to 1 200 °C.

**Ni 6975**

Consumables of this classification are used for welding nickel-chromium-molybdenum alloy (UNS N06975) to itself, to steel, to other nickel-base alloys, and for cladding steel with nickel-chromium-molybdenum weld metal using gas tungsten arc welding, gas shielded metal arc welding, submerged arc welding, and plasma arc welding.

**Ni 6985**

Consumables of this classification are used for welding nickel-chromium-iron-molybdenum alloys (UNS N06007, UNS N06985) to each other, steel, other nickel-base alloys, and for cladding steel with nickel-chromium-iron-molybdenum weld metal.

**Ni 7069**

Consumables of this classification are used for cladding steel with nickel-chromium-iron weld metal and for joining steel to nickel-base alloys using gas tungsten arc welding, gas shielded metal arc welding, submerged arc welding, and plasma arc welding. The weld metal age hardens on heat treatment.

**Ni 7092**

Consumables of this classification are used for welding nickel-iron-chromium alloys (e.g. UNS N08800) and nickel-chromium-iron alloys (e.g. UNS N06600), and has particular application to dissimilar material welds. They may be used for applications at temperatures up to about 980 °C but their weld metal does not exhibit optimum oxidation resistance and strength above 820 °C.

**Ni 7718**

Consumables of this classification are used for welding nickel-chromium-niobium-molybdenum alloy (e.g. UNS N07718) to itself using gas tungsten arc welding. The weld metal age hardens on heat treatment. For specific information concerning age hardening, consult the manufacturer or the accompanying technical literature.

**Ni 8025**

Consumables of this classification deposit weld metals of higher chromium content than Ni 8125 or Ni 8065 consumables. They are used for welding copper alloyed chromium-nickel-molybdenum alloys (e.g. UNS N08904) and nickel-iron-chromium molybdenum alloys (e.g. UNS N08825). They may also be used for surfacing of steel.

**Ni 8065, Ni 8125**

Consumables of these classifications are used for welding copper alloyed chromium-nickel-molybdenum alloys (e.g. UNS N08904) and nickel-iron-chromium-molybdenum alloys (e.g. UNS N08825). They may also be used for surfacing of steel; a nickel alloy barrier layer is typically applied prior to weld overlay.

**A.6 Nickel-Molybdenum**

**Ni 1001**

Consumables of this classification are used for welding nickel-molybdenum alloy UNS N10001.

**Ni 1003**

Consumables of this classification are used for welding nickel-molybdenum alloy (e.g. UNS N10003) to itself, to steel, to other nickel-base alloys, and for cladding steel with nickel-molybdenum weld metal using gas tungsten arc welding, and gas shielded metal arc welding.

**Ni 1004**

Consumables of this classification are used for welding dissimilar metal combinations of nickel-base, cobalt-base, and iron-base alloys.

**Ni 1008, Ni 1009**

Consumables of this classification are used for welding 9 % (by mass) nickel steel (e.g. UNS K81340) to itself using gas tungsten arc welding, gas shielded metal arc welding and submerged arc welding.

**Ni 1024**

The nominal composition of consumables of this classification is 65 Ni, 25 Mo, 8 Cr, where the numbers are percentages by mass. Consumables of this classification are used for welding nickel-molybdenum alloy having UNS number N10242 to itself and for cladding steel with nickel-molybdenum weld metal using gas tungsten arc welding and gas metal arc welding processes.

**Ni 1062**

Consumables of this classification are used for welding nickel-molybdenum alloys (especially UNS N10629), for welding the clad side in steel clad with a nickel-molybdenum alloy, and for welding nickel-molybdenum alloys to steel and other nickel-base alloys.

**Ni 1066**

Consumables of this classification are used for welding nickel-molybdenum alloys (especially UNS N10665), for welding the clad side in steel clad with a nickel-molybdenum alloy, and for welding nickel-molybdenum alloys to steel and other nickel-base alloys.

**Ni 1067**

Consumables of this classification are used for welding nickel-molybdenum alloy (e.g. UNS N10675) to itself, for welding the clad side of joints in steel clad with nickel-molybdenum alloy, and for welding nickel-molybdenum alloys to steel and to other nickel-base alloys using gas tungsten arc welding, gas shielded metal arc welding, and plasma arc welding.

**Ni 1069**

Consumables of this classification are used for welding dissimilar metal combinations of nickel-base, cobalt-base, and iron-base alloys.

**A.7 Nickel-Chromium-Molybdenum****Ni 6012**

Consumables intended for welding high alloyed austenitic stainless steels of the 6 Mo type. The weldments exhibit very good resistance to pitting and crevice corrosion in chloride-containing environments. The low niobium content improves weldability.

**Ni 6022**

Consumables of this classification are used for welding low-carbon nickel-chromium-molybdenum alloys (especially UNS N06022) and chromium-nickel-molybdenum austenitic stainless steels; for welding the clad side in steel clad with low-carbon nickel-chromium-molybdenum alloy, and joining low-carbon nickel-chromium-molybdenum alloys to steel and other nickel-based alloys, as well as for surfacing of steel with nickel-chromium-molybdenum alloys.

**Ni 6035**

The nominal composition of consumables of this classification is 58 Ni, 33 Cr, 8 Mo, where the numbers are percentages by mass. Consumables of this classification are used for welding nickel-chromium-molybdenum alloy having UNS number N06035 to itself and for cladding steel with nickel-chromium-molybdenum weld metal.

**Ni 6057**

The nominal composition of consumables of this classification is 60 Ni, 30 Cr, 10 Mo, where the numbers are percentages by mass. Consumables of this classification are used for corrosion-resistant (especially excellent to crevice corrosion) overlaying with gas tungsten arc welding, gas shielded metal arc, and plasma arc welding processes.

**Ni 6058**

The nominal composition of consumables of this classification is 58 Ni, 21 Cr, 20 Mo, 1 Fe, where the numbers are percentages by mass. Consumables of this classification are used for welding nickel-chromium-molybdenum alloys (especially UNS N06058) to each other, to steel, to other nickel-base alloys, and for cladding steel with nickel-chromium-molybdenum weld metal.

**Ni 6059**

Consumables of this classification are used for welding low-carbon nickel-chromium-molybdenum alloys (especially UNS N06059) and chromium-nickel-molybdenum austenitic stainless steels, for welding the clad side in steel clad with low-carbon nickel-chromium-molybdenum alloy, and for welding low-carbon nickel-chromium-molybdenum alloys to steel and other nickel-base alloys.

**Ni 6200**

Consumables of this classification are used for welding the nickel-chromium-molybdenum alloy UNS N06200 to itself, to steel, to other nickel-base alloys, and for cladding steel.

**Ni 6205**

Consumables of this classification are used for welding nickel-chromium-molybdenum alloys (especially UNS N06058) to each other and welding chromium-nickel-molybdenum austenitic stainless steels to steel to other nickel-base alloys, and for cladding steel with nickel-chromium-molybdenum weld metals.

**Ni 6276**

Consumables of this classification are used for welding low-carbon nickel-chromium-molybdenum alloys (especially UNS N10276) for welding the clad side in steel clad with low-carbon nickel-chromium-molybdenum alloy, and for welding low-carbon nickel-chromium-molybdenum alloys to steel and other nickel-base alloys.

**Ni 6452, Ni 6455**

Consumables of these classifications are used for welding low-carbon nickel-chromium-molybdenum alloys (especially UNS N06455), for welding the clad side in steel clad with low-carbon nickel-chromium-molybdenum alloy, and for welding low-carbon nickel-chromium-molybdenum alloys to steel and other nickel-base alloys.

**Ni 6625**

Consumables of this classification are used for welding nickel-chromium-molybdenum alloys (especially UNS N06625) to each other and to steel, and for surfacing steel with nickel-chromium-molybdenum alloys. The weld metal is comparable with UNS N06625 in resistance to corrosion.

**Ni 6650**

Consumables of this classification are used for welding low-carbon nickel-chromium-molybdenum alloys and chromium-nickel-molybdenum austenitic stainless steels for offshore and chemical industry applications (e.g. UNS N08926). They are also used for cladding and for welding dissimilar metal joints, e.g. low-carbon nickel-chromium-molybdenum alloys welded to carbon steel or nickel-base alloys. They may also be used for the welding of 9 % nickel steel.

**Ni 6660**

Consumables of this classification are used for gas shielded metal arc welding and gas tungsten arc welding of superduplex, superaustenitic, cryogenic 9 % nickel steels and for coating of low-alloyed steels. Compared to Ni 6625, the weld metal shows a good or better corrosion resistance, no hot cracking problem, and a good toughness at low temperature for cryogenic applications.

**Ni 6686**

Consumables of this classification are used for welding low-carbon nickel-chromium-molybdenum alloys (especially UNS N06686) and chromium-nickel-molybdenum austenitic steels, for welding the clad side in steel clad with low-carbon nickel-chromium-molybdenum alloy, and for welding low-carbon nickel-chromium-molybdenum alloys to steel and other nickel-base alloys, as well as for surfacing of steel with nickel-chromium-molybdenum-tungsten alloys.

**Ni 7725**

Consumables of this classification are used for welding high-strength corrosion-resistant nickel alloys (especially UNS N07725 and UNS N09925) to each other and to steel, and for surfacing with high-strength nickel-chromium-molybdenum alloy. Post-weld precipitation hardening is required to develop maximum strength; a variety of heat treatments can be used.

**A.8 Nickel-Chromium-Cobalt****Ni 6160**

Consumables of this classification are used for welding the nickel-cobalt-chromium-silicon alloy (UNS N12160) to itself using gas tungsten arc welding, gas shielded metal arc welding, and plasma arc welding. This alloy is sensitive to iron pickup. Alternative filler metals are required to weld the base alloy to iron-bearing alloys. The weld metal has excellent resistance to sulfidation and chloride attack in both reducing and oxidizing environments, and can withstand temperatures up to 1 200 °C.

**Ni 6617**

Consumables of this classification are used for welding low-carbon nickel-chromium-cobalt-molybdenum alloys (especially UNS N06617) to each other and to steel, and for surfacing steel. They are also used for joining dissimilar alloys where high-temperature strength and oxidation resistance are required up to about 1 150 °C (e.g. for UNS N08800, UNS N08811, and cast high-nickel alloys).

**Ni 7090**

Consumables of this classification are used for welding nickel-chromium-cobalt alloys (e.g. UNS N07090) to each other using gas tungsten arc welding. The weld metal age hardens on heat treatment. For specific information concerning age hardening, consult the manufacturer or the accompanying technical literature.

**Ni 7263**

Consumables of this classification are used for welding nickel-chromium-cobalt-molybdenum alloys (e.g. UNS N07263) to each other and others using gas tungsten arc welding. The weld metal age hardens on heat treatment. For specific information concerning age hardening, consult the manufacturer or the accompanying technical literature.

**A.9 Nickel-Chromium-Tungsten****Ni 6231**

Consumables of this classification are used for welding nickel-chromium-cobalt-molybdenum alloy (e.g. UNS N06617) to itself with gas tungsten arc welding, gas shielded metal arc welding, and plasma arc welding.

## Annex B (informative)

### System for designation of welding consumables

The designations used in this International Standard derive from the project of the International Institute of Welding described in Reference [5], and subsequently updated and published in References [8] and [9]. The aim is to develop internationally accepted designations for welding consumables, since national designation systems are not readily changed and a generic system allows comparability among the various national specifications.

The system provides for one or two initial alpha designators, the first letter representing the type of filler metal and the second, the alloy system. A four-digit numeric designator follows the initial letters and, for a number of alloy welding consumables, this designator is similar to those assigned by the Unified Numbering System (UNS). In this way, the welding consumables are frequently related to the base metals with which they are often used (see Annex A).<sup>1)</sup>

STANDARDSISO.COM : Click to view the full PDF of ISO 18274:2010

---

1) For further information, see Bibliography.

**Annex C**  
(informative)

**Corresponding national classifications  
and typical weld metal tensile strengths**

STANDARDSISO.COM : Click to view the full PDF of ISO 18274:2010