



# Textiles — Binary fibre mixtures — Quantitative chemical analysis

## AMENDMENT 1

Amendment 1 to International Standard ISO 1833-1977 was developed by Technical Committee ISO/TC 38, *Textiles*, and was circulated to the member bodies in November 1978.

It has been approved by the member bodies of the following countries :

Australia	Germany, F. R.	Romania
Brazil	Ghana	South Africa, Rep. of
Bulgaria	Hungary	Spain
Canada	India	Sweden
Cyprus	Israel	Switzerland
Czechoslovakia	Japan	Turkey
Denmark	Korea, Rep. of	United Kingdom
Egypt, Arab Rep. of	Mexico	USA
Finland	New Zealand	USSR
France	Poland	Yugoslavia

The member bodies of the following countries expressed disapproval of the document on technical grounds :

Belgium  
Italy  
Netherlands

Page 6

Sub-clause 5.1 : Add at the end of the sub-clause the following sentences :

"However, for certain types of modal fibre which are difficult to dissolve, it is possible to repeat the procedure modified as described in 5.5. This procedure is not always applicable to mixtures containing cotton which has been mercerised".

Sub-clause 5.3.1 : Replace the first paragraph by the following text :

"5.3.1 Formic acid/zinc chloride. Prepare a solution

containing 20 g of anhydrous (fused) zinc chloride and 68 g of anhydrous formic acid {or the equivalent quantity of aqueous formic acid [85 to 98 % (m/m)]}, made up to 100 g with water.

Attention is drawn to 1.3, as the purity of these reagents is essential in this method."

Sub-clause 5.4.2 : Replace this sentence by the following text :

"5.4.2 Heating apparatus, suitable for maintaining the temperature at  $40 \pm 2$  °C (or  $70 \pm 2$  °C if the high temperature is used)."

UDC 677.014.23 : 543.062

Ref. No. ISO 1833-1977/A1-1980 (E)

Descriptors : textiles, fibres, chemical analysis, determination of content, mixtures.

© International Organization for Standardization, 1980 •

Printed in Switzerland

Price based on 2 pages