

INTERNATIONAL STANDARD

**ISO
18928**

Second edition
2002-02-01

Imaging materials — Unprocessed photographic films and papers — Storage practices

*Matériaux pour l'image — Films et papiers photographiques non traités —
Pratiques de stockage*

STANDARDSISO.COM : Click to view the full PDF of ISO 18928:2002



Reference number
ISO 18928:2002(E)

© ISO 2002

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 18928:2002

© ISO 2002

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

	Page
1 Scope	1
2 Term and definition	1
3 Storage conditions	1
3.1 General	1
3.2 Relative humidity	1
3.3 Temperature	2
3.4 Gases	2
3.5 Extraneous radiations	2
4 Temperature acclimatization	3
5 Mechanical requirements	3
6 Handling conditions	3
 Annexes	
A Numbering system for related International Standards.....	5
B Background radiation	7
Bibliography.....	8

STANDARDSISO.COM : Click to view the full PDF of ISO 18928:2002

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 18928 was prepared by Technical Committee ISO/TC 42, *Photography*.

This second edition cancels and replaces the first edition (ISO 10331:1991), which has been technically revised.

This International Standard is one of a series of standards dealing with the physical properties and stability of imaging materials. To facilitate identification of these International Standards, they are assigned a number within the block from 18900 to 18999 (see annex A).

Annexes A and B of this International Standard are for information only.

Introduction

International Standards have been written specifying the recommended practices for the storage of processed safety photographic film (ISO 18911), processed photographic reflection prints (ISO 18920), processed photographic plates (ISO 18918) and the specifications for safety film (ISO 18906).

This International Standard is concerned with the storage of unprocessed photographic materials. While many of the recommendations for unprocessed and processed storage are very similar, there are some important differences. These include the very beneficial effects of low temperature and the harmful effects of adverse storage and radiation.

STANDARDSISO.COM : Click to view the full PDF of ISO 18928:2002

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 18928:2002

Imaging materials — Unprocessed photographic films and papers — Storage practices

1 Scope

This International Standard specifies recommended storage conditions for unprocessed photographic materials. It is not applicable to processed films and prints.

This International Standard is applicable to black-and-white and colour photographic materials (negative films, positive films, reversal films, positive papers, and X-ray films) as well as to safety films.

2 Term and definition

For the purposes of this International Standard, the following term and definition apply.

2.1

raw photographic material

photographic material that has not been exposed to actinic radiation and has not been processed

3 Storage conditions

3.1 General

The photographic properties of imaging materials change during ageing. These changes result from high temperatures and high relative humidities and may also be influenced by plastics, papers, solvents, lacquers, varnishes, gases (see 3.4) and extraneous radiation (see 3.5). Frequent temperature changes may also have adverse effects.

Changes caused by unfavourable storage conditions may be much greater than those due to variations in original manufacture. It is important to comply with the manufacturer's recommended storage conditions and, where given, to an expiration date.

Films and papers should be exposed and processed as soon as possible after the original package has been opened. Opened packages should be resealed under recommended conditions for further storage.

3.2 Relative humidity

Photographic material should generally be kept in equilibrium with 40 % to 60 % relative humidity (RH). Containers shall be kept sealed until the material is used.

Films and papers are not usually stored for long periods between exposing and processing. Production schedules, customer needs, latent image fading or growth, etc., are important factors here. Furthermore, vesicular, diazo, thermally processed silver and electrographic type materials are normally processed immediately.

If conventional sheet films or papers are not to be processed immediately, they may be stored in commercially available light-tight "paper safes" or in the manufacturer's original container.

The relative humidity of the storage area shall be maintained below 65 % because higher humidities can damage containers (e.g. rust), cause labels, tapes and cartons to deteriorate and encourage the growth of fungi. It can also induce adhesion (blocking) between adjacent laps or layers.

Humidities below 30 % can make film and paper temporarily brittle and lead to unacceptable curl and possible emulsion cracking.

3.3 Temperature

Recommended temperatures during storage depend on the kind of photographic material and on the duration of storage. General guidelines are given in Table 1. In all cases, the information provided by the manufacturer shall be followed.

When storing for less than a month, photographic materials may be kept at approximately 25 °C. Most manufacturers recommend a maximum temperature of 13 °C for longer periods. Manufacturers' expiration dates can be extended by storing at still lower temperatures. Note that infrared-sensitive films shall be stored at -18 °C.

If films or papers are to be kept for several days or more between exposing and processing, many of the considerations in clause 3 apply. Storage temperatures should be the same for exposed as for unexposed material.

Table 1 — Storage temperature for films and papers

Sensitive layer of films and papers	Storage from 1 month to 6 months	Storage for more than 6 months
Wet-processable silver-gelatin Thermally-processable silver Photoplastic Diazo	Below 21 °C	Below 13 °C
Chromogenic colour	Below 13 °C	Below 13 °C
Infrared (IR)	-18 °C to -20 °C	-18 °C to -20 °C
NOTE 1 For very long storage of all types of photographic materials, the recommended storage temperature shall be between -18 °C and -20 °C.		
NOTE 2 The manufacturer's recommendations take precedence over the suggested guidelines of this table.		

3.4 Gases

Storage rooms shall be protected against harmful gases such as hydrogen sulphide, sulphur dioxide, formaldehyde, oxidizing gases, industrial emissions and mercury vapour. Any of these may penetrate the container seal and fog or desensitize the material.

Materials shall not be stored in the same area as developer or activator solution.

3.5 Extraneous radiations

Photographic materials shall be protected from extraneous penetrating radiation until they are processed. Storage rooms and housings shall be measured for their radiation level before being used. For most materials, a maximum of $1,29 \times 10^{-4}$ C/kg is recommended. However, the maximum may be $0,129 \times 10^{-4}$ C/kg for X-ray materials and certain other films (see [5] in the Bibliography).

Some stones or stone aggregates in concrete can emit sufficient radiation (average up to $0,516 \times 10^{-4}$ C/kg/yr) to fog very sensitive films after long storage. However, most films and papers are not damaged under normal conditions.

The radiation exposure during airport inspection of carry-on baggage is usually small (see [6] in the Bibliography). Recently, new technology for inspection of checked baggage at airports uses radiation that fogs many, if not most, unprocessed photographic products. This has been a special problem with international flights, but may also be serious for flights within national borders (see [7], [8] in the Bibliography).

Government regulations in many countries provide for hand inspection of photographic materials which is strongly recommended, thus avoiding the X-ray inspection. Repeated X-ray exposures can damage films faster than ISO 400, scientific films and X-ray films.

4 Temperature acclimatization

Packages of radiation sensitive films and papers should be opened only immediately before use. If materials have been stored at low temperatures, a warm-up period is necessary to prevent condensation on film or paper.

The required warm-up period depends on the size of the package, its isolation, the temperature difference between storage and surround and the dew-point of the surround. Recommended periods are given in Table 2. All values are for individual packages separated from each other, except for a carton containing ten 35 mm rolls. The length of material on a roll is less important than the thickness and the insulation of the package.

Table 2 — Minimum recommended warm-up times

Films and papers	Warm-up hours for the difference between storage and surround temperatures	
	15 °C	40 °C
Short roll films ^a		
Magazines	1 to 1,5	1 to 2
Cartridges		
Packages with 50 sheets	2	3
Single 16 mm rolls	0,5 to 1,5	1 to 2
Single 35 mm rolls	1,5 to 3	3 to 5
70 mm and 105 mm rolls	3 to 5	5 to 8
Aerial films	2 to 6	8 to 25
Large packages		
Large rolls	10 to 25	15 to 25
Carton with ten 35 mm rolls	10 to 30	30 to 45
X-ray films	10	25

^a 120-size and 220-size rolls have the same times as the short film rolls.

5 Mechanical requirements

Rolls, mounted on cores and packed in specially designed containers, shall be stored with the radius of the roll in the horizontal position, in order to avoid the weight of the roll exerting a pressure on the lower part of the roll and thereby causing physical damage.

If sheet materials are unopened and are 203 mm × 250 mm or larger, they should be stored in the vertical position. If the boxes have been opened, they should be stored in the horizontal position. Smaller boxes of sheet materials can be stored in either way.

6 Handling conditions

Climatic conditions of 20 °C to 24 °C and 40 % to 65 % RH are recommended for handling in laboratories. In printing rooms, the RH should not be too low in order to prevent static discharges and attraction of dirt. In these cases, low humidity can also cause curl and temporary dimensional changes so that proper handling is no longer possible.

Excessive exposure to recommended safelights may degrade the sensitometry of some products. The manufacturer's literature should be consulted for recommended maximum cumulative exposure.

Air-conditioning systems in laboratories should be equipped with suitable dust filters.

Care should be taken in the handling of sheets of film or paper to avoid physical damage caused by sliding materials over one another, kinking or fingerprinting. Use of lint-free cotton gloves is recommended.

STANDARDSISO.COM : Click to view the full PDF of ISO 18928:2002

Annex A (informative)

Numbering system for related International Standards

The current numbering system for TC 42 documents dealing with the physical properties and stability of imaging materials is confusing since the five digit numbers that are used are not in any consecutive order. To facilitate remembering the numbers, ISO has set aside a block of numbers from 18900 to 18999 and all revisions and new International Standards will be given a number within this block. The last three digits will be identical to the current ANSI/PIMA numbers of published documents. This will be advantageous to the technical experts from Germany, Japan, Switzerland, United Kingdom and the USA who have prepared the standard and who are familiar with the ANSI/PIMA numbers.

As the current International Standards are revised and published, their new numbers will be as given in Table A.1.

Table A.1 — New ISO numbers

Current ISO number	Title	New ISO number
10602	Photography — Processed silver-gelatin type black-and-white film — Specifications for stability	18901
10214	Photography — Processed photographic materials — Filing enclosures for storage	18902
6221	Photography — Films and papers — Determination of dimensional change	18903
5769*	Imaging materials — Processed films — Method for determining lubrication	18904
8225	Photography — Ammonia-processed diazo photographic film — Specifications for stability	18905
543*	Imaging materials — Photographic films — Specifications for safety film	18906
6077*	Imaging materials — Photographic films and papers — Wedge test for brittleness	18907
8776*	Imaging materials — Photographic film — Determination of folding endurance	18908
10977	Photography — Processed photographic colour films and paper prints — Methods for measuring image stability	18909
4330*	Imaging materials — Photographic film and paper — Determination of curl	18910
5466*	Imaging materials — Processed safety photographic films — Storage practices	18911
9718	Photography — Processed vesicular photographic film — Specifications for stability	18912
—	Imaging materials — Glossary of terms pertaining to stability	18913
—	Imaging materials — Photographic film and papers — Method for determining the resistance of photographic emulsions to wet abrasion	18914
12206*	Imaging materials — Methods for the evaluation of the effectiveness of chemical conversion of silver images against oxidation	18915
14523	Photography — Processed photographic materials — Photographic activity test for enclosure materials	18916
417*	Photography — Determination of residual thiosulfate and other related chemicals in processed photographic materials — Methods using iodine-amylose, methylene blue and silver sulfide	18917
3897*	Imaging materials — Processed photographic plates — Storage practices	18918
—	Imaging materials — Thermally processed silver microfilm — Specifications for stability	18919
6051*	Imaging materials — Processed photographic reflection prints — Storage practices	18920
—	Imaging materials — Life expectancy of information stored on compact discs (CD-ROM) — Method for estimating, based on effects of temperature and relative humidity	18921
—	Imaging materials — Processed photographic films — Methods for determining scratch resistance	18922

Table A.1 — New ISO numbers

Current ISO number	Title	New ISO number
—	Imaging materials — Polyester-base magnetic tape — Storage practices	18923
—	Imaging materials — Test method for Arrhenius-type predictions	18924
—	Imaging materials — Optical disc media — Storage practices	18925
—	Imaging materials — Life expectancy of information stored on magneto-optical (MO) discs — Method for estimating, based on effects of temperature and relative humidity	18926
—	Imaging materials — Life expectancy of information stored on recordable compact disc systems — Method for estimating, based on effects of temperature and relative humidity	18927
10331	Imaging materials — Unprocessed photographic films and papers — Storage practices	18928
—	Imaging materials — Wet-processed silver — Gelatin type black-and-white photographic reflection prints — Specifications for dark storage	18929
* This document has already been replaced by an International Standard with the new ISO number.		

STANDARDSISO.COM : Click to view the full PDF of ISO 18928:2002