
Plastics — Acrylonitrile-styrene-acrylate (ASA), acrylonitrile-(ethylene-propylene-diene)-styrene (AEPDS) and acrylonitrile-(chlorinated polyethylene)-styrene (ACS) moulding and extrusion materials —

**Part 2:
Preparation of test specimens and
determination of properties**

Plastiques — Matériaux à base d'acrylonitrile-styrène-acrylate (ASA), d'acrylonitrile-(éthylène-propylène-diène)-styrène (AEPDS) et d'acrylonitrile-(polyéthylène chloré)-styrène (ACS) pour moulage et extrusion —

Partie 2: Préparation des éprouvettes et détermination des propriétés



STANDARDSISO.COM : Click to view the full PDF of ISO 19065-2:2019



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	3
4 Preparation of test specimens	3
4.1 General.....	3
4.2 Treatment of the material before moulding.....	3
4.3 Injection moulding.....	3
4.4 Compression moulding.....	4
5 Conditioning of test specimens	4
6 Determination of properties	4
Annex A (normative) Determination of the bound-acrylonitrile content in the continuous phase ...	8

STANDARDSISO.COM : Click to view the full PDF of ISO 19065-2:2019

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This first edition of ISO 19065-2 cancels and replaces ISO 6402-2:2003, which has been technically revised mainly to update the normative references in [Clause 2](#):

- ISO 3167 has been replaced by ISO 20753;
- ISO 1183 has been replaced by ISO 1183-1, ISO 1183-2 and ISO 1183-3;
- IEC 60093 has been replaced by IEC 62631-3-1 and IEC 62631-3-2.

A list of all parts in the ISO 19065 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

There are many methods for testing properties of plastics. For some methods, the data obtained by different standards are not comparable. Even when the same standards have been used, they often allow the adoption of a wide range of alternative test conditions, and the data obtained are not necessarily comparable. The purpose of this document is to specify methods and conditions of test to be used for the acquisition and presentation of data to ensure that valid comparisons between acrylonitrile-styrene-acrylate (ASA), acrylonitrile-(ethylene-propylene-diene)-styrene (AEPDS) and acrylonitrile-(chlorinated polyethylene)-styrene (ACS) materials can be made.

.

STANDARDSISO.COM : Click to view the full PDF of ISO 19065-2:2019

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 19065-2:2019

Plastics — Acrylonitrile-styrene-acrylate (ASA), acrylonitrile-(ethylene-propylene-diene)-styrene (AEPDS) and acrylonitrile-(chlorinated polyethylene)-styrene (ACS) moulding and extrusion materials —

Part 2:

Preparation of test specimens and determination of properties

1 Scope

This document specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of acrylonitrile-styrene-acrylate (ASA), acrylonitrile-(ethylene-propylenediene)-styrene (AEPDS) and acrylonitrile-(chlorinated polyethylene)-styrene (ACS) moulding and extrusion materials. Requirements for handling the test material and for conditioning both the test material before moulding and the specimens before testing are given.

Procedures and conditions for the preparation of test specimens and procedures for measuring properties of the materials from which these specimens are made are given. Properties and test methods which are suitable and necessary to characterize ASA, AEPDS and ACS moulding and extrusion materials are listed.

The properties have been selected from the general test methods in ISO 10350-1. Other test methods in wide use for, or of particular significance to, these moulding and extrusion materials are also included in this document, as are the designatory properties specified in ISO 19065-1.

In order to obtain reproducible and comparable test results, it is intended to use the methods of specimen preparation and conditioning, the specimen dimensions and the test procedures specified in this document. Values determined will not necessarily be identical to those obtained using specimens of different dimensions or prepared using different procedures.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 62, *Plastics — Determination of water absorption*

ISO 75-1, *Plastics — Determination of temperature of deflection under load — Part 1: General test method*

ISO 75-2, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite*

ISO 178, *Plastics — Determination of flexural properties*

ISO 179-1, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*

ISO 179-2, *Plastics — Determination of Charpy impact properties — Part 2: Instrumented impact test*

ISO 180, *Plastics — Determination of Izod impact strength*

ISO 293, *Plastics — Compression moulding of test specimens of thermoplastic materials*

ISO 19065-2:2019(E)

ISO 294-1, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens*

ISO 294-3, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 3: Small plates*

ISO 306, *Plastics — Thermoplastic materials — Determination of Vicat softening temperature (VST)*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 527-4, *Plastics — Determination of tensile properties — Part 4: Test conditions for isotropic and orthotropic fibre-reinforced plastic composites*

ISO 899-1, *Plastics — Determination of creep behaviour — Part 1: Tensile creep*

ISO 1133-1, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method*

ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 1183-2, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method*

ISO 1183-3, *Plastics — Methods for determining the density of non-cellular plastics — Part 3: Gas pycnometer method*

ISO 1656, *Rubber, raw natural, and rubber latex, natural — Determination of nitrogen content*

ISO 2561, *Plastics — Determination of residual styrene monomer in polystyrene (PS) and impact-resistant polystyrene (PS-I) by gas chromatography*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 4581, *Plastics — Styrene/acrylonitrile copolymers — Determination of residual acrylonitrile monomer content — Gas chromatography method*

ISO 4589-2, *Plastics — Determination of burning behaviour by oxygen index — Part 2: Ambient-temperature test*

ISO 4589-3, *Plastics — Determination of burning behaviour by oxygen index — Part 3: Elevated-temperature test*

ISO 8256, *Plastics — Determination of tensile-impact strength*

ISO 10350-1, *Plastics — Acquisition and presentation of comparable single-point data — Part 1: Moulding materials*

ISO 11357-1, *Plastics — Differential scanning calorimetry (DSC) — Part 1: General principles*

ISO 11357-2, *Plastics — Differential scanning calorimetry (DSC) — Part 2: Determination of glass transition temperature and glass transition step height*

ISO 19065-1, *Plastics — Acrylonitrile-styrene-acrylate (ASA), acrylonitrile-(ethylene-propylene-diene)-styrene (AEPDS) and acrylonitrile-(chlorinated polyethylene)-styrene (ACS) moulding and extrusion materials — Part 1: Designation system and basis for specifications*

ISO 20753, *Plastics — Test specimens*

IEC 60112, *Method for the determination of the proof and the comparative tracking indices of solid insulating materials*

IEC 60243-1, *Electrical strength of insulating materials — Test methods — Part 1: Tests at power frequencies*

IEC 60296, *Fluids for electrotechnical applications — Unused mineral insulating oils for transformers and switchgear*

IEC 60695-11-10, *Fire hazard testing — Part 11-10: Test flames — 50 W horizontal and vertical flame test methods*

IEC 62631-2-1, *Dielectric and resistive properties of solid insulating materials-Part 2-1: Relative permittivity and dissipation factor-Technical frequencies (0,1 Hz to 10 MHz)-AC Methods*

IEC 62631-3-1, *Dielectric and resistive properties of solid insulating materials — Part 3-1: Determination of resistive properties (DC methods) — Volume resistance and volume resistivity — General method*

IEC 62631-3-2, *Dielectric and resistive properties of solid insulating materials — Part 3-2: Determination of resistive properties (DC methods) — Surface resistance and surface resistivity*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Preparation of test specimens

4.1 General

It is essential that specimens always be prepared by the same procedure (either injection moulding or compression moulding), using the same processing conditions. The procedure to be used for each test method is indicated in [Tables 3](#) and [4](#).

The material shall be kept in moisture-proof containers until it is required for use. The moisture content of filled or reinforced materials shall be expressed as a percentage of the total mass of the compound.

4.2 Treatment of the material before moulding

Before processing, the material shall be dried under appropriate conditions to produce samples without surface defects such as spray marks.

4.3 Injection moulding

Injection-moulded specimens shall be prepared in accordance with ISO 294-1 or ISO 294-3, using the conditions specified in [Table 1](#), in which the temperature values given are target values (see ISO 294-1 or ISO 294-3 for tolerances).

Table 1 — Conditions for injection moulding of test specimens

Material	Melt temperature	Mould temperature	Injection velocity
	°C	°C	mm/s
ACS	200	60	200 ± 100
ASA and AEPDS, general and high-heat grades	250	60	200 ± 100

4.4 Compression moulding

Compression-moulded sheets shall be prepared in accordance with ISO 293, using the conditions specified in [Table 2](#), in which the moulding temperatures given are target values (see ISO 293 for tolerances).

The test specimens required for the determination of the properties shall be machined from the compression-moulded sheets in accordance with ISO 2818 or stamped.

Table 2 — Conditions for compression moulding of test specimens

Material	Moulding temperature °C	Average cooling rate °C/min	Demoulding temperature °C	Full pressure MPa	Full pressure time min	Preheating time min
ACS	180 ± 5	10 ± 5	≤ 60	4 ± 0,5	5 ± 1	5 ± 1
ASA and AEPDS, general and high-heat grades	220 ± 5	10 ± 5	≤ 60	4 ± 0,5	5 ± 1	5 ± 1

5 Conditioning of test specimens

Test specimens for the determination of the melt mass-flow rate shall be conditioned for 4 h at 80 °C ± 2 °C and then stored in a desiccator according to ISO 19065-1. Test specimens for electric strength shall be conditioned for not less than 24 h at (23 ± 2) °C, (50 ± 5) % relative humidity according to IEC 60243-1. Test specimens for oxygen index shall be conditioned for 24 h at (23 ± 2) °C and (50 ± 5) % relative humidity. After 24 h conditioning, if the stability of the mass of the specimen reaches 0,1 % or if less changes, then allow to conduct the test. Otherwise, keep the specimen at (23 ± 2) °C and (50 ± 5) % relative humidity for at least 88 h in conditioning chamber according to ISO 4589-2. Test specimens for other properties shall be conditioned for at least 16 h at (23 ± 2) °C and (50 ± 10) % relative humidity.

6 Determination of properties

In the determination of properties and the presentation of data, the standards, supplementary instructions and notes given in ISO 10350-1 shall be applied. All tests shall be carried out in the standard atmosphere of (23 ± 2) °C and (50 ± 10) % relative humidity unless specifically stated otherwise in [Tables 3](#) and [4](#).

[Table 3](#) is compiled from ISO 10350-1, and the properties listed are those which are appropriate to ASA, AEPDS and ACS moulding and extrusion materials. These properties are those considered useful for comparisons of data generated for different thermoplastics.

[Table 4](#) contains those properties, not found specifically in [Table 3](#), which are in wide use or of particular significance in the practical characterization of ASA, AEPDS and ACS moulding and extrusion materials.

Table 3 — General properties and test conditions (selected from ISO 10350-1)

Property	Symbol	Unit	Test method	Specimen type (dimensions in mm)	Specimen preparation	Test conditions and supplementary instructions
Rheological properties						
Melt mass-flow rate (MFR)	MFR	g/10 min	ISO 1133-1	Moulding compound	—	220 °C, load 10 kg ^a
Melt volume-flow rate (MVR)	MVR	cm ³ /10 min				
Mechanical properties						
Tensile modulus	E_t	MPa	ISO 527-2, ISO 527-4	ISO 20753	Injection moulding	Test speed 1 mm/min.
Yield stress	σ_y					Test speed 50 mm/min.
Yield strain	ε_y	Test speed 50 mm/min.				
Strain at break	ε_B	%				Test speed 50 mm/min. Failure without yielding, test speed, according to ISO 10350-1.
Stress at 50 % strain	σ_{50}	MPa	ISO 899-1	80 × 10 × 4	Injection moulding	Test speed 50 mm/min. Only to be quoted if no yielding is observed up to 50 % nominal strain.
Tensile creep modulus	E_{tc1} E_{tc10^3}	MPa				At 1 h At 1 000 h
Flexural modulus	E_f	MPa	ISO 178	80 × 10 × 4	Injection moulding	Test speed 2 mm/min.
Flexural strength	σ_{fM}					
Charpy impact strength	a_c	kJ/m ²	ISO 179-1 ISO 179-2	80 × 10 × 4 80 × 10 × 4 V-notch, $r = 0,25$	Injection moulding	Edgewise impact. Also record type of failure.
Charpy notched impact strength	a_{cA}					
Tensile notched impact strength	a_{tN}					ISO 8256
Thermal properties						
Glass transition temperature	T_g	°C	ISO 11357-1 ISO 11357-2	In any form See ISO 11357-1	—	Record midpoint temperature. Use 10 °C/min.
Temperature of deflection under load	$T_f1,8$ $T_f0,45$	°C	ISO 75-1 ISO 75-2	80 × 10 × 4	Injection moulding	0,45 MPa and 1,8 MPa.
Vicat softening temperature	$T_{V50/50}$	°C	ISO 306	≥ 10 × ≥ 10 × 4		Heating rate 50 °C /h, load 50 N.
Burning behaviour	B50/3	mm/min	IEC 60695-11-10	125 × 13 × 3	Injection moulding	Record one of classifications with thickness, for example V-0@3,0 mm, V-1@ 3,0 mm, V-2@3,0 mm, HB40@3,0 mm, HB75@ 3,0 mm
Oxygen index	OI	%	ISO 4589-2 ISO 4589-3	80 × 10 × 4		Procedure A — top surface ignition.
Electrical properties						

Table 3 (continued)

Property	Symbol	Unit	Test method	Specimen type (dimensions in mm)	Specimen preparation	Test conditions and supplementary instructions		
Relative permittivity	ϵ_r100	—	IEC 62631-2-1	$\geq 60 \times \geq 60 \times 1$ Or $\geq 60 \times \geq 60 \times 2$	Compression moulding	100 Hz	Compensate for electrode edge effects.	
	ϵ_r1M					1 MHz		
Dissipation factor	$\tan\delta100$	—	IEC 62631-2-1	$\geq 60 \times \geq 60 \times 2$		100 Hz		1 min value
	$\tan\delta1M$					1 MHz		
Volume resistivity	ρ_e	$\Omega \cdot m$	IEC 62631-3-1	$\geq 100 \times \geq 100 \times 1$	Injection moulding	Voltage 100 V	1 min value	
Surface resistivity	σ_e	Ω	IEC 62631-3-2	$\geq 60 \times \geq 60$		Injection moulding		
Electric strength	E_{B1}	kV/mm	IEC 60243-1	$60 \times 60 \times 1$	Injection moulding		Use 25 mm/75 mm coaxial-cylinder electrodes. Immerse in transformer oil in accordance with IEC 60296. Use a 20 s step-by-step test.	
Comparative tracking index	CTI	—	IEC 60112	$\geq 20 \times \geq 20 \times 4$	Injection moulding	Use solution A.		

STANDARDSISO.COM : Click to view the full PDF of ISO 19065-2:2019