
**Buildings and civil engineering
works — Sealants — Determination of
curing behaviour**

*Bâtiments et ouvrages de génie civil — Mastics — Détermination du
comportement de durcissement*

STANDARDSISO.COM : Click to view the full PDF of ISO 19861:2015



STANDARDSISO.COM : Click to view the full PDF of ISO 19861:2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Test materials	1
5.1 One part sealants	1
5.2 Multi component sealants	1
6 Preparation of test specimens	2
6.1 General	2
6.2 One part sealants	2
6.3 Multi component sealants	2
7 Conditioning of test specimens	2
8 Test procedure	2
8.1 One part sealants	2
8.2 Multi component sealants	2
9 Expression of results	3
9.1 One part sealants	3
9.2 Multi component sealants	3
10 Test report	3

STANDARDSISO.COM : Click to view the full PDF of ISO 19861:2015

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 59, *Buildings and civil engineering works*, Subcommittee SC 8, *Sealants*.

Buildings and civil engineering works — Sealants — Determination of curing behaviour

1 Scope

This International Standard specifies a method for the determination of the curing behaviour of sealants used in joints in building construction.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness)*

ISO 6927, *Buildings and civil engineering works — Sealants — Vocabulary*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6927 apply.

4 Principle

Test specimens are prepared such that the sealant to be will be subjected to a curing environment. A one part sealant has the time recorded when its cure in depth reaches 2 mm. A multi component sealant has the time recorded to reach 33 % of its ultimate hardness.

5 Test materials

5.1 One part sealants

5.1.1 Plastic or metal cylindrical cups, 35 mm - 75 mm internal diameter; 35 mm - 50 mm deep, wall thickness 1 mm - 3 mm.

5.1.2 Measuring device, scaled to 0,5 mm.

5.2 Multi component sealants

5.2.1 Draw down device, capable of producing a 6 mm minimum constant thickness of the sealant.

5.2.2 Indentation hardness measurement device, capable of measurements on the A scale.

Extremely soft sealants that measure less than 5 on the A scale should be measured on the 00 scale.

6 Preparation of test specimens

6.1 General

The sealant and test materials shall be brought to (23 ± 2) °C over 24 h.

6.2 One part sealants

6.2.1 Fifteen test specimens shall be prepared. For each specimen the cup shall be filled with the sealant and tooled flat.

6.2.2 The following precautions shall be taken:

- a) the formation of air bubbles shall be avoided;
- b) the sealant shall be pressed on the inner surfaces of the substrates;
- c) the sealant surface shall be tooled so that it is flush with the top of the open cup.

6.3 Multi component sealants

6.3.1 A tooled slab of sealant 6 mm minimum thick, 50 mm wide and 300 mm long on a flat non-absorbing surface is required.

6.3.2 The instructions of the sealant manufacturer concerning the mixing procedure for multi-component sealants shall be followed.

7 Conditioning of test specimens

The test specimens shall be extruded, tooled and cured at a temperature of (23 ± 2) °C and relative humidity (RH) of (50 ± 10) %.

8 Test procedure

8.1 One part sealants

The cured skin on top of three cups shall be removed at the following intervals, 16 h, 24 h, 48 h, 72 h, 96 h and 168 h. The cured skin is wiped of uncured sealant. The thickness of each specimen shall be measured and recorded.

8.2 Multi component sealants

The measurement of hardness is performed according to ISO 868. The sealant shall be extruded onto a flat surface and tooled to 6 mm minimum thickness. The hardness of the air side extruded cured slab of sealant shall be measured three times at the following intervals: Once prior to and twice after the manufacturer recommended cure time for 33 % ultimate hardness at (23 ± 2) °C and (50 ± 10) % RH (hardness at 28 days cure). One measurement shall be made 4 h to 8 h prior to the predicted time, one measurement shall be made at the predicted time, and two final measurements shall be taken, rather evenly spaced, over the subsequent 24 h. The test may cease when two subsequent hardness readings are within 3 % of final hardness (generally published on manufacturer's literature).