
INTERNATIONAL STANDARD



2000

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Rubber, natural (NR) – Specifications

Caoutchouc naturel (NR) – Spécifications

Second edition – 1976-02-01

STANDARDSISO.COM : Click to view the full PDF of ISO 2000:1976

UDC 678.4

Ref. No. ISO 2000-1976 (E)

Descriptors : natural rubber, crude rubber, materials specifications, plastic properties, impurities.

FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO Member Bodies). The work of developing International Standards is carried out through ISO Technical Committees. Every Member Body interested in a subject for which a Technical Committee has been set up has the right to be represented on that Committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the Technical Committees are circulated to the Member Bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 2000 (second edition) was drawn up by Technical Committee ISO/TC 45, *Rubber and rubber products*. It was submitted directly to the ISO Council, in accordance with clause 6.12.1 of the Directives for the technical work of ISO.

This second edition cancels and replaces International Standard ISO 2000-1975, which had been approved by the Member Bodies of the following countries :

Australia	Germany	Spain
Belgium	Hungary	Sweden
Brazil	India	Turkey
Bulgaria	Italy	United Kingdom
Canada	Malaysia	U.S.A.
Chile	Netherlands	U.S.S.R.
Czechoslovakia	New Zealand	Yugoslavia
Egypt, Arab Rep. of	Poland	
France	Romania	

No Member Body had expressed disapproval of the document.

Rubber, natural (NR) – Specifications

1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies the minimum quality requirements and the corresponding methods of test for four grades of raw natural rubber sampled in accordance with ISO 1795 or as agreed between the interested parties.

2 REFERENCES

ISO 247, *Rubber – Determination of ash in raw rubbers, compounded rubbers and vulcanizates.*¹⁾

ISO 248, *Rubber – Determination of volatile matters in raw rubbers.*²⁾

ISO 249, *Raw natural rubber – Determination of dirt.*

ISO 1656, *Raw natural rubber and natural rubber latex – Determination of nitrogen.*

ISO 1795, *Raw rubber in bales – Sampling.*

ISO 1796, *Raw rubber – Sample preparation.*

ISO 2007, *Raw rubber and unvulcanized compounded rubber – Rapid plasticity test.*

ISO 2930, *Raw natural rubber – Plasticity retention index (PRI).*

3 REQUIREMENTS

NOTE – Dirt content and plasticity retention index (PRI) are considered the primary specification parameters.

3.1 Raw rubber supplied in accordance with this specification shall not have had skim rubber included in it.

3.2 Each bale of the sample shall be tested for compliance with the requirements shown in the following table.

4 COMPLIANCE

The lot shall be regarded as still complying with the specification if only one bale of the sample fails to meet any one of the limits given in the table and if only one further bale of the sample fails to meet any other single limit. Alternatively, the compliance requirements shall be as agreed between the interested parties.

TABLE – Requirements

Characteristic	Limits for grade of rubber				Test method
	5	10	20	50	
	Colour code				
	Green	Brown	Red	Yellow	
Dirt content, % (m/m) retained on 45 µm sieve, max.	0,05	0,10	0,20	0,50	ISO 249
Initial plasticity, min.	30	30	30	30	ISO 2007
PRI, min	60	50	40	30	ISO 2930
Nitrogen content*, % (m/m) max.	0,6	0,6	0,6	0,6	ISO 1656
Volatile matter content**, % (m/m) max.	1,0	1,0	1,0	1,0	ISO 248
Ash**, % (m/m) max.	0,6	0,75	1,0	1,5	ISO 247

* For initial concentration rubber (ICR), the nitrogen content shall not exceed 0,7 % (m/m).

** For initial concentration rubber, volatile matter and ash contents shall be agreed between the interested parties and neither shall exceed 1,5 % (m/m).

1) At present at the stage of draft. (Revision of ISO/R 247-1962.)

2) At present at the stage of draft. (Revision of ISO/R 248-1962.)