
**Natural rubber latex concentrate —
Centrifuged or creamed, ammonia-
preserved types — Specifications**

*Latex concentré de caoutchouc naturel — Types centrifugés ou
crémés, préservés à l'ammoniaque — Spécifications*

STANDARDSISO.COM : Click to view the full PDF of ISO 2004:2017



STANDARDSISO.COM : Click to view the full PDF of ISO 2004:2017



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Requirements	2
5 Sampling	3

STANDARDSISO.COM : Click to view the full PDF of ISO 2004:2017

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This sixth edition cancels and replaces the fifth edition (ISO 2004:2010), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the dry rubber content in [Table 1](#) has been corrected from 60 % to 60,0 %, for type HA, LA and XA natural rubber latex concentrate;
- the coagulum content in [Table 1](#) has been reduced from 0,03 % to 0,02 %;
- the sludge content in [Table 1](#) has been reduced from 0,10 % to 0,06 %.

Natural rubber latex concentrate — Centrifuged or creamed, ammonia-preserved types — Specifications

1 Scope

This document gives specifications for natural rubber latex concentrate types which are preserved wholly or in part with ammonia and which have been produced by centrifuging or creaming.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 35, *Natural rubber latex concentrate — Determination of mechanical stability*

ISO 123, *Rubber latex — Sampling*

ISO 124, *Latex, rubber — Determination of total solids content*

ISO 125, *Natural rubber latex concentrate — Determination of alkalinity*

ISO 126, *Natural rubber latex concentrate — Determination of dry rubber content*

ISO 127, *Rubber, natural latex concentrate — Determination of KOH number*

ISO 506, *Rubber latex, natural, concentrate — Determination of volatile fatty acid number*

ISO 706, *Rubber latex — Determination of coagulum content (sieve residue)*

ISO 2005, *Rubber latex, natural, concentrate — Determination of sludge content*

ISO 7780, *Rubbers and rubber latices — Determination of manganese content — Sodium periodate photometric methods*

ISO 8053, *Rubber and latex — Determination of copper content — Photometric method*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

natural rubber latex concentrate

natural rubber latex containing ammonia and/or other preservatives, which has been subjected to some process of concentration

3.2

type HA natural rubber latex concentrate

centrifuged latex preserved after concentration with ammonia only, with an alkalinity of at least 0,60 % (by mass) calculated with respect to the latex

3.3

type LA natural rubber latex concentrate

centrifuged latex preserved after concentration with ammonia together with other preservatives, with an alkalinity of not more than 0,29 % (by mass) calculated with respect to the latex

3.4

type XA natural rubber latex concentrate

centrifuged latex preserved after concentration with ammonia together with other preservatives, with an alkalinity between 0,30 % and 0,59 % (by mass) calculated with respect to the latex

3.5

creamed type HA natural rubber latex concentrate

creamed latex preserved after concentration with ammonia only, with an alkalinity of at least 0,55 % (by mass) calculated with respect to the latex

3.6

creamed type LA natural rubber latex concentrate

creamed latex preserved after concentration with ammonia together with one or more additional preservatives, with an alkalinity of not more than 0,35 % (by mass) calculated with respect to the latex

4 Requirements

The latex concentrate shall conform to all the requirements in [Table 1](#).

If one or more preservatives other than ammonia are added to the latex concentrate, the chemical nature and approximate quantity of such preservative(s) shall be stated. The latex concentrate shall not contain fixed alkali added at any stage in its production.

STANDARDSISO.COM : Click to view the full PDF of ISO 2004:2017